


Eldar Bahadır oğlu Zeynalov

Polimer materialları üçün antioksidantlar



Eldar Bahadır oğlu Zeynalov

POLİMER MATERİALLARI ÜÇÜN ANTİOKSIDANTLAR

Nə səbəbə biz polimerlər üçün stabilizatorlardan istifadə edirik?

Polimer materiallar hal-hazırda müasir həyatımızda çox mühüm yer tutur. Bu gün şüşə, farfor, metal, kağız, ağaç kimi geniş yayılmış materiallar polimer materiallarla əvəz oluna bilir.

Polimerlərdən uzun müddətli istifadə təcrübəsi göstərir ki, bu maddələr işığın, istiliyin, oksigenin təsiri altında qocalmaya məruz qalır ki, bu səbəbdən də onlar əvvəlki davamlılığını və elastikliyini itirir, rəngləri solqunlışır, bərkliyir, strukturunu itirir və dağılmağa məruz qalır. Lakin polimer materialların tərkibində termostabilizator, antioksidant və işıq stabilizatorları kimi əlavələr olarsa bu arzuolunmaz prosesləri ləngitmək və ya tamamilə aradan qaldırmaq mümkündür.

(SpecialChem: Polymer Additives & Colors)

Bakı - «Elm» - 2009

Eldar Bahadır oğlu Zeynalov : **Polimer materialları üçün**

antioksidantlar.

Bakı : Elm, 2009 – 342s.

Elmi məsləhətçi:

akademik Musa İ. Rüstəmov

ISBN 978-9952-453-37-9

Yaxşı məlumdur ki, termiki, oksidləşdirici, fotolitik, radioaktiv, hidrolitik, bioloji və bu kimi qocalma proseslərini aradan qaldırmaq nöqtəyi-nəzərindən üzvi birləşmələr, polimerlər, kompozisiya və materiallara əlavələr kimi bir sıra kimyəvi birləşmələrdən praktikada geniş istifadə olunur. Stabilizator, ingibitor, antioksidant, antiozonant, antirad, aşkar, konservant, işiq absorberləri adlanan bu birləşmələr müxtəlif polimerlərin destruksiya və dağılmazı prosesini longidir, mineral sürtkü yağlarının istismar müddətini uzadır, motor və reaktiv yanacaqlarının yüksək keyfiyyətinin uzun müddət saxlanması kömək edir, yeyinti məhsullarının xarab olması və qaxsimasının qarşısını alır, dərman preparatlarının istifadə müddətini artırır.

Təqdim olunan monoqrafiyanın başlıca məqsədi bu birləşmələrin mühüm əhəmiyyətini nəzərə alaraq polimer materiallarda istifadə olunan antioksidantların əsas sinifləri haqda xüsusi məlumatları diqqətə çatdırmaqdan ibarətdir. İlk dəfə olaraq spesifik-özünəməxsus antioksidəşmə aktivliyinə malik birləşmələr sırasına sürətlə daxil olan yeni antioksidant sinifləri - fulleren nanoklasterləri və karbon nanoboruları haqda məlumat verilmişdir. Əsas diqqət polimer materialları və kompozisiyaların tərkibində antioksidantların həm aktivliyinin və təsir mexanizminin öyrənilməsinə, həm də onların tətbiq olunması istiqamətinə yönəlmüşdür.

Monoqrafiya Web of Science və Web of Knowledge elektron saytlarının məlumat bazası, həmçinin monoqrafiyanın müəllifinin tədqiqatları əsasında tərtib edilmişdir.

Monoqrafiya polimer materiallarının kimya və texnoloqiyası sahəsindəki alim və mütəxəssislər, aspirantlar və doktorantlar üçün təxəxis edilmişdir.

Azərbaycan dilində nəşrə təqdim olunmuş variantdan başqa monoqrafiyanın rus və ingilis dilində variantları da çapa hazırlanmışdır.

1701000000
655(07) – 2009

qrifli nəşr

© «Elm», 2009

Mündəricat

	<i>Səh.</i>
Ön söz. Aerob oksidləşmə proseslərinin ümumi görünüşü.....	5
1. Polimerlərin qocalması, polimer materiallarının destruksiyasının müxtəlif növləri haqda qısa məlumat.....	6
1.1. Polimerlərin termiki destruksiyası (piroliz)...	6
1.2. Polimerlərin termoooksidləşdirici destruksiyası.....	12
1.3. Ozonun təsirindən kauçuk, rezin və plastiklərin qocalması.....	13
1.4. Polimerlərin fotodestruksiyası.....	14
1.5. Polimerlərin radiosiyannın təsirindən destruksiyası...15	
1.6. Polimerlərin hidrolitik destruksiyası.....	16
1.7. Polimerlərin mexaniki destruksiyası.....	17
1.8. Polimerlərin bioloji destruksiyası.....	18
2. Polimerlərin oksidləşməsi və destruktiv proseslərin aradan qaldırılması üsulları.....	18
3. Əsas antioksidantlar – radikal akseptorları.....	22
3.1. Fəzavi-çətinləşmiş fenollar.....	23
3.2. Aromatik aminlər.....	28
3.3. Fəzavi-çətinləşmiş aminlər.....	31
3.4. Hidroksilaminlər.....	34
3.5. Benzofuranonlar (laktonlar).....	35
3.6. Xinonlar.....	37
3.7. Karbon hisi və polikondensləşmiş aromatik karbohidrogenlər.....	39
3.8. Fulleren və karbon nanoboruları antioksidəşdirici inqibitorlar kimi.....	41
3.9. Hidroperoksidlərin dağıdıcıları.....	54
3.10. Metalların dezaktivatorları.....	59
4. Müxtəlif antioksidantlardan istifadənin temperatur intervalları.....	61

5.	Antioksidantların kombinasiyası.....	63
5.1.	Antioksidantların sinregik qarışıqları.....	64
5.2.	Antioksidantların antoqonist qarışıqları.....	64
6.	Antioksidantların polimerlərdə tətbiqi.....	65
6.1.	Poliolefinlər.....	65
6.2.	Poliamidlər.....	68
6.3.	Polistiollar.....	70
6.4.	Poliefirlər.....	71
6.5.	Polikarbonatlar.....	72
6.6.	Poliasetallar.....	72
6.7.	Poliuretanlar.....	73
6.8.	Kauçuklar.....	73
6.9.	Polivinilxloridlər.....	76
6.10.	Yanacaq və yağlar.....	76
7.	Sınaq metodları.....	78
7.1.	Polimerlər.....	78
7.2.	Sürtgü yağları.....	80
8.	Antioksidantların əlavə xassələri.....	81
8.1.	Uçuculuq.....	82
8.2.	Uğyunluq.....	82
8.3.	Rəngədavamlılıq.....	82
8.4.	Fiziki hal.....	83
8.5.	Dad və qoxu.....	83
8.6.	Kanserogenlik və təhlükəsizlik faktorları.....	83
8.7.	İqtisadi cəhətdən effektivlik.....	84
9.	İstifadə olunmuş ədəbiyyatın siyahısı.....	85
10.	Sənaye tipli antioksidantlar.....	102
11.	Əlavə. Poliolefinlərin stabillaşdırılması üçün dünya miqyasında istehsal olunan antioksidantların siyahısı....	102

ÖN SÖZ

AEROB OKSIDLƏŞMƏ PROSESLƏRİNİN ÜMUMİ GÖRÜNÜŞÜ

Üzvi birləşmələrin aerob oksidləşmə prosesləri təbiət elmləri içərisində ən mühüm yerlərdən birini tutur və elm və sənayenin aktual problemlərinin həlli istiqamətinə yönəlmüşdir.

Əgər $S + O_2 \longrightarrow$ oksidləşmə – çevrilmə məhsulları üzrə aerob oksidləşmə prosesini nəzərdən keçirsek (burada S – üzvi substrat – neft, polimer, karbohidrogen, boyaq maddəsi, dərman preparati, yeyinti məhsulu, ətriyyat mayesi, sellüloza və s.-dir), bu prosesə iki diametral-əks mövqedən yanaşmaq mümkündür:

- 1 – oksidləşmə-çevrilmə məhsulları arzuolunandır
- 2 – oksidləşmə-çevrilmə reaksiyaları arzuolunan deyil.

Oksidləşmə-çevrilmənin birinci yolu kimyaçılar üçün qiymətli kimyəvi məhsulların alınmasında səmərəli oksidləşmə prosesləri aparma imkanı yaradır. Bu zaman proseslərin aparılması üçün uyğun şərait – oksigenin təzyiqi, katalitik sistemlər, zaman və temperatur rejimi, reaktorların quruluşu və s. seçilir ki, bu da tələb olunan məhsulların məqsədyönlü olaraq alınmasına imkan verir.

Oksidləşmə-çevrilmənin ikinci yolu üzrə olan tədqiqatlar tamamilə əks məqsəd – substratin əvvəlki qiymətli xassələrini saxlamaq məqsədi daşıyır. Belə ki, maddələr yüksək temperaturun təsirindən destruktiv şüalanmadan, aqressiv mühitdən, güclü oksidləşdiricilərdən, atmosferin zərərli təsirindən mühafizə olunurlar. Bu məqsədlə ilkin maddənin saxlanması, istifadəsi və emalında yumşaq rejim seçilməklə yanaşı, az miqdarda əlavələrinin tətbiqi ilə effektiv müdafiəçi rolunu oynayan müxtəlif protektorlar,

stabilizator və konservantların vasitəsi ilə substratların stabilləşməsi də təmin olunur.

Oksidləşmə prosesləri üzrə qeyd olunan hər iki istiqamət kimya elmində mühüm əhəmiyyət kəsb edir və onlar bu sahədə mövcud olan bir çox fundamental və praktiki işlərdə öz əksini tapmışdır.

Hazırkı monoqrafiya diqqəti ikinci istiqamət üzərində cəmləmiş və polimerlərin stabilləşməsini təmin edən antioksidantlara həsr edilmişdir. Polimerlərin nizamının pozulmasına (destruksiyası) səbəb olan proseslərin müxtəlifliyi və onların aradan qaldırılması üsulları haqda materiallar kitabda ardıcılıqla verilir. Bu zaman əsas diqqət polimer materiallarının antioksidanslılığı stabiləşdirilməsinin daha vacib nəzəri və təcrübi cəhətlərini işıqlandırılmasına yönəldilmişdir. Polimer kompozisiyaları və materialları üçün yeni və perspektiv antioksidantlar kimi fullerenlər, bir- və çoxdivarlı karbon nanoboruları nəzərdən keçirilmişdir.

1. Polimerlərin qocalması, polimer materialların destruksiyasının müxtəlif növləri haqda qısa məlumat

Polimerlərin qocalması və onların stabiləşdirilməsi problemi polimer materiallarının yaradılması, emalı, saxlanması və onların istismar xassələrinin tənzimlənməsi ilə məşğul olan polimer materialşunaslığı adlanan elmin böyük bir bölməsini təşkil edir. Hazırda bu mövzu ətrafında çox zəngin və böyük əhəmiyyət daşıyan praktiki material mövcuddur.

Polimerlərin ətraf mühitin təsiri altında baş verən qocalması və ya köhnəlməsi, onların emalı, istismarı və saxlanması zamanı xassələrinin dönen və dönməyən kimi dəyişikliklərə (pisləşməyə) gətirib çıxaran fiziki və kimyəvi proseslərin mürəkkəb kompleks toplusudur. Çox zaman

«qocalma» termini əvəzinə «destruksiya» (dağılma) termini işlədir.

Qocalma prosesləri fiziki və kimyəvi olmaqla iki yerə bölünür. Fiziki qocalma prosesləri dönərdir. Bu proses polimer zəncirin dağılması və ya tikilməsinə gətirib çıxarmır. Misal olaraq kristallaşma və yenidən kristallaşma proseslərini, polimerin tərkibinə arzuolunmaz həllədicilərin daxil olaraq kristallararası korroziyaya və polimer məməlatlarının mexaniki xassələrinin pisləşməsinə səbəb olan prosesləri göstərmək olar.

Kimyəvi qocalma prosesləri isə geri dönməyəndir. Bu proseslər kimyəvi rəbitələrin qırılmasına, bəzən isə makromolekulların tikilməsinə, polimerin kimyəvi quruluşunun dəyişməsinə, polimerin molekul kütłosinin azalmasına və ya artmasına gətirib çıxarır.

Polimerlərin stabilliyi – onların emalı, istismarı və saxlanması zamanı ətraf mühitin təsiri nəticəsində xassələrinin dəyişməməsi qabiliyyəti deməkdir. Polimerlərin stabilləşməsi dedikdə isə polimer və polimer məməlatlarının qocalma sürətini aşağı salan kimyəvi və fiziki metodların tətbiqi nəzərdə tutulur.

Stabilləşmənin fiziki metodu əsas etibarilə qarşılıqlı təsirdə olan hissəciklərin diffuziya sürətinin dəyişməsi ilə əlaqələndirilir. Məsələn, polimerlərin hidrolitik destruksiya proseslərini ləngitmək məqsədilə aqressiv mühitin (suyun, turşu, əsas və duz məhlullarının və s.) polimer matrisaya diffuziya sürətini aşağı salmaq olar.

Stabilləşmənin kimyəvi üsulu polimerin qocalmasına (destruksiyasına) cavabdeh olan aktiv hissəcikləri (əsasən, atom, radikal və ionları) tutub saxlayan müxtəlif kimyəvi birləşmələrin polimerlərə əlavə edilməsi ilə səciyyələnir.

Hal-hazırda dunyada polad, çuqun, əvan metallar və s.-nin birlikdə götürülmüş istehsalı qədər polimer materiallar buraxılır. İstehsalın dinamikası da mühüm amillərdən biridir. Polimer istehsalının artım tempi metal

istehsalı artım tempini 25-30 % üstələyir. Aydındır ki, istehsalın belə geniş həcmi üçün buraxılan məhsulun keyfiyyəti birinci dərəcəli əhəmiyyətə malikdir. Polimer məmulatın ömrünün iki dəfə uzadılması bu maddələrin istehsalının iki dəfə artmasına bərabərdir.

Başqa bir məsələ – polimer materialların davamlılığının miqdari cəhətdən proqnozudur. Əgər polimerlərin etibarlı istismar müddəti aşağı düşərsə, bu zaman polimerdən hazırlanmış detalların ehtiyatı tükənməmiş onlar istifadədən kənarlaşdırılacaqdır. Bu isə iqtisadi cəhətdən sərfəli deyil. İstifadə müddəti artırıldığda isə polimer məmulatı iş əsnasında sıradan çıxa bilər ki, bu da qəzaya və ya daha ağır nəticələrə səbəb ola bilər.

Daha bir məsələ isə destruksiya prosesindən polimer məmulatların modifikasiya olunmasında bir metod kimi istifadə etməkdir. Bu metoddan triasetat sellülozadan hazırlanmış sapların nazik üst qatının hidrolitik destruksiyası zamanı müvəffəqiyyətlə istifadə olunur ki, bu da elektrikləşməyən, çirkətab (toz hissəciklərini özünə çəkməyən), yaxşı rənglənən parçaların alınmasında istifadə olunur. Belə ki, sapın üst qatının üzərində mürəkkəbefirli asetat qrupları əvəzinə (təbiətcə hidrofob olan və bu səbəbdən də elektrikləşən) hidroksil qrupları əmələ gəlir ki, onların da üzərində elektrik yükleri axıb gedir.

Dördüncü məsələ - artıq işlənmiş və ya qocalmış polimer məmulatlarının təkrar istifadəsi ilə bağlıdır. Həl-hazırda öz istifadə müddətini başa vurmuş polimer məmulatlardan ibarət tullantıların miqdarı kifayət qədər çox olduğu səbəbindən polimerlərin təkrar emalı, monomerlərin regenerasiyası, polimer tullantılarının pirolizi kimi məsələlər böyük aktuallıq daşıyır.

Ətraf mühitin mühafizəsi və iqtisadi məsələlər də mühüm problemlərdən sayılır. Polimer materiallar üçün xammal olan neftin daha uzaqlarda – şimal və şərqdə, dənizin dibində və yerin dərin qatlarında olduğu nəzərə al-

narsa, gələcəkdə polimerlərin qiyməti arta bilər. Polimer tullantılarının zibilxanalarda yandırılması isə külli miqdarda zəhərli maddələrin, eyni zamanda, sianid turşusu və doksinin əmələ gəlməsinə səbəb olur.

Altıncı problemi də qeyd etmək məqsədə uyğundur – bu, birdəfəlik istifadəyə malik öz-özünə parçalanan polimerlərin alınması və onların tətbiq sahələrinin axtarışı problemidir. Bu ideyanın məqsədi şarnir (həncəmə) qrupları ilə birləşmiş bloklardan polimer yaratmaqdır. Bir şərtlə ki, bloklar davamlı olmalı, şarnir qrupları isə bir şəraitdə davamlı (istismar zamanı), digər şəraitdə isə (istismardan sonra) davamsız olmalıdır. Belə şarnir qrupları bir qayda olaraq, işığa və hidrolitik proseslərə qarşı davamsızdır. Buna görə də istifadədən sonra tullanti halına keçən polimerlər bu qruplaşmalar üzrə asanca blok-oliqomerlərə parçalanırlar ki, bu maddələr də torpaqda yaxşı həll olur və sonradan bakteriyalarla məhv edilir.

1.1. Polimerlərin termiki destruksiyası (piroliz)

Termiki təsir nəticəsində və oksigensiz mühitdə polimer materiallar kimyəvi rabitələr üzrə parçalanırlar. Polimerlərin bu cür destruksiyası termiki destruksiya adlanır.

Polimer zəncirinin iki əsas parçalanma növü vardır: bu depolimerləşmə (polimerləşmə prosesinin əksi) və polimer zəncirdə mövcud olan istənilən rabitənin parçalanma ehtimalı eyni olan parçalanmadır.

Monomerin son radikaldan qopma sürətinin əmsali: $k \approx 10^{13} \cdot e^{-E/RT} s^{-1}$, burada $10^{13} - A - B$ rabitəsində A və B atomlarının rəqsi hərəkətlərinin miqdarını göstərən əmsaldır. $E = E_p + q$, burada E_p - monomerin makromolekula birləşməsinin aktivləşmə enerjisi, q - monomerin makrorađikala birləşmə istiliyidir (q nə qədər az olarsa, depolimerləşmə ehtimalı da bir o qədər çox olar).


Zəncirvari mexanizm üzrə polimerlərin termoparçalanmasını nəzərdən keçirək. Karbon zəncirli polimerin ümumişdirilmiş formulunu yazaq:

$\sim\text{CH}_2\text{-CHX-CH}_2\text{-CHX}\sim$, burada X – hər hansı heteroatom və ya qrupdur.


Əgər $\overset{\text{k1}}{\underset{\text{O}}{\text{X}}} \text{- C - OCH}_3$ qrup olarsa, bu zaman polimer polilme-

takrilatdır, X – xlor olduqda isə polimer polivinilxloriddir (PVX).

Polimerin parçalanması qıcıqlandırma mərhələsin-dən başlayır. Əksər hallarda bu parçalanma aşağıdakı kimi baş verir:





Polimer molekulunun belə qırılması nəticəsində iki radikal (molekul qalıqları) əmələ gəlir. Makroradikallar sonradan aşağıdakı sxem üzrə monomerin əmələ gəlməsi ilə nəticələnən depolimerləşmə prosesinə məruz qala bilər:




Polimer molekulun qırılması nəticəsində iki radikal əmələ gəlir (molekulun qəlpələri).


Növbəti iki mühüm mərhələ – zəncirin molekulda xili və molekularası ötürülməsi mərhələsidir:



Daha mühüm bir mərhələ makromolekulun destruksiyasıdır:




Zəncirin qırılması iki radikalın görüşməsi nəticəsində baş verir.



Qeyd olunan radikal parçalanma mexanizmindən başqa (bu mexanizm daha çox müşahidə olunur) ion tipli (əsas etibarilə poliformaldehid və başqa hidrozəncirli molekullar belə parçalanır) və molekul tipli parçalanma da mövcuddur.

Misal olaraq daha bir parçalanma – PVX-in parçalanmasını göstərək. Temperaturun artması nəticəsində polivinilxloriddən HCl molekulu ayrılır və ikiqat rabitə yaranır. Bu ikiqat rabitə sonrakı dehidroxlorlaşma üçün katalizator rolunu oynayır. Qeyd etmək lazımdır ki, bu rabitə PVX-nin parçalanmasını 10 dəfə artırır:



Bu zaman $\sim\text{CH=CH-CH=CH} \sim$ qrupu dehidroxlorlaşma prosesini $\sim\text{CH=CH} \sim$ qrupu ilə müqayisədə 1000 dəfə artırır və nəticədə PVX-də polien ardıcılılığı alınır.

Beləliklə, polimerin termiki parçalanması makromolekulun sonlarından (depolimerləşmə) və ya molekulun ortasından (təsadüfi baş verən paçalanma) başlaya bilər. Depolimerləşmənin qarşısını almaq üçün belə polimolekulun ucları blokada edilməlidir. Məsələn, polioksimetilendə (poliformaldehid) polimolekulun uclarını $-\text{OCH}_3$ qrupları ilə blokada etmək mümkündür:




Təsadüfi baş verən parçalanma molekulda rabitə enerjisi ilə təyin olunduğundan onun qarşısını almaq mümkün deyildir. Lakin bütün mövcud sərbəst radikalları sərbəst radikal reaksiyaları ingibitorlarının köməyi ilə neytrallaşdırmaq olar. Bu reaksiyaların mexanizmi aşağıda nəzərdən keçiriləcəkdir. Yüksək temperaturlarda termiki parçalanma piroliz də adlanır.

1.2. Polimerlərin termooksidləşdirici destruksiyası

Ancaq hidroperoksidlərin əmələ gəldiyi maye fazada üzvi – RH (polimerlər də daxil olmaqla) birləşmələrin oksidləşmə prosesinin mexanizmi aşağıdakı kimi ifadə oluna bilər:


Sxem 1.



k_1 sürət sabiti k_2 -dən dəfələrlə çox olduğundan alkil radikalları böyük sürətlə RO_2^\bullet peroksid radikallarına çevirirlər. Polimerin oksidləşmə sürəti bu zaman $W_{\text{O}_2} = W_i^{1/2} k_2 / k_6^{-1/2} [\text{RH}]$ düsturu ilə təsvir olunur, burada W_i – inisiatorla (qıcıqlandırıcı) aktivləşən oksidləşmə prosesinin sürətidir (adətən zəncirlərin əmələgəlmə və şaxələnmə sürətlərinin cəminə bərabərdir).


1.3. Ozonun təsirindən kauçuk, rezin və plastiklərin gəcalması

$\text{C}=\text{C}$ ikiqat rabitə saxlayan maddələrin ozonla reaksiyasının sürəti $\text{C}-\text{C}$ birqat ratibəli maddələrin ozonla reaksiya sürətindən 100 000 dəfə çoxdur. Buna görə də, ilk növbədə ozonun təsirindən kauçuk və rezinlər zərər çekir. Ozon ikiqat rabitə ilə qarşılıqlı təsirdə olaraq aralıq kompekləşmə əmələ gətirir.




Bu reaksiya 0°C -dən aşağı temperaturda kifayət qədər tez gedir. Kompleks iki cür çevrilməyə məruz qala bilər:

1) molozonid əmələ gətirə bilər:



və ya


2) olefinin (kauçukun) digər molekülləri ilə toqquşaraq ilkin maddələri əmələ gətirə bilər.



Eksperimental olaraq müşahidə olunan reaksiya sürətinin əmsali:

$k_{\text{müs. edilən.}} = k_{3,1} \cdot k_2 / k_2 + k_3$ (olefin fragməti)

İkiqat rabitəli əksər birləşmələr üçün $k_{3,1} 10^4-10^5$ l/mol·san təşkil edir. Doymuş birləşmələr üçün ozon sadəcə olaraq adı oksidləşmə reaksiyasının inisiatoru (qıcıqlandırıcısı) rolunu oynayır.




Kauçuk və rezinlərin ozonun təsirindən baş verən destruksiyasının qarşısını almaq üçün əsas yol ozonun kauçuk və rezində mövcud olan ikiqat rabitə ilə qarşılıqlı təsirə daxil olmazdan əvvəl ozonla daha tez reaksiyaya girə bilən maddələrin axtarışıdır.

1.4. Polimerlərin fotodestruksiyası

İşığın təsirindən polimerdə müxtəlif çevrilmələr baş verir ki, bu da sonda onun dağılmamasına götərib çıxarır. Günəş işığı $\lambda > 200$ nanometr dalğa uzunluğu olan kvantlardır. Yer səthində qısalalğalı spektr sərhədi $\lambda = 290$ nanometrə uyğun gəlir. 200 nanometrdən 290 nanometrədək dalğa uzunluqlu işığın bir hissəsi atmosferlə

ətrafa yayılır. Ultrabənövşəyi şüaların bu sahəsində doymuş karbohidrogen molekulları işığı uda bilmir. Ultrabənövşəyi şüaların $\lambda > 290$ nm dalğa uzunluğunda işiqi oksigen və azot daşıyan qruplar, ikiqat rabitələr, aromatik nüvələr, dəyişkən valentli metal birləşmələrinin qarışıqları (polimerləşmə katalizatorlarının qalıqları) udurlar. İşığın udulması, radikalların əmələ gəlməsi və polimerlərin destruksiyası ilə müşayiət olunur. Əgər polimerin daxilində onun oksidləşmə məhsulları varsa, məsələn ketonlar, bu zaman bu maddələr polimerin (RH) parçalanma reaksiyasının fotoinişiatorları (aktivləşdiriciləri) rolunu oynayırlar.




Sxemin davamı oksidləşmə prosesinə uygun olaraq göstərilir.



1.5. Polimerlərin radiasiyanın təsirindən destruksiyası

İşiq udularkən onun tezliyi molekulun udulma tezliyinə uyğun gölərsə, radiasiya enerjisi bütün molekullarla udularaq ionlaşma aktını yaradır və molekullar həyəcanlanmış vəziyyətə keçir. İonlaşdırıcı şüalanma 2 növə - korpuskulyar (elektronlar, protonlar, neytronlar, alfahissəciklər, elektron verən atomlar) və elektronaqnit şüalanması (rentgen şüalanması, qammaşüalar) növlərinə ayrıılır.


«A» maddəsinin ionlaşdırıcı şüalanma ilə qarşılıqlı təsirinin ilkin reaksiyasının sxemini verək:



Burada A^+ - müsbət yüksələnmiş hissəcik, e^- - elektrondur.





(həyəcanlanmış hissəciyin radikal parçalanması)



(polimerdən hidrogen atomunun qopması)

Sonra oksidləşmə prosesi davam edir.

Şüalanma nəticəsində molekullar nəinki qırılır, bu zaman tikilmə də baş verə bilər. Kauçukun radiasiya nəticəsində vulkanlaşma prosesinin sxemi aşağıdakı kimidir:




Polietilenin də radiasiya nəticəsində (radiasyon) vulkanlaşması bu sxem üzrə baş verir.

1.6. Polimerlərin hidrolitik destruksiyası

Məlumdur ki, hidroliz prosesi radikal mexanizmi üzrə deyil, ion mexanizmi üzrə baş verir. Bu hal hidroliz prosesinin qarşısını almaq üçün antioksidantlardan istifadə etmək imkanını yox edir. Hidrolizin sürətinin aşağı salınmasında əsas metod – aqressiv mühitin (su, əsaslar, turşular və duzlar) polimer matritsaya çatdırılmasını

çətinləşdirməkdir. Misal olaraq amid rabitəli (kapron, naylon) birləşmələrin turşu ilə hidrolizini göstərmək olar:



Amid rabitəsinin elektron quruluşu protonlaşmanın iki mümkün yolunu müəyyən edir: amid qrupundakı azota və karboksil qrupundakı oksigenə görə protonlaşması. Birinci forma reaksiya qabiliyyətlidir, ikinci forma isə stabildir. Azotla protonlaşma sonradan oksigenlə protonlaşmanı qadağan edir və əksinə.

1.7. Polimerlərin mexaniki destruksiyası

Eyrinq və Uotsona görə polimerlərin mexanokimyəvi destruksiyasının mexanizmi $\text{R}' + \text{R}''$ yerdəyişmə qüvvəsi $\xrightarrow{\quad}$ $\text{R}'' + \text{R}'''$ sxemi üzrə gedir. Əmələ gəlmış makroradikallar havada peroksid radikallarına çevrilir və sonradan inisiatorun iştirakı ilə mexanokimyəvi reaksiya vasitəsilə aktivləşdirilmiş oksidləşdirici destruksiya prosesi baş verir. Mexaniki gərginliyin (σ) makromolekullara təsiri nəticəsində destruksiya reaksiyasının aktivləşmə enerjisi azalır və beləliklə də, prosesin sürəti artır. Destruksiyanın sürət sabiti

$$k = k_0 \cdot \exp(E - \gamma\sigma / RT) \text{ san.}^{-1} \text{-dir.}$$

Burada γ - proporsionallaşma əmsalıdır. Bu tənlik Jurkov tənliyil adlanır. Lakin bu tənlik bəzi adı hallarda əlverişlidir. Adətən, bu tənlik işlənilmir, çünki

mexanodestruksiya prosesi əksər hallarda daha mürəkkəb mexanizm üzrə baş verir.


1.8. Polimerlərin bioloji destruksiyası

Bioloji destruksiya dedikdə polimerlərin bakteriyalarla qarşılıqlı təsiri nəzərdə tutulur. Bu zaman, bir qayda olaraq, polimerlərin hidrolitik fermentativ parçalanma prosesi baş verir. Fermentlər xeyli böyük ölçüyə malik olduqlarından polimerlər matrisanın daxilinə nüfuz edə bilmir və polimerlərin bioparçalanması adətən, polimer məmələtin səthində baş verir.

Polimerlərin destruksiyasının yuxarıda nəzərdən keçirilən növləri arasında termoooksidləşdirici destruksiya daha geniş yayılmış və çox müüm əhəmiyyətə malikdir. Bir çox destruksiya növləri nəticə etibarilə termoooksidləşdirici destruksiyyaya gətirib çıxarır. Termoooksidləşmə ingibitorları – antioksidanlılar eyni vaxtda müxtəlif energetik və aqressiv təsirlərə məruz qalan polimerlərin stabillaşməsində əhəmiyyətli və yararlıdır.

2. Polimerlərin oksidləşməsi və destruktiv proseslərin aradan qaldırılması üsulları

Antioksidantların təsir mexanizmini aydın təsəvvür etmək üçün polimerlərin oksidləşmə proseslərini aşağıdakı piktoqram şəklində nəzərdən keçirək:




Səkil 1. Polimer materiallarının oksidləşmə mərhələlərinin sxemi

Piktoqramdan göründüyü kimi, müxtəlif energetik təsirlər və qarışıqlar polimerin destruksiyasına gətirib çıxaran radikal-zəncirvari oksidləşmənin iki dövrəsini əmələ gətirir. Göstərilən energetik təsirlər nəticəsində radikalların əmələ gəlməsi, bir qayda olaraq, polimerin karbohidrogen zəncirindən hidrogen atomunun qopması nəticəsində baş verir ($\text{RO}_2\cdot + \text{RH} \rightarrow \text{RO}_2\text{H} + \text{R}\cdot$ - zəncirin davamı reaksiyası, bax Sxem 1)

Polimerin təbiətindən asılı olaraq hidrogenin qopması makromolekulun müxtəlif yerlərində baş verir.





Doymamış polimerlər –



Poliamidlər –



Poliefirlər –



Poliasetallar -

1-ci cədvəldə polimerin oksidləşdirici destruksiya zəncirinin inkişaf prosesini müəyyən edən C–H rabitəsinin dissosiasiya enerjisinin qiymətləri verilmişdir.



Cədvəl 1. Karbon-hidrogen rabitəsinin dissosiasiya enerjisi (D_{R-H})

R-H	D_{R-H} , kkal/mol	Rabitənin tipi
$\text{CH}_2=\text{CH}-\text{CH}_2 - \text{H}$	85,1	Allil
$(\text{CH}_3)_3-\text{C} - \text{H}$	91,1	Üçlü
$(\text{CH}_3)_2-\text{CH} - \text{H}$	94,4	İkili


Antioksidantlar oksidləşmə tsikllərini istənilən mərhələdə qıra bildiyindən, adətən, 2 mühüm sinfə – sərbəst radikal akseptoru kimi təsir edən ilkin (baza) və ya əsas antioksidantlara və ikinci dərəcəli - hidroperoksidlərlə qarşılıqlı təsir nəticəsində molekulyar məhsullar əmələ gətirən antioksidantlara bölünür.

Polimerlərin ingibitor iştirakı ilə oksidləşməsi sxemini daha dəqiq aşağıdakı kimi göstərmək olar:

Sxem 2*.



*Oksidləşmənin elementar reaksiyaları üçün dünya ədəbiyyatında qəbul olunmuş nömrələnmədən istifadə olunmuşdur.




Sxemdə: RH – polimer, R^\bullet və RO_2^\bullet - uyğun olaraq alkil və peroksid makroradikalları, ROOH - polimer hidroperoksididir, InH – ingibitor – antioksident, In^\bullet - ingibitor - antioksidentin radikalı, m – hər hansı radikal və ya molekulyar məhsuludur ki, bu maddələrlə qarşılıqlı təsir nəticəsində öz xassələri ilə ilkın molekuldan fərqlənən yeni ingibitor-antioksident molekulu əmələ gəlir, i – antioksident xassəli ingibitor-antioksident və ya onun məhsullarının radikallarını göstərən və nəzərə alan indeksdir.

Sxemdə göstərilən bütün reaksiyaları ləngimə proseslərinə təsir nöqtəyi-nəzərindən dörd yerə - zəncirin əmələ gəlməsi, davamı, qırılması və molekulyar reaksiyalara bölmək olar.

İngibitor-antioksidantın bir çox reaksiyalarda iştirak etməsinə baxmayaraq, yalnız bəzi əsas reaksiyalar prosesin ləngiməsini qərarlaşıdır. İlk növbədə, bu, InH ingibitor-antioksidantın oksidləşməsinin aktiv mərkəzi – RO_2^{\bullet} peroksid radikalı ilə qarşılıqlı təsir reaksiyasıdır (7). Belə reaksiyalara həmçinin (8), (9) və (11) reaksiyaları, ingibitor-antioksidantın sərbəst radikalının molekulyar məhsul əmələ gəlməsi istiqamətində gedən rekombinasiya reaksiyalarını və aktiv radikalların qeyri-aktiv radikallarla əvəz olunmasına gətirib çıxaran dəyişmə reaksiyalarını (14), (15), həmçinin ingibitor-antioksidant molekulunun regenerasiya (-7), (9), (10) və (11) reaksiyalarını göstərmək olar.

3. Əsas antioksidantlar – radikal akseptorları

Əsas antioksidantlar oksidləşmə zəncirini üç əsas radikal tipi - alkil, alkoksil və peroksid radikalları ilə qarşılıqlı təsir nəticəsində qırır (şəkil 2).



Şəkil 2. Radikal akseptorlar vasitəsi ilə oksidləşmə zəncirinin qırılması sxemi


Fəzavi-çətinləşmiş fenollar və ikili aromatik aminlər peroksid radikalları ilə qarşılıqlı təsirdə olaraq oksidləşmə tsiklini qırmaqla oksidləşməni ləngidir (7-ci reaksiya, sxem 2). Bu reaksiya analoji reaksiya - zəncirin davamı reaksiyası ilə rəqabət aparsa da, o, daha sürətlə gedir. Məsələn, kumilperoksid radikallarının reper antioksidant olan 2,6-di-tret-butil – 4 metilfenolla (ionol) qırılmasının sürət əomsalının 333 K-də zəncirin davamının sürətinə nisbəti təxminən $k_7/k_3 \approx 10^4$ - ə bərabərdir. Bu səbəbdən polimerin peroksid radikalları əsas antioksidantlarla daha yaxşı qarşılıqlı təsirdə olur və zəncirin inkişaf reaksiyaları zəifləyir. Əmələ gəlmış antioksidant radikalları bir qayda olaraq, passivləşdirmə prosesini gücləndirməklə zənciri 2-ci dəfə qırır (reaksiya 8, sxem 2). Peroksid radikalları ilə qarşılıqlı təsir sürətinin çox fərqlənməsi səbəbindən əsas antioksidantlar polimerə çox az miqdarda əlavə olunur. Məsələn, termoplastik polimerlər üçün - 0,01- 0,05 kütə %-i, doymamış elastomerlər və akrilonitril-butadienstirool sopolimerləri üçün - 0,5-2 kütə %-i istifadə olunur.

3.1. Fəzavi-çətinləşmiş fenollar

Fəzavi-çətinləşmiş fenol tipli antioksidantların təsir mexanizmi ionol misalında göstərilmişdir (şəkil 3).

Passivləşdirmə zamanı antioksidantdan təkrar ingibitor aktivliyi göstərən məhsullar – məsələn, xinonlar alına bilər ki, (3-ci şəkildə 2, 3 və 5-ci birləşmələr) bunlar da alkil radikalları üçün yaxşı akseptor rolunu oynayır.

Aminli birləşmələrdən fərqli olaraq fenol tipli antioksidantlar polimerin rəngini dəyişmir və onlar eyni zamanda rənglənmiş polimer materiallarını rəngsizləşdirə bilməyən birləşmələr sinfinə daxildirlər.



Şəkil 3. Fəzavi-çətinləşmiş fenol tipli antioksidant – 2,6 – di-tret-butil – 4 metilfenolun ingibitor iştirakı ilə oksidləşmə mərhələsində çevrilmələrinin sxemi.

Orto-vəziyyətdə heç olmasa bir böyük alkil qrupu olan fenol-hidroksil qrupu sterik mühafizə olunmuş olur və yüksək antioksidantlıq xassələri göstərir. Göstərilən fəzavi çətinləşmələr 10-cu reaksiya üzrə (sxem 2) fenoksil radikallarının polimer zəncirdən - substratdan hidrogen atomunu qoparması qabiliyyətini azaldır. Bu akt (reaksiya 10) peroksid radikallarının yenidən yaranmasına və zəncirin inkişafına götirib çıxarır ki, nəticədə antioksidantın aktivliyi kəskin aşağı düşür.


Para vəziyyətdə olan metil qrupunun üçlü alkil qrupu ilə əvəz olunması antioksidləşmə aktivliyini azaldır. Meta vəziyyətdə olan alkil qrupları orto-əvəzedicilərin

iştiraki ilə orto-para əvəzedilmiş fenol antioksidantlarına xas olan yüksək aktivliyi saxlamaqla və təkrar əvəzətmə effekti adlanan prosesi reallaşdırmaqla özlərini paravəziyyətindəki əvəzediciləri kimi aparırlar. Praktiki olaraq senayedə istifadə olunan bütün fenol tipli antioksidantlar bu effekt üzərində qurulmuş və orto-para vəziyyətlərdə müxtəlif əvəzedicilər daşıyırlar. Sian və karboksi qrupları kimi güclü elektron-akseptor qrupları fenolun peroksid radikalına hidrogen atomunun ötürməsi qabiliyyətini aşağı salır və bununla da antioksidantın effektivliyini azaldırlar.

Ümumiyyətlə, sterik əvəzlənmiş fenolun polimerlər üçün antioksidant kimi effektivliyi onun radikalları tutub saxlama qabiliyyətinin dərəcəsindən, polimer matrisada həll olmasından, materialın müxtəlif şəraitlərində istismarı zamanı uçuculuq dərəcəsindən asılıdır. 2-ci cədvəl fenollardan antioksidantlar kimi səmərəli istifadəsi edilməsi üçün bu faktorların əhəmiyyətini daha aydın əks etdirir.

Cədvəl 2. 140°C emperaturda polipropilendə (PP) hidrodarçın turşusunun efirlərindən ibarət antioksidantların həllolma və uçuculuq xassələrinin onların effektivliyinə təsiri

n	t ^{1/2} , saat **	PP-də antioksidantın istifadə müddəti, saat		Dodekanda istifadə müddəti, saat
		O ₂ -nin udulması	Hava axımında	
1	0.28	95	2	25
6	3.6	312	2	23
12	83	420	2	20
18	660	200	165	20



(6)


** - 140°C -də azot axınında antioksidantın polipropilendə (PP) yarımparçalanma dövrüdür.

3,5-di-tret-butil-4-hidrodarçın turşusunun alkil efirlərinin ekvimolyar miqdarı polipropilendə (PP) müxtəlif şəraitdə 140°C -də sinaqdan keçirilmişdir. Hava axınında aparılan sinaqlarda yalnız yüksəkmolekullu oktadesil efiri (6-cı birləşmə, $n = 18$) polipropilendə yüksək aktivləşmə effekti nümayiş etdirir. Eyni şəraitdə daha aşağı molekullu homoloqlar yüksək uçuculuq xüsusiyyətinə malik olması səbəbindən effektiv olmamışdır.


Buxarlanma ilə bağlı itkilərin minimuma salan qapalı sistemdə oksigenin udulmasına görə aparılan sinaqlar homoloqların müxtəlif effekt göstərməsini müəyyən etmişdir. Bu müxtəlifliyi homoloqların polipropilenin amorf fazasında fərqli dərəcədə həllolması ilə izah etmək olar. Dodekanda maddələrin həll olması praktiki olaraq eyni olduğundan müxtəliflik yox olur və maddələr eyni effektivliyə malik olur.

Stabilizatorun molekuluna uzun alifatik fragmentlərin daxil edilməsi antioksidantların uçuculuq xüsusiyyətini aşağı salır və karbonzəncirli polimerlərdə onların həllolmasını artırır. Bu faktorlar, şübhəsiz ki, yüksək molekullu fenol tipli antioksidantların istismar göstəricilərini yaxşılaşdırır, lakin antioksidantların aktiv tərkib hissələrinin ekvivalent kütləsini artırır. Bunun qarşısını almaq məqsədilə sənayedə, əsasən, aşağı ekvivalent çəkili və az uçucu olan di-, tri- və polifenol kombinasiyalı əsas fenol tipli


antioksidantların qarışığından istifadə olunur. Misal olaraq daha geniş yayılmış di- tri- və polifenol kombinasiyalı fenol tipli antioksidantları göstərmək olar ki, onlar da aşağıdakı polimerlərdə istifadə olunur: bisfenol 2,2' - metilen- bis (6 - tret-butil-4-metilfenol) və ya antioksidant 2246, trifenol-1,3,5 – trimetil-2,4,6 – tri (3,5-di- tret -butil-4-hidroksi-benzil) benzol və ya İrquanoks 330 və polifenol – tetra – (3- (4-hidroksi-3,5-di- tret -butilfenil) propioniloksimetil) metan və ya İrquanoks 1010:



(7)




(8)




(9)

3.2. Aromatik aminlər




törəmələrindən olan antioksidantlar peroksid radikallarının çox effektiv akseptorlarıdır və polimeri aşağıdakı sxemə uyğun qoruyurlar (şəkil 4.).

Onlar hətta asan oksidləşən üzvi polimerlərin – məsələn, doymamış elastomerlərin stabillaşması zamanı fenol tipli antioksidantlardan daha effektivdir. Lakin bu antioksidantlar və onların məhsulları 4-cü şəkildən göründüyü kimi, polikonyuqə olunan birləşmələrdən sayılır, polimeri rəngləmək xüsusiyyətlərinə malik olduğuna görə əsas etibarilə tünd hislə doldurulmuş materiallarda istifadə olunur.



Səkil 4. Aromatik aminlərin ingibitorlarının iştirakı ilə baş verən oksidləşmə reaksiyalarının sxemi

Digər antioksidant sinifləri ilə müqayisədə N,N'-diəvəzolunmuş-p- fenilendiaminlərdən – N-fenil-N'-(1,3-dimetilbutil)-p-fenilendiamin (Santoflex 13 və ya antioksidant 4020, birləşmə 10), daha geniş istifadə olunur.




(10)


Göstərilmiş amin tipli antioksidantlar doymamış elastomerləri aerob oksidləşmədən və ozonun dağıdıcı təsirindən effektiv mühafizə edir.

N,N'-di-sec-butil-p-fenildiaminin kimi alkilləşmiş para-fenilen diaminlərin kiçik dozalarından benzin və açıq rəngli neft məhsullarında antioksidləşdirici əlavələr kimi istifadə olunur.


Alkilləşmiş difenilaminlər (11) və dihidroxinolinin (12) və 2, 2, 4-trimetil-1,2-dihidroxinolin polimerinin (13) törəmələri polimer materiallarının p-fenilendiaminə nisbətən daha az rəngləyirlər və bu səbəbdən də yarımrəngləyici antioksidantlar sinfinə aid edilirlər. Dihidroxinolinin törəmələri həm də heyvanlar üçün yemək və əlavələrin stabilləşməsində istifadə olunur.



(11)




(12)



(13), $n = 0 - 6$


Difenilaminin törəməsi - 4, 4'- bis ($\alpha\alpha'$ - dimetilbenzil) - difenilamin (Nauqard 445, birləşmə 14) polimeri

rəngləməyə daha az meylli olduğundan mütəxəssislər tərəfindən onlardan həm plastik maddələrdə, həm də elastomerlərdə istifadə etmək tövsiyə olunur.




3.3. Fəzavi-çətinləşmiş aminlər

Fəzavi-çətinləşmiş aminlər poliolefinlər və digər polimer materiallar üçün fotodestruksiyaya qarşı mübarizədə daha effektivdirlər. Bu birləşmələr, əsas etibarilə antioksidant kimi deyil, işıq stabilizatorları kimi təsnifata ayrılır. Sənayedə istifadə olunan sterik əvəzolunmuş işıq stabilizatorlarının əksəriyyəti 2, 2', 6, 6' tetrametilpiperidinin (15) törəmələridirlər (dünya kimya ədəbiyyatında bu birləşmələr HALS kimi işaret olunur).




Bu stabilizatorlar, bir qayda olaraq, işığa davamlı antioksidantlar kimi təsir göstərirlər. Onların antioksididləşdirici təsirini aşağıdakı elementar aktlar şəklində göstərmək olar (şəkil 5).




Səkil 5. 2,2',6,6' tetrametilpiperidinin törəmələrinin antioksidləşdirici təsir mexanizmi

Bu mexanizmə əsasən, fəzavi-çətinləşmiş aminlərin törəmələri oksidləşmə zəncirini polimer-substratın peroksid və alkil radikalları ilə qarşılıqlı təsirdə olaraq qırır. Bu zaman NO^{\cdot} nitroksil radikalının yaranması zəncirin çoxsaylı qırılmasına və nəticədə antioksidantın tutumu və effektivliyinin artmasına götərib çıxarır. Bu səbəbdən də belə sterik-çətinləşmiş aromatik aminlər polimerə çox az qatılıqda əlavə edilir.

Qeyd etmək lazımdır ki, tərkibində nitroksil radikalı daşıyan maddələr stabil nitroksil radikalları sinfinə (iminoksil, azotoksid) aid olunurlar və sintetik üsullarla da alınır bilərlər. Onların əksəriyyəti fərdi olaraq tsiklik aminlərdən ayrılmış (I-VIII) və 2, 2', 6, 6' tetrametilpiperidin - 1 oksil (I) birləşməsi əsasında sintez edilmişdir.





Xarici ədəbiyyatda 2,2',6,6' tetrametilpiperidin -1 oksil (I) stabil radikalı TEMPO adını daşıyır. Bu radikalın stabililiyi nitroksil fragmentin 4 ədəd qonşu metil qruplar tərəfindən törədilən fəzavi ekranlaşma ilə bağlıdır.


Stabil nitroksil radikalları alkil radikallarının effektiv akseptorlarından sayılırlar və oksidləşmənin ilk mərhələsində zənciri qırmaqla substratın (polimerin) alkil radikallarının peroksid radikallarına çevirildiyi 2 reaksiya (sxem 2) ilə rəqabət apara bilən antioksidantlar tipinə aid edilirlər. Antioksidləşmənin elə bu mexanizmi üzrə digər alkil akseptorları - xinonlar, yod, kondenslənmiş aromatik birləşmələr, həmçinin nanokarbon birləşmələri, əsasən də, fulleren və karbon nanoboruları da təsir göstərirlər.

Son illərdə HALS-ın polimer materiallarının tərkibində termo-oksi stabillaşdırıcı funksiyası da sübuta yetirilmişdir. Maye model sistemlərdə və bir sıra poliolefinlər üzərində aparılmış sınaqlar nəticəsində qəti müəyyən olunmuşdur ki, Chimassorb, Lowilite, Cyasorb və s. sinfinə aid məlum sənaye tipli HALS işq stabilizatorları termooksidləşdirici destruksiyanın qarşısının alınmasında

çox güclü effekt göstərilər. Bu antioksidantların model kumilalkil radikalları ilə qarşılıqlı təsirinin sürət sabitləri hesablanmış və 333-353K temperatur intervalında 10^7 - 10^8 l/mol·san. kimi yüksək göstəricilərə malik olduqları tapılmışdır.

3.4. Hidroksilaminlər

Hidroksilaminlər, demək olar ki, nisbətən yeni stabilizatorlar sinfinə daxildirlər və sənayedə tətbiqi 1996-cı illərə təsadüf edir. Bu birləşmələrin təsir effekti oksidləşmə reaksiyalarında hidrogen atomunun çox güclü donoru və sərbəst radikal akceptoru kimi çıxış edən hidroksilamin qrupu ilə bağlıdır (şəkil 6).



Şəkil 6. Hidroksilaminlərin antioksidləşdirici təsir mexanizmi. $**R\cdot$ = alkil radikalı


Hidroksilaminlərin istifadəsi zamanı çox maraqlı bir fakt nəzərə alınmışdır. Belə ki, təsir effektinə görə ekvivalent çəki miqdarına hidroksilaminlərin təkcə fenol

tipli antioksidantlarla deyil, həmçinin polimer ərintilərinin fosfit tipli stabilizatorları ilə də müqayisə oluna bilməsinə baxmayaraq, onlar ərintidə polimerlərin emalı zamanı sərbəst radikal akseptorları kimi bərk polimerlərin uzunmüddətli termoqocalmasında olduğundan daha böyük effektə malikdirlər. Başqa sözlə, hidroksilaminlər radikal akseptoru kimi əsas fenol tipli antioksidantlardan daha fərqli temperatur intervalında özlərini büruzə verirlər.

Poliolefinlərin stabilizasiyası üçün bir qayda olaraq alkiləvəzlənmiş hidroksilaminlərdən istifadə olunur.

3.5. Benzofuranonlar (laktonlar)


1997-ci ildə benzofuranonlar adlı yeni perspektivliyə malik antioksidant sinfi irəli sürüldü ki, bu maddələrin də təsir mexanizmi yalnız polimerin avtooksidləşməsini ləngitmək xüsusiyəti ilə deyil, həmçinin bu prosesin inkişafının ilkin mərhələlərində onun tam olaraq qarşısını alması ilə səciyyələnir. Benzofuranonların belə qeyri-adi stabillaşdırma aktivliyi benzil qrupunun zəif birləşmiş olan hidrogen atomunu ötürməsi hesabına stabil benzofuranil radikallarının öz-özünə əmələ gəlməsi ilə bağlıdır (Şəkil 7).



Şəkil 7. Arilbenzofuranonların əsas antioksidləşmə mərhələləri. $R\cdot$ = karbon və ya oksigen-mərkəzli radikaldır.

Rezonans-stabilləşdirilmiş benzofuranil (laktonil) radikalları ya dimerləşə, ya da digər sərbəst radikallarla qarışlıqlı təsirdə ola bilirlər (Şəkil 8).

Model eksperimentlər vasitəsilə müəyyən olunmuşdur ki, benzofuranonlar hidrogenin aktiv donoru olmaqla sərbəst karbon mərkəzli alkil, həmçinin oksigen -mərkəzli alkoksil və peroksid radikallarının akseptoru rolunu oynayır, başqa sözlə, benzofuranonlar çoxmərkəzli təsirə malik antioksidantlardandırlar.



Şəkil 8. Karbon-mərkəzli radikalların arilbenzofuranonlarla tutulması mexanizmi

Bir daha qeyd etmək lazımdır ki, əsas fenol tipli antioksidantlar oksidləşmə zəncirini əsas etibarilə oksigen-mərkəzli alkoksil və peroksid radikalları ilə qırıldığı halda, benzofuranonlar bütün tip radikallar üçün akseptor rolunu oynaya bilirlər. Bu səbəbdən benzofuranonlardan adətən polimerlərin oksidləşmə prosesinin şaxələnməsinin qabağını alan əsas inqibitorlar kimi istifadə olunur. Qeyd etmək lazımdır ki, karbon-mərkəzli radikal akseptorları - stabil nitroksil radikalları, fullerenlər və nanorkarbon boruları və

lifləri, materialın «destruksiyasına nəzarət» rejimində işləyən ənənəvi fenol, amin və fosfit stabilizatorlarından fərqli olaraq daha çox «qarşısını alan - preventiv» stildə təsir göstərən stabilizatorlardandır.

Hidroksilaminlər kimi benzofuranonlar da ekvivalent çəki miqdardında polimer ərintiləri üçün əsas fenol və fosfit tipli antioksidantlardan daha effektiv stabilizatorlar sayılır.

Bu səbəbdən də benzofuranonların temperatur intervalları ənənəvi sənaye tipli əsas antioksidantlara nisbətən daha yüksəkdir ki, bu intervalda da onlar daha güclü effektivliyə malikdirlər.


3.6. Xinonlar

Xinonların bəzi tipləri alkil R· radikallarının effektiv akseptoru olan birləşmələr sinfinə aiddirlər. Əsas etibarilə bu birləşmələr 1,4- benzoxinoxonun törəmələridirlər.



3-cu şəkildə göstərildiyi kimi, ingibitor iştirakı ilə gedən proseslər nəticəsində fenol tipli antioksidantlardan antioksidləşmə aktivliyinə malik 2, 3 və 5 birləşmələri kimi məhsullar alına bilər. Bu birləşmələr polimerə oksigenin məhdud miqdardında və diffuzion nəzarət şəraitində daxil edilməsi zamanı termooksidan kimi istifadə oluna bilər. Lakin onlar polimerlərin işıqstabillaşması zamanı daha effektivdir.

Ədəbiyyatda xinonların digər törəmələri - xinonometidlər (şəkil 9) də öz əksini tapmışdır ki, onlar da xüsusi ingibitorlaşdırma aktivliyinə malik birləşmələrdir. Buna baxmayaraq, polimerdə onların aktivliyi 120°C temperatur həddində məhdudlaşır. Eyni zamanda xinonometidlər fenol tipli antioksidantlardan «in suti» əmələ gəldiyi təqdirdə poliolefinlər üçün stabilizatorlar kimi daha effektivdir.




Şəkil

9. Xinonometidlərin nümayəndələri

Qeyd etmək lazımdır ki, antraxinonlar və onların törəmələri isə əksinə, üzvi substratların oksidləşməsində fotosensibilizator rolunu oynayırlar.

Molekulunda hər iki ingibitorlaşdırma funksiyasını - alkil və peroksid radikalları akseptoru daşıyan birləşmələr, məsələn, fenol-xinonometidlər və bis-fenol-aminoxinonlar antioksidant kimi geniş yayılmışlar (şəkil 10).



Şəkil 10. Çoxfunksiyalı təsirə malik antioksidantlar - fenol-xinonometidlər və bis-fenol-aminoxinonlar


Bis-fenol-aminoxinon birləşmələri sinfi poliolefinlərdə yüksək stabilləşmə xüsusiyyəti göstərmişlər. Belə ki, bu birləşmələr işığın, ultrabənövşəyi şüalanmanın təsirindən və

ya metal qarışıqları ilə (məsələn, mislə) qıcıqlandırma nəticəsində yaranan oksidləşdirici destruksiyani effektiv şəkildə stabillaşdırır bilirlər. Bundan əlavə, qeyd olunan stabilizatorların özləri də çox yüksək termodavamlılığı malikdirlər.

3.7. Karbon hisi və polikondensləşmiş aromatik karbohidrogenlər

Bəzi oksidləşmə ingibitorlarının, xüsusilə də, təbii neft antioksidantlarının öyrənilməsi zamanı müxtəlif kondensləşmiş aromatik və qarışq politsiklik birləşmələrin antioksidələşmə aktivliyinin nəzərə alınması problemi ilə qarşılaşmaq məcburiyyəti yaranır.

Ədəbiyyatdan politsiklik aromatik birləşmələrin karbohidrogen və polimerlərin oksidləşmə reaksiyalarında effektivliyi və mexanizmi barədə heç bir dəqiq və birmənalı məlumat yoxdur. Politsiklik aromatik karbohidrogenlərin aldehydlərin oksidləşmə reaksiyalarında yaxşı peroksid radikalı akseptoru, eyni zamanda, bəzi karbohidrogen və polimerlərin oksidləşməsində isə zəif peroksid və güclü alkil radikalı akseporu olması haqda ədəbiyyatda müəyyən məlumatlar verilir. Bu prosesin aşağıda göstərilən mexanizm üzrə baş verməsi ehtimal olunur:




Alkil radikalı qoşulmuş aromatik sistemə birləşərək aromatik qoşulmanı dien qoşulmasına çevirir, peroksid radikalı isə dien radikalı ilə disproportsiyaya daxil olaraq aromatik qoşulmanı bərpa edir. Konyuqali aromatik həlqələrin sayı çox olduğundan maddənin yaxşı qoruyucu


xassələri təmin olunur. Göstərilən mexanizm güclü kondensləşmiş sistemlərdə, oksigen üçün məhdudlaşdırılmış diffuziya şəraitində, məsələn, bərk polimerlərdə daha yaxşı təsir göstərir. Oksigenin kifayət qədər yüksək qatılığında ($10^{-2} \div 10^{-3}$ mol/l) alkil radikalları R^\bullet kəmiyyətə peroksid radikallarına RO_2^\bullet çevirilir ki, bunun da nəticəsində politsiklik aromatik karbohidrogenlərin ingibitor qabiliyyəti zəifləyir.

Kumol və stirolun inisiatorlu oksidləşmə model reaksiyalarının vasitəsi ilə aşağıda verilən politsiklik kondensləşmiş aromatik karbohidrogenlərin ingibitor aktivliyi təyin edilmişdir.


naftalin




fenantren



xrizen



perilen



Müəyyən olunmuşdur ki, həqiqətən də, göstərilən politsiklik karbohidrogenlər model karbohidrogenlərin peroksid radikallarına qarşı biganədirlər, lakin kumil və stirolalkil radikallarının yaxşı akseptorlarıdırılar. Bu zaman kondensləşmiş həlqələrin sayının çoxalması və uyğun olaraq, molekulda elektronların delokallaşma dərəcəsinin artması göstərilən birləşmələrin antioksidləşmə indeksini artırır.


Siloksan kauçuklarının radioaktiv şualanması nəticəsində yaranan destruksiyası zamanı antrasen (An) özünə sərbəst alkil radikallarını birləşdirərək $R - An - R$ və ya $R - An - An - R$ tipli birləşmələr əmələ gətirir. Aşağı temperaturda (77 K) naftalin, antrasen və fenantren aşqarları əlavə olunmuş polietilenin radiolizi zamanı polietilen makrora-

dikallarının politsiklik aromatik karbohidrogen əlavələri ilə tutulması müşahidə edilir.

Radikal mexanizmi üzrə gedən makromolekulyar reaksiyaların öyrənilməsi sahəsində aparılan xeyli sayıda işlər göstərmüşdir ki, karbon hisi alkil radikallarının effektiv akseptorudur. Onun alkil radikalları ilə qarşılıqlı təsirdə olması xassəsi stirolun, metilmətakrilatın, vinilasetatin toluol məhlulunda sərbəst radikal mexanizmi üzrə azobisisobutironitril (AİBN) və benzoil peroksid (BPO) inisiatorlarının iştirakı baş verən polimerizasyasının öyrənilməsi zamanı müşahidə edilmişdir. Qeyd olunmuşdur ki, göstərilən polimerizasiya prosesləri karbon hisinin təsirindən əhəmiyyətli dərəcədə ləngiyir. Stirol və 4-polivinilpiridinin, stirol və malein anhidrinin homo və sopolimerlərinin termiki disosiasiyası nəticəsində yaranan və zəncirin sonu 2,2',6,6'-tetrametil-1-piperidiniloksi (TEMPO) qruplarından ibarət bütün polimer radikallarının karbon hisinin polikondesləşmiş aromatik fragmənləri ilə birləşməsi faktı müəyyən edilmişdir.

3.8. Fulleren və karbon nanoboruları antioksidəşdirici inhibitorlar kimi

Karbonun yeni birləşmələrindən sayılan və bağlı karkas struktura malik olan fullerenlər 1985-ci ildə bir sıra ingilis və amerikalı alimlər qrupu tərəfindən lazerin təsiri altında qrafitin buxarlanmasından əmələ gələn karbon buxarlarında aşkar edilmişdir.




Şəkil 11. Fulleren C₆₀ və C₇₀-in molekul quruluşu

1996-ci ildə təbiətşünaslıq sahəsində Nobel mükafatına layiq görülmüş bu kəşf fullerenlərin unikal fiziki və kimyəvi xassələrinin öyrənilməsi üçün çoxsaylı tədqiqatların aparılmasına böyük stimul yaratmışdır.

Fulleren molekulları üzəri kondensləşmiş tsiklik sistemdə birləşən qoşulmuş birqat və ikiqat rabitələr sistemi ilə örtülmüş içi boş olan sferik formaya malikdir. Fullerenlərin bu cür elektron quruluşu molekullara güclü elektrofil xassələri verərək elektronları, sərbəst radikalları, anionları, hidrogen atomu kimi nukleofil hissəciklərini birləşdirmək qabiliyyətinin yaranmasına səbəb olur. Fullerenlər üçün elektrona hərislik (elektron qohumluğu) qiymətləri çox böyükdür və məlum fullerenlər üçün bu hədd 2,65 eV-dən (C₆₀) 3,5 eV-dək (C₈₄) təşkil edir. Elektronların intensiv olaraq birləşdirilməsi həmmərz substrati oksidləşdirir və fulleren nüvəsində mənfi yükün yaranmasına səbəb olur, sərbəst radikalların birləşməsi isə fulleren molekulunda ikiqat rabitənin qırılması nəticəsində qoşalaşmamış tək elektronun əmələ gəlməsinə gətirib çıxarır. Əgər birinci xüsusiyyət fullerenin oksidləşmə-reduksiya xassəsini stimullaşdırırsa, ikinci – sərbəst valentliyin yaranması ilə radikallarda zəncirin qırılmasını reallaşdırır.

Beləliklə, elektrona hərisliyin yüksək qiyməti bir çox elektron azlığı olan üzvi radikalların intensiv olaraq birləşdərilməsinə imkan yaradır. Misal olaraq, benzil və tret-butil radikallarının ikiqat fulleren rabitələrinə birləşməsini göstərmək olar. Bu səbəbdən hətta fullerenləri «radikal sünğərləri» də adlandırırlar. 12-ci şəkildə tret-butil radikalının fullerenin səthində birləşməsi nəticəsində əmələ gələn radikal adduktun piktoqramı göstərilmişdir.



Şəkil 12. C_{60} bakminsterfullerenin radikal adduktunun fraqmenti.

Alkil radikallarının fullerenlərə intensiv birləşməsi faktı, həmçinin aparılan tədqiqatlar nəticəsində bu reaksiya üçün alınan sürət sabitinin yüksək qiymətləri $k_{C_{60}+R\cdot} = 10^{8\pm 1} M^{-1}s^{-1}$ ilə də sübut olunmuşdur.

3-cü cədvəldə ədəbiyyatda mövcud olan müxtəlif radikalların C_{60} və C_{70} fullerenlərə birləşməsinin sürət sabitlərinin qiymətləri verilmişdir

Cədvəl 3. Radikalların C_{60} fullerenə birləşməsinin sürət sabitləri

R(radikal)	$k, M^{-1} s^{-1}$	T°K	Metod
$\cdot CH_3$	$(4.6 \pm 2.0) \times 10^8$	295	İmpulslu radioliz
$\cdot C(CH_3)_3$	$(2.2 \pm 0.5) \times 10^7$	293	EPR (spin tələsi)
$\cdot C(CH_3)_3$	3.0×10^9	293	EPR(lazer impulslu fotoliz / radioliz)
$\cdot CCN(CH_3)_2$	3.0×10^6	295	EPR (spin tələsi)
$\cdot CCN(CH_3)_2$	1.8×10^9	-	EPR impulslu radioliz
$\cdot CH_2Ph$	4.5×10^6	241	EPR (fotoliz)
$\cdot CH_2Ph$	6.7×10^6	263	EPR (fotoliz)
$\cdot CH_2Ph$	9.3×10^8	293	EPR (lazer impulslu fotoliz / radioliz)

$\cdot \text{CH}_2\text{Ph}$	2.7×10^5	293	EPR (spin tələsi)
$\cdot \text{CH}_2\text{Ph}$	$(1.4 \pm 0.2) \times 10^7$	298	EPR (fotoliz)
$\cdot \text{C}(\text{CCl}_3)_3$	$(2.7 \pm 0.5) \times 10^8$	293	EPR (lazer impulslu fotoliz / radioliz)
$\cdot \text{OOC}(\text{CCl}_3)_3$	2.0×10^6	293	EPR (lazer impulslu fotoliz / radioliz)
$\cdot \text{C}(\text{CCl}_3)_3$	1.3×10^9	-	Lazer impulslu fotoliz / radioliz)
$\cdot \text{CH}_2\text{CH}_2\text{Cl}$	2.6×10^9	-	EPR (lazer impulslu fotoliz / radioliz)
$\cdot \text{C}(\text{CH}_3)_2\text{Ph}$	$(2.0 \pm 0.8) \times 10^8$	333-353	Mayefazalı oksidləşmə model reaksiyası (kumol)
$\cdot \text{OOC}(\text{CH}_3)_2\text{Ph}$	$(3.1 \pm 1.1) \times 10^2$	303	Mayefazalı oksidləşmə model reaksiyası (kumol)
$\cdot \text{C}(\text{CH}_3)_2\text{Ph}$	8.1×10^5	295	EPR (spin tələsi)
$\text{CCl}_3\text{CH}_2\cdot \text{CHPh}$	8.5×10^5	295	EPR (spin tələsi)
$\cdot \text{C}_2\text{H}_5$	$(5.3 \pm 0.4) \times 10^6$	293	EPR (spin tələsi)
$\cdot \text{CH}_2(\text{CH}_2)_3\text{CH}_3$	$(4.5 \pm 0.4) \times 10^6$	293	EPR (spin tələsi)
$\cdot \text{CHCH}_3\text{C}_2\text{H}_5$	$(4.8 \pm 0.2) \times 10^6$	293	EPR (spin tələsi)
$\cdot \text{CH}_2\text{CH=CH}_2$	$(6.5 \pm 0.5) \times 10^5$	293	EPR (spin tələsi)
$\cdot \text{C=CH}_2\text{Ph}$ $(\text{C}_{60}/\text{C}_{70} : 3/1,$ hissə)	$(9.0 \pm 1.5) \times 10^7$	333	Mayefazalı oksidləşmə model reaksiyası (stirol)
$\cdot \text{C}(\text{CH}_3)_2\text{Ph}$	$(1.9 \pm 0.2) \times 10^8$	333	Mayefazalı oksidləşmə model reaksiyası (kumol)
$\cdot \text{C}(\text{CH}_3)_2\text{Ph}$ $(\text{C}_{60}/\text{C}_{70} : 93/7,$	$(2.3 \pm 0.2) \times 10^8$	333	Mayefazalı oksidləşmə model

(%)			reaksiyası (kumol)
· C(CH ₃) ₂ Ph (C ₆₀ /C ₇₀ : 3/1, doli)	(2.7 ± 0.2) × 10 ⁸	333	Mayefazalı oksidləşmə model reaksiyası (kumol)
· C(CH ₃) ₂ Ph (C ₇₀)	(3.0 ± 0.3) × 10 ⁸	333	Mayefazalı oksidləşmə model reaksiyası (kumol)

Beləliklə, fullerenlər zəncirvari proseslərdə, eyni zamanda polimerizasiya və destruksiya proseslərində effektiv sərbəst radikal akseptorları kimi iştirak edirlər. Bu proseslər alkil və alkil-peroksid radikallarının iştirakılə baş verir və bu səbəbdən də belə radikalların tutulmasını həyata keçirmək qabiliyyətinə malik birləşmələr tərəfindən ingibitorlaşmaya həssas sayila bilərlər. Həqiqətən də, C₆₀ və C₇₀ fullerenləri müvafiq eksperimental testlərdə polimerlərin termiki və termoooksidləşdirici destruksiyalarının ləngidiciləri kimi özlərini göstərirlər. Ədəbiyyatda fullerenlərin iştirakı ilə polimer kompozisiyalarının termiki və termoooksidləşdirici destruksiyyaları barədə kifayət qədər əsaslandırılmış işlər vardır. Bu işlərdə əsas etibarilə bir çox polimerlərdə baş verən destruksiya proseslərinə C₆₀ və C₇₀ fullerenlərin stabilizator kimi təsiri eks olunmuşdur.

Belə ki, fulleren C₆₀-in stabiləşdirici effektiinin məlum «Irganox 1076» polimer stabilizatorunun analoji effekti ilə demək olar ki, eyni olması iki üsulla sübuta yetirilmişdir: inisiator iştirakı ilə kumolun oksidləşməsinin model reaksiyasının köməyi ilə; və fulleren C₆₀ saxlayan polistirol (PS) və polidimetilsilosan (PDMS) kauçukunun termoooksidləşdirici destruksiya prosesində sürətləndirilmiş sınaqları zamanı.

Göstərilmişdir ki, C₆₀ və C₇₀ fullerenləri polimerlər üçün yüksək temperaturlu yeni antioksidantlardandır və oksidləşmədə istifadə olunan məlum ingibitorlardan daha yüksək effektivliyə malikdirlər. Müəyyən olunmuşdur ki,

PS-in termooksidləşdirici destruksiyası zamanı fulleren C₆₀ Ph₃Sb və fenil-2-naftilaminlə (neozon-D) sinergik qarışığı əmələ gətirir. Fullerenəsəslü bu sinergik qarışqları PS üçün yeni, effektiv yüksək temperaturlu antioksidant kimi təklif olunmuşdur.

Kütlə-spektrometrik termiki analiz və differensial-skan kalorimetriya (DSK) üsullarının köməyi ilə 1-4%-li C₆₀ və C₇₀ fullerenlərin iştirakı ilə poli-2,6-dimetil-1,4-fenilenoksid və onun qarışıqlarının termiki destruksiyası zamanı fullerenlərin stabiləşdirici effekti öyrənilmişdir. Müəyyən olunmuşdur ki, fulleren əlavələri termiki destruksiya proseslərini, qaz halında məhsulların alınması ilə gedən polimerlərin oksidləşdirici dağılıması və homolitik parçalanması proseslərini daha yüksək temperatur istiqamətinə yönəldir. Bu zaman fulleren C₇₀-in ingibitor xüsusiyyəti C₆₀-dan daha güclü olmuşdur.

Fulleren C₆₀ təbii kauçuk və sintetik sis-1,4 poliizopren üçün termiki stabilizator və antioksidant kimi tədqiq olunmuşdur. Bu tədqiqat əlavəsiz kauçuk nümunələri və təyin olunmuş müəyyən miqdarda fulleren əlavələri olan nümunələr üzərində aparılmışdır. Təcrübələr əvvəlcə təsirsiz qaz (azot) axını şəraitində, sonra isə paralel müqayisədici nəzarət ilə hava axınında aparılıraq termoqravimetrik (TQ) və differensial-termiki analiz üsullarından (DTA) istifadə olunmuşdur. Nəticələr göstərmişdir ki, fulleren oksigensiz mühitdə 1,4-poliizopren üçün effektiv termostabilizator kimi təsir effektinə malikdir ki, bu da onun, polimer zəncirinin termiki dağılıması nəticəsində əmələ gələn poliizopren makroradikalları ilə aktiv qarşılıqlı təsirdə olması ilə izah olunur. Əksinə, termooksidləşdirici destruksiya şəraitində (hava cərəyanında) fulleren C₆₀ yalnız müəyyən şəraitdə – temperaturun artma sürəti 5°C/dəq.-dən çox olmadıqda sis-1,4 poliizopren üçün antioksidant rolunu oynayır. Temperaturun daha yüksək artan sürətində (20°C /dəq.)

fulleren C₆₀ heç bir antioksidant effekti göstərmir. Bu məqalənin müəllifləri tərəfindən izah edilən bu fakt nəzəri cəlb etməklə yanaşı, daha böyük diqqətə layiqdir. Bu fakt intensiv oksidləşmə şəraitində (güclü hava axını, temperaturun kəskin artması) polimerin makroperoksid radikallarının qatılığının kəskin artımı zamanı fullerenin antioksidantlıq effektiininitməsini təsdiqləyir ki, bunun da səbəbi izah olunduğu kimi, fullerenin oksigen mərkəzli radikallara qarşı fullerenin indeferent (təsirsiz) olmasıdır. Bu məlumatlar kondensləşmiş sistemlərin aerob oksidləşmə proseslərində fullerenin ikili funksiyası haqqında bizim əvvəl irəli sürdüyümüz konsepsiya və son müasir tədqiqatların nəticəsi ilə yaxşı uzlaşır.

İzotaktik polipropilenin (i-PP) fulleren C₆₀, fullerenin levopimar turşusunun adduktu, nanokarbon və karbon hisi ilə termiki stabilləşməsi prosesləri xemilüminessensiya (XL) üsulunun köməyi ilə tədqiq edilmişdir.

i-PP nümunələrinin termiki oksidləşməsi hava atmosferində 170, 180 və 190°C temperaturda aparılmışdır. XL intensivliyinin qiymətlərinə əsasən, müxtəlif kinetik parametrlər – oksidləşmənin induksiya vaxtı, destruktiv çevrilmələr dövrünün 50%-i, oksidləşmə sürəti, XL-in maksimum intensivliyi və oksidləşmənin maksimum müddətləri hesablanmışdır. Stabilləşmənin təsir effektinə görə additivlər aşağıdakı aktivlik sırasına düzülə bilər: fulleren C₆₀ < nanokarbon < karbon hisi < fulleren C₆₀ adduktu.

Fulleren C₆₀-in polimetilmətakrilatin (PMMA) termiki və termooksidləşdirici destruksiyasına təsirinin öyrənilməsinə həsr olunmuş kifayət qədər işlər vardır.

0,06 % oksigen daşıyan helium axınında və 282, 238°C-də təmiz oksigen axınında DSK və TQ üsullarından istifadə etməklə fulleren C₆₀-in PMMA və PS-nin destruksiyasına təsiri istiqamətində tədqiqat işləri yerinə yetirilmişdir. Müəyyən olunmuşdur ki, fulleren C₆₀

polimerlərin destruksiyasını ləngidir. TQ üsulundan alınan nəticəyə görə, fullerenin iştirakı ilə baş verən proseslərdə polimerin kütləsinin azalmasının destruksiya zamanından asılılıq əyrilərində induksiya periodu nəzərə çarpacaq dərəcədə artır. DSK metodu ilə isə müəyyən olunmuşdur ki, fulleren C₆₀ polimerin destruksiyasının başlama temperaturunu kifayət qədər artırır. Tədqiqat işində fullerenin iştirakı ilə baş verən polimerlərin destruksiya mexanizminin bütün detalları nəzərdən keçirilmişdir. Alınmış nəticələrin ümumiləşdirilməsindən sonra belə fikir irəli sürülmüşdür ki, termiki destruksiya zamanı fulleren C₆₀-in ləngidici effkti, onun R[•] makroradikalları ilə qarşılıqlı təsirdə olaraq daha az aktiv birləşmələr əmələ gətirməsi ilə əlaqədardır. Eyni zamanda, qeyd olunmuşdur ki, PMMA-nın yüksək temperaturlarda termooksidləşdirici destruksiyası zamanı fulleren C₆₀-in ingibitor effekti, onun R[•] və oksigendaşıyan radikallarla qarşılıqlı təsirdə olaraq, daha az aktiv məhsullar əmələ gətirməsi ilə səciyyələnir. PS üçün isə fullerenin destruksiyani ləngidici rolu əsas etibarilə onun oksigen daşıyan radikallarla qarşılıqlı təsiri ilə izah edilməsinə baxmayaraq, fulleren C₆₀-in R[•] radikalları ilə qarşılıqlı təsiri də istisna olunmur.

Əlavə olaraq 5-15 mol/% vahid metilmətakrilatın PMMA-ya yeridilməsi qonşu somonomerlər arasındaki qarşılıqlı təsir nəticəsində anhidrid həlqələrin əmələ gəlməsi səbəbindən termooksidləşdirici destruksiyanın sürətini azaldır. Fulleren C₆₀ əlavəsi MMA-nın stirol, butilakrilat, qlisidilmətakrilat və hidroksietillmetakrilatla əmələ gətirdiyi sopolimerlərin termooksidləşdirici destruksiyasını uzun müddətə ləngidir. Aparılan tədqiqatlardan alınan nəticələr əsasında daha həqiqətə uyğun reallaşan sxemlər təklif olunur ki, bu da fulleren C₆₀-in sopolimerlərin termooksidləşdirici destruksiyası boyu yaranan makroradikallarla reaksiyasını tam əks etdirir və fullerenin ingibitor effektini tam təfərrüati ilə izah edir.

Eyni zamanda, «sərbəst radikallı PMMA-nın» termiki və termooksidləşdirici destruksiyası və bu proseslərə fullerenin təsirinin öyrənilməsindən alınan nəticələr təqdim olunmuşdur. Bu tədqiqatlarda DSK, TQ, DTA, diferensial-termoqravimetrik (DTQ) və kütlə-spektrometriya (KS) metodlarından istifadə olunmuşdur. Müəyyən olunmuşdur ki, PMMA-nın havada baş verən oksidləşdirici destruksiya-sı zamanı eyni vaxtda üç proses baş verir: polimer zəncirin qırılması ilə baş verən destruksiya; oksigenin polimer zəncirin daxilinə keçməsi və ya oksidləşməsi; destruksiya məhsullarının sublimasiyası.

Fulleren C₆₀-in az miqdarda sistemə əlavə olunması polimer zəncirdə fullerenin oksigeni əvəz etməsinə və ya tədricən polimeri oksidləşmədən «xilas etməyə» gətirib çıxarır ki, bunun da nəticəsində birinci mərhələdə yalnız az miqdarda destruksiya və oksidləşmə məhsulları əmələ gəlir. PMMA-nın oksidləşdirici destruksiyası zamanı C₆₀ molekulları iki qrupa bölünür:

- 1) PMMA makroradikalları ilə birləşmiş (təxminən 20%);
- 2) PMMA makroradikalları ilə birləşməmiş molekullar.

Fulleren C₆₀-in makroradikallarla birləşməyən bu molekulları da öz növbəsində oksidləşən və eyni zamanda oksidləşmə və destruksiya baş vermədən buxarlanan molekullara bölünür. Fulleren C₆₀-in termooksidləşdirici destruksiyaya ingibitor effekti əsas etibarilə iki prosesə – tərkibində fulleren daşıyan PMMA zəncirin yaranmasına və qeyri-zəncirvari ingibitorlaşmaya, yəni ləngiməyə gətirib çıxarır. PMMA matrisası da C₆₀-in termiki davranışına əhəmiyyətli dərəcədə təsr göstərir. Fulleren C₆₀-in bu cür özünü aparması PMMA-nın ataktik, anion, sindiotaktik və izotaktik növlərinə də şamil edilir. Bununla bağlı belə bir fikir irəli sürürlür ki, PMMA-nın termiki və termooksidləşdirici destruksiyasından alınan fullerensaxlayan polimerlər PMMA-nın oksidləşməsinin qeyri-zəncirvari ingibitorlaş-

ması ilə yanaşı, fullerenin stabillaşdırıcı effektinin yaranmasına da səbəb olur.

Fulleren C₆₀ həmçinin PMMA və metilmətakrilatın metakril turşusu ilə sopolimerlərinin yüksək temperaturlu oksidləşdirici destruksiyasını da ləngidir. Metilmətakrilatın metilakrilamidlərlə sopolimerləri PMMA-nın özünə nisbətən termooksidləşdirici destruksiyaya daha az məruz qalır. Fulleren C₆₀-in əlavələri bu zaman destruksiyani ləngidir.

Fulleren (C₆₀-C₇₀) polimer (PMMA, PS) sistemlərinin termiki və termooksidləşdirici destruksiyası zamanı fullerenin stabillaşdırıcı effekti üçün onun qatılıq həddi təyin edilmişdir ki, bu hədd də fullerenin polimerlərdə həll olmasından asılıdır. PS və PMMA üçün bu qiymətlər müvafiq olaraq 4×10^{-3} və 8×10^{-3} mol/ kq təşkil edir. Polimerlərin fullerenin iştirakı ilə baş verən termiki və termooksidləşdirici destruksiyası həmçinin ingibitorların effektiv təsirinin temperatur məhdudiyyətlərinin mövcud olması mövqeyindən də xarakterizə olunur. Fulleren C₆₀ və ya C₇₀ tərkibli əsas PS sistemləri üçün termiki destruksiyanın temperatur həddi 380°C-yə bərabər olduğu halda, əsas PMMA sistemləri üçün (müvafiq olaraq fulleren C₆₀ və fulleren C₇₀ üçün) bu parametr 339 və 336°C təşkil edir. Bu polimerlərin və polikarbonatın termooksidləşdirici destruksiyası zamanı 335-348°C temperatur intervalı fulleren C₆₀ üçün antioksidant kimi ən yüksək temperatur hüdudu olmuşdur. Bu maksimum temperatur həddi fullerenin intensiv oksidləşməsinin başlanmasına uyğun gələn temperaturdan, yəni 370°C-dən çox aşağıdır.

Kütlə spektrometriya termiki analiz üsullarından DSK, DTQ və rentgenanalizdən istifadə etməklə fullerendəsiyici iki tip polimer sistemin (FDPS) termiki və termooksidləşdirici destruksiya prosesləri öyrənilmişdir:

1) polimerlərlə kovalent rabitələr vasitəsi ilə birləşmiş fullerendən ibarət FDPS və

2) fulleren C₆₀-in polimerlərlə əmələ gətirdiyi qarışqdan ibarət olan FDPS. Bu qarışqda komponentlər arasındaki rabiṭə yalnız Van-der-Vaals qüvvələri hesabına reallaşır. FDPS-in hər iki növü üçün elektron akseptoru xassəsi müşahidə olunmuşdur. Birinci növün bəzi sistemlərində polimer komponentinin termiki stabilliyinin güclü artması qeydə alınmışdır; ikinci növ sistemlərdə isə fulleren C₆₀-in sərbəst radikallar üçün tələ rol oynaması xassəsi qabarıq tərzdə özünü göstərmüşdir. Polimer matrisanın fulleren C₆₀-in termiki davranışında əhəmiyyətli bərəcədə rolü olduğu müəyyən olunmuşdur. O cümlədən, fulleren polimerin destruksiyası zamanı baş verən kimyəvi proseslərdə xüsusi zond rolunu da oynaya bilər. Tərkibində 1-10 kütłə % C₆₀ (FDPS) olan PS və PMMA-nın müxtəlif nümunələri tədqiq edilmişdir.


Fulleren C₆₀/C₇₀ və C₇₀-in PS də göstərdiyi antioksidant xassələrinin təyini üzrə ikimərhələli tədqiqat işi yerinə yetirilmişdir. Birinci mərhələdə stirolun inişiator iştirakı ilə oksidləşməsinin model reaksiyasından istifadə etməklə, sonra isə PS-lə qarışıqlar üzərində aparılan sürətləndirilmiş sınaqlarda C₆₀/C₇₀ və C₇₀ fullerenlərin antioksidləşmə aktivliyi öyrənilmişdir. Müəyyən olunmuşdur ki, model reaksiyanın qıcıqlandırılma və oksidləşmə sürətləri C₆₀/C₇₀ və C₇₀ fullerenləri iştirak etdikdə nəzərə çarpacaq dərəcədə aşağı düşür. İlk dəfə olaraq stirolun alkil radikallarının 60°C-də fulleren C₆₀/C₇₀-ə birləşməsinin sürət Sabiti təyin edilmiş və bu qiymət $k_{(333K)} = (9.0 \pm 1.5) \times 10^7 \text{ M}^{-1} \text{ s}^{-1}$. DTA və TQA metodları ilə müəyyən olunmuşdur ki, fullerenlər polistirolun tərkibində polimerin termooksidləşdirici destruksiyası zamanı stabilləşdirici effekt göstərir. Bu zaman fullerenlə stabilləşmə effekti, fenol tipli Irganox 1010 və amin tərkibli Agerite White kimi güclü fəza-çətinləşmiş antioksidantlardan alınan analoji effektlə tam üst-üstə düşməsdür. Qeyd olunan işdə fullerenlərin ləngidici effektinin onların R[•] makroradikallarla qarlılıqlı təsirdə olaraq daha

az aktivliyə malik radikal adduktları əmələ gətirməsi ilə əla-qədar olması göstərilir.

Fulleren C₆₀ əlavələrinin butildən heptilədək poli-n-alkilakrilatların, və müvafiq olaraq PMMA-nın termo-destruksiyalarına və termiki davranışına təsiri öyrənilmişdir. Analiz dinamiki rejimdə, TQA-dan istifadə etməklə və piroliz qaz xromatoqrafiyasının köməyi ilə izotermik rejimdə 400-600°C temperatur intervalında aparılmışdır. Fullerenlər yaxşı məlum effektiv radikal akseptorları olduğundan parçalanma proseslərinin mexanizmini radikal yoldan qeyri-radikal səmtə çevirməklə akril polimerlərin termiki destruksiya proseslərinə əhəmiyyətli dərəcədə təsir edirlər. Poli-n-akrilatlar üçün fulleren əlavələri qeyri-radikal mexanizmi ilə reallaşan destruksiya prosesinin məhsullarından olan olefinlər və spirtlərin çıximini atır. Digər tərəfdən, əsas polimer zəncirin nizamsız qırılması nəticəsində baş verən piroliz prosesinin məhsullarının, yəni monomer, dimer, doymuş efir, trimer, müvafiq asetat və metakrelatin çıxımı aşağı düşür. Termoqrafimetrik eksperimentlər zamanı alınan və maksimum kütlə itkisinin baş verdiyi müəyyən olunmuş temperatur bir qədər artır ki, bu da fullerenin iştirakı ilə izah edilir. Poli-n-alkilmətakrilatların termiki davranışsı zamanı fullerenlərin effekti daha qabarıq şəkildə nəzərə çarpır. Maksimum kütlə itkisinin temperatur artımı 19-25°C təşkil edir. Tərkibində fulleren olan qarışqlar monomerin çıxımının əhəmiyyətli dərəcədə aşağı düşməsinə səbəb olur və eyni zamanda, əmələ gələn olefin və metakril turşusunun miqdarını artırır. Radikal akseptoru kimi təsir göstərən fulleren proseslərin inkişafını ləngidir və radikal olmayan qeyri-zəncirvari reaksiyalara gətirib çıxarır.

Karbon nanoboruları (şəkil 13) fullerenlər kimi yüksək elektrona hərislik, elektron qohumluğu xassəsi göstərməsi səbəbindən polimerizasiya və destruksiya

proseslərinin zəncirvari reaksiyalarında effektiv radikal akseptorları kimi hipotetik olaraq tövsiyə oluna bilərlər.



Şəkil 13. Birdivarlı karbon nanoborusu (SWCNT).

Karbon nanoborularının radikalları tutmaq və oksidləşmə zəncirini qırmaq kimi potensial xassəyə malik olmasına rəğmən, onların polimer materiallarının tərkibində müəyyən antioksidant və stabilizədirici funksiya yerinə yetirməsini gözləmək olardı.

Həqiqətən də, tərkibində aşqar kimi karbon nanoboruları daşıyan polimer kompozitləri şübhəsiz polimerdə Jouł istiliyinin generasiyasını yaradan yüksək sıxlıqlı elektrik cərəyanı daşımaq qabiliyyətinə malikdirlər. Bir sıra tədqiqatçılar polimer kompozitdən birbaşa cərəyan keçərkən onun yüksək dərəcədə qızmasını ($>200^{\circ}\text{C}$) müşahidə etmişlər. Buradan belə bir nəticə çıxarmaq olar ki, yüksək temperaturda karbon nanoborularının polimerin stabilliyinə necə təsir etməsini bilmək çox vacibdir. Bu məsələyə dair artıq müəyyən material mövcuddur. TQ və XL əyrilərinin profil görünüşünə əsasən, müəyyən olunmuşdur ki, karbon nanoboruları polietilen (PE), PS, PP və polivinilidenflorid əsaslı polimer kompozitlərində antioksidant kimi təsir göstərilər. Karbon nanoborularının 5%-dan qatılığının çox artırılması antioksidant effektiinin yalnız əhəmiyyətsiz dərəcədə artmasına gətirib çıxarır. Polivinilidenfloridə göldikdə isə, görünür, bu zaman karbonboruları həm antioksidant, həmdə halogenlərin adsorberi kimi təsir göstərə bilirlər.

Karbon nanoborularının ingibitor aktivliyinin təyin edilməsi sahəsində aparılan son işlər çox maraqlı nəticələr

vermişdir. Belə ki, alman alımları ilə birgə hazırlanmış la-yihə çərçivəsində, bu kitabın müəllifi tərəfindən kumolun inisiator iştirakı ilə oksidləşməsinin model reaksiyası üzə-rində aparılan təcrübələr belə bir faktın müəyyən edilmə-sinə imkan vermişdir ki, karbon nanoboruları yaxşı sərbəst radikal akseptorları olmaqla yanaşı antioksidant effekti də göstərilər. Lakin göstərilən bu effekt karbon nanoboru-larının tərkibində, əsas etibarilə bu boruların sintezində istifadə olunan katalizator qalığı kimi Fe, Ni, Co və başqa metal qatışqlarının olması səbəbindən əhəmiyyətli dərəcədə zəifləyir. Karbon nanoborularının aktiv stabillaşdırıcı rolü prinsipial planda PE, polietilenvinilasetat, polivinil spirti, polikarbonat, poliamid və PMMA-nın termiki və termook-sidləşdirici destruksiyasının tədqiqi zamanı müəyyən olun-musdur.


Bələliklə, analiz olunmuş material C₆₀ və C₇₀ fuleren-lərinin polimerlərin termiki və termooksidləşdirici radikal destruksiyası reaksiyalarda ehtimal olunan ingibitor və stabilizator kimi rolunu müəyyən edir. Xüsusi olaraq qeyd etmək lazımdır ki, əksər çap olunmuş işlərdə fullerenlərə əsasən karbonmərkəzli radikalların birləşməsi göstərilir ki, bu da fullerenlərin hər şeydən əvvəl antioksidant kimi deyil, termostabilizator kimi təsir mexanizminin üstünlüyünü təs-diqləyir.

3.9. Hidroperoksidlərin dağıdıcıları

100°C-dən yuxarı temperaturlarda peroksid və hidro-peroksidlərin sərbəst radikallara homolitik parçalanması baş verən prosesləri intensivləşdirir və oksidləşmə sürətini çoxaldır. Lakin bir sıra birləşmələr var ki, onlar da hidroperoksidlərlə aktiv qarşılıqlı təsirdə olaraq qeyri-radikal, molekulyar məhsullar əmələ gətirirlər. Hidroperoksidlərin radikalsız məhvədiciləri rolunu oynayan bu birləşmələrin vəzifəsi oksidləşmə prosesinin hidroperoksidlər vasitəsi ilə

qıcıqlandırılmış inkişaf mərhələsini maksimum dərəcədə aşağı salmaqdan ibarətdir. Bu birləşmələr polimer materialların stabillaşdırılməsi praktikasında geniş yayılmış və ikinci dərəcəli antioksidantlar adlandırılırlar (əsas fəzavi-çətinləşmiş fenol və ya aromatik amin tipli birinci dərəcəli antioksidantlardan sonra).

Məlum sənaye tipli ikinci dərəcəli hidroperoksid dağıdıcıları olan antioksidantların böyük əksəriyyəti ikivalentli kükürd və üçvalentli fosforun törəmələridirlər. Tiodipropion turşusunun dialkil efiri 20 moladək hidroperokсидi parçalamaq qabiliyyətinə malikdirlər. Bu birləşmələrin antioksidləşmə mexanizmini əks etdirən bəzi reaksiyalar 14-cü şəkildə verilir. Bu mexanizmə görə hidroperoksidlər spirtlərə çevrilir və sulfid qrupu bir sira stexiometrik reaksiyalar nəticəsində proton turşusu və Luis turşusunadək oksidləşir. Əmələ gələn məhsullar – sulfin (21), sulfon (22) və sulfat turşuları, həmçinin kükürd üç oksid hidroperoksidlərin radikalsız parçalanmasını kataliz etmək qabiliyyətinə malikdirlər və tiodipropion turşusunun əsas efirləri üçün hidroperoksidin parçalınmasında yaxşı dayaq rolunu oynayırlar.




Səkil 14. Tiodipropion turşusunun efirlərinin antioksidləşdirici təsir mexanizmi

Tiodipropion turşusunun efirləri aşağı temperaturda istifadə zamanı zəif antioksidant kimi təsir göstərilərlər. Lakin onların məkanı-çətinləşmiş fenollarla qarışqlarında bu birləşmələr geniş temperatur intervalında gözəl sinergik effekt göstərdiklərindən poliolefinlər, ABS plastik, zərbəyə davamlı PS kimi polimerlərin stabillaşdırılməsində geniş istifadə olunur. Lakin tiodipropion turşusunun efirlərinin çatışmayan cəhəti də vardır. Belə ki, polimerlərin yüksək temperaturda emalı zamanı onlar qismən destruksiyaya məruz qalırlar ki, bu zaman yaranan qoxu yeyinti məhsulları üçün polimer qablaşdırma materialının hazırlanmasında onları yararsız edir.



Tərkibində kükürd olan antioksidantlar kimi fosforun üçvalentli birləşmələri də hidroperoksidləri spirtlərə çevirir və eynilə olduğu kimi, əsas, birinci dərəcəli antioksidantlarla – fəzavi-çətinləşmiş fenollarla olan kombinasiyaları kauçuk və plastik kütlələrin stabillaşdırılməsində geniş istifadə olunur. Bu zaman onlar polimer materialın istifadə prosesi müddətində onun rənginin saralmasının qarşısını amaq kimi əlavə səmərəli xassəyə də malik olmaları ilə səciyyələnirlər. Bilavasitə fosfor tərkibli stabilizatorlar bəzi fenol və amin tipli stabilizatorlardan fərqli olaraq polimer materialların rəngini dəyişmirlər.

Alifatik spirtlər və adı aşağımolekullu fenolların törəmələrindən olan fosforit turşusunun efirləri, məsələn, tri-nonilfenilfosfit (24) asan hidroliz olduqlarından istifadədən əvvəl su və yaş atmosferlə kontaktdan mühafizə olunmaları üçün yüksək maksimum hazırlıq tələb edir.




Qeyd olunan hidroliz nəticəsində əmələ gələn fosforit turşusu aqressiv korroziyaya uğrama xüsusiyyətinə malikdir və xüsusilə də, yüksək temperaturda avadanlıq və cihazlar üçün böyük təhlükə daşıyır. Praktikada belə fosfitlərin hidroliz prosesi trietanolamin kimi azacıq miqdarda xüsusi əlavələrin köməyi ilə aradan qaldırılır.

Effektiv fosfitlərin alınmasında digər alternativ üslub onların sintezində fəzavi-çətinləşmiş fenppardan istifadə edilmişdir. Bu efirlər, məsələn tri-(2.4-di-tret-butilfenilfosfit) (25) və ya tetra-(2.4-di-tret-butilfenil)-4,4-bifenilen-difosfonit (26) hidroliz olunmaya qarşı nisbətən daha davamlıdır.




Son illərdə hidroperoksidlərin radikalsız parçalanmasını təmin etmək xüsusiyyətini saxlayan hidrolitik – stabil fosfitlərin alınması sahəsində əhəmiyyətli işlər görülür. Nəticədə dikumilfosfit kimi ikinci dərəcəli yeni sənaye tipli antioksidantlar hazırlanmış və polimerlərdə istifadədə üçün tövsiyə edilmişdir.

İkinci dərəcəli antioksidantları nəzərdən keçirərkən effektiv radikal akseptoru kimi yuxarıda təqdim olunan hidrosilaminləri də xüsusilə qeyd etmək lazımdır. Hidrosilaminlər radikalları tutmaq qabiliyyətinə malik olmaqla yanaşı, həmçinin sxemdə göstərildiyi kimi, hidroperoksidlərlə qarşılıqlı təsirdə olmaq kimi gözəl xüsusiyyətə də malikdir-lər (şəkil 15).



(burada R – alkil qruplarıdır – C₁₆H₃₃, C₁₈H₃₇, C₂₀H₄₁ və C₂₂H₄₅) və ya




Şəkil 15. Hidroksilaminlərin hidroperoksidlərlə qarşılıqlı təsir reaksiyaları

Bu zaman qarşılıqlı təsir nəticəsində spirt və nitron əmələ gəlir ki, sonuncu adıçəkilən maddə stabil nitroksil radikallarının prekursorudur. Beləliklə, hidroksilaminin bir molekulu birinci və ikinci dərəcəli antioksidant funksiyasını yerinə yetirməklə yanaşı, eyni zamanda, əlavə olaraq alkil radikalları akseptorlarını generasiya edir. Bu səbəbdən hidroksilaminlər polimer sənayesində güclü çoxmərkəzli təsir mexanizminə malik birləşmələr kimi tövsiyə olunurlar.

3.10. Metalların dezaktivatorları


Praktiki olaraq bürün polimer materiallarının tərkibində keçid metalların qatışıqları vardır. Bu qatışıqlar, bir qayda olaraq, polimerlərin sintezində istifadə olunan katalizatorların qalıqlarıdır. Keçid metalların qatışıqları hidroperoksidlərlə qarşılıqlı təsirdə olaraq, onları parçalamaqla, sərbəst radikallar əmələ gətirir və bununla da polimerlərdə oksidləşmə proseslərini güclü kataliz edirlər. Bir elektronlu keçidi reallaşdırın metallar – Cu, Co, Fe, Mn, Cr, Ni daha aktivdirlər. Qarşılıqlı təsir məlum Qaber-Veys sxeminə uyğun olaraq baş verir (şəkil 16):



Şəkil 16. Keçid metalların hidroperoksidlərlə qarşılıqlı təsirindən radikal hissəciklərin əmələgəlmə sxemi (Qaber-Veys sxemi)


Metalların oksidləşmə proseslərini kataliz etmək xassəsi polimer sistemə metal dezaktivatorlarının əlavə olunması ilə aradan qaldırıla bilər. Bu stabilizatorlar polimerdə metal ionlarını xelatlaşdıraraq, onların oksidləşmiş və reduksiya olunmuş vəziyyətləri arasındaki potensiallar fərqini artırırlar. Başqa sözlə, bu birləşmələrin metallarla kompleks əmələ gətirməsi Qaber-Veys sxemində bir elektronlu keçid enerjisini və metalların katalitik xüsusiyyətlərinin müvafiq dezaktivləşməsini əhəmiyyətli dərəcədə artırır.

Polimer materiallarda istifadə olunan sənaye tipli metal dezaktivatorlarına misal olaraq oksalil-bis (benzilden) hidrazid (27), N,N-bis-(3,5-di-tret-butil-4-hidroksitsinnamoil) hidrazin (28), 2,2 - oksamidobis-etil (3,5 – di-tret-butil-4-hidroksihidrotsinnamat) (29), N,N-(disalisiliden)-1,2-propandiamin (30), etilendiamintetrasirkə turşusu (31) və onun duzları, həmçinin, limon turşusu (32) kimi birləşmələri göstərmək olar.



4. Müxtəlif antioksidantlardan istifadənin temperatur intervalları

Yuxarıda göstərildiyi kimi, antioksidantların radikal akseptoru olması xüsusiyəti əhəmiyyətli dərəcədə temperatur intervalından asılıdır. 17-ci şəkildə əyani olaraq müxtəlif antioksidant sinifləri üçün 0°C -dən 300°C -dək effektiv temperatur intervalı göstərilmişdir.



Şəkil 17. Müxtəlif antioksidant sinifləri üçün effektiv temperatur intervalları.

Şəkildən göründüyü kimi, fenol tipli antioksidantlar ərimə temperaturundan aşağı temperaturlarda polimerləri mühafizə etmək qabiliyyətinə malik olmaqla, polimer materialların uzunmüddətli istifadəsi zamanı 150°C -dək temperatur şəraitində onları stabillaşdırmaqla yanaşı, ərimə temperaturundan yuxarı temperaturda da polimer ərintilərinin yaxşı stabilizatorlarından sayılırlar. Bu zaman qeyd olunan bu xüsusiyyət praktiki olaraq fenol tipli antioksidantlara aid edilir. Tiosinergistlər məkanı-çətinləşmiş fenollarla kombinasiyada polimerlərin ərimə temperaturundan aşağı temperaturlarda stabilizatorlar paketinin aktiv komponentlərindən sayılırlar. Müstəsna hallarda, tiosinergistlərdən ikinci dərəcəli polimer ərintilərinin stabillaşməsində istifadə olunur. Bu, bir qayda olaraq, təkrar emala məruz qalan və tərkibində yüksək miqdarda hidroperoksid qrupları olan materiallardır.

Fəzavi-çətinləşmiş aminlər praktikada ultrabənövşəyi UB işıq stabilizatorları kimi məlumurlar və cəni zamanда 150°C -dək temperaturda polimerlər üçün effektiv stabilizatorlar rolunu oynayırlar. Lakin daha yüksək temperaturlarda bu aminlər öz effektivliyini itirdiyindən onlardan polimer materiallar üçün polimer ərintilərinin effektiv stabilizatorları ilə kombinasiyada istifadə olunması tövsiyə olunur.

Fosfitlər, hidroksilaminlər və laktonlar polimerlərin ərimə temperaturlarında daha effektivdirler. Bu zaman onlar ya radikal akseptorları, ya da hidroperoksidlərin məhvədiciləri kimi təsir göstərirler. Lakin onlar verilmiş temperatur şəraitində istismarı zamanı bərk polimerlərin uzunmüddətli mühafizəsini təmin edə bilmirlər. Fosfitlər, hidroksilaminlər və laktonlar polimerlərin ərintidən emalı prosesində sərf olunaraq əhəmiyyətli dərəcədə fenol tipli

stabilizatorların vəzifələrini öz üzərinə götürməklə onların sərfini aşağı salır və bununla da polimer maddələrin qənaət olunmuş əsas fenol tipli antioksidantlarla sonrakı uzunmüddətli stabilləşməsini təmin edirlər.

Polimerlərin stabilləşdirilməsi nöqteyi-nəzərindən fəzavi-çətinləşmiş fenol tipli antioksidantlar sinfinə aid olan Tokoferol (E vitamini, Trolox) istisna təşkil edir. Ondan istifadə praktikası göstərmişdir ki, tokoferol duru polimerlər üçün daha effektiv stabilizatorlardır və bu səbədən də istehsalçılar tərəfindən əsas etibarilə axıcı-özlü halda polimerlərin emalında istifadə etmək tövsiyə olunur.

5. Antioksidantların kombinasiyası

Polimer materialların emalı və istismarı proseslərində müxtəlif növ destruksiyaların qarşısını almaq üçün praktikada stabilizatorlar paketindən istifadə daha məqsədə uyğun hesab olunur. Polimerlərin stabilləşdirilməsində istifadə olunan fenol və fosfit tipli birləşmələrin qarışqlarından ibarət antioksidant kombinasiyaları daha geniş yayılmışdır. Digər geniş yayılmış kombinasiyalar içərisində uzunmüddətli istismar prosesində bərk polimerlərin stabilləşdirilməsi məqsədilə istifadə olunan fenol tipli antioksidantlar və tioefirlərin qarışığından ibarət kombinasiyanı misal göstərmək olar. Fenol, fosfit və laktон tipli antioksidantlar kombinasiyası daha effektiv sistem hesab olunur. Belə ki, bu antioksidantlardan hər biri ayrıca stabilləşdirmə mexanizminə malikdir və polimerlərin stabilləşdirilməsində bir-birindən asılı olmadan təsir göstərirlər. Əgər polimerin rəngsizləşdirilməsi material üçün «fenolsuz stabilləşmə» tələb edən əsas faktorlardan sayılırsa, onda fəzavi-çətinləşmiş aminlər və hidroksiaminlərdən ibarət sinergik qarışqlardan istifadə olunur (benzofuranonlar və fosfitlər qarışığı). Bu halda ərintidə işlənmə və bərk halda uzunmüddətli istismar zamanı polimerin temperaturun təsirindən hərtərəfli mühafizəsi reallaşır və mate-

rialın işiqstabibiləşdiriciliyi təmin olunur. Belə stabilleşmə lentlərin, liflərin və poliolefinlərdən ibarət termoplastik materialların istehsalında geniş istifadə olunur.

5.1. Antioksidantların sinregik qarışıqları

Müxtəlif mexanizmlər üzrə fəaliyyət göstərən antioksidant qarışıqları sinergik və antoqonist ola bilər. Sinergik qarışıqlar polimeri hər bir antioksidantın ayrı-ayrılıqda göstərdiyi təsir effektlərinin cəminə nisbətən daha yüksək səviyyədə mühafizə edir. Başqa sözlə, sinergik effekt antioksidantların additiv effektini üstləyir. Radikal akceptorları və hidroperoksidlər dağıdıcılarının kombinasiyası praktikada istifadə edilən geniş yayılmış sinergik qarışıqlardandır. Optimal sinergik qarışq daha yüksək nəticələr alinanadək, onu təşkil edən maddələrin faizli nisbətinin çox zəhmət tələb edən eksperimental seçim yolu ilə yaradılır. Bu zaman müxtəlif sürətləndirilmiş sınaqlardan istifadə olunur ki, burada da əsas amil kimi polimer materialların iştismar parametrləri götürülür.

5.2. Antioksidantların antoqonist qarışıqları

Antioksidant qarışıqlarından istifadə zamanı bəzən son effekt additiv effektdən aşağı olur, yəni antioksidantlar bir-birinə mənfi təsir göstərilərlər. Misal olaraq, polimer materialların stabilleşməsi üçün fenol tipli antioksidantlar, iki-valentli kükürd birləşmələri və fəzavi-çətinrləşmiş aminlərdən ibarət stabilizator paketindən istifadə etmək olar ki, bu da prinsip etibarilə məmulatın istifadəsi zamanı onun ömrünün uzunmüddəti olmasını və materialın işiqstabilliyini təmin etməlidir. Lakin antioksidantların göstərilən ahəngdə birləşməsindən istifadə zamanı temperaturun təsirindən kü-kürdərkibli antioksidantların oksidləşməsi nəticəsində turşu məhsullarının alınması müşahidə edilmişdir ki, bu məhsullar aminlərlə qarşılıqlı təsirə girərək kompleks bir-

ləşmələr əmələ gətirirlər. Bununla da aminlər radikalları tutmaq xassəsini itirərək, radikal akseptorları kimi oksidləşmə mərhələsindən çıxırlar (şəkil 1). Bu antaqonizm tədqiqatçılara yaxşı məlumdur və təfərrüati ilə öyrənilərək istehsalçılara müvafiq tövsiyələr şəklində təqdim olunmuşdur.

Digər antaqonist qarşılıqlı təsirlər bir qayda olaraq sistemdə Brensted və Lyuis turşu və əsasları daxil olmaqla güclü turşu və ya əsasların olması ilə əlaqədardır ki, bu maddələr də antioksidantları kimyəvi çevirilmələrə cəlb etməklə qarşılıqlı təsirdə olaraq onların orijinal antioksidəşmə qabiliyyətini heçə endirərək bu birləşmələri polimerin stabilləşməsi prosesindən kənarlaşdırır.

6. Antioksidantların polimerlərdə tətbiqi

Parktiki olaraq bütün polimerlər materialın ilkin mü hüüm fiziki xassələrini saxlamağa zəmanət verən və polimer məmulatların ömrünün uzunmüddətli olmasını təmin edən antioksidant əlavələri tələb edir. Bu və ya digər antioksidant seçimi polimer materialın təbiətindən və onun işləmə şəraiti və tətbiq olunma məqsədindən asılıdır.

6.1. Poliolefinlər


Oksidləşdiricərlə tamada olarkən (oksigen, hava, ozon) oksidləşmə proseslərini ləngitmək üçün PE və PP-nin sintezindən dərhal sonra və onların izolyasiya olunmuş halda ayrılmışından əvvəl bu maddələrə aşağı qatılıqda antioksidant əlavə ($<0,01\%$) olunur. Daha yüksək qatılıqli əlavələr polimerin dənəvər şəklində formalaşmasının sonrakı mərhələlərində həyata keçirilir. Polimer materialın ümumi və ya xüsusi təyinathlı istiqamətdə olmasından asılı olaraq, istehsalçı tərəfindən antioksidant qarışığın komponentləri və qatılıqları seçilir.

Adi praktikada poliolefinlər ekstruziya, sıxılma və ya təzyiq altında tökmə prosesləri zamanı 300°C -dək tempe-

ratura məruz qala bilərlər. Bu zaman belə işlənməyə məruz qalan polimerlər onların özlülüyünün (başqa sözlə, ilkin molekulyar kütlənin saxlanması) təmin etmək) və rənginin dəyişməsinin qarşısını almağa imkan verən birləşmələrlə stabilizirlər. Belə stabilləşmə üçün fosfitlərdən, məsələn, tri-(2,4-di-tret-butilsfenil) fosfit (25) və ya bis-(2,4-di-tret-butilsfenil) pentaeritritol difosfitin oktadesil – 3,5 – di-tret-butil-4-hidroksihidrotsinnamat (6) kimi fenol tipli oksidantlarla kombinasiyasından istifadə etmək olar. Bu maddələr poliolefirlərin növündən və emal şəraitindən asılı olaraq 0,01-dən 0,5 kütłə %-dək qatılıqda götürülə bilər.

Poliolefirlərin uzunmüddətli işləməsini təmin etmək üçün tetra- [metilen(3,5-di-tret-butil-4-hidrotsinnamat)] metan (9) (İrqanoks 1010) kimi davamlı və effektiv antioksidantdan istifadə olunur ki, bu da ümumi stabilizator paketiñə 0,1-dən 0,5 kütłə % -dək qatılıqda əlavə olunur. Məmulatın maya dəyərinin aşağı salınması üçün tərkibində kükürd birləşmələri olan sinergik stabilizatorlar qarışığından istifadə olunur.

140°C-də PP-ni stabilləşdirilməsi zamanı hidroperoksidlərin dağıdıcılarından (dilauriltilipropionat, DLTDP) (33) və radikal akseptorundan (İrqanoks 1010, 9-cu birləşmə) eyni vaxtda istifadə zamanı alınan sinergik stabilləşmənin effekti əyani olaraq 4-cü cədvəldə verilmişdir:




Cədvəl 4. Polipropilenin 140°C-də oksidləşdirici destruksiyası zamanı fəzavi-çətinləşmiş fenol və kükürd tərkibli antioksidant arasındakı sinergizm

İrqanoks 1010, kütlə %	DLTDP, kütlə %	İnduksiya dövrü, günlər
0.0	0.3	4
0.1	0	16
0.1	0.3	45

Cədvəldən göründüyü kimi, hər bir antioksidantın təsirindən alınan ümumi stabillaşmə effekti 20 gün təşkil etdiyi halda, bu antioksidantların birgə təsirindən polimeri mühafizə effekti 45 günədək artır.

Oliqomer fəzavi-çətinləşmiş aminlər (HALS) işıq-stabillaşdırma ilə yanaşı, PP-nin effektiv termiki antioksidantı sayılırlar. Belə ki, tərkibində 2,4,6-trixlor-1,3,5-triazin və 2,4,4-trimetil-2-pentamin fraqmentləri (34-cü birləşmə) daşıyan N,N'-bis (2,2',6,6'- tetrametil-4-piperidinil) -1,6-heksadiamin polimer stabilizatorunun 0,5% miqdarda əlavəsi çoxdamarlı polipropilen materialını 120°C temperaturda sobada sürətli hava verilməsi şəraitində, oksidləşmədən 47 gün ərzində qorumaq xüsusiyətinə malikdir. Analoji şəraitlərdə adı fəzvia-çətinləşmiş 3,5-di-tret-butil-4-hidrok-sitoluol (ionol, 1-ci birləşmə) materialı yalnız 14 gün ərzində qoruyur.



34

Mis elektrik naqilləri üçün izolyasiyaedici material kimi tətbiq olunan poliolefinlərin təkcə əsas antioksidantlarla deyil, metal dezaktivatorları ilə də stabilləşməsinə ehtiyac duyulur. Hər iki, 28 və 29 birləşməsi metal dezaktivatorları funksiyalı bifunksional antioksidantlardır. Antioksidant 27, həmçinin, misin effektiv dezaktivatoru olmaqla, poliolefinlər üçün müvafiq antioksidant paketində istifadə olunur.

6.2. Poliamidlər

Poliamidlərin yüksək temperaturlarda yüksək mexaniki xassələrə malik olması səbəbindən bu birləşmələr və həmçinin, mineral və şüşə-aşqarlardan təşkil olunmuş materiallar praktikada geniş tətbiqin tapır və sənayenin müxtəlif sahələrində, məsələn, avtomobilqayırmada bu maddələrə böyük ehtiyac duyulur. Ədəbiyyatda poliamidlərin stabilləşməsinə həsr olunmuş nisbətən az miqdarda işlər vardır. Əsas etibarilə, alifatik poliamidlər – PA 6; PA 4,6; PA 6,6; PA 11; PA 12 nəzərdən keçirilir. Poliamidlərin stabilliyi amorf və kristal fazaların sıxlığından asılıdır. Çünkü yalnız bu iki faktor polimer matrisaya oksigenin miqrasiyasını nəzarətdə saxlayır.

Aromatik poliamidlər alifatik poliamidlərə nisbətən daha stabildirlər və praktiki olaraq stabilləşməni tələb etmirlər.

Alifatik poliamidlər üçün ənənvi stabilizatorlar mis duzları sayılır. Tipik stabilizatorlar sistemi misin, yod və brom duzlarının az qatılıqlarından ibarət ($< 50 \text{ ppm}$) əlavələrə əsaslanır. Poliamidlərin stabilləşmə mexanizmi axıradək aydınlaşdırılmışdır. Amma, təxmini olaraq, demək olar ki, bu mexanizm metal ionları ilə hidroperoksidlərin katalitik dağılmamasına əsaslanır. Poliamidlər üçün stabilizatorlar paketi digər polimerlər üçün yararlı deyil. Məsələn, mis əlavələri poliolefinlərdə özlərini promotor və ya destruksiya

katalizatorları kimi aparır. Güclü dispersiya olunmuş mis nümunələri daha effektiv sayılır. Onlar müsbət (poliamidlər üçün) və ya mənfi (poliolefinlər üçün) işarəli təsirə malik polimerin istismar xassələrinin əsas faktorundan sayılır.

Mis duzları suda həll olunduğundan, bir sıra hallarda polimerin tərkibində yuyula bilər ki (məsələn, boyayıcı vannalarda istifadə zamanı), bu da təbii olaraq, onların effektivliyini və qəbul olunmuş ekoloji statusunu aşağı salır. Aromatik aminlərin uzunmüddətli təsirə malik çox effektiv stabilizator olmalarına baxmayaraq, onlar əhəmiyyətli dərəcədə polimerin rəngini dəyişir və bu səbəbdən də onların poliamidlərdə tətbiqi hislə doldurulmuş materiallarla məhdudlaşır.

Fenol tipli antioksidantların bilavasitə polikondensasiya reaksiyalarının gedisində əlaevə edilməsi, əsasən aşağı temperaturlarda poliamidlərin əvvəlki rəngini və termiki stabilliyini yaxşılaşdırır. Poliamidlərdə müxtəlif stabilizator sistemlərinin keyfiyyəti 5-ci cədvəldə göstərilmişdir.

Cədvəl 5. Poliamidlərdə müxtəlif stabilizator sistemlərinin istifadəsinin üstünlükleri və çatışmayan cəhətləri.

Antioksidantlar sistemi	Üstünlükler	Çatışmayan cəhətlər
Mis/haloid duzlar	Yuxarı temperaturlarda ($>150^{\circ}\text{C}$) yüksək stabilləşmə effekti Az miqdarda dozalar	Polimerin rəngsizləşdirilməsi (rəngin dəyişməsi) Yaş atmosferlə kontaktda polimer matrisadan yuyulma Xırda-dispers nümunələri tələb olunur
Aromatik aminlər	Uzunmüddətli istismarda polimerin yüksək	Polimerin rəngsizləşdirilməsi (rəngin dəyişməsi)

	mühafizə effekti	Antioksidantın yüksək dozaları tələb olunur
Fenollar	Mis duzları tətbiq olunmadığı halda aşağı temperaturlarda effektivdir. Uzun müddət ərzində əvvəlki rəngi sabit saxlayır.	Yüksək temperatur şəraitində effektiv deyil, məsələn, avtomobilin qabaq açılıb-bağlanan örtüyünün (kapot) daxili hissəsində

6.3. Polistiollar

Modifikasiya olunmamış polistiollar, məsələn adı kristallik PS, nisbətən stabil törəmələrdən sayılır və əksər hallarda bu maddələrə antioksidantların əlavə edilməsi tələb olunur. PS-in tullantılarının stabillaşdırılməsi məqsədilə onların təkrar emalı zamanı fəzavi-çətinləşmiş fenol tipli antioksidantların aşağı qatlıqlarından (0,1 kütlə %) istifadə olunur.

Stirolakrilonitril sopolimerləri 220°C-dən yuxarı temperaturlarda emal proseslərində rəngini itirirlər. Hərçənd ki, rəngitirmə hadisəsi oksidləşmə prosesləri səbəbindən baş verir, lakin, fenol tipli antioksidantlar və fosfitlərin kombinasiyasından ibarət əlavələr müəyyən dərəcədə sopolimerin rənginin dəyişməsinin qarşını alır.

Zərbəyədavamlı PS-in tərkibində doymamış butadien kauçuku fraqmenti olduğundan o, oksidləşdirici destruksiyaya daha həssasdır. Antioksidantlar zərbəyədavamlı PS ya polimerin alınması prosesində, ya da polimerləşmədən sonra əlavə olunur. Antioksidantlar polimerizasiya prosesi zamanı əlavə olunduqda polimerin rəngi və PS-in zərbəyə davamlılığı bir qayda olaraq daha yaxşı olur. Lakin bu zaman fosfitlərin polimerləşmənin peroksid inisiatorları ilə qarşılıqlı təsiri nəticəsində prosesin kinetikasına mənfi effekt göstərməsi ehtimalı artır.

Akrilonitrilbutadienstirol sopolimeri stirolun akrilonitrilə emulsiyalı aşılanması və sonradan butadien kauçuk ilə qarışması nəticəsində alınır. Akrilonitrilbutadienstirol sopolimerinin hansı növünün alınmasının lazım olmasından asılı olaraq, kauçuk stirolakrilonitril sopolimeri ilə müxtəlif nisbətlərdə qarışdırılır. Burada antioksidantlar kauçuk fazasında oksidləşdirici proseslərin qarşısını almaq məqsədilə hazır sopolimerin koaqulyasiya və qurudulması proseslərində tələb olunurlar. Antioksidantların sinergik kombinasiyası – fəzavivi-çətinləşmiş fenonlar (0,25 kütlə %) və tioefirlər (0,5 kütlə %) daha yaxşı effekt nümayiş etdirirlər.

6.4. Poliefirlər

Polietilentereftalat kifayət qədər stabil polimer olub, termiki işləmə prosesində azacıq miqdarda (və ya heç tələbat olmur) antioksidant əlavələri tələb edir. Bəzi hallarda rəngin yaxşılaşması məqsədilə xirdalanma zamanı polietilentreftalata fosfitlər əlavə olunur. Polietilentreftalatin alınmasında polikondensasiya zamanı sistemə cəni zamanda fosforun beşvalentli birləşmələrindən olan trifenil və ya trimetilfosfat kimi birləşmələr də əlavə oluna bilərlər. Bu additivlər yenidən eterefikasiya katalizatorlarının qalıqları ilə (manqan, qalay, sink duzları) komplekslər əmələ gətirməklə azalmış miqdarda son hidroksil qrupları olan polietilentreftalatin əmələ gəlməsinə zəmin yaradırlar. Alınmış polimer hidrolitik stabilliyə və sabit rəngə malik olur. Polibutilentriftalat makromolekulunda yüksək miqdarda karbohidrogen hissə olduğundan o, polietilentreftalatla müqayisədə daha çox termoooksidləşdirici destruksiyaya məruz qalır və müvafiq olaraq fenol tipli antioksidantlar (0,05- 0,1 kütlə %) və fosfitlər (0,1 kütlə %) kombinasiyası ilə stabilşdırılır.

6.5. Polikarbonatlar

Polikarbonatlar termooksidləşməyə nisbətən, fotooksidləşməyə daha çox həssasdırular və emal prosesi zamanı antioksidantlar bu polimerlərdə lazımı rəng tonunu və yüksək şəffaflığı təmin edirlər. İslənmə prosesində lazım olan rəngin saxlanması məqsədilə polikarbonatlara fosfitlər (0,1 kütlə %) əlavə olunur.

Müəyyən olunmuşdur ki, polikarbonatlara xas olan stabillik bilavasitə son fenol fraqmentlərinin miqdarından asılıdır – bu fraqmentlər nə qədər çox olsalar, polimer bir o qədər az stabil olar. Polikarbonatların nəm atmosferdə işlənməsi zamanı turşularla kataliz olunan hidroliz nəticəsində belə son qrupların miqdarı çoxalır. Bu səbəbdən də istifadə olunan fosfitlər elə seçilməlidirlər ki, fosfit turşusunun katalitik miqdarda əmələ gəlməsi istisna olunsun.

6.6. Poliasetallar

Poliasetallar temperaturun təsirindən daha çox depolymerizasiya proseslərinə məruz qalırlar. Müəyyən olunmuşdur ki, depolymerizasiya makromolekulyar zəncirin sonundan başlayır və bir qayda olaraq turşuların iştirakı ilə kataliz olunur. Bununla əlaqədar olaraq, poliasetalların stabilşdırılməsi metodlarından biri, son qrupların təcrid olunması və ya inkişaf edən zəncirin qırılmasını tənzimləmək üçün somonomerlərin daxil edilməsidir.

Depolymerizasiya prosesi avtokatalitik prosesdir, belə ki, bu zaman əmələ gələn formaldehid asanlıqla polimerin parçalanmasını kataliz edən qarışqa turşusuna dək oksidləşir. Poliasetallar və onların əsasında kompozisiyaların stabilşdırılməsi üçün formaldehidin qarışqa turşusuna keçməsini təcrid edən birləşmələr, həmçinin fenol tipli antioksidantlar tətbiq edilir.


6.7. Poliuretanlar

Poliuretanların oksidləşdirici stabilliyi onların yüksəkmolekullu spirt komponenti və izosianatın kimyəvi təbiətindən əhəmiyyətli dərəcə asılıdır. Belə ki, mürəkkəb poliefirlərin və yüksəkmolekullu spirtlərin törəmələrindən olan poliuretanlar sadə poliefirlər tərkibində əsas olan poliuretanlardan daha stabilidlərlər. Sadə poliefirlərdə efir rabitəsinə qonşu olan metilen qrupu, hətta adı saxlanması prosesində belə hidroperoksidlərə asanlıqla oksidləşir. Əgər ingibitorlaşma aparılmasa, yiğilmiş hidroperoksid kütłəsi yüksəkmolekullu spirt və izosianatın ekzotermik reaksiyası nəticəsində materialın dəhşətli destruksiyasına götirib çıxara bilər. Fəzavi-çətinləşmiş fenollar (0,2 kütłə %) və aromatik aminlərin (0,1 kütłə %) qarışıqları, adətən, poliefir sistemlərin saxlanması istifadə olunan stabilizatorlardır. Onlar poliuretandan hazırlanan penomateriallara gözəl sabit rəng verir. Belə stabilizatorlar paketi az miqdarda olmaq şərtilə yüksəkmolekullu spirtlərin mürəkkəb poliefirlərində də istifadə olunur.

6.8. Kauçuklar


Polidoymamış elastomerlər oksidləşməyə çox həssasdırlar. Bir qayda olaraq, stabilizatorlar quruma və saxlanması prosesində elastomerlərin mühafizəsi məqsədilə vulkanizasiya prosesindən əvvəl onlara əlavə olunur. Həmçinin polimerləri rəngləməyən stabilizatorlardan olan butilləşmiş hidroksitoluol (ionol, antioksidant 1), 2,4-bis-(oktiltiometil)-6-metilfenol, 4,4-bis(α,α -dimetilbenzil) difenilamin (antioksidant 14) və ya fosfitdən, məsələn, tri(nonilfenil) fosfit (antioksidant 24) 0,01-dən 0,5 kütłə %-dək qatılıqda istifadə oluna bilər. Rəngləyici stabilizatorlardan olan N-izopropil-N-fenil-p-fenilendiamin (antioksidant 35)-dən şin istehsalında istifadə olunur. Bu antioksidantlar eyni zamanda yaxşı antiozonantlar

olduqlarından vulkanlaşmış kauçukları yükün təsirindən dağılmadan və onun çatlamadan effektiv olaraq qoruyur.




Şinlərin möhkəmliyini artırmaq məqsədilə istifadə olunan karbon hisi yuxarıda adları çəkilən stabilizatorların materialı rəngləməsinə mane olur. Texniki tələbata uyğun olaraq, 3 kütlə %-dək miqdarda antiozonant aktivliyinə malik amin tipli stabilizatorlar vulkanlaşmadan əvvəl bişməmiş kauçuk materialına əlavə olunmalıdır. Əgər amin tipli antioksidantlar hesabına polimerin rənglənməsi qəbul edilmiş normadan yuxarı olarsa, bu zaman kauçukların qorunması məqsədilə yarımrəngləyici antioksidantlardan istifadə olunur. Belə maddələrə polimerləşmiş birləşmə 13 və birləşmə 14-ü göstərmək olar. Lakin bu antioksidantlar antiozonant aktivliyə malik deyillər.


Avtomobil sənayesi üçün aralıq qatların, kipgəclərin (salnik) və rezin boruların hazırlanmasında istifadə olunan kauçuk materiallarının stabilləşdirilməsi üçün yağı və benzinlə ekstraksiyaya davamlı antioksidantlara üstünlük verilir. Karbohidrogenlərdə az həll olan və kauçukdan yavaş sürətlə ekstraksiya olunan belə antioksidantlara misal olaraq aromatik amin tipli stabilizator N-fenil-N-(toluolsulfonil)-p-fenilendiamini (birləşmə 36) göstərmək olar.



Sopolimerizasiya, modifikasiya və ya calağ yolu ilə antioksidantın elastomerlə kimyəvi birləşməsi, avtomobil-qayırmada kauçukların stabillaşdırılməsi probleminin həlli yollarında yaxşı nəticələr verir. Butadiennitril kauçukunun polimerizasiyası zamanı N-(4-anilinofenil) metakrilamidin (birləşmə 37) əlavə edilməsi karbohidrogenlər tərəfindən ekstraksiyaya qarşı yüksək sabitliyə malik antioksidant bloklu polimerin alınmasına götirib çıxarıır.



Tərkibində 1,5 kütlə % kimyəvi yolla birləşmiş antioksidant 37 olan bişməmiş utadiennitril kauçuku metanola intensiv ekstraksiyadan sonra ilkin kauçuku oksidləşməyə davamlılığını 92%-dək saxlayır. Tərkibi adı aromatikamin tipli antioksidantdan ibarət kauçuk, məsələn, oktiləşmiş difenilamin analoji işlənmədə özünün ilkin antioksidədirici stabilliyini yalnız 4% saxlaya bilir. Molekulunda sulfhidril qrupu olan aromatik amin tipli antioksidantların elastomerin əsas molekulyar zəncirinə kimyəvi aşilanmasını da həyata keçirmək olar. 4-(merkaptoasetamido) difenilaminin (birləşmə 38) etilenpropilendien kauçukuna əlavə edilməsi və bu kompozisiyani fırlanan qarışdırıcı cihazda 15 dəqiqə müddətində 150°C temperaturda qarışdırılması nəticəsində bu birləşmənin 87 faizi elastomerlə kimyəvi olaraq birləşir.



Bələ qısamüddətli qarışdırma nəticəsində elastomer mexaniki və termiki təsirə məruz qalır və bunun da nəticəsində polimer zəncirin qırılması antioksidantın əsas makromolekulyar zəncirə aşılanmasını qıcıqlandıran radikal qırıntıları əmələ gətirir.

6.9. Polivinilxloridlər


Polivinilxloridlər və onların törəmələri oksidləşdirici atmosferdə qismən stabillik xassəsi göstərmələrinə baxmayaraq, termiki təsirə qarşı çox davamsızdır. PVX-nin termiki destruksiyası dehidroxlorlaşma reaksiyasına səbəb olur və polimerin qorunması ilk növbədə ayrılan hidrogenxloridin birləşdiricilik xüsusiyyətindən asılıdır. Bundan əlavə, hal-hazırda PVX-nin stabiləşdirilməsi üçün antioksidləşdiricilik funksiyasını yerinə yetirən additivlər təklif olunur. Ələlxüsus aralkilfosfitlər, PVX üçün termiki stabilizatorlar paketinin effektiv antioksidləşdirici komponentlərin-dən biri sayılır.

6.10. Yanacaq və yağlar

Benzin və aviasiya yanacaqlarının tərkibində saxlanma müddəti ərzində asan oksidləşən və nəticədə qətran birləşmələri və çöküntülər əmələ gətirən doymamış birləşmələr vardır. Karbohidrogenli neft xammalının stabiləşdirilməsi üçün 2,4,-dimetil-6-tret-butilfenol, 2,6-di-tret-butil-p-krezol (birləşmə 1), 2,6-di-tret-butilfenol kimi radikal akseptorları və 5-10 ppm qatlılıq intervalında alkilləşdirilmiş parafenildiaminlər tətbiq olunur.

Yanacaq və yağların oksidləşməsinə gətirib çıxaran digər faktor metal qatışqlarıdır. Yanacaq və yaqlarda oksidant rolunu oynayan misin katalitik aktivliyi 5-10 ppm qatlılıqda götürülən N,N'-disalisiliden-1,2-diaminopropan (birləşmə 30) kimi metal dezaktivatorlarından istifadə etməklə neytrallaşdırıla bilər. Müasir stardartlara görə,

avtomobil lərin benzin mühərrikləri üçün yağlar və sürtkü yağları hətta ən sərt şəraitdə belə çox davamlı olmalıdır. Məsələn, mühərriklərdə porşenin divarlarında nazik yağ qatı temperaturun, oksigenin, azot oksidlərinin və mexaniki təzyiqin təsirlərinə məruz qalır. Bu səbəbdən sürtkü yağlarının stabillaşdırılməsinə böyük diqqət yetirilir. Bunun üçün nisbətən yüksək qatılıqlı birinci dərəcəli antioksidantlar 1 kütlə%-dək fəzavi-çətinləşmiş fenollar və aromatik aminlər qarışığından, məsələn, alkilləşdirilmiş difenilamin və fenil- α -naftilamin qarışığından və həmçinin yüksək qatılıqlı sinergist, 1 kütlə %-ə qədər sinkdialkil-ditiofosfat (birləşmə 39) qarışığından istifadə olunur. Sinkdialkil-ditiofosfat - elektronvermə ilə baş verən radikal akseptoru mexanizminə əsasən oksidləşmə zəncirini qırmağa malik olan və radikal əmələ gətirmədən hidroperoksidləri parçalayan çoxfunksiyalı və ucuz antioksidantlardandır. Eyni zamanda, antioksidant 39 korroziya ingibitoru və yeyilməyə qarşı aşqar funksiyasını yerinə yetirir. Lakin o, avtonəqliyyat tullantılarının tərkibinin normal saxlanması tənzimləyən katalizatorları dezaktivləşdirmək qabiliyyətinə malik olduğundan müasir standartlara uyğun olaraq onların 0,1 kütlə% qatılıqda tətbiqi ilə kifayətlənmək zərurəti yaranır.



7. Sınaq metodları

7.1. Polimerlər

Polimerlərin oksidləşmə stabilliyinin sınaqdan keçirilməsinin müxtəlif metodları vardır. Müxtəlif təsirlər nəticəsində polimerin tərkibində baş verən dəyişikliklər, fiziki və estetik (vizual) olmaqla, iki yerə bölünür. Fiziki çəvrilmələr dedikdə molekul çökisi, molekulyar kütlə paylanması və kristallıq dərəcəsinin dəyişməsi, estetik transformasiya isə rəngin dəyişməsi, bulanıqlığın əmələ gəlməsi və mikroskopik çatlar nəticəsində polimerin üst qatının parlaqlığının itməsi nəzərdə tutulur. Fiziki və estetik çəvrilmələrin qiymətləndirilməsi üzrə apalıran sınaqlar ASTM-də əks olunmuş (məsələn, qırılmaya davamlılıq həddi, zərbəyə davamlılıq, rənglənmənin intensivliyi, oksidləşmənin induksiya dövrü, termoşkafta süni qocalma) standart sınaqlar sistemində sadə metod və cihazların köməyi ilə aparıla bilər. Lakin istismar şəraitində oksidləşmə stabilliyinin qiymətləndirilməsi uzunmüddətli və daha mürəkkəb əməliyyatların aparılmasını tələb edir. Bu zaman oksidləşmə nəticəsində polimerin xarab olmasına lazımlı olan vaxtı qısaltmaq məqsədilə sürətləndirilmiş metodlardan istifadə olunur, o cümlədən, real işləmə temperaturundan daha yüksək temperatur verməklə sınaqlar aparılır. Ərimə nöqtəsindən aşağı temperaturlarda polimerin sürətləndirilmiş termoqocalması uzunmüddətli istismar şəraitində polimerin termostabilliyinin təyini metodlarından biri sayılır. Bu zaman müxtəlif temperatur dəstindən istifadə olunur ki, bu da oksidləşdirici destruksiya sürətinin temperaturdan Arrenius asılılığını qurmağa və bununla da polimerin parçalanma sürətini istismarın real temperatur şəraitinə ekstrapolyasiya etməyə imkan verir. Bəzən konkret sınaq temperaturunun polimerin hansısa xassəsinin müəyyən səviyyədə əldə olunan zamandan (məsələn, kövrəkliyin, möhkəmlik həddinin və termoqocal-

ma zamanı elastikliyin 50% saxlanması) Arrenius asılılığını qurmaq lazımlı gəlir. Lakin nəzərə almaq lazımdır ki, polimer matrisada baş verən real proseslər kifayət qədər mürrəkkəb olduğundan Arrenius asılılığı - polimerin dağıılma vaxtının əks temperaturdan loqarifmi – düz asılılıqdan əhəmiyyətli dərəcədə kənara çıxa bilər və ekstrapolyasiya zamanı ciddi səhvlerə səbəb ola bilər.

Polimer materialın estetik xassələrinin meyarları özündə rəngin dəyişməsi, parlaqlığın itməsi, tutqunlaşmanın artması, layların yaranması, səthin hamarlığının itməsi, tərləmə həddi, polimerin aşağı molekullu fraksiyalarının üzə çıxması və ləkələrin əmələ gəlməsinin qiymətləndirilməsini səciyyələndirir.

Fiziki və estetik xassələrin qiymətləndirilməsi zamanı nəzərə almaq lazımdır ki, səthin həcmə doğru sahəsinin artması polimerin oksidləşmə həssaslığını artırır ki, bunun da səbəbi buxarlanma nəticəsnidə antioksidant itkisinin baş verməsidir.

Əvvəllər yüksək temperaturlarda polimerin oksidləşməsi zamanı oksigenin udulmasına əsaslanan oksidləşmə stabilliyinin təyini metodu geniş tətbiq edildirdi. Bu metod çox gözəl nəticələr vermək imkanına malikdir, lakin hal-hazırda digər yanaşmalardan, məsələn, oksidləşmə zamanı induksiya dövrünün təyini, DTA və XL üsullarından istifadə olunur. Udulan oksigenin həcminin ölçülməsinə əsaslanan metodun tətbiqi zamanı müəyyən həcm oksigenin udulmasına lazım olan vaxt oksidləşdirici parçalanmanın dərəcəsinin göstəricisidir və polimerin fiziki-mexaniki xassələrinin dəyişilməsinin həddi ilə korrelyasiya oluna tənzimlənə bilər. Lakin bu tip testlər intensiv hava axınında polimerin effektiv işləmə müddətini tam qiymətləndirmək üçün kifayət deyil.

Polimerin nisbi oksidləşmə stabilliyinin öyrənilməsində oksidləşmənin induksiya dövrünün təyini üsulundan geniş istifadə olunur. Bu təcrübələr, adətən, sərt sınaq şərai-

tində, bir qayda olaraq, polimerin ərimə temperaturundan yüksək temperaturlarda və oksidləşdirici kimi oksigendən istifadə etməklə aparılır. Qeyd etmək lazımdır ki, bu metod uzunmüddətli istilik stabilliyi barədə qabacqadan məlumat əldə etmək üçün qəbulunmaz sayılsa da, müxtəlif stabilizator sistemlərinin potensial antioksidəşmə aktivliyinin daha tez öyrənilməsində çox yararlı və effektivdir.

Xemilümessensiya üsulunun tətbiqi ilə əlaqədar olan təcrübələrdə proses yuxarıda nəzərdən keçirilən induksiya dövrünə görə aparılan eksperimentlərlə oxşarlıq təşkil edir. Xemilüminessensiya üsulu eyni müvəffəqiyyətlə polimerin destruksiyasının başlanğıc mərhələlərində və oksidləşdirici dağılmışın dərin konversiyaları (çevrilmə) zamanı istifadə oluna bilər. Oksidləşmə zamanı xemilüminessent şüalanmanın intensivliyi əmələ gələn peroksidlərin miqdarına müttənasibdir və polimer matrisada baş verən oksidləşmə proseslərinin intensivlik meyarlarından sayılır. Son 10 illiklərdə işlənib hazırlanmış bu üsul tədqiqatçılara polimerin oksidləşmə stabilliyi barədə az bir zamanda – sürətləndirilmiş termoqocalma üsullarına sərf olunan zamandan daha qısa müddətdə və oksidləşmənin induksiya dövrünün təyin olunduğu şəraitlə müqayisədə oksidləşdirici qocalmanın real şəraitinə daha çox uyğunlaşdırılmış şəraitlər üçün qiymətli və faydalı məlumat verir.

7.2. Sürtkü yağları

Motor yağlarında istifadə olunan antioksidantların öyrənilməsində xeyli sınaq testləri seriyası mövcuddur. Belə laboratoriya testlərin dən ən geniş yayılanı dünya praktikasında istifadə olunan ISOT (Indiana Stirring Oxidation Test) sınağıdır. Testin mahiyyəti neft nümu-nəsinin hava atmosferində və metal katalizatorları kimi istifadə olunan mis və dəmir lövhələrinin iştirakı ilə $165,5^{\circ}\text{C}$ -də qızdırılması və intensiv qarışdırılmasından ibarətdir. Qızdırıl-

ma boyu dövrü olaraq qətran çöküntülərinin artımla əmələ gəlməsinə, özlülüyün və turşu ədədinin tədqiq olunan nümunədə artmasına nəzarət olunur. Turşuluq ədədinin 0,4 mq KOH/q qiymətinə çatdığı zaman böhran nöqtəsi hesab olunur. Bu testdən keçən sürtkü yağları sonradan avtomobil mühərriklərində real sınaqlardan və daha sonra çox kilometrli yarışlarda iştirak edən müxtəlif avtomobillərdə son yoxlamalardan keçir.

Göstərilən laboratoriya testindən başqa tərkibində müxtəlif antioksidantlar olan yağların oksidləşmə stabilitiyinin təyin edilməsində eynilə polimer materiallar üçün istifadə olunan test sınaqları tətbiq olunur.

Piy və yağ stabilizatorları kimi antioksidantların effektivliyi də aktiv oksigenin müəyyən olunması üsulunun köməyi ilə hidroperoksidlərin əmələ gəlmə sürətinə əsasən təyin edilir.

Qida maddələrinin tərkibindəki antioksidantların aktivliyinin və bu maddələrin sağlam saxlanılma vaxtının təyin edilməsində, sınaqdan keçirilən birləşmələrdə yaranan acılığın və ya xarab olarkən əmələ gələn qoxunun intensivliyinin ölçülməsinə görə testlər tətbiq olunur.

8. Antioksidantların əlavə xassələri

Polimer materialın stabilliyini təmin edən antioksidantlara radikal akseptorluq xassəsi göstərmək və hidroperoksidləri radikalsız parçalamaq qabiliyyətindən başqa digər tələblər də qoyulur. Effektivlik xassəsindən əlavə antioksidantlar qarşısında uçuculuq, uyğunluq, rəng stabilliyi, fiziki forma, dad, qoxu, maya dəyəri və s. kimi xassələrə, xüsusilə də, qida maddələri antioksidantlarına əlavə tələblər qoyulur.

8.1. Uçuculuq

Additivlərin böyük eksəriyyəti ərinti halında emalı zamanı və polimerizasiya mərhələsindən sonra polimerə əlavə olunur. Emal prosesi polimer məməlatın sonrakı formalaşması prosesində olduğu kimi materiala təsir edən istilik yükü ilə müşahidə edilir. Məhsulun saxlanması da isti yerlərdə həyata keçirilir. Bu əməliyyatlar zamanı antioksidant və onun antioksidləşmə aktivliyinə malik çevrilmə məhsulları polimerin tərkibindən buxarlanmamalıdır. Bu səbəbdəndir ki, eksər sənaye tipli antioksidantlar elə sintez olunmalı, modifikasiyası edilməli və işlənməlidir ki, nəticədə yüksək molekul kütləsinə malik antioksidantlar alınsin.

8.2. Uyğunluq

Antioksidantlar polimer materiallarda yaxşı həll olmalıdır. Öks təqdirdə, polimer matrisada onların miqrasiyası gec baş verir. Bir neçə vaxtdan sonra antioksidantlar polimer materialda üzə çıxaraq materialın rənginin tutqunlaşmasına səbəb olur. Antioksidant nazik pərdə şəklində polmerin səthində tərləyir ki, bu da materialın parlaqlığının və hamarlığının azalmasına səbəb olur. Nəticədə polimer bərkəşir və plastik formalaşma və reproduksiya üçün yararsız hala düşür.

8.3. Rəngə davamlılıq

Antioksidantın polimerin rəngini dəyişməməsi çox mühüm şərtlərdən biridir. Belə ki, bu hal arzuolunmaz oksidəşdirici çevrilmələrin inkişafı kimi qiymətləndirilə bilər. Bəzi antiodksidantlar təbiət etibarilə polimerlə qarışan kimi onun rəngini dəyişməyə meyllidirlər. Bəziləri isə oksidləşdirici təsir prosesində rəngin dəyişməsinə səbəb olurlar. Bəzən belə arzuolunmaz dəyişmələri gizlətmək üçün piqmentlər-

dən istifadə olunur ki, bu pigmentlər antioksidantların və ya onların çevirlmə məhsullarının təsirindən polimerin əsas rənginin hətta əhəmiyyətsiz dəyişməsini də aradan qaldıra bilir.

8.4. Fiziki hal

Çoxlu miqdarda toz əmələ gəlmənin qarşısını almaq məqsədilə antioksidantlar istehsalçılara dənəvər və ya həblər şəklində təklif olunur. Duru və ya ərimiş antioksidantlar polimer materialları ilə yaxşı qarışdıqları üçün, digər alternativ forma kimi istehsalçılar üçün daha böyük maraq kəsb edir. Lakin polimer sənayesində xırda dispers formalı antioksidantlara tələbat hələ də qalmaqdır. Bunun da səbəbi belə formalı antioksidantların həbləşdirilmiş antioksidantlarla müqayisədə polimerin ərinti halında emalı prosesinə qədər onun additivlərlə qarışmasını daha yaxşı təmin etməsidir.

8.5. Dad və qoxu

Qida maddələri ilə temasda olan və şəxsi, həmçinin möişət məqsədilə istifadə olunan polimer materiallarının tərkibindəki antioksidantlar üçün dad və qoxu əsas faktorlardan biri sayılır. İnsanın qoxu orqani bəzi analitik cihazlardan daha çox həssasdır və birləşmələrdə yarana bilən qoxunu milyardda bir dəqiqliklə hiss etmək qabiliyyətinə malikdir. Buna görə də belə antioksidantlar üçün dad və qoxuya qarşı çox sərt tələblər qoyulur.

8.6. Kanserogenlik və təhlükəsizlik faktorları

Antioksidantların təhlükəsizlik faktorlarının tətbiqi heyvanlar üzərində aparılan bir sıra test sınaqlarında yoxlanılır. Ağız boşluğununa, nəfəs yollarına, gözə və dəri örtüyünə düşən antioksidantların kanserogenliyi üzərində

testlər aparılır. Antioksidantların mutagen aktivliyinin sı-naqdan keçirilməsi xüsusi tərzdə aparılır. Sınaqlar bir neçə heyvanın kəskin zəhərlənməsinədək antioksidantın polimerin tərkibindən qida məhsulu ilə ekstraksiyası nəticəsində qidanın tərkibində yaranan qatılığında aparılır. Bu zaman antioksidant elə qatılıqda götürür ki, o, təbiətcə qida məhsuluna oxşar hər hansı həllədici ilə polimerin tərkibindən yuyula bilsin. Antioksidantların kanserogenlik faktoru və onların təhlükəsizliyinin tətbiqi üzrə vahid Dünya Standardları Sistemi mövcuddur.

8.7. İqtisadi cəhətdən effektivlik

Stabilizatorların tətbiqində əsas məsələlərdən biri uyğun tip antioksidantın və real işlənmə şəraitiində polimerin effektiv stabilləşməsi üçün antioksidantın rasional istifadəsinin seçimidir. Məsələn, əgər hər hansı bir əşya birdəfəlik istifadə üçündürsə – misal olaraq səbətlər və ya sellofandan hazırlanmış qida örtükləri – antioksidantın növü və qatılığı elə seçilməlidir ki, polimerin stabilləşməsi ilə bağlı əlavə xərclər ortaya çıxmasın. Bu zaman antioksidant ərintidə kompaundlaşma (komponentlərin polmerlə qarışıığı) və son məmulatın alınması mərhələlərində polimerin stabilləşməsini təmin etmək üçün tələb olunur. Praktikada, adətən, məmulatların tullantıları, qırıqları təkrar emala məruz qalır ki, bu da materialın iqtisadi cəhətdən qənaəti deməkdir.

Əgər material uzunmüddətli istismar üçün nəzərdə tutulursa, məsələn, geosintetik materiallardan olan membranlar, kabellər və elektrik məstilleri üçün izolyasiyaedici material, qaz-boru və su kəmərləri – bu zaman antioksidantın tipi və qatılığı obyektlərin etibarlı işləməsinin təmin olunması istiqamətində seçilməlidir. Bu tip antioksidantların istifadəsi ilə bağlı xərclər məmulatların uzunmüddətli stabil fəaliyyəti ilə kompensasiya olunur.

9. İstifadə olunmuş ədəbiyyatın siyahısı

1. Ahmad S., Pawelke B., Zulfigar S., Habicher W.D. *New stabilizers for polymers on the basis of IPDI protected 2,2-thiobis(4-methyl-6-tert-butylphenol) and hindered amines.* Polym Degrad Stab 2001; 72(1) : 47-51
2. Allen N.S. In: Allen N.S., editor. *Degradation and Stabilisation of Poly-olefins.* London: Elsevier Science Publishers Ltd; 1983; ch.8
3. Allen N.S., Edge M. *Fundamentals of polymer degradation and stabilisation.* Chichester: Chapman and Hall, 1992.
4. Allen N.S., Ortiz R.A., Anderson G.L., Sideridou I., Malamidou E. *Comparison of the thermal and light stabilizing action of novel imine and piperazine based hindered piperidine stabilizers in polyolefins.* Polym Degrad Stab 1994; 46 (1): 85-91
5. Allen N.S., Zeynalov E.B., Sanchez K.T., Edge M., Kabetkina Yu.P., Johnson B. *Comparative evaluation of the efficiency of a series of commercial antioxidants studied by kinetic modelling in a liquid phase and during the melt processing of different polyethylenes.* Journal of Vinyl & Additive Technology 2009; (in press).
6. Al-Malaika S., Scott G. In: Allen N.S., editor *Degradation and Stabilization of Polyolefins.* London: Elsevier Applied Science Publishers, 1983; ch.6&7.
7. Anacleto J.F., Boyd R.K., Pleasance S., Quilliam M.A., Howard J.B., Lafleur A.L., Makarovskiy Y.Y. *Analysis of minor constituents in fullerene soots by LC-MS using a heated pneumatic nebulizer interface with atmospheric-pressure chemical.* Canadian Journal of Chemistry – Revue Canadienne de Chimie 1992; 70(10):2558- 658

8. *Antioxidation and antioxidants* // New – York – London
Terscience Publisher, 1961 – 62, ch.4.
9. Arsalani N., Geckeler K.E. *Radical bulk polymerization of styrene in the presence of fullerene [60]*. Fullerene Science and Technology 1996; 4 (5):897-912
10. Bakry R., Vallant R.M., Najam-Ul-Haq M, Rainer M., SzaboZ., Huck C.W., Bonn G.K. *Medicinal applications of fullerenes*. International Journal of Nanomedicine 2007; 2(4): 639-49
11. Belz T., Schlogl R. *Characterization of fullerene soots and carbon arc electrode deposits*. Synthetic Metals 1996; 77(1-3) : 223-6
12. Bocchini S., Frache A., Camino G., Claes M. *Polyethylene thermal oxidative stabilisation in carbon nanotubes based nanocomposites*. European Polymer Journal 2007; 43 (8) : 3222-35
13. Borghi R., Lunazzi L., Placucci G., Cerioni G., Plumitallo A. *Photolysis of dialkoxy disulfides: A convenient source of alkoxy radicals for addition to the sphere of fullerene C-60*. Journal of Organic Chemistry 1996; 61(10) : 3327-31
14. Borghi R., Lunazzi L., Placucci G., Krusic P.J., Dixon D.A., Knight L.B. *Regiochemistry of radical-addition to C-70*. Journal of Physical Chemistry 1994; 98(21) : 5395- 98
15. Bulgakov R.G., Ponomareva Yu. G., Maslennikov S. I., Nevyadovsky E. Yu., Antipina S. V. *Inertness of C60 fullerene toward RO₂[•] peroxy radicals*. Russian Chemical Bulletin, International Edition, 2005; 54(8) : 1862-65
16. Bystrzejewski M., Huczko A., Lange H., Drabik J., Pawelec E. *Influence of C-60 and fullerene soot on the oxidation resistance of vegetable oils*. Fullerenes Nanotubes and Carbon Nanostructures 2007;15(6) : 427-38

17. Camp A.G., Lary A., Ford W.T. *Free-radical polymerization of methyl-methacrylate and styrene with C(60)*. Macromolecules 1995; 28(23): 7959-61
18. Cao T., Webber S.E. *Free radical copolymerization of styrene and C₆₀*. Macromolecules 1996; 29 (11) : 3826-30
19. Cataldo F. *On the reactivity of C-60 fullerene with diene rubber macroradicals. I. The case of natural and synthetic cis-1,4-polyisoprene under anaerobic and thermo-oxidative degradation conditions*. Fullerene Science and Technology 2001; 9(4):407-513
20. Chasan D., In J. Pospisil and P. P. Klemchuk, eds., *Oxidation Inhibition in Organic Materials*, Vol. 1, CRC Press, Inc., Boca Raton, Fla., 1990, pp. 291–326
21. Chen Y, Lin KC. *Radical polymerization of styrene in the presence of C-60*. Journal of Polymer Science Part A-Polymer Chemistry 1999; 37(15): 2969-75
22. Chi Y., Bhonsle J.B., Canteenwala T., Huang J-P., Shiea J., Chen B-J., Chiang L.Y. *Novel water-soluble hexa(sulfobutyl)fullerenes as potent free radical scavengers*. Chemistry Letters 1998; 5: 465-66
23. Cioslowski J. *Electronic Structure Calculations on Fullerenes and Their Derivatives*. Oxford University Press, New York, Chaps. 3-5. 1995
24. Costache M.C., Wang D.Y., Heidecker M.J., Manias E., Wilkie C.A. *The thermal degradation of poly(methyl methacrylate) nanocomposites with montmorillonite, layered double hydroxides and carbon nanotubes*. Polymers for Advanced Technologies 2006; 17(4) : 272-80
25. Crecely R.W., Charles E.D. Analytical methods for additives in plastics.In: Pritchard G, editor. Plastic Additives. London: Chapman&Hall, 1998. p.26-31
26. Cremonini M.A., Lunazzi L., Placucci G., Krusic P.J. *Addition of alkylthio and alkoxy radicals to C-60*

- studied by ESR.* Journal of Organic Chemistry 1993; 58(17): 4735-38
- 27. Dexter M., In: Kroschwitz J. I., ed., Encyclopedia of Chemical Technology, 4th ed., Vol. 3, Wiley-Interscience, New York, 1992
 - 28. Dimitrijevic N.M. *Reaction of trichloromethyl and trichloromethylperoxyl radicals with C-60 – A pulse-radiolysis study.* Chemical Physics Letters 1992; 194(4-6): 457-60
 - 29. Dimitrijevic N.M., Kamat P.V., Fessenden R.W. *Radical adducts of fullerenes C-60 and C-70 studied by laser flash-photolysis and pulse-radiolysis.* Journal of Physical Chemistry 1993; 97(3):615-18
 - 30. Dixon K.W. In:Brandrup J, Immergut E.H., Grulke E.A., editors. Polymer Handbook. New York: JohnWiley, 1999; 4th edition, II
 - 31. Emanuel N.M, Zaikov G.E., Maizus Z.K.*Oxidation of organic compounds.* Oxford: Pergamon Press N.Y.,1984
 - 32. Emanuel N.M., Denisov E.T., Maizus Z.K. *Liquid phase oxidation of hydrocarbons.* New York: Plenum Press, 1967
 - 33. End MJ, Davis LH, Vulic I. Proceedings 2nd World Congress - Polypropylene in Textiles Queensgate Huddersfield,UK. 2000; p.295-313
 - 34. Enes, R.F., Tome A.C., Cavaleiro J.A.S., Amorati R., Fumo M.G., Pedulli G. F., Valgimigli L. *Synthesis and antioxidant activity of [60]fullerene-BHT conjugates.* Chemistry-A European Journal 2006; 12(17):4646-53
 - 35. Ford W.T., Graham T.D., Mourey T.H. *Incorporation of C-60 into poly(methyl methacrylate) and polystyrene by radical chain polymerization produces branched structures.* Macromolecules 1997; 30(21):6422-29
 - 36. Ford W.T., Lary A.L., Mourey T.H. *Addition of polystyryl radicals from TEMPO-terminated*

- polystyrene to C-60.* Macromolecules 2001; 34(17) : 5819-26
37. Ford W.T., Nishioka T., McCleskey S.C., Mourey T.H., Kahol P. *Structure and radical mechanism of formation of copolymers of C-60 with styrene and with methyl methacrylate.* Macromolecules 2000; 33(7):2413-23
 38. Foti M.C. *Antioxidant properties of phenols* Journal of Pharmacy and Pharmacology 2007; 59(12): 1673-85
 39. Gasanov R.G., Kalina O.G., Bashilov V.V., Tumanskii B.L. *Addition of carbon-centered radicals to C-60. Determination of the rate constants by the spin trap method.* Russian Chemical Bulletin 1999; 48(12):2344-46
 40. Gasanov R.G., Tumanskii B.L. *Addition of (Me₂CCN)-C-center dot, (Me₂CPh)-C-center dot, and (CCl₃CH₂CHPh)-C-center dot radicals to fullerene C-60.* Russian Chemical Bulletin 2002; 51(2):240-42
 41. Geckeler K.E., Samal S. *Rapid assessment of the free radical scavenging property of fullerenes.* Fullerene Science and Technology 2001; 9(1):17-23
 42. Gensler R., Plummer C.J.G., Kausch H.H., Kramer E., Pauquet J.R., Zweifel H. *Thermo-oxidative degradation of isotactic polypropylene at high temperatures: phenolic antioxidants versus HAS.* Polym Degrad Stab 2000;67(2):195-208
 43. Gharbi N., Pressac M., Hadchouel M., Szwarc H., Wilson S.R., Moussa F. *[60]Fullerene is a powerful antioxidant in vivo with no acute or subacute toxicity.* Nano Letters 2005; 5(12): 2578-85
 44. Ghosh H.N., Pal H., Sapre A.V., Mukherjee T., Mittal J.P. *Formation of radical adducts of C-60 with alkyl and halo-alkyl radicals - Transient absorption and emission characteristics of the adducts.* Journal of the

- Chemical Society-Faraday Transactions 1996; 92(6): 941- 4
- 45. Gijsman P., Gitton M. *Hindered amine stabilisers as long-term heat stabilisers for polypropylene.* Polym Degrad Stab 1999; 66(3): 365-71
 - 46. Gijsman P., Gitton-Chevalier M. *Aliphatic amines for use as long-term heat stabilizers for polypropylene.* Polym Degrad Stab 2003; 81 (3): 483-9
 - 47. Gijsman P., *The mechanism of action of hindere amine stabilizers(HAS) as long-term heat stabilizers.* Polym Degrad Stab 1994; 43(2):171-6
 - 48. Ginzburg B.M., Shibaev L.A., Kireenko O.F., Shepelevskii A.A., Melenevskaya E.Y., Ugolkov V.L. *Thermal degradation of fullerene-containing polymer systems and formation of tribopolymer films.* Polymer Science A 2005; 47(2):160-174
 - 49. Ginzburg B.M., Shibaev L.A., Ugolkov V.L. *Effect of fullerene C-60 on thermal oxidative degradation of polymethyl methacrylate prepared by radical polymerization.* Russian Journal of Applied Chemistry 2001; 74(8):1329-37
 - 50. Ginzburg B.M., Shibaev L.A., Ugolkov V.L., Bulatov V.P. *The effect of fullerene C-60 on the thermooxidative degradation of a free-radical PMMA studied by thermogravimetry and calorimetry.* Techn. Phys. Lett. 2001; 27(10):806-9
 - 51. Ginzburg B.M., Shibaev L.A., Ugolkov V.L., Bulatov V.P. *Influence of C-60 fullerene on the oxidative degradation of a free radical poly(methyl methacrylate).* Journal of Macromolecular Science – Physics B 2003; 42 (1):139-66
 - 52. Grassie N. *Developments in Polymer Degradation.* London: Elsevier Applied Science Publishers, 1985
 - 53. Grattan D.W.,Carlsson D.J.,Wiles D.M. *Polyolefin photo-stabilization mechanisms. Reactions of*

- tetramethylpiperidine derivatives in model systems.*
Polym Degrad Stab 1979; 1(1): 69-84
- 54. Gross R., Dinse K.P. *Light-induced formation of C-60 radical adducts as studied with Fourier transform EPR . Recent advances in the chemistry and physics of fullerenes and related material* Ed(s): Kamat P.V., Guldi D.M., Kadish KM vol. 7 Book Series: Electrochemical Society Series 1999; 99(12) : 18-27
 - 55. Gugumus F. *Advances in the stabilization of polyolefins.* Polym Degrad Stab 1989; 24(4): 289-301
 - 56. Gugumus F. *Aspects of the impact of stabilizer mass on performance in polymers. 2. Effect of increasing molecular mass in polymeric HALS in PP.* Polym Degrad Stab 2000; 67(2): 299-311
 - 57. Gugumus F. *Current trends in mode of action of Hindered Amine Light Stabilizers.* Polym Degrad Stab 1993; 40(2): 167-215
 - 58. Gugumus F. *Mechanisms of thermooxidative stabilisation with HAS.* Polym Degrad Stab 1994; 44(3):299-322
 - 59. Gugumus F. *New trends in the stabilization of polyolefin fibers.* Polym Degrad Stab 1994; 44(3): 273-297
 - 60. Gugumus F., In H. Zweifel, ed., *Plastics Additives Handbook*, 5th ed., Carl Hanser Verlag, Munich, 2001
 - 61. Guldi D.M., Ford W.T., Nishioka T. *Rate constants of reactions with 2-cyano-2-propyl radical and triplet state lifetimes of low molar mass and polymeric substituted [60]fullerenes.* In: *Recent Advances in the Chemistry and Physics of Fullerenes and Related Material*, Eds. Kamat P.V., Guldi D.M., Kadish K.M., vol. 7 Book Series: Electrochemical Society Series 1999; 99(12):315-18
 - 62. Guldi D.M., Hungerbuhler H., Janata E., Asmus K.D. *Radical- induced redox and addition-reactions with C-60*

- studied by pulse-radiolysis.* Journal of the Chemical Society-Chemical Communications 1993; 1:84-6
- 63. Hirsch A. *Addition-reactions of Buckminsterfullerene (C-60).* Synthesis-Stuttgart 1995; 8 : 895-913
 - 64. Jensen A.W., Wilson S.R., Schuster D.I. *Biological applications of fullerenes (Review article).* Bioorganic & Medicinal Chemistry 1996; 4(6):767-79
 - 65. Jipa S., Zaharescu T., Santos C., Gigante B., Setnescu R., Setnescu T, Dumitru M., Kappel W., Gorghiu L.M., Mihalcea I., Olteanu R.L. *The antioxidant effect of some carbon materials in polypropylene.* Materiale Plastice 2002; 39(1):67-72
 - 66. Kanowski M., Vieth H.M., Luders K., Buntkowsky G., Belz T., Werner H., Wohlers M., Schlogl R. *The structure of fullerene black and the incorporation of C-60 investigated by C-13 NMR.* Carbon 1997; 35(5): 685- 95.
 - 67. Kelar K. *Polyamide 6 modified with fullerenes, prepared via anionic polymerization of epsilon-caprolactam.* Polimery 2006; 51 (6): 415-24
 - 68. Kimwomi R.R.K., Koßmehl G., Zeinalov E.B., Gitu P. M. & Bhatt B.P. *Polymeric antioxidants from vernonia oil.* Macromol Chem Physics 2001; 202(13): 2790-2796
 - 69. Kirkwood K., Stewart D., Imrie C.T. *Role of C₆₀ in the free radical polymerization of methyl methacrylate.* Journal of Polymer Science Part A- Polymer Chemistry 1997; 35(15):3323-25
 - 70. Klemchuk P.P., Gande M.E. *Stabilization mechanisms of hindered amines.* Polym Degrad Stab 1988; 22(3):241- 274
 - 71. Klemchuk P.P., Gande M.E., Cordola E. *Hindered Amine mechanisms: Part III- Investigations using isotopic labelling.* Polym Degrad Stab 1990; 27(1): 65-74

72. Krusic P.J., Wasserman E., Keizer P.N., Morton J.R., Preston K.F. *Radical reactions of C₆₀*. Science 1991; 254(5035):1183-85
73. Lens M., Medenica L., Citernesi U. *Antioxidative capacity of C-60 (buckminsterfullerene) and newly synthesized fulleropyrrolidine derivatives encapsulated in liposomes*. Biotechnology and Applied Biochemistry 2008; 51:135-140, Part 3-4
74. Li J., Tong L.F., Fang Z.P., Gu A.J., Xu Z.B. *Thermal degradation behavior of multi-walled carbon nanotubes/polyamide 6 composites* Polym. Degrad. Stab. 2006; 91 (9): 2046 – 52
75. Liauw C.M., Quadir A., Allen N.S., Edge M. and Wagner A., *Effect of Hindered Piperidine Stabiliser Molecular Structure And UV Absorber Addition on the Oxidation of HDPE Films: Part I: Long Term Thermal and Photooxidation Studies*. J. Vinyl Additive Technol., (2004), 10 : 79-87
76. Maillard B., Ingold K.U., Scaiano J.C. *Rate constants for the reactions of free radicals with oxygen in solution*. J Amer Chem Soc 1983; 105(15) : 5095-5099
77. Markovic Z., Trajkovic V. *Biomedical potential of the reactive oxygen species generation and quenching by fullerenes (C-60)*. Biomaterials 2008; 29(26):3561-73
78. Mathis C., Schmaltz B., Brinkmann M. *Controlled grafting of polymer chains onto C-60 and thermal stability of the obtained materials*. Comptes Rendus Chimie 2006; 9(7-8): 1075-84
79. Minsker K.S. *The Chemistry of Chloride – Containing Polymers: Degradation Stabilization, Syntheses*. New Horizons Vova Sci. Publ., Inc., Commack, USA, 2000
80. Minsker K.S., Kolesov S.V., Zaikov G.E.. *Degradation and Stabilization of Polymers on the Base of VinylChloride*, Pergamon Press, 1988

81. Morlat-Therias S., Fanton E., Gardette J.L., Peeterbroeck S., Alexandre M., Dubois P. *Polymer/carbon nanotube nanocomposites: Influence of carbon nanotubes on EVA photodegradation* Polym. Degrad. Stab. 2007; 92 (10): 1873-82
82. Morton J.R., Negri F., Preston K.F. *Addition of alkyl radicals to C-60.3. The EPR-spectra of R3C60 radicals and a theoretical study of HC60 and H3C60 radicals.* Canadian Journal of Chemistry – Revue Canadienne de Chimie 1994; 72(3) : 776-82
83. Morton J.R., Negri F., Preston K.F. *Addition of free radicals to C-60.* Accounts of Chemical Research 1998; 31(2):63-9
84. Morton J.R., Preston K.F., Krusic P.J. *EPR spectroscopy of fullerene adducts.* Hyperfine Interactions 1994; 86(1-4):763-77
85. Morton J.R., Preston K.F., Krusic P.J., Hill S.A., Wasserman E. *ESR studies of the reaction of alkyl radicals with C-60.* Journal of Physical Chemistry 1992; 96(6):3576-78
86. Pabin-Szafko B., Wisniewska E., Szafko J. *Carbon nanotubes and fullerene in the solution polymerisation of acrylonitrile.* European Polymer Journal 2006; 42(7):1516–20
87. Pace M.D. *EPR of C-60 thermal/photochemical reactions with polystyrene and polymethyl methacrylate.* Applied Magnetic Resonance 1996; 11(2):253-61
88. Parfenov E.A., Zaikov G.E. *Biotic Type Antioxidants.* Utrecht: VSP Intern. Sci. Publ., 2000.
89. Pliss E.M. , Aleksandrov A.L. *Relative rate constants of an interaction of alkyl radicals of methacrylates and acrylates with oxygen and stable nitroxyl radicals.* Izvest AN SSSR, chem. iss. 1977; 4: 753-756

90. Pospisil J. *Aromatic and heterocyclic amines in polymer stabilization*. In: Adv Polym Sci, 124. Berlin: Springer, 1995, p.87-189
91. Pospisil J. *Chemical and photochemical behaviour of phenolic antioxidants in polymer stabilization – a state of the art report*. Part I. Polym Degrad Stab 1993;40(2):217-232
92. Pospisil J. *Chemical and photochemical behaviour of phenolic antioxidants in polymer stabilization – a state of the art report*. Part II. Polym Degrad Stab 1993 ; 39(1):103-115
93. Pospisil J., Klemchuk P.P., eds., *Oxidation Inhibition in Organic Materials*, Vols. I and II, CRC Press, Inc., Boca Raton, Fla., 1990
94. Rabek J.F. *Photostabilisation of Polymers: Principles and Applications*. London: Elsevier Applied Science Publishers, 1990
95. Roginsky V.A. *Phenolic Antioxidants: Efficiency and Reactivity*. M.: Nauka, 1988
96. Rozantsev E.G. *Organic Chemistry of Free Radicals*. M.: Khimiya, 1979
97. Schroeder H.F., Zeynalov E.B., Bahr H., Rybak Th. *Analysing the content of antioxidants in PP materials*. Polymer & Polymer Composites 2002; 10(1):73-82
98. Schroeder H.F., Zeynalov E.B., Bahr H., Rybak Th. Proceedings 7th International Plastics Additives and Modifiers Conference - Addcon World 2001; paper 20
99. Schwarzenbach K. In: Plastics additives handbook (Eds.: Gachter R, Muller H.) Munich: Hanser; 1989, ch.1.
100. Schwarzenbach K., In H. Zweifel, ed., *Plastics Additives Handbook*, Hanser, Munich, 2000, pp. 1–137
101. Schwetlick K., Habicher W.D. *Antioxidant action mechanisms of hindered amine stabilizers*. Polym Degrad Stab 2002; 78 (1): 35-40

102. Scott G. *Atmospheric Oxidation and Antioxidants*. London: Elsevier, 1993
103. Scott G., *Atmospheric Oxidation and Antioxidants*. Amsterdam: Elsevier, 1965
104. Sedlar J., Marshal J., Petruj J. *Photostabilizing mechanisms of HALS –a critical review*. Polym Photochem 1982; 2(3): 175-207
105. Sedlar J., Petruj J., Zahradnickova A. *Photostabilizing activity of sterically hindered piperidines-i: Peroxide decomposing and hydrogen donating ability*. Eur Polym J 1980; 16(7): 659-662
106. Seno M., Fukunaga H., Sato T. *Kinetic and ESR studies on radical polymerization of methyl methacrylate in the presence of fullerene*. Journal of Polymer Science Part A- Polymer Chemistry 1998; 36(16):2905-12
107. Seno M., Maeda M. and Sato T. *Effect of fullerene on radical polymerization of vinyl acetate*. Journal of Polymer Science Part A- Polymer Chemistry 2000; 38 (14): 2572-78
108. Shibaev L.A., Egorov V.M., Zgonnik V.N., Antonova T.A., Vinogradova L.V., Melenevskaya E.Y., Bershtein V.A. *An enhanced thermal stability of poly(2,6-dimethyl-1,4-phenylene oxide) in the presence of small additives of C₆₀ and C₇₀*. Polymer Science A 2001; 43(2):101-5
109. Shlyapnikov Y.A., Kiryushkin S.G., Mar'in A.P. *Antioxidative Stabilization of Polymers*. London: Taylor and Francis Ltd., 1996
110. Stewart D., Imrie C.T. *Role of C-60 in the free radical polymerisation of styrene*. Chemical Communications 1996; 11:1383-84
111. Taylor R. *The pattern of additions to fullerenes*. Plilosophical Trans.Royal Soc. A- Mathem. Phys.and Engineer. Sci. 1993; 343(1667): 87-101

112. Thilen M, Shishio R. Proceedings 2nd World Congress - Polypropylene in Textiles.Queensgate Huddersfield,UK. 2000; p.87-97
113. Troitskii B.B., Domrachev G.A., Khokhlova L.V., Anikina L.I. *Thermooxidative degradation of poly(methyl methacrylate) in the presence of C-60 fullerene.* Polymer Science A 2001; 43(9):964-9
114. Troitskii B.B., Domrachev G.A., Semchikov Y.D., Khokhlova L.V., Anikina L.L., Denisova V.N., Novikova M.A., Marsenova Y.A., Yashchuk L.M. *Fullerene-C-60, a new effective inhibitor of high-temperature thermooxidative degradation of methyl methacrylate copolymers.* Russian Journal of General Chemistry 2002; 72(8):1276-81
115. Troitskii B.B., Troitskaya L.S., Dmitriev A.A., Yakhnov A.S. *Inhibition of thermo-oxidative degradation of poly(methyl methacrylate) and polystyrene by C-60.* European Polymer Journal 2000; 36 (5):1073-84
116. Tsepalov V.F., Kharitonova A.A., Zeinalov E.B., Gladyshev G.P. *Investigation of antioxidants in complex compositions.* Azerb Khim Zhurn 1981; 4:113-116
117. Tsepalov V.F., Kharitonova A.A., Gladyshev G.P., Emanuel N.M. *Determination of the rate constants and inhibition coefficients of phenol antioxidants with the aid of model chain reactions / Determination of rate constants and inhibition coefficients of inhibitors using a model chain reaction.* Kinetics and Catalysis1977; 18(5) : 1034-41 / 18(6) : 1142-51
118. Wakai H., Shinno T., Yamauchi T., Tsubokawa N. *Grafting of poly(ethylene oxide) onto C-60 fullerene using macroazo initiators.* Polymer 2007; 48(7):1972-80

119. Walbiner M., Fischer H. *Rate constants for the addition of benzyl radical to C-60 in solution.* Journal of Physical Chemistry 1993; 97(19):4880-81
120. Yongcheng Y. *Thermal oxidation of polypropylene containing hindered piperidine compounds.* Polym Degrad Stab 1992; 37(1):11-17
121. Zaharescu T., Kaci M., Hebal G. et al. *Thermal stability of gamma irradiated low density polyethylene films containing hindered amine stabilizers.* Macromol Mater Eng 2004; 289(6): 524-530
122. Zaikov G.E. *Degradation and Stabilization of Polymers.* N.Y.: Nova Sci. Publ., 1999
123. Zeinalov E.B., Kossmehl G., Kimwomi R.R.K. *Synthesis and reactivity of antioxidants based on vernolic acid and 3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionic acid.* Angew Makromol Chem 1998; 260: 77-81
124. Zeinalov E.B., Koßmehl G. Fullerene C₆₀ as an antioxidant for polymers. Polymer Degradation and Stability 2001; 71(2): 197-202
125. Zeinalov EB, Schroeder HF, Bahr H. *Determination of Phenolic Antioxidant Stabilizers in PP and HDPE by Means of an Oxidative Model Reaction.* Proceedings 6th International Plastics Additives and Modifiers Conference - Addcon World 2000; paper 3
126. Zeynalov E.B., Aliyeva A.Z., Friedrich J.F. *Factors affecting the intrinsic anti-oxidative activity of carbon nanofibers: metallic impurities.* Materials Testing (Materials and Components ,Technology and Application) section Nanotechnology and Polymer Materials 2009; 51(4), 210-14
127. Zeynalov E.B., Allen N.S. *Simultaneous determination of the content and activity of sterically hindered phenolic and amine stabilizers by means of an*

- oxidative model reaction.* Polym Degrad Stab 2004; 85(2): 847-53
128. Zeynalov E.B., Friedrich J.F. *Antioxidant properties of multiwall carbon nanotubes: first measurements using a model oxidative reaction.* Polymers & Polymer Composites 2006; 14(8), 779-85
129. Zeynalov E.B., Friedrich J.F. *Antioxidative activity of carbon nanotube and nanofiber.* The Open Materials Science Journal 2008; 2 : 28-34
130. Zeynalov E.B., Friedrich J.F. *Anti-radical activity of fullerenes and carbon nanotubes in reactions of radical polymerization and polymer thermal/thermooxidative degradation (A review)* Materials Testing (Materials and Components ,Technology and Application), section Polymer Materials 2007; 49(5), 265-70
131. Zeynalov E.B., Magerramova M.Y., Ischenko N.Y. *Fullerenes C-60/C-70 and C-70 as antioxidants for polystyrene.* Iranian Polymer Journal 2004; 13(2):143-8
132. Zeynalov E.B., Vasnetsova O.A. *Kinetic Screening of Inhibitors of Radical Reactions.* Baku : Elm, 1993
133. Zeynalov E.B., Allen N.S. *Modelling light stabilizers as thermal antioxidants.* Polymer Degradation and Stability 2006; 91(12):3390-96
134. Zeynalov E.B., Allen N.S., Salmanova N.I. *Radical scavenging efficiency of different fullerenes C60-C70 and fullerene soot.* Polymer Degradation and Stability 2009; 94(8) : 1183 – 89
135. Zuev V.V., Bertini F., Audisio G. *Fullerene C₆₀ as stabiliser for acrylic polymers.* Polym Deg Stab 2005; 90(1) : 28-33
136. Zweifel H. *Stabilization beyond the year 2000.* Macromol Symp. 1997; 115:181-201
137. Zweifel H. *Stabilization of Polymeric Materials.* Berlin: Springer, 2000.

138. Zweifel H. *Stabilization of Polymeric Materials*, Berlin: Springer-Verlag, 1998,
139. Гладышев Г.П., Ершов Ю.А., Щустова О.А. *Стабилизация Термостойких Полимеров*. М.: Химия, 1979
140. Горбунов Б.Н., Гурвич Я.А., Маслова И.П. *Химия и Технология Стабилизаторов Полимерных Материалов*. М.: Химия, 1981
141. Гордон Г.Л. *Стабилизация Синтетических Полимеров*. М.: Химиздат, 1963
142. Грасси Н. *Химия Процессов Деструкции Полимеров* / под ред. Малинского Ю.М.М.: Издатинлит, 1959
143. Грасси Н., Скотт Дж. *Деструкция и Стабилизация Полимеров*. М.: Мир. 1988
144. Денисов Е.Т. *Константы Скорости Гомолитических Жидкофазных Реакций*. М.: Наука, 1971
145. Денисов Е.Т. *Окисление и Деструкция Карбоцепных Полимеров*. Л.: Химия, 1990
146. Заиков Г.Е. *Почему стареют полимеры ?* Соровский Общеобразовательный Журнал. 2000; 6(12) :48-55
147. Заиков Г.Е. *Деструкция и Стабилизация Полимеров*. М.: Изд-во МИТХТ им. М.В. Ломоносова, 1993
148. Зейналов Э.Б. *Природные ингибиторы азербайджанских нефлей* Баку : Элм, 1988
149. Зуев Ю.С., Дегтева Т.Г. Стойкость Эластомеров в Эксплуатационных Условиях М.: Химия, 1986
150. Кузьминский А.С., Кавун С.М., Кирпичев В.П. *Физико - Химические Основы Получения, Переработки и Применения Эластомеров*. М.: Химия, 1976
151. Пиотровский К.Б., Тарасова З.Н. *Стабилизация Синтетических Каучуков и Вулканизатов*. М.: Химия, 1980
152. Попов А.А., Рапорт Н.Я., Заиков Г.Е. *Окисление Ориентированных и Напряженных Полимеров*. М.: Химия, 1987

153. Рогинский В.А. *Фенольные Антиоксиданты. Реакционная Способность и Эффективность.* М.: Наука, 1988
154. Самедова Ф.И., Мир-Бабаев М.Ф. *Высокомолекулярные Гетероатомные Соединения Нефти Азербайджана.* Баку: Элм, 1992
155. Фойгт И. *Стабилизация Синтетических Полимеров Против Действия Тепла и Света.* М.: Химия, 1972
156. Шлятитох В.Я. *Фотохимические превращения и стабилизация полимеров.* М.: Химия, 1979
157. Эмануэль Н.М. *Задачи фундаментальных исследований в области старения и стабилизации полимеров.* Лекция 1. 4-ая полимерная школа, ГКНТ СМ СССР, 1970
158. Эмануэль Н.М., Бучаченко А.Л. *Химическая Физика Молекулярного Разрушения и Стабилизации полимеров.* М.: Наука, 1988
159. Эмануэль Н.М., Бучаченко А.Л. *Химическая Физика Старения и Стабилизации Полимеров.* М.: Наука, 1984
160. Эмануэль Н.М., Гладышев Г.П. Денисов Е.Т., Цепалов В.Ф., Харитонов В.В., Пиотровский К.Б. *Тестирование химических соединений как стабилизаторов полимерных материалов – Черноголовка, ОИХФ АН СССР, 1973 – 51с. /препринт/*
161. Эмануэль Н.М., Гладышев Г.П. Денисов Е.Т., Цепалов В.Ф., Харитонов В.В., Пиотровский К.Б. *Порядок тестирования химических соединений как стабилизаторов полимерных материалов – Черноголовка, ОИХФ АН СССР, 1976 – 36с. /препринт/*
162. Эмануэль Н.М., Денисов Е.Т., Майзус З.К. *Цепные реакции окисления углеводородов в жидкой фазе.* М.: Наука, 1965

10. Sənaye tipli antioksidantlar

Poliolefinlərin stabilləşdirilməsi üçün dünya miqyasında istehsal olunan antioksidantların əsas növləri və sinifləri aşağıda əlavədə verilir. Müxtəlif kimya müəssisələri, kompaniyaları və korporasiyaları tərəfindən alınan 214 adda müxtəlif çeşidli antioksidantlar verilmişdir.

11. Əlavə.

Poliolefinlərin stabilləşdirilməsi üçün dünya miqyasında istehsal olunan antioksidantların siyahısı



Ciba® CHIMASSORB® 119 FL



Monomeric Hindered Amine Light Stabilizer (HALS)

Characterization CHIMASSORB 119 FL is a monomeric, sterically hindered amine light stabilizer. The main advantage of CHIMASSORB 119 FL over other commercial HALS is that it enhances the color yield of the pigmented polyolefin articles. Because of its high molecular weight structure, it is the light stabilizer of choice for all applications calling for low volatility and high migration resistance. CHIMASSORB 119 FL is also effective as antioxidant and contributes significantly to the long term heat stability of polyolefins.

Chemical Name 1,3,5-Triazine-2,4,6-triamine,N,N''-[1,2-ethane-diyl-bis [[[4,6-bis-[butyl (1,2,2,6,6-pentamethyl-4-piperidinyl)amino]-1,3,5-triazine-2-yl] imino]-3,1-propanediyl]] bis [N',N''- dibutyl-N',N'-bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-]

CAS Number Preparation (106990-43-6, 90%)

Structure CHIMASSORB 119



Molecular weight 2286

Applications CHIMASSORB 119 FL is particularly effective in polypropylene, polyethylene, α -olefin copolymers and blends with EPR, EPDM, ERR, PE, EVA, EAA, EVOH and filled PP.

It can be also used in elastomers, e.g. EPDM, SBS, SIS, SEBS, styrenics and α -methyl styrenics, e.g. ABS, SAN, AES, ASA, IPS, SMA blends or alloys of these polymers with others, adhesives, hot melts, flexible and rigid PVC, PVDC, polyurethanes, polyamides, e.g. PA 6, PA 6,6, PA 12, POM (homo- and copolymers), PPE, PET, PBT and blends PMMA cast sheets and thermoplastic resins, UPE, PET and PA fibers.

Features/ Benefits Benefits of using CHIMASSORB 119 FL is the high light-stabilizing performance, particularly in PP fibers. It has broad compatibility and can be easily dispersed. CHIMASSORB 119 FL shows a unique long-term thermal performance in filled PP thick articles, specifically when containing carbon black. It is therefore recommended in under-the-hood automotive applications when sulfur-containing stabilizers are undesirable because of odor. CHIMASSORB 119 FL significantly enhances the color yield of many

organic pigments and therefore it finds broad usage in PP fibers. Combined with other HALS it gives rise to synergistic mixtures, e.g. TINUVIN 111.

Product Forms	Code: CHIMASSORB 119 FL	Appearance: slightly yellow granules
Guidelines for use	Thick sections	UV stabilization of PP 0.15 - 0.5%
	Fibers	UV stabilization of PP 0.05 - 1.0%
Physical Properties		
	Melting Range	115 - 150°C
	Flashpoint	278°C ASTM D92 - 78
	Specific Gravity (20°C)	1.03 g/cm³
	Vapor Pressure (20°C)	4.7 E-11 Pa
	Bulk density	500 - 600 g/l
	Solubility (20°C)	g/100g Solution
	Acetone	~ 2
	Chloroform	20
	Ethanol	5
	Ethyl acetate	~ 1
	n-Hexane	~ 1
	Methanol	~ 1
	Methylene chloride	20
	Toluene	25
	Water	< 0.01
	Volatility (pure substance; TGA-data, heating rate 20°C/min in air)	
	Temperature (°C)	% weight loss
	200	0.7
	250	1.1
	300	2.7
Handling & Safety		
	In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Protect skin. Prevent contamination of the environment. Avoid dust formation and ignition sources.	
	For more detailed information please refer to the material safety data sheet.	
Registration		
	The registration status for CHIMASSORB 119 FL is derived from the single components. The components are registered in: Australia, Canada, China, EU, Japan, Korea, Philippines, USA.	
	They are approved in various countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Dec.-75 Product Name: CHIMASSORB 119 FL
Printing Date: Nov-99

page 2
©Ciba Specialty Chemicals, Inc.


Ciba® IRGANOX® 1010**Phenolic Primary Antioxidant for Processing and Long-Term Thermal Stabilization**

Characterization IRGANOX 1010 - a sterically hindered phenolic antioxidant - is a highly effective, non discoloring stabilizer for organic substrates such as plastics, synthetic fibers, elastomers, adhesives, waxes, oils and fats. It protects these substrates against thermo-oxidative degradation.

Chemical Name Pentaerythritol Tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)

CAS Number 6683-19-8

Structure IRGANOX 1010



Molecular weight 1178

Applications IRGANOX 1010 can be applied in polyolefins, such as polyethylene, polypropylene, polybutene and olefin copolymers such as ethylene-vinylacetate copolymers. Also, its use is recommended in other polymers such as polyacetals, polyamides and polyurethanes, polyesters, PVC, styrene homo- and copolymers, ABS, elastomers such as butyl rubber (IIR), SBS, SEBS, EPM and EPDM as well as other synthetic rubbers, adhesives, natural and synthetic tackifier resins, and other organic substrates.

Features/ Benefits IRGANOX 1010 has good compatibility, high resistance to extraction and low volatility. It is odorless and tasteless. The product can be used in combination with other additives such as costabilizers (e.g. thioethers, phosphites, phosphonites), light stabilizers and other functional stabilizers. The effectiveness of the blends of IRGANOX 1010 with IRGAFOS 168 (IRGANOX B-blends) or with IRGAFOS 168 and HP-136 (IRGANOX HP products) is particularly noteworthy.

Product Forms	Code:	Appearance:
Powder :	powder	white, free-flowing powder
	FF (C)	white, free-flowing granules
	DD	white to slightly green pellets

Guidelines for Use Already 500 ppm - 1000 ppm of IRGANOX 1010 provide long-term thermal stability to the polymer. Concentrations up to several percent may be used depending on the substrate and the requirements of the end application.
In polyolefins the concentration levels for IRGANOX 1010 range between 0.05% and 0.4% depending on substrate, processing conditions and long-term thermal stability requirements. The optimum level has to be determined application specific.
Concentration levels of IRGANOX 1010 in hot melt adhesives range from 0.2% to 1%, in synthetic tackifier resins, IRGANOX 1010 concentration ranges between 0.1% and 0.5%. Extensive performance data of IRGANOX 1010 in various organic polymers and applications are available upon request.

Physical Properties

Melting Range (°C)	110-125
Flashpoint (°C)	297
Specific Gravity (20°C)	1.15 g/cm ³
Bulk density	powder: 530 - 630 g/l FF (C): 480 - 570 g/l DD: 450 - 550 g/l
Solubility (20°C)	g/100g solution
Acetone	47
Chloroform	71
Ethanol	1.5
Ethylacetate	47
n-Hexane	0.3
Methanol	0.9
Methylene Chloride	63
Toluene	60
Water	<0.01

Handling & Safety

In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources.
For more detailed information please refer to the material safety data sheet.

Registration

IRGANOX 1010 is listed on the following inventories:

Australia: AICS	Canada: DSL	China: First Import
Europe: EINECS	Japan: MITI	Korea: ECL
Philippines: PICCS	USA: TSCA	

IRGANOX 1010 is approved in many countries for use in food contact applications.
For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Product Name: IRGANOX 1010
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.


**Ciba® IRGANOX® 1035****Antioxidant and Heat Stabilizer for Wire and Cable Applications**

Characterization IRGANOX 1035 is a sulfur containing primary (phenolic) antioxidant and heat stabilizer used for the process stabilization of polyethylene wire and cable resins.

Chemical Name Thiodiethylene bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate].

CAS Number 41484-35-9

Structure IRGANOX 1035



Molecular weight 643

Applications Carbon black containing wire and cable resins

LDPE wire and cable PVA

XLPE wire and cable Polyol/PUR

PP Elastomers

HIPS Hot melt adhesives

ABS

Features/ Benefits The world's most widely used antioxidant for PE and XLPE wire and cable resins, IRGANOX 1035, provides efficient processing stabilization and long-term thermal stability with excellent system compatibility and low color. The high quality of IRGANOX 1035 eliminates the concern over microcontaminants that can effect the insulation properties of the wire. Compared with other wire and cable base stabilization antioxidants, IRGANOX 1035 offers better heat stability and is less likely to exude. IRGANOX 1035 prevents scorching of PUR flexible foams in combination with an aminic antioxidant such as IRGANOX 5057 and is used as a replacement for BHT.

Product Forms

Code
powder
FF

Appearance:
white to off-white crystalline powder
white to off-white crystalline granules

Guidelines for use In XLPE or carbon black containing polymers, IRGANOX 1035 offers optimum performance when used in combination with the thiosynergist, IRGANOX PS 800. Recommended levels:

IRGANOX 1035 0.2-0.3%
IRGANOX PS 800 0.2-0.3%

In polyol, the recommended concentration of an IRGANOX 1035/IRGANOX 5057 blend is:
IRGANOX 1035 0.3-0.4%
IRGANOX 5057 0.3-0.4%

Physical Properties

Melting Range (°C)	63-67
Flashpoint (°C)	279
Specific Gravity (20°C)	1.00 g/cm ³
Vapor Pressure (20°C)	10 ⁻¹¹ Torr
Bulk density	powder: 530 - 630 g/l
Bulk density	FF: 480 - 570 g/l
Solubility (20°C)	g/100g solution
Water	< 0.01
Acetone	56
Benzene	56
Chloroform	35
Cyclohexane	56
Ethyl acetate	45
n-Hexane	5
Methanol	5

Handling & Safety In accordance with good industrial practice, handle with care and avoid release to the environment. Avoid dust formation and ignition sources.
For more detailed information please refer to the material safety data sheet.

Registration

IRGANOX 1035 is listed on the following inventories:
Australia: AICS Canada: DSL China: First Import
Europe: EINECS Japan: MITI Korea: ECL
Philippines: PICCS USA: TSCA

IRGANOX 1035 is approved in many countries for use in food contact applications.
For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Aug-73 Product Name: IRGANOX 1035
Printing Date: Sep-99

page 2
©Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® 1076


Phenolic Primary Antioxidant for Processing and Long-Term Thermal Stabilization

Characterization IRGANOX 1076, a sterically hindered phenolic antioxidant, is highly efficient, non discoloring stabilizer for organic substrates such as plastics, synthetic fibers, elastomers, adhesives, waxes, oils and fats. It protects these substrates against thermo-oxidative degradation. IRGANOX 1076 is odorless, stable to light and has excellent color retention. It has good compatibility with most substrates, low volatility and high resistance to extraction.

Chemical Name Octadecyl-3-(3,5-di-tert.butyl-4-hydroxyphenyl)-propionate

CAS Number 2082-79-3

Structure



Molecular weight 531 g/mol

Applications IRGANOX 1076 can be applied in polyolefins such as polyethylene, polypropylene, polybutene-1 as well as in other polymers such as engineering plastics, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/ Benefits IRGANOX 1076 can be used in combination with other additives such as costabilizers (e.g. thioesters, phosphites, phosphonites), light stabilizers, and other functional stabilizers. The effectiveness of the blends of IRGANOX 1076 with IRGAFOS 168 (IRGANOX B-blends) or with IRGAFOS 168 and Lactone HP-136 (IRGANOX HP-products) is particularly noteworthy.

Product Forms	Code: IRGANOX 1076 IRGANOX 1076 FF (C) IRGANOX 1076 FD	Appearance: white powder white, free-flowing granules white, free-flowing, dust free pastilles

Guidelines for use 500 ppm - 2000 ppm of IRGANOX 1076 provide long-term thermal stability to the polymer. Concentrations up to several percent can be used depending on the substrate and the requirements of the end application.

In polyolefins the concentration levels for IRGANOX 1076 range between 0.1% and 0.4% depending on substrate, processing conditions and long-term thermal stability requirements. The optimum level is application specific.

IRGANOX 1076 is recommended for styrene homo- and copolymers at a concentration level ranging from 0.1 to 0.3 %.

Concentration levels of IRGANOX 1076 in hot melt adhesives range from 0.2% to 1% and in synthetic tackifier resins between 0.1% and 0.5%.

Extensive performance data of IRGANOX 1076 in various organic polymers and applications are available upon request.

Physical Properties

Melting Range	50 - 55°C
Flashpoint	273°C
Vapor Pressure (20°C)	2.5 E-7 Pa
Bulk density	Powder: 260 - 320 g/l

Volatility (TGA, in air at 20°C/ min)

Temp. at 1% weight loss	230°C
Temp. at 10% weight loss	288°C

Solubility (20°C) % w/w

Water	< 0.01
Acetone	19
Benzene	57
Chloroform	57
Cyclohexane	40
Ethanol	1.5
Ethylacetate	38
n-Hexane	32
Methanol	0.6
Toluene	50

Handling & Safety

In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources.
For more detailed information please refer to the material safety data sheet.

Registration

IRGANOX 1076 is listed on the following Inventories:
Australia: AICS Canada: DSL China: First Import
Europe: EINECS Japan: MITI Korea: ECL

Philippines: PICCS USA: TSCA

IRGANOX 1076 is approved in many countries for use in food contact applications.
For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Feb-76 Product Name: IRGANOX 1076
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



[®]IRGANOX 1081

High Performance Antioxidant and Heat Stabilizer for Wire and Cable Applications

Date first Edition: May-80 Product Name: IRGANOX 1081
Printing Date: Oct-99

page 1

Physical Properties

Melting Range (°C)	81-86
Flashpoint (°C)	> 150
Specific Gravity (20°C)	1.15 g/cm ³
Vapor Pressure (20°C)	1.5x10 ⁻⁴ Torr
Bulk density	powder: 530 - 630 g/l
Solubility (20°C)	g/100g solution
Acetone	> 50
Benzene	> 50
Chloroform	> 50
Ethyl acetate	> 50
n-hexane	28
Methanol	35
Methylene chloride	> 50
Water	< 0.01

Handling & Safety

In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Protect skin. Prevent contamination of the environment. Avoid dust formation and ignition sources.
For more detailed information please refer to the material safety data sheet.

Registration

IRGANOX 1081 is listed on the following inventories:

Australia: AICS Canada:NDSL Europe: EINECS

Japan: MITI Philippines: PICCS USA: TSCA

IRGANOX 1081 is approved in many countries for use in food contact applications.
For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: May-80 Product Name: IRGANOX 1081
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® 1330


Phenolic Primary Antioxidant for Processing and Long-Term Thermal Stabilization

Characterization IRGANOX 1330 - a sterically hindered phenolic antioxidant - is as highly effective stabilizer for organic substrates such as polymers, synthetic fibers, elastomers, adhesives, waxes, oils and fats. It protects these substrates against thermo-oxidative degradation.

Chemical Name 3,3',3",5,5',5'-hexa-tert-butyl-a,a'-mesitylene-2,4,6-triyl)tri-p-cresol

CAS Number 1709-70-2

Structure IRGANOX 1330



Molecular weight 775

Applications IRGANOX 1330 is used in polyolefins e.g. polyethylene, polypropylene, polybutene for the stabilization of pipes, molded articles, wires and cables, dielectric films etc. Furthermore, it is applied in other polymers such as engineering plastics like linear polyesters, polyamides, and styrene homo- and copolymers. It may also be used in PVC, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/ Benefits IRGANOX 1330 has good compatibility with most substrates, high resistance to extraction and is odorless. It offers also excellent dielectrical properties. The product can be used in combination with other additives such as costabilizers (e.g. thioethers, phosphites, phosphonites), light stabilizers and other functional stabilizers. The effectiveness of the blends of IRGANOX 1330 with IRGAFOS 168 (IRGANOX B-blends) is particularly noteworthy. IRGANOX 1330 is particularly recommended for polyolefin applications requiring good water extraction resistance combined with low color development. Furthermore, IRGANOX 1330 reduces water carry-over in polypropylene tape extrusion.

Product Forms	Code: powder FF :	Appearance: white, free-flowing powder white, free-flowing granules
Guidelines for Use	In polyolefins, the concentration levels for IRGANOX 1330 range typically between 0.05% and 0.3% depending on substrate, processing conditions and long-term thermal stability requirements. The optimum level is application specific. Concentration levels of IRGANOX 1330 in hot melt adhesives range from 0.2% to 1%, in synthetic tackifier resins, IRGANOX 1330 concentration ranges between 0.1% and 0.5%. Extensive performance data of IRGANOX 1330 in various organic polymers and applications are available upon request.	
Physical Properties		
Melting Range (°C)	240 - 245	
Flashpoint (°C)	321	
Specific Gravity (20°C)	1.04 g/cm ³	
Bulk density	powder : 530 - 630 g/l FF : 480 - 570 g/l	
Solubility (20°C)	g/100g solution	
Acetone	18	
Chloroform	28	
Ethanol		
Ethylacetate	27	
n-Hexane	10	
Methanol	3	
Methylene Chloride	34	
Toluene		
Water	<= 0.01	
Handling & Safety	In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	IRGANOX 1330 is listed on the following inventories: Australia: AICS Canada: DSL China: First Import Europe: EINECS Japan: MITI Korea: ECL Philippines: PICCS USA: TSCA IRGANOX 1330 is approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Nov-80 Product Name: IRGANOX 1330
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.


**Ciba® IRGANOX® 1425 WL****Phenolic Antioxidant**

Characterization IRGANOX 1425 WL is a combination of Irganox 1425 and Wax (ratio 1:1). IRGANOX 1425 is a calcium phosphonate derivative of IRGANOX 1222. It is characterized by a very high extraction resistance and extreme low volatility. IRGANOX 1425 WL provides thermo-oxidative stability to polyolefins.

Chemical Name 1:1-Combination of Phosphonic acid, [(3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl)methyl], monoethylester, calcium salt (2:1) and polyethylene-wax

CAS Number Preparation

Structure IRGANOX 1425



Molecular weight IRGANOX 1425: 695

Applications IRGANOX 1425 WL is particularly well suited for polypropylene fibers, when combined with IRGAFOS 168.

Features/ Benefits IRGANOX 1425 WL in combination with IRGAFOS 168 (IRGAFOS B 501 W) gives good processing stability during polypropylene fiber production. It shows good gas fading resistance and low color development during storage. IRGANOX 1425 WL performance is practically not influenced by alkaline additives (e.g. spin finishes, HALS, antacids). It makes PP fibers brilliant, which is of particular interest in some BCF/CF applications. Its long-term thermal performance is unmatched by any other phenolic in the market.

Product Forms Code: IRGANOX 1425 WL Appearance: white to off-white powder odourless

Guidelines for use Recommended use levels are 0.10-0.25%.

Physical Properties	
Melting Range (°C)	90 - 300
Flashpoint (°C)	> 150
Vapor Pressure (20°C)	<0.01
Bulk density	420 - 460
Solubility (20°C)	g/100g solution
Water	<0.01 %

Handling & Safety	In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Avoid continuous or repetitive breathing of dust. Use only with adequate ventilation. In case of insufficient ventilation wear suitable respiratory equipment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.
Registration	The registration status for IRGANOX 1425 WL is derived from the single components. The components are registered in: Australia, Canada, China, EU, Japan, Korea, Philippines, USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: 1981 Product Name: Irganox 1425 WL
Printing Date: 24.01.2000

page 2
©Ciba Specialty Chemicals, Inc.

Ciba® IRGANOX® 3114


Phenolic Primary Antioxidant for Processing and Long-Term Thermal Stabilization

Characterization IRGANOX 3114 - a sterically hindered phenolic antioxidant - is a highly effective, non discoloring stabilizer for organic substrates such as polymers, synthetic fibers, elasto-mers, adhesives, waxes, oils and fats. It protects these substrates against thermo-oxidative degradation and contributes to their light stability.

Chemical Name 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione.

CAS Number 27676-62-6

Structure IRGANOX 3114



Molecular weight 784

Applications IRGANOX 3114 can be applied in polyolefins, namely polyethylene, polypropylene, polybutene as well as in other polymers such as styrene homo- and copolymers. It may also be used in linear polyesters, PVC, polyamides and polyurethanes, elastomers such as SBS, EPR, EPDM and other synthetic rubbers, adhesives, natural and synthetic tackifier resins and other organic substrates.

Features/ Benefits IRGANOX 3114 has good compatibility with most substrates, high resistance to extraction, and low volatility. It is odorless and stable to light. The product can be used in combination with other additives such as costabilizers (e.g. thioethers, phosphites, phosphonites), light stabilizers and other functional stabilizers. The effectiveness of the blends of IRGANOX 3114 with IRGAFOS 168 (IRGANOX B-blends) or with IRGAFOS 168 and HP-136 (IRGANOX HP products) is particularly noteworthy.

Product Forms	Code: powder FF	Appearance: white, free-flowing powder white, free-flowing granules		
Guidelines for Use	In polyolefins, the concentration levels for IRGANOX 3114 range typically between 0.05% and 0.3% depending on substrate, processing conditions and long-term thermal stability requirements. The optimum level is application specific. Extensive performance data of IRGANOX 3114 in various organic polymers and applications are available upon request.			
Physical Properties				
Melting Range (°C)	218 - 223			
Flashpoint (°C)	289			
Specific Gravity (20°C)	1.03 g/cm ³			
Bulk density	powder : 530 - 630 g/l FF : 480 - 570 g/l			
Solubility (25°C)	g/100g solution			
Acetone	29			
Chloroform	21			
Ethanol	1.5			
Ethylacetate				
n-Hexane	0.6			
Methanol	0.5			
Methylene Chloride				
Toluene				
Water	0.01			
Handling & Safety	In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.			
Registration	IRGANOX 3114 is listed on the following inventories:			
Australia: AICS	Canada: DSL	Europe: EINECS		
Japan: MITI	Korea: ECL	Philippines: submitted		
USA: TSCA				
IRGANOX 3114 is approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.				

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Sep-87 Product Name: IRGANOX 3114
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® B 215


Synergistic Processing and Long-Term Thermal Stabilizer System

Characterization IRGANOX B 215 - a processing and long-term thermal stabilizer system - is a synergistic blend of IRGAFOS 168 and IRGANOX 1010.

Chemical Name 67 % IRGAFOS 168 ; 33 % IRGANOX 1010

CAS Number Preparation

Structure



Molecular weight

646.9

1178

Applications

IRGANOX B 215 is used in polyolefins and olefin-copolymers such as polyethylene, polypropylene, polybutene and ethylene-vinylacetate copolymers. The blend can also be used in other polymers such as engineering plastics, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates. IRGANOX B 215 can be used in combination with light stabilizers of the TINUVIN and CHIMASSORB range.

Features/Benefits

IRGANOX B 215 is a convenient blend addressing a range of stabilization needs. In the recommended applications IRGANOX B 215 provides significant advantages, such as

- Maintenance of original melt flow
- Low color formation
- Improvement of long-term thermal stability

IRGAFOS 168 - an organophosphite of low volatility and particularly resistant to hydrolysis - protects during processing organic polymers which are prone to oxidation. IRGANOX 1010 - a hindered phenolic antioxidant - contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life.

Additional performance improvements can be achieved in synergistic combinations with other Ciba additives (e.g. thioethers). Blends of IRGANOX 1010 and IRGAFOS 168 with HP-136 (IRGANOX HP products) are particularly effective.

Product Forms	Code: powder FF:	Appearance: white, free-flowing powder white, free-flowing granules
Guidelines for Use In polyolefins, the concentration levels for IRGANOX B 215 range typically between 0.1% and 0.25%, depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of IRGANOX B 215 in various organic polymers and applications are available upon request.		
Physical Properties	Bulk Density FF	530 - 630 g/l 480 - 570 g/l
Handling & Safety IRGANOX B 215 requires no special safety measures provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet		
Registration	The registration status for IRGANOX B 215 is derived from the single components. The components are registered in: Australia, Canada, China, EU, Japan, Korea, Philippines, USA They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Apr-86 Product Name: IRGANOX B 215
Printing Date: FEB-01

page 2
© Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® B 501W


Synergistic Mixture of Phenolic Antioxidant with Phosphite

Characterization IRGANOX B 501W is a synergistic mixture of IRGANOX 1425 WL and IRGAFOS 168 (ratio 1:1). It is highly effective in polypropylene fibers against thermo-oxidative degradation.

Chemical Name 1:1:2-Combination of Phosphonic acid, [(3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl)methyl]-, monoethylester, calcium salt (2:1); polyethylene-wax and phenol, 2,4-bis(1,1-dimethylethyl)-, phosphite

CAS Number Preparation

Structure IRGANOX 1425 WL and IRGAFOS 168



Molecular weight 695

647

Applications IRGANOX B 501W is particularly well suited for polypropylene fibers.

Features/ Benefits IRGANOX B 501W gives good processing stability during polypropylene fiber production. It shows good gas fading resistance and provides superior long-term thermal performance. IRGANOX B 501W gives brilliance to PP fibers, which is of particular interest in some BCF/CF applications. It is not influenced by alkaline additives.

Product Forms Code:
IRGANOX B 501W
IRGANOX B 501W FF Appearance:
white powder
white, free-flowing granules

Guidelines for use Recommended use levels are 0.15-0.25%.

Physical Properties

Melting Range (°C)	50 - 300
Flashpoint (°C)	>150
Bulk density (g/l)	Powder: 420 - 460 FF: 400 - 500
Solubility (20°C)	g/100g solution
Water	<0.01%

Handling & Safety

In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Avoid continuous or repetitive breathing of dust. Use only with adequate ventilation. In case of insufficient ventilation wear suitable respiratory equipment. Avoid dust formation and ignition sources.

For more detailed information please refer to the material safety data sheet.

Registration

The registration status for IRGANOX B 501W is derived from the single components.
The components are registered in: Australia, Canada, China, EU, Japan, Korea, Philippines, USA.

They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: 1982 Product Name: IRGANOX B 501W
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



CIBA® IRGANOX® HP 2215


High Performance Melt Processing Stabilizer System

Characterization IRGANOX HP 2215 - a processing and long-term thermal stabilizer system - is a synergistic blend of IRGAFOS 168, IRGANOX 1010 and HP-136.

Chemical Name 57 % IRGAFOS 168 ; 28 % IRGANOX 1010 ; 15 % HP 136

CAS Number Preparation

Structure IRGAFOS 168 IRGANOX 1010 HP-136



Molecular weight 646.9 1178 350.5

Applications IRGANOX HP 2215 provides outstanding processing stability in a variety of substrates and applications. The increased effectiveness over conventional stabilizers such as IRGANOX B 215 or IRGANOX B 561 is particularly pronounced in Polypropylene and for demanding processing applications in Polyethylenes. IRGANOX HP 2215 can also be used in other polymers such as engineering plastics including aliphatic polyketone, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/Benefits The relatively high phosphite content of IRGANOX HP 2215 addresses applications with demanding processing conditions. In the recommended applications IRGANOX HP 2215 offers superior performance and increased productivity over conventional antioxidant systems in terms of:

- Improved melt flow control
- Low initial color and outstanding color maintenance
- Superior effectiveness at high processing temperature for demanding applications
- Lower use levels leading to improved additive compatibility.

 The lactone HP-136 functions as a carbon-centered radical scavenger which inhibits processing induced oxidation as soon as it starts. IRGAFOS 168 - an organophosphite of low volatility and particularly resistant to hydrolysis - protects the polymer during processing by decomposing the hydroperoxides.

IRGANOX 1010 - a hindered phenolic antioxidant - contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life.
 Additional performance improvements can be achieved in synergistic combinations with other Ciba additives (e.g. thioethers).
 The lactone HP-136 present in the blend can also be beneficial for the reduction of the monomer level in the final polymer such as styrene homo- and copolymers.

Product Forms	Code: FF:	Appearance: white, free-flowing granules
Guidelines for Use	In the recommended applications the concentration levels for IRGANOX HP 2215 range typically between 0.05% and 0.15% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of IRGANOX HP 2215 in various organic polymers and applications are available upon request.	
Physical Properties	Bulk Density FF	480 - 570 g/l
Handling & Safety	IRGANOX HP 2215 requires no special safety measures, provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	The registration status for IRGANOX HP 2215 is derived from the single components. The components are registered in: Canada, EU, Japan, Korea, USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: *The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.*

Date first Edition: Mar-97 Product Name: IRGANOX HP 2215
 Printing Date: Oct-99

page 2
 ©Ciba Specialty Chemicals, Inc.



CIBA® IRGANOX® HP 2225


High Performance Melt Processing Stabilizer System

Characterization IRGANOX HP 2225 - a high performance melt processing stabilizer system - is a syner-gistic blend of IRGAFOS 168, IRGANOX 1010 and HP-136.

Chemical Name 42.5 % IRGAFOS 168 ; 42.5 % IRGANOX 1010 ; 15 % HP-136

CAS Number Preparation

Structure IRGAFOS 168 IRGANOX 1010 HP-136



Molecular weight 646.9 1178 350.5

Applications IRGANOX HP 2225 provides outstanding processing stability in a variety of substrates and applications. The increased effectiveness over conventional stabilizers such as IRGANOX B 215 or IRGANOX B 225 is particularly pronounced in Polypropylene and for demanding processing applications in Polyethylenes.

IRGANOX HP 2225 can also be used in other polymers such as engineering plastics including aliphatic polyketone, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/Benefits In the recommended applications IRGANOX HP 2225 offers superior performance and increased productivity over conventional antioxidant systems in terms of:

- Improved melt flow control
- Low initial color and outstanding color maintenance
- Superior effectiveness at high processing temperature for demanding applications
- Lower use levels leading to improved additive compatibility.

The lactone HP-136 functions as a carbon-centered radical scavenger which inhibits processing induced oxidation as soon as it starts.

IRGAFOS 168 - an organophosphite of low volatility and particularly resistant to hydrolysis - protects the polymer during processing by decomposing the hydroperoxides.

IRGANOX 1010 - a hindered phenolic antioxidant - contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life.

Additional performance improvements can be achieved in synergistic combinations with other Ciba additives (e.g. thioethers).

The lactone HP-136 present in the blend can also be beneficial for the reduction of the monomer level in the final polymer such as styrene homo- and copolymers.

Product Forms	Code: FF	Appearance: white, free-flowing granules
Guidelines for Use		
		In the recommended applications the concentration levels for IRGANOX HP 2225 range typically between 0.05% and 0.15% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of IRGANOX HP 2225 in various organic polymers and applications are available upon request.
Physical Properties		
	Bulk Density FF	480 - 570 g/l
Handling & Safety		
		IRGANOX HP 2225 requires no special safety measures, provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.
Registration		
		The registration status for IRGANOX HP 2225 is derived from the single components. The components are registered in: Canada, EU, Japan, Korea, USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Mar-97 Product Name: IRGANOX HP 2225
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



CIBA® IRGANOX® HP 2411


High Performance Melt Processing Stabilizer System

Characterization IRGANOX HP 2411 - a high performance melt processing stabilizer system - is a synergistic blend of IRGAFOS 168, IRGANOX 3114 and HP-136.

Chemical Name 42.5 % IRGAFOS 168 ; 42.5 % IRGANOX 3114 ; 15 % HP-136

CAS Number Preparation

Structure IRGAFOS 168 IRGANOX 3114 HP-136



Molecular weight	646.9	784	350.5
-------------------------	-------	-----	-------

Applications IRGANOX HP 2411 provides outstanding processing stability in a variety of substrates and applications. The increased effectiveness over conventional stabilizers such as IRGANOX B 1411 or IRGANOX B 1412 is particularly pronounced in polypropylene (e.g. injection molded applications, filled grades, fibers..). IRGANOX HP 2411 can also be used in other polymers such as engineering plastics, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/Benefits In the recommended applications IRGANOX HP 2411 offers superior performance and increased productivity over conventional antioxidant systems in terms of:

- Improved melt flow control
- Low initial color and outstanding color maintenance
- Superior effectiveness at high processing temperature for demanding applications
- Lower use levels leading to improved additive compatibility.

The lactone HP-136 functions as a carbon-centered radical scavenger which inhibits processing induced oxidation as soon as it starts.
 IRGAFOS 168 - an organophosphite of low volatility and particularly resistant to hydrolysis - protects the polymer during processing by decomposing the hydroperoxides.
 IRGANOX 3114 - a hindered phenolic antioxidant - contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life.
 The lactone HP-136 present in the blend can also be beneficial for the reduction of the monomer level in the final polymer such as styrene homo- and copolymers.
 Additional performance improvements can be achieved in synergistic combinations with other Ciba additives (e.g. thioethers).

Product Forms	Code: FF :	Appearance: white, free-flowing granules
Guidelines for Use	In the recommended applications the concentration levels for IRGANOX HP 2411 range typically between 0.05% and 0.15% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of IRGANOX HP 2411 in various organic polymers and applications are available upon request.	
Physical Properties	Bulk Density	FF 480 - 570 g/l
Handling & Safety	IRGANOX HP 2411 requires no special safety measures, provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	The registration status for IRGANOX HP 2411 is derived from the single components. The components are registered in: Canada, EU, Japan, Korea, USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Mar-97 Product Name: IRGANOX HP 2411
 Printing Date: Oct-99

page 2
 ©Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® HP 2921


High Performance Melt Processing Stabilizer System

Characterization IRGANOX HP 2921 - a processing and long-term thermal stabilizer system - is a synergistic blend of IRGAFOS 168, IRGANOX 1076 and HP-136.

Chemical Name 57 % IRGAFOS 168 ; 28 % IRGANOX 1076 ; 15 % HP-136

CAS Number Preparation

Structure	IRGAFOS 168	IRGANOX 1076	HP-136
------------------	-------------	--------------	--------



Molecular weight	646.9	531	350.5
-------------------------	-------	-----	-------

Applications IRGANOX HP 2921 provides outstanding processing stability in a variety of substrates and applications. The increased effectiveness over conventional stabilizers such as IRGANOX B 921 or IRGANOX B 900 is particularly pronounced in demanding processing Polyethylenes applications. IRGANOX HP 2921 can also be used in other polymers such as engineering plastics including aliphatic polyketone, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/Benefits The relatively high phosphite content of IRGANOX HP 2921 addresses applications with demanding processing conditions. In the recommended applications IRGANOX HP 2921 offers superior performance and increased productivity over conventional antioxidant systems in terms of:

- Improved melt flow control
- Low initial color and outstanding color maintenance
- Superior effectiveness at high processing temperature for demanding applications
- Lower use levels leading to improved additive compatibility.

The lactone HP-136 functions as a carbon-centered radical scavenger which inhibits processing induced oxidation as soon as it starts.

IRGAFOS 168 - an organophosphite of low volatility and particularly resistant to hydrolysis.
 - protects the polymer during processing by decomposing the hydroperoxides.
 IRGANOX 1076 - a hindered phenolic antioxidant - contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life.
 Additional performance improvements can be achieved in synergistic combinations with other Ciba additives (e.g. thioethers).
 The lactone HP-136 present in the blend can also be beneficial for the reduction of the monomer level in the final polymer such as styrene homo- and copolymers.

Product Forms	Code: FF	Appearance: white, free-flowing granules
Guidelines for Use	In the recommended applications the concentration levels for IRGANOX HP 2921 range typically between 0.05% and 0.15% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of IRGANOX HP 2921 in various organic polymers and applications are available upon request.	
Physical Properties	Bulk Density FF	480 - 570 g/l
Handling & Safety	IRGANOX HP 2921 requires no special safety measures, provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	The registration status for IRGANOX HP 2921 is derived from the single components. The components are registered in: Canada, EU, Japan, Korea, USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Mar-97 Product Name: IRGANOX HP 2921
 Printing Date: Oct.-99

page 2
 ©Ciba Specialty Chemicals, Inc.



Ciba® IRGANOX® XP 620


High performance stabilizer system

Characterization IRGANOX XP 620 provides highly effective protection of polymer properties across a broad range of processing conditions. IRGAFOS 126, IRGANOX 1010 and HP-136 perform synergistically for improved stabilization and reduced stabilizer use-levels.

Chemical Name 33 % IRGAFOS 126 ; 50 % IRGANOX 1010 ; 17 % HP-136

CAS Number Preparation

Structure IRGAFOS 126 IRGANOX 1010



Molecular weight

604 g/mol

1178 g/mol

350 g/mol

Applications IRGANOX XP 620 provides outstanding processing stability in a variety of substrates and applications. The increased effectiveness is particularly pronounced in HDPE, when processing conditions are particularly demanding. IRGANOX XP 620 can also be used in other polymers such as polypropylene, engineering plastics including aliphatic polyketone, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Features/Benefits IRGANOX XP 620 provides cost/performance improvements in polymer stabilization. IRGANOX XP 620 offers

- improved melt flow control
- low initial color and outstanding color maintenance
- superior effectiveness at high processing temperature for demanding applications
- up to 50% reduction of phosphite concentration

The lactone, HP-136, functions as a carbon-centered radical scavenger which inhibits processing induced oxidation as soon as it starts. IRGAFOS 126, an organic phosphite of low volatility, protects the polymer during processing by decomposing the hydroperoxides. IRGANOX 1010, a hindered phenolic antioxidant, contributes synergistically to polymer stabilization during processing and provides long-term thermal stability by preventing degradation during service life. Additional performance improvements are achieved with synergistic combinations of, IRGANOX hindered phenolics and thioethers.

Product Forms

Code:

Appearance:

Date first Edition: Sep-98 Product Name: IRGANOX XP 620
Printing Date: Oct-99

page 1

©Ciba Specialty Chemicals, Inc.

	Powder DD	white, free-flowing powder white to slightly green pellets			
Guidelines for Use	In the recommended applications, concentration levels for IRGANOX XP 620 range typically between 0.05% and 0.15% depending on substrate and processing conditions. The optimum level is application specific. Performance data of IRGANOX XP 620 in various polymers and applications are available upon request.				
Physical Properties	<table> <tr> <td>Bulk Density</td> <td>Powder DD</td> <td>450 - 550 g/l 480 - 580 g/l</td> </tr> </table>		Bulk Density	Powder DD	450 - 550 g/l 480 - 580 g/l
Bulk Density	Powder DD	450 - 550 g/l 480 - 580 g/l			
Handling & Safety	IRGANOX XP 620 requires no special safety measures, provided the usual precautions for handling chemicals are observed. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.				
Registration	The registration status for IRGANOX XP 620 is derived from the single components. The components are registered in: Canada, EU, Japan, Korea and USA. They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.				

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Sep-98 Product Name: IRGANOX XP 620
Printing Date: Oct-99

page 2
©Ciba Specialty Chemicals, Inc.



Ciba® IRGASTAB® CABLE KV10


**High Performance, Multifunctional Antioxidant and Heat Stabilizer
for Wire and Cable Applications.**

Characterization IRGASTAB CABLE KV10 is a liquid, sulphur-containing, high performance primary (phenolic) antioxidant and heat stabilizer for the base stabilization of polyethylene wire and cable resins.

Chemical Name 4,6-bis (octylthiomethyl) -o-cresol

CAS Number 110553-27-0

Structure IRGASTAB CABLE KV10



Molecular weight 424.7 g/mol

Applications XLPE wire and cable resins.

Features/ Benefits IRGASTAB CABLE KV10 provides high efficient processing and long-term heat aging stability combined with excellent system compatibility. IRGASTAB CABLE KV10 performs highest scorch resistance and simultaneously has low impact on crosslinking efficiency. IRGASTAB CABLE KV10 is a liquid and thus allows total purity control by filtration. IRGASTAB CABLE KV10 is highly effective at low levels and can be used alone without costabilizers.

Product Forms Code: IRGASTAB CABLE KV10 Appearance: low viscous, pale yellow liquid

Guidelines for use The normal usage levels for IRGASTAB CABLE KV10 range between 0.05 and 0.3%. Extensive performance data for IRGASTAB CABLE KV10 are available on request.

Physical Properties

Melting Range ~ 14°C

Date first Edition: Jun-01 Product Name: IRGASTAB CABLE KV10

Printing Date: Jun-01

page 1

©Ciba Specialty Chemicals, Inc.

Flashpoint	> 200°C
Density (20°C)	0.98 g/cm ³
Vapor Pressure (20°C)	2 E-5 Pa
Dynamic Viscosity (20°C)	85 - 90 mPa.s
Solubility / miscibility (20°C)	% w/w
Water	< 0.01
Acetone	> 50
Chloroform	> 50
Ethanol	> 50
Ethyl acetate	> 50
n-Hexane	> 50
Methanol	> 50
Methylene chloride	> 50
Toluene	> 50

Handling & Safety In accordance with good industrial practice, handle with care and prevent contamination of the environment.
For more detailed information please refer to the material safety data sheet.

Registration IRGASTAB CABLE KV10 is listed on the following countries:
Australia, Canada, China, EU, Japan, Korea, Philippines and USA.
It is approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or for uses for which implantation within the human body is intended.

Date first Edition: Jun-01 Product Name:IRGASTAB CABLE KV10 page 2
Printing Date:Jun-01 ©Ciba Specialty Chemicals, Inc.



Ciba® IRGASTAB® FS 301

Phenol free Processing Stabilizer System

Characterization	Ciba® IRGASTAB® FS 301 is a system composed of a phosphite processing stabilizer (Ciba IRGAFOS 168) and a high molecular weight hydroxylamine (IRGASTAB FS 042). It is designed specifically as a powerful non-phenolic processing stabilizer system with excellent color control, compatibility, low volatility and high resistance to extraction.
CAS Number	Preparation
Chemical Composition	50% Ciba IRGASTAB FS 042 & 50% Ciba IRGAFOS 168
Structure	IRGASTAB FS 042: Oxidized bis(hydrogenated tallow alkyl) amines $\text{C}_{18}\text{H}_{37}-\overset{\text{OH}}{\underset{ }{\text{N}}}-\text{C}_{18}\text{H}_{37}$ Molecular weight: 508g/mol
Applications	IRGASTAB FS 301 is used as a processing stabilizer in polyolefin applications where low color and low gas fade discoloration are required. IRGASTAB FS 301 is particularly suited for PP fiber applications such as carpets, hygienic non-wovens and apparel as well as in polypropylene moldings (such as automotive TPO's and outdoor construction applications) where high UV stability is required. When post processing thermal and /or UV stability is required, IRGASTAB FS 301 should be used in combination with a hindered amine stabilizer.
Features/ Benefits	IRGASTAB FS 301 provides outstanding processing stability to polyolefins while virtually eliminating gas fade discoloration that may occur when phenolic systems are used. When used in combination with a Ciba CHIMASSORB or Ciba TINUWIN hindered amine stabilizer, the system also provides both long-term thermal stability as well as a higher level of light stability in comparison to phenolic processing stabilizer systems. Furthermore IRGASTAB FS systems also enhance the ability of hindered amines to act as light stabilizers.
Product Forms	Code: Appearance:

Date first Edition: Mar. 00 Product Name: Ciba IRGASTAB FS 301
Printing Date: 03.01.2002

page 1

	IRGASTAB FS 301 FF	Granules
Guidelines for use	IRGASTAB FS systems are effective as processing stabilizers when used at 0.05 -0.15% depending upon the polymer substrate, processing conditions and application. They are generally effective at 50 to 60% of the concentration of conventional phenolic - phosphite process stabilizers.	
Physical Properties	IRGASTAB FS 301 FF	
	Melting Range (°C)	> 88
	Bulk Density (g / cm ³)	0.434
Handling & Safety	In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Protect skin. Avoid continuous or repetitive breathing of dust. Use only with adequate ventilation. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	The registration status for IRGASTAB FS 301 is derived from the single components. The components are registered in: Australia: to import, agreement is required from Ciba Specialty Chemicals Canada : free for marketing China: free for marketing Europe : to import, agreement is required from Ciba Specialty Chemicals Japan : to import, agreement is required from Ciba Specialty Chemicals Korea: free for marketing Philippines: free for marketing USA: free for marketing They are approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT:

The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No Statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, Strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claim shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.



Ciba® RECYCLOBLEND® 660

Granulated stabilizer system with repair properties

Characterization RECYCLOBLEND 660 has been specifically developed for desensibilization of polyolefins against the negative influences of impurities such as paint or ink residues during processing and heat aging. Furthermore it acts as a deactivator for compounds such as carbon black, fillers etc.

Chemical Name Blend of antioxidants, co-stabilizers and reactive additives.

CAS Number Preparation

Applications RECYCLOBLEND 660 has been specifically developed to re-stabilize and improve the mechanical properties of recycled plastics. The product enhances the processing, long-term stability and the mechanical properties of the recyclate.

It is intended to be used for:

- PP/EPDM contaminated with paint residues, e.g. TPO bumper scrap
- polyolefins containing fillers and/or carbon black
- post consumer polyolefins, degraded
- PC/polyester blends contaminated with paint residues, e.g. PC/PBT bumper scrap
- compatibilization of impurities in the polymer matrix

Features/ Benefits RECYCLOBLEND 660 is a ready to add additive package which the compounder / recycler can use without further premixing. The granulated non-dusting product form provides safe handling and metering. Improved mechanical and long term thermal properties combined with preserved rheological properties add value and enhance the application possibilities of the recyclate. RECYCLOBLEND 660 helps to desensitize plastic recyclates against the negative influences of impurities such as paint or ink residues during processing and heat aging.

Product Forms	Code: RECYCLOBLEND 660	Appearance: off-white granules
----------------------	----------------------------------	------------------------------------------

Guidelines for use Depending on the residual stabilizer content and the amount of impurities of the recyclate, RECYCLOBLEND 660 can be used in quantities from 0.1% to 2.0 %.

Physical Properties

Melting Range	> 79 °C
Bulk density	0.68 g/cm ³

Handling & Safety

In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Avoid contact with skin. Prevent contamination of the environment. Avoid dust formation and ignition sources.
For more detailed information please refer to the material safety data sheet.

Registration

The registration status for RECYCLOBLEND 660 is derived from the single components. The components are registered in: Australia, Canada, EU, Japan, Korea, Philippines and USA

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: Aug-98 Product Name: RECYCLOBLEND 660
Printing Date: Dec-99

page 2
©Ciba Specialty Chemicals, Inc


**Ciba® TINUVIN® 622****Oligomeric Hindered Amine Light Stabilizer (HALS)**

Characterization TINUVIN 622 is the light stabilizer of choice for all applications calling for low volatility and minimal migration, because of its oligomeric structure with high molecular weight. Furthermore TINUVIN 622 is effective as antioxidant and contributes significantly to the long term heat stability of polyolefins and tackifier resins.

Chemical Name Butanedioic acid, dimethylester, polymer with 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol

CAS Number 65447-77-0

Structure TINUVIN 622



Molecular weight $M_n = 3100 - 4000$

Applications TINUVIN 622 areas of application include polyolefins (PP, PE), olefin copolymers such as EVA as well as blends of polypropylene with elastomers.

In addition TINUVIN 622 is highly effective in polyacetals, polyamides and polyurethane applications.

Features/ Benefits The effectiveness of TINUVIN 622 surpasses significantly that of UV absorbers, particularly in pigmented systems. Combinations of TINUVIN 622 with UV absorbers, e.g. TINUVIN range or other HALS, e.g. CHIMASSORB range in many cases result in synergistic effects. Typical examples are TINUVIN 783 and TINUVIN 111.

Product Forms	Code: TINUVIN 622 FB TINUVIN 622 LD	Appearance: colorless to light yellowish granules coarse, white to slightly yellow powder
----------------------	-------------------------------------------	-------------------------------------------------------------------------------------------------

Guidelines for use	Thick sections	UV stabilization of HDPE, LLDPE, LDPE and PP	0.15 -0.5%
	Films	UV stabilization of LDPE and LLDPE	0.1 -1.2%
	Tapes	UV stabilization of HDPE and PP	0.2- 0.8%

Fibers	UV stabilization of PP fibers	0.1 -1.0%
*The presence of a UV absorber (e.g. TINUVIN 326/327/328 and CHIMASSORB 81) is recommended in unpigmented or slightly pigmented articles or to improve the light fastness of certain organic pigments.		

Physical Properties

Melting Range	50 - 70 °C
Flashpoint	>250°C Cleveland
Specific Gravity (20°C)	1.22 g/cm ³
Vapor Pressure (20°C)	2.5 E-6 Pa
Bulk density	
TINUVIN 622 FB	500 - 700 g/l
TINUVIN 622 LD	300 - 500 g/l
Solubility (20°C)	g/100g Solution
Acetone	4.0
Chloroform	> 40
Ethanol	0.08
Ethyl acetate	3.0
n-Hexane	< 0.01
Methanol	0.05
Methylene chloride	> 40
Toluene	15
Water	< 0.01
Volatility (pure substance; TGA-data, heating rate 20°C/min in air)	
Temperature (°C)	% weight loss
200	0.1
225	0.2
250	0.4
275	1.1
300	3.1
325	8.4

Handling & Safety

In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.

Registration

TINUVIN 622 is listed on the following Inventories:

Australia: AICS	Canada: DSL	China: First Import
Europe: polymer, monomers on EINECS		Japan: MITI
Korea: ECL	Philippines: PICCS	USA: TSCA
TINUVIN 622 is approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.		

IMPORTANT: The following supersedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Date first Edition: 1977 Product Name: TINUVIN 622

Printing Date: Nov-99

page 2
©Ciba Specialty Chemicals, Inc.

Irganox® 129
Ciba

Technical Assistance: [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Typical properties	Value	Unit
Melting range	182 - 186	°C
Flash point	> 380	°F
Molecular weight	2600 - 3400	g/mol
Bulk density	35	lb/ft ³
Specific Gravity	0.98 - 1.04	g/cm ³
Assay	99	%
APHA color	< 30	

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user must contact product manufacturer in order to receive complete information about the product. The information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of Food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

Irgastab® FS 102
Ciba

Discover Ciba's TechCenters:
 Antioxidants
 UV/Light Stabilizers
 Fluorescent Whiteners Agents
 Melamine Compounds
 Antimicrobial Center

[Find out For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
 Light Stabilizer / UV Absorber
 Heat Stabilizer >> Organic
 Processing aid >> Polymeric Processing Aid
 Light Stabilizer / UV Absorber >> HALS, Hindered Amine
 Processing aid
 Antioxidant >> Amine

Physical form:	Powder
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
 Blend of hydroxylamine , hindered amine and a hydrolytically stable phosphite. Offers very good compatibility. Possesses high resistance to extraction and low volatility. Provides outstanding processing stability. Imparts both long term thermal stability as well as a higher level of light stability.

Best suitable Polymer

- PP, Polypropylene
- PE, Polyethylene

Typical properties	Value	Unit
Molecular weight	3100 - 4000	g/mol

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or any other legal or equitable theory, to any person, for amounts resulting loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are based on the fact that they require a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

Irgastab® FS 110
Ciba

Discover Ciba's TechCenters:

- Antioxidants
- UV/Light Stabilizers
- Fluorescent Whitening Agents
- Melamine Compounds
- Antimicrobial Center

Technical Assistance: [Request For Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Light Stabilizer / UV Absorber
Heat Stabilizer >> Organic
Processing aid >> Polymeric Processing Aid
Light Stabilizer / UV Absorber >> HALS, Hindered Amine
Processing aid
Antioxidant >> Amine

Physical form:	Granules	
Food contact approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Mixture of hydroxylamine and hindered amine. Offers very good compatibility. Possesses high resistance to extraction and low volatility. Provides outstanding processing stability. Imparts both long term thermal stability as well as a higher level of light stability.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PP, Polypropylene • PE, Polyethylene 		
Typical properties	Value	Unit
Molecular weight	538	g/mol

Irgastab® FS 210
Ciba

Discover Ciba's TechCenters:

- Antioxidants
- UV/Light Stabilizers
- Fluorescent Whitening Agents
- Melamine Compounds
- Antimicrobial Center

[Request Free Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Light Stabilizer / UV Absorber
Heat Stabilizer >> Organic
Processing aid >> Polymeric Processing Aid
Light Stabilizer / UV Absorber >> HALS, Hindered Amine
Processing aid
Antioxidant >> Amine

Physical form: Granules
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Mixture of high molecular weight hydroxylamine and a high molecular weight hindered amine. Offers very good compatibility. Exhibits high resistance to extraction and low volatility. Provides very good processing stability. Imparts long-term thermal stability as well as a higher level of light stability.

Best suitable Polymer
• PE, Polyethylene
• PP, Polypropylene

Discover Ciba's TechCenters:

- [Antioxidants](#)
- [UV/Light Stabilizers](#)
- [Fluorescent Whitening Agents](#)
- [Melamine Compounds](#)
- [Antimicrobial Center](#)

Irgastab® FS 302
Ciba

Technical Assistance: [Request For Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store In My Library](#) [Print](#)

Additive
Processing aid
Light Stabilizer / UV Absorber >> HALS, Hindered Amine
Antioxidant >> Blend

Physical form:	Granules
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Blend of phosphite and hydroxylamine. Used as a processing stabilizer for PP fiber applications such as carpets, hygienic non wovens and apparel as well as in PP moldings (such as TPO's and outdoor construction applications). Offers very good color control, compatibility and low volatility. Provides high resistance to extraction. Exhibits both long-term thermal stability as well as higher level of light stability.

Best suitable Polymer
• PP, Polycaprolactone
• PE, Polyethylene

Typical properties	Value	Unit
Melting range	> 86	°C

Irgastab® FS 410
Ciba

Discover Ciba's TechCenters:
Antioxidants
UV/Light Stabilizers
Fluorescent Whitening Agents
Melamine Compounds
Antimicrobial Center

 [Request For Information](#)  [Tech Direct](#)  [Search amongst 10,000+ Additives and Modifiers](#)  [Store in my Library](#)  [PDF](#)

Additive
Light Stabilizer / UV Absorber
Heat Stabilizer >> Organic
Processing aid >> Polymeric Processing Aid
Light Stabilizer / UV Absorber >> HALS, Hindered Amine
Processing aid
Antioxidant >> Amine

Physical form: Granules
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Blend of hydroxylamine and hindered amine. Used as a processing stabilizer. Offers very good compatibility. Provides high resistance to extraction and low volatility. Imparts outstanding processing stability. Possesses long-term thermal stability as well as a higher level of light stability.

Best suitable Polymer
• PP, Polypropylene
• PE, Polyethylene

Discover Ciba's TechCenters:

- [Antioxidants](#)
- [UV/Light Stabilizers](#)
- [Fluorescent Whitening Agents](#)
- [Melamine Compounds](#)
- [Antimicrobial Center](#)

Irgastab® FS 533 FF
Ciba

Technical Assistance: [Tech Direct](#)

[Request For Information](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my library](#) [Print](#)

Additive
 Light Stabilizer / UV Absorber
 Heat Stabilizer >> Organic
 Processing aid >> Polymeric Processing Aid
 Light Stabilizer / UV Absorber >> HALS, Hindered Amine
 Processing aid
 Antioxidant >> Amine

Physical form: Masterbatch / One Pack:	Granules No													
Product description Mixture of phosphite, hydroxylamine and hindered amine. Used as a processing stabilizer. Imparts very good process control. Possesses very good long-term thermal stability and light stability.														
Best suitable Polymer <ul style="list-style-type: none"> • PP, Polypropylene • PE, Polyethylene 														
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th style="text-align: center;">Value</th> <th style="text-align: center;">Unit</th> </tr> </thead> <tbody> <tr> <td>Melting range</td> <td style="text-align: center;">93 - 182</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Softening Point</td> <td style="text-align: center;">47</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Bulk Density</td> <td style="text-align: center;">0.40 - 0.50</td> <td style="text-align: center;">g/ml</td> </tr> </tbody> </table>				Value	Unit	Melting range	93 - 182	°C	Softening Point	47	°C	Bulk Density	0.40 - 0.50	g/ml
	Value	Unit												
Melting range	93 - 182	°C												
Softening Point	47	°C												
Bulk Density	0.40 - 0.50	g/ml												

ADK STAB AO-26

Adeka Palmarole

Request For Information Technical Assistance [Tech Direct](#)

Discover Adeka Palmarole's TechCenters:
Blowing Agent Center

Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: Thiobis-[2-tert-butyl-5-methyl-4,1-phenylene] bis [3-(dodecyl)propionate]
 Physical form: Liquid
 Masterbatch / One Pack: No

Product description
 Liquid thio-ether antioxidant. Suitable for applications demanding high thermal stability under extreme conditions such as severe processing temperatures, high heat aging and exposure to hot water in use. Exhibits superior long term stability and/or high thermal stability. Provides low volatility. Possesses non staining and low odor.

Best suitable Polymer

- PP, Polypropylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PUR, polyurethane
- PS, Polystyrene
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Terephthalate

	Value	Unit
Molecular Weight	830	
Relative Density @25°C	0.999	
Viscosity @ 25°C	2120	

ADK STAB AO-30
Adeka Palmarole

Discover Adeka Palmarole's TechCenters:
[Blowing Agent Center](#)

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Star in My Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Highly effective phenolic antioxidant. Used for the protection of various polymers. Offers long term thermal stability with outstanding extraction resistance.

Best suitable Polymer
• Rubbers
• PVC rigid, polyvinylchloride
• Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
• PP, Polypropylene
• Thermoplastics, other >> PPO, Polymethylene Oxide
• PA, Polyamide
• ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
• PBT, Polybutylene Terephthalate
• PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
• PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Melting Point	185 - 187	°C
Molecular Weight	545	

ADK STAB AO-50
Adeka Palmarole

Discover Adeka Palmarole's TechCenters:
 Blowing Agent Center

[Request For Information](#) [Tech Direct](#)

Technical Assistance: [Search amongst 10,000+ Additives and Modifiers](#)

[Save in my library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition: *n*-octadecyl-3-(4'-hydroxy-3',5'-di-t-butylphenyl)propionate
 Physical form: Powder
 CAS Number: 2082-79-3
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description
 Highly effective antioxidant. Offers good compatibility with most common polymers. Possesses good substitute for BHT.

Best suitable Polymer

- Rubber
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene
- PS, Polystyrene

Typical properties	Value	Unit
Melting Point	50	°C
Molecular Weight	531	

SpecialChem | Polymer Additives & Colors

Home Resources TechCenter My SpecialChem Log-out

Search Bookmarks Composite PVC Masterbatch Formulation Contact Us Help Links

Bookmark SpecialChem4Polymers Free newsletter subscription >> Eldar Zeynalov Discover Adeka Palmarole's TechCenters: Blowing Agent Center

Request For Information Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

ADK STAB AO-60
Adeka Palmarole

Additive
Antioxidant >> Phenolic

Chemical composition: Tetraakis[methylene(3,5-di-t-butyl-4-hydroxy hydrocinnamate)]methane
Physical form: Powder
CAS Number: 6683-19-8
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Versatile and highly effective antioxidant. Offers synergistic activity with phosphite process stabilisers. Provides long term thermal stability.

Best suitable Polymer
Rubbers >> EPM, Ethylene Propylene Diene Rubber
• PS, Polystyrene
• Rubbers >> SBR, Styrene-butadiene rubber
• PP, Polypropylene
• Thermoplastics, other
• PA, Polyamide
• ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
• PBT, Polybutylene Terephthalate
• PE, Polyethylene
• PC, Polycarbonate

Typical properties	Value	Unit
Melting Point	115	°C
Molecular Weight	1178	

Disclaimer
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S. A.

SpecialChem | Polymer Additives & Colors
Innovation & Solutions through Technology

[About Us](#) [Contact Us](#) [Help](#) [Links](#)

[Home](#) [Resources](#) [TechCenter](#) [My SpecialChem](#)

[Search](#) [Bookmark SpecialChem4Polymers](#) [Free newsletter subscription](#) [>> Eldar Zeynalov](#) [Logout](#)

Discover Adeka Palmarole's TechCenters:
[Browning Agent Center](#)

[Request for Information](#) [Tech Direct](#) [Store in my Library](#) [Print](#)

ADK STAB PEP-36
Adeka Palmarole

Additive
Antioxidant >> Phosphite

Chemical composition: Bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol-di-phosphite
 Physical form: Powder
 CAS Number: 80693-00-1
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description
Phosphite. Used in food packaging. Offers very good process stability and colour improvement at higher temperature.

Best suitable Polymer

- Thermoplastics, other
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene

Typical properties

	Value	Unit
Melting Point	237	°C
Molecular Weight	633	
Solubility @ 25°C in Water	0	g/100g
Solubility @ 25°C in Acetone	0.4	g/100g
Solubility @ 25°C in Toluene	3.2	g/100g
Solubility @ 25°C in n-hexane	0.2	g/100g
Solubility @ 25°C in Methanol	< 0.01	g/100g
Solubility @ 25°C in Tetrahydrofuran	2	g/100g

Disclaimer
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or warranty or equitable theory to any party for any amounts resulting loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Product manufacturers and suppliers are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S. A.

SpecialChem - Polymer Additives & Colors
 Innovation & Solutions through Technology

[About Us](#) [Innovation](#) [Compounds](#) [E&C](#) [Contact Us](#) [Help](#) [Links](#)

[Home](#) [Resources](#) [TechCenter](#) [My SpecialChem](#)

[Search](#) [Log-out](#)

Discover Adeka Palmarole's TechCenters:
[Blowing Agent Center](#)

[Request For Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phosphite

Physical form:	Flakes
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
 Phosphite. Offers very good colour stability and high melt stability. Possesses outstanding solubility characteristics.

Best suitable Polymer

- PS, Polystyrene
- PVC rigid, polyvinylchloride
- PP, Polypropylene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- ABS / SAN / ASA, Acrylonitrile-Styrenic based
- PA, Polyamide
- PBT, Polybutylene Therephthalate

	Value	Unit
Molecular Weight	733	
Softening point	50	°C

Disclaimer
 All technical information on this site is given for information purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the user is provided with no implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to the party for any damages representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

ADK STAB QL
Adeka Corporation

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phosphite

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phosphite stabilizer.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol • PE, Polyethylene >> LDPE, Linear Low Density Polyethylene • PS, Polystyrene • PP, Polypylene • Thermoplastic, other >> PPO, Polyphenylene Oxide • PA, Polyamide • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PBT, Polybutylene Therophthalate • PE, Polyethylene >> HDPE, High Density Polyethylene • PC, Polycarbonate 	
Typical properties	Value
Viscosity @ 25°C	1000
	Unit
	cps

Request for Information Technical Assistance Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Mixture of PEP-8 and CA-ST.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- PS, Polystyrene
- PA, Polyamide
- ABS/SAN/ASA, Acrylonitrile-Styrene based
- PBT, Polybutylene Terephthalate
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

ADK STAB P
Adeka Corporation

Request For Information Technical Assistance [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phosphite

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phosphite stabilizer.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PS, Polystyrene • PP, Polypropylene • Thermoplastics, other >> PPO, Polyphenylene Oxide • PA, Polyamide • ABS, Acrylonitrile-Butadiene-Styrene based • PBt, Polybutylene Terephthalate • PE, Polyethylene >> HDPE, High Density Polyethylene • PC, Polycarbonate 	
Typical properties	Value
Viscosity @ 25°C	2900
	Unit
	cps

ADK STAB AO-18
Adeka Corporation

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Physical form:	Powder
Masterbatch / One Pack:	No
Product description	
Hindered phenol stabilizer. For PP composites and PE cables. Protection from thermal degradation.	
Best suitable Polymer	
<ul style="list-style-type: none"> • Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde • PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol • PP, Polypropylene • Thermoplastics, other >> PPO, Polyphenylene Oxide • PE, Polyethylene >> LDPE, Low Density Polyethylene • PVDF • ABS / SAN / ASA, Acrylonitrile-Styrene based • PE, Polyethylene >> HDPE, High Density Polyethylene • PBT, Polybutylene Therephthalate 	
Typical properties	Value
Melting Point	<210
	Unit
	°C

ADK STAB AO-15
Adeka Corporation

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#)

Store in my Library [Print](#)

Additive
Antioxidant >> Phenolic

Physical form:	Powder
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Hindered phenol stabilizer.

Best suitable Polymer

- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- Thermoplastics, other
- PP, Polypropylene
- Thermoplastics, other >> PPO, Polyphenylene Oxide
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PE, Polybutylene Thersphthalate
- PA, Polyamide
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PE, Polyethyans >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Melting Point	-210	°C

ADK STAB 522A
Adeka Corporation

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Log In

Additive
Antioxidant >> Phosphite

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Heat and color stabilizer for high temperature processing.

Best suitable Polymer

- PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PS, Polystyrene
- PP, Polypropylene
- Thermoplasticics, other >> PPO, Polyphenylene Oxide
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PBT, Polybutylene Therephthalate
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Viscosity @ 25°C.	1800	cP
Molecular weight	1851	

Antioxidant 1010
Akrochem

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition: Tetrakis [methylene (3,5-di-*tert*-butyl-4-hydroxyhydrocinnamate)] methane
 Physical form: Powder
 Masterbatch / One Pack: No

Product description
 Application in plastics, rubber, latex, varnishes, adhesives, TPR's and Hot Melts.

Best suitable Polymer

- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> IR, Polysisoprene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- Thermoplastics >> PA, Polyamide
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PE, Polyethylene
- PC, Polycarbonate
- PVC rigid, polyvinylchloride
- PS, Polystyrene

Typical properties	Value	Unit
Melting Point	110 - 125	°C
Ash Content	< 0.1	%
Volatile Matter	< 0.5	%
Acetone Solubility at 20°C	47	%
Chloroform Solubility at 20°C	71	%
Water Solubility at 20°C	0.01	%

Uvinul® 4050 H

BASF

Discover BASF's TechCenters:
SBC - Impact Modifier for GPPS Center

Request For Information 

Technical Assistance: 

Search amongst 10,000+ Additives and Modifiers  

Additive
Antioxidant >> Phenolic
Light Stabilizer / UV Absorber >> HALS, Hindered Amine

Chemical composition:	Sterically hindered amine	
Physical form:	Powder	
CAS Number:	124172-53-8	
Masterbatch / One Pack:	No	
Product description		
Sterically hindered amine. Used as light stabilizer for polyolefins, ABS and nylons. Offers very high fastness to light and weathering. Exhibits very little water carry-over from the quench bath during the manufacture of PP film tape.		
Best suitable Polymer		
<ul style="list-style-type: none"> ABS/ SAN/ ASA, Acrylonitrile-Styrenic based PE, Polyethylene >> HDPE, High Density Polyethylene PE, Polyethylene >> LDPE, Low Density Polyethylene PMMA, Polymethylmethacrylate PP, Polypropylene 		
Typical properties		
Molecular weight	400	Value
Density @ 25°C	1.04	g/cm³
Melting range	153 - 158	°C
Heat stability	> 200	°C
pKa	8.8	
Solubility @ 25°C in Methylol	11	%wt
Solubility @ 20°C in Tetrahydrofuran	8	%wt
Solubility @ 20°C in Water	0.5	%wt

Uvinul® 2003 AO
BASF

Discover BASF's TechCenters:
 SBC – Impact Modifier for GPPS Center

[Request for Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Share in my Library](#) [Print](#)

Additive
 Antioxidant
 Heat Stabilizer
 Light Stabilizer / UV Absorber

Physical form:	Liquid
Food contact approval:	Yes
Product description	
Tocopherol preparation with an organophosphorus compound. Hydrolysis-resistant processing stabilizer intended for protecting organic substrates against thermooxidative degradation.	
Best suitable Polymer	
<ul style="list-style-type: none"> • TPU, Thermoplastic Polyurethane • PP, Polycarbonate • PE, Polyethylene • Thermoplastic Elastomers, TPE 	
Typical properties	Value
Density @ 20°C	0.95
	Unit
	g/cm ³

Ethaphos™ 326
Albermarle

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library...](#) [Print](#)

Additive
Antioxidant >> Phosphite

Chemical composition:	Bis (2,4-ditertbutylphenol) pentaerythritol diphosphite
Physical form:	Powder
CAS Number:	26741-53-7
Masterbatch / One Pack:	No
Product description	
Bis(2,4-ditertbutylphenol) pentaerythritol diphosphite. Offers very good color stability. Reduces polymer degradation and improves gas fading performance.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PP, Polypropylene • PVC, flexible; polyvinyl-chloride • PVC, rigid; polyvinylchloride • PE, Polyethylene • PS, Polystyrene 	
Typical properties	
Molecular Weight	Value
Flash point, PM closed cup	694
Bulk density@ 20°C	168
Phosphorus, %	27.0
Acid no.	10 - 10.3
	%
	mg KOH/g

Lankromark™ LE109
Akzo Nobel-Akros Chemicals

Request for Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite

Chemical composition: Tris (nonylphenol) phosphite
Physical form: Liquid
Food contact approval: Yes

Product description
Organophosphite ester. Non-toxic tris (nonylphenol) phosphite.
Possesses a wide approval for food contact applications.
Commonly used to boost the performance of calcium/zinc stabilised flexible and rigid PVC formulations for non-toxic applications.
Also has a high resistance to hydrolysis and is a major antioxidant for ABS and polypropylene.

Best suitable Polymer
• PP, Polypropylene
• PVC rigid, polyvinylchloride
• ABS/ SAN/ ASA, Acrylonitrile-Styrenic based

Antioxidant BHT
Akrochem

[Request for Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition:	2,6-Di-tert-butyl-para-cresol
Physical form:	Crystals
Masterbatch / One Pack:	No

Product description
Used in waxes, insecticides, synthetic lubricants, paints. Protects polymers against the effect of heat and oxygen during drying operations. Reduces the danger of cyclization during storage and processing and also helps to protect vulcanizates against autoxidation.

Best suitable Polymer

- Rubbers >> NR, Natural Rubber
- Rubbers
- Thermoplastic Elastomers, TPE
- Thermoplastics, other >> Polyvinyl (excluding PVC)
- Thermoplastics, other
- PUR, polyurethane
- PA, Polyamids
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PC, Polycarbonate
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Specific Gravity	1.03	%
Purity	99	%
Ash	< 0.01	%
Bulk Density	6 - 42	lb/ft ³

Antioxidant 1076
Akrochem

Request For Information Technical Assistance: [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers [X](#) Save in my Library [PDF](#)

Additive
Antioxidant >> Phenolic

Chemical composition: Stearyl 3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)-propionate
 Physical form: Powder
 Masterbatch / One Pack: No

Product description
 Used in plastics, rubber, latex, varnishes, adhesives, TPR's and Hot Melts.

Best suitable Polymer

- Rubbers >> IR, Polysoprene
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- Thermoplastics, other
 - Rubbers >> SBR, Styrene-butadiene rubber
 - PE, Polyethylene
 - PC, Polycarbonate
 - PVC rigid, polyvinylchloride
 - PS, Polystyrene

Typical properties	Value	Unit
Melting Point	48 - 54	°C
Ash Content	< 0.1	%
Viscosity Matter	< 0.5	%
Water Solubility at 20°C	0.01	%
Airborne Solubility at 20°C	25	%

Antioxidant 1024
Akrochem

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Metal deactivator

Physical form:	Powder
Masterbatch / One Pack:	No

Product description
Improved properties in polymers exposed to sour gasoline. Excellent extraction resistance in fuels and oils.

Best suitable Polymer
 - Rubbers >> EPDM, Ethylene Propylene Diene Rubber
 - PE, Polyethylene
 - PA, Polyamide

Typical properties	Value	Unit
Melting Point	225 - 230	°C
Specific Gravity	1.12	
Water Solubility @ 20°C	< 0.01	%
Acetone Solubility @ 20°C	1	%
Toluene Solubility @ 20°C	< 0.01	%

Weston® 501B
Chemtura

[Request for Information](#) Technical Assistance [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Blend

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Is a blend of a primary and secondary stabilizer in one easy to handle liquid form: 50% Weston 399, 50% Ultrinox 276. Improves color and inhibits degradation of molecular weight. Pre-blending of antioxidants are eliminated. Easy handling- accurate feeding rates. Is a low cost stabilizer.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PVC rigid; polyvinylchloride
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties

	Value	Unit
Color APHA	< 100	
Ultrinox 276	47 - 53	%
Additive part	< 0.1	mg KOH/g
Specific gravity @ 25°C	0.94	
Density @ 25°C	7.8	g/ml
Phosphorus content	2.2	%

Weston® 398
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant > Phosphite

Chemical composition:	Triphenylphenyl Phosphite																						
Physical form:	Liquid																						
CAS Number:	26523-78-4																						
Food contact approval:	Yes	No																					
Masterbatch / One Pack:																							
Product description																							
Used when high purity stabilizers are required. Improves color and processing stability during recovery, drying, compounding, processing and end use. Synergism with other stabilizers.																							
Best suitable Polymer																							
<ul style="list-style-type: none"> • PVC rigid, polyvinyl chloride • Polypropylene, Styrene-butadiene rubber • PE, Polyethylene > LLDPE, Linear Low Density Polyethylene • ABS/ SAN/ ASA, Acrylonitrile-Styrene based • PE, Polyethylene >> HDPE, High Density Polyethylene 																							
Typical properties <table border="1" style="width: 100%;"> <thead> <tr> <th></th> <th>Value</th> <th>Unit</th> </tr> </thead> <tbody> <tr> <td>Phosphorous content</td> <td>4.1 - 4.8</td> <td>%</td> </tr> <tr> <td>Refractive index @ 25°C</td> <td>1.526 - 1.527</td> <td></td> </tr> <tr> <td>Acid number</td> <td>< 0.05</td> <td>mg KOH/g</td> </tr> <tr> <td>Viscosity @ 80°C</td> <td>250</td> <td>°C</td> </tr> <tr> <td>Density</td> <td>0.98</td> <td>g/ml</td> </tr> <tr> <td>Specific gravity @ 25°C/15.5°C</td> <td>0.983 - 0.98</td> <td></td> </tr> </tbody> </table>				Value	Unit	Phosphorous content	4.1 - 4.8	%	Refractive index @ 25°C	1.526 - 1.527		Acid number	< 0.05	mg KOH/g	Viscosity @ 80°C	250	°C	Density	0.98	g/ml	Specific gravity @ 25°C/15.5°C	0.983 - 0.98	
	Value	Unit																					
Phosphorous content	4.1 - 4.8	%																					
Refractive index @ 25°C	1.526 - 1.527																						
Acid number	< 0.05	mg KOH/g																					
Viscosity @ 80°C	250	°C																					
Density	0.98	g/ml																					
Specific gravity @ 25°C/15.5°C	0.983 - 0.98																						

Weston 503B
Chemtura

Request for Information Technical Assistance: [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Blend

Physical form:	Liquid																					
Food contact approval:	Yes																					
Product description																						
Blend of 75% Weston TNPP phosphite and 25% Ultrinox 276. Appearance at room temperature is soft. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.																						
Best suitable Polymer																						
<ul style="list-style-type: none"> • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PVC rigid; polyvinylchloride • ABSI SAN ASA, Acrylonitrile-Styrenic based • PE, Polyethylene >> HDPE, High Density Polyethylene 																						
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">Property</th> <th style="text-align: right;">Value</th> <th style="text-align: right;">Unit</th> </tr> </thead> <tbody> <tr> <td>Specific Gravity</td> <td style="text-align: right;">0.97</td> <td style="text-align: right;">kg/m³</td> </tr> <tr> <td>Flash Point, closed cup</td> <td style="text-align: right;">220</td> <td style="text-align: right;">°C</td> </tr> <tr> <td>Solidification Temperature</td> <td style="text-align: right;">23</td> <td style="text-align: right;">°C</td> </tr> <tr> <td>Color, APHA</td> <td style="text-align: right;">< 100</td> <td style="text-align: right;">mg KOH/g</td> </tr> <tr> <td>Acid number, KOH</td> <td style="text-align: right;">< 0.1</td> <td style="text-align: right;">mg KOH/g</td> </tr> <tr> <td>Density @ 25°C</td> <td style="text-align: right;">0.91</td> <td style="text-align: right;">kg/m³</td> </tr> </tbody> </table>		Property	Value	Unit	Specific Gravity	0.97	kg/m³	Flash Point, closed cup	220	°C	Solidification Temperature	23	°C	Color, APHA	< 100	mg KOH/g	Acid number, KOH	< 0.1	mg KOH/g	Density @ 25°C	0.91	kg/m³
Property	Value	Unit																				
Specific Gravity	0.97	kg/m³																				
Flash Point, closed cup	220	°C																				
Solidification Temperature	23	°C																				
Color, APHA	< 100	mg KOH/g																				
Acid number, KOH	< 0.1	mg KOH/g																				
Density @ 25°C	0.91	kg/m³																				

Weston 503
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant >> Blend

Physical form:	Liquid																					
Food contact approval:	Yes																					
Product description: Blend of 75% Weston TNPP phosphite and 25% Ultrinox 276. Appearance at room temperature is soft. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.																						
Best suitable Polymer																						
<ul style="list-style-type: none"> • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PVC rigid; polyvinylchloride • ABS/ SAN ASA, Acrylonitrile-Styrenic based • PE, Polyethylene >> HDPE, High Density Polyethylene 																						
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;"></th> <th style="text-align: center;">Value</th> <th style="text-align: center;">Unit</th> </tr> </thead> <tbody> <tr> <td>Specific Gravity</td> <td style="text-align: center;">0.97</td> <td style="text-align: center;">-</td> </tr> <tr> <td>Flash Point, closed cup</td> <td style="text-align: center;">220</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Solidification Temperature</td> <td style="text-align: center;">23</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Color, APHA</td> <td style="text-align: center;">< 100</td> <td style="text-align: center;">-</td> </tr> <tr> <td>Acid number KOH</td> <td style="text-align: center;">< 0.1</td> <td style="text-align: center;">mg KOH/g</td> </tr> <tr> <td>Density @ 25 °C</td> <td style="text-align: center;">8.1</td> <td style="text-align: center;">lb/gal</td> </tr> </tbody> </table>			Value	Unit	Specific Gravity	0.97	-	Flash Point, closed cup	220	°C	Solidification Temperature	23	°C	Color, APHA	< 100	-	Acid number KOH	< 0.1	mg KOH/g	Density @ 25 °C	8.1	lb/gal
	Value	Unit																				
Specific Gravity	0.97	-																				
Flash Point, closed cup	220	°C																				
Solidification Temperature	23	°C																				
Color, APHA	< 100	-																				
Acid number KOH	< 0.1	mg KOH/g																				
Density @ 25 °C	8.1	lb/gal																				

Naugard™ AO-71076
Chemtura

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition:	Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate
Physical form:	Powder
CAS Number:	2082-79-3
Masterbatch / One Pack:	No

Product description
Sternically hindered phenolic antioxidant. Possesses low volatility, good compatibility, high resistance to exudation and is non-discoloring.

Best suitable Polymer

- PP, Polypropylene
- TPU, Thermoplastic Polyurethane
- PE, Polyethylene

Typical properties	Value	Unit
Melting range	50 - 55	°C
Bulk density	260 - 320	g/l

Naugard™ AO 71010
Chemtura

[Request for Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Share in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: Pentaerythritol Tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)
 Physical form: Powder
 CAS Number: 6683-19-8
 Masterbatch / One Pack: No

Product description
 Sterically hindered phenolic antioxidant. Possesses low volatility, good compatibility, high resistance to exudation and is non-discoloring.

Best suitable Polymer

- TPU, Thermoplastic Polyurethane
- PP, Polypropylene
- PVC, flexible; polyvinylchloride
- PA, Polyamide
- PVC rigid; polyvinylchloride
- Thermoplastic Elastomers, TPE

Typical properties	Value	Unit:
Melting range	100 - 125	°C
Specific gravity @ 20°C	1.15	g/cm³

Naugard® XL-1
Chemtura

Resource For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library **FrH**

Additive
Antioxidant
Metal deactivator

Chemical composition:	2,2'-oxamidobis-[ethyl-3-(3,5-di-1-butyl-4-hydroxyphenyl) propionate]	
Physical form:	Powder	
Food industry approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Antioxidant		
Best suitable Polymer		
<ul style="list-style-type: none"> • PS, Polystyrene • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • Rubbers >> EPDM, Ethylene Propylene Diene Rubber • PP, Polypropylene • PE, Polyethylene >> HDPE, High Density Polyethylene • ABS SAN ASA, Acrylonitrile-Styrene based • PA, Polyamide • PC, Polycarbonate 		
Typical properties		
Melting range:	170 - 180	Unit: °C
Color, Trans @ 425nm:	98	
Specific gravity @ 20°C:	1.08	
Foam point, TOC:	290	Unit: °C
Molecular weight:	697	

Naugard® Super Q
Chemtura

Request For Information Technical Assistance: **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in Library Print

Additive
Antioxidant >> Amine

Chemical composition:	Polymerized 1,2-dihydro-2,2,4-trimethylquinoline																		
Physical form:	Pastilles																		
Masterbatch / One Pack:	No																		
Product description																			
Designed for carbon black filled systems such as wire and cable and geomembranes.																			
Best suitable Polymer																			
<ul style="list-style-type: none"> • PE, Polyethylene >> LLDP-E, Linear Low Density Polyethylene • PE, Polyethylene >> LDPE, Low Density Polyethylene • PE, Polyethylene >> HDPE, High Density Polyethylene 																			
Typical properties <table border="1"> <thead> <tr> <th></th> <th>Value</th> <th>Unit</th> </tr> </thead> <tbody> <tr> <td>Softening point</td> <td>128</td> <td>°C</td> </tr> <tr> <td>Gardner</td> <td>11</td> <td>Gardner</td> </tr> <tr> <td>Specific gravity @ 25°C</td> <td>1.08</td> <td></td> </tr> <tr> <td>Flash point, C.C.C.</td> <td>274 - 282</td> <td>°C</td> </tr> <tr> <td>Molecular weight</td> <td>874</td> <td></td> </tr> </tbody> </table>			Value	Unit	Softening point	128	°C	Gardner	11	Gardner	Specific gravity @ 25°C	1.08		Flash point, C.C.C.	274 - 282	°C	Molecular weight	874	
	Value	Unit																	
Softening point	128	°C																	
Gardner	11	Gardner																	
Specific gravity @ 25°C	1.08																		
Flash point, C.C.C.	274 - 282	°C																	
Molecular weight	874																		

Naugard® HM-22
Chemtura

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Add to my Library](#) [Print](#)

Additive
Antioxidant
Heat Stabilizer >> Organic

Chemical composition:	Blend of hindered phenolic and diphenylamine	
Physical form:	Granules	
Food contact approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Granular blend of hindered phenolic and diphenylamine. Provides synergistic short and long-term thermal protection. Exhibits very good color and viscosity stability.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PE, Polyethylene • Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS) • EVA, Ethylene Vinyl Acetate Copolymer • PA, Polyamide • Rubbers >> SBR, Styrene-butadiene rubber • Rubbers >> NBR, Acrylonitrile-butadiene Rubber • Rubbers >> BR, Butadiene Rubber, Polybutadiene 		
Typical properties		
Color	25	Value
Specific gravity @ 25°C	1.09	Unit
Flash point, COC	277	APHA
Molecular weight	531	°C

Naugard® HM-11
Chemtura

Technical Assistance 

Search amongst 10,000+ Additives and Modifiers 

Additive
Antioxidant
Heat Stabilizer >> Organic

Chemical composition:	Blend of hindered phenolic and diphenylamine
Physical form:	Granules
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Granular blend of hindered phenolic and diphenylamine. Provides synergistic short and long-term thermal protection against oxidation in polypropylene. Exhibits very good color and viscosity stability. Offers gelation and skinning resistance.

Best suitable Polymer

- PE, Polyethylene
- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- EVA, Ethylene Vinyl Acetate Copolymer
- PA, Polyamide
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene

Typical properties

	Value	Unit
Color	25	APHA
Specific gravity @ 25°C	1.16	
Flash point, COC	296	°C
Molecular weight	1178	

Disclaimer
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. Specitechem shall not be liable or obligated under any contract, negligence, strict liability, or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 Specitechem S. A.

Naugard® DSTDP
Chemtura

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Add to my Library](#) [Print](#)

Additive
Antioxidant >> Thioester

Chemical composition:	Distearyl thiodipropionate													
Physical form:	Flakes													
CAS Number:	693-36-7													
Masterbatch / One Pack:	No													
Product description														
Distearyl thiodipropionate. Used as an antioxidant for polyolefins and other polymeric systems and as an auxiliary stabilizer in conjunction with primary antioxidant for polypropylene, polyethylene, and synthetic rubbers to promote long-term ambient aging properties. Offers very good color, processing and aging stability.														
Best suitable Polymer														
<ul style="list-style-type: none"> • PP, Polypropylene • Rubbers • PE, Polyethylene 														
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th style="text-align: right;">Value</th> <th style="text-align: right;">Unit</th> </tr> </thead> <tbody> <tr> <td>Molecular weight</td> <td style="text-align: right;">693</td> <td></td> </tr> <tr> <td>Soft point</td> <td style="text-align: right;">67</td> <td>°C</td> </tr> <tr> <td>Weight loss @ 339°C in air, 10°C/min</td> <td style="text-align: right;">50</td> <td>%</td> </tr> </tbody> </table>				Value	Unit	Molecular weight	693		Soft point	67	°C	Weight loss @ 339°C in air, 10°C/min	50	%
	Value	Unit												
Molecular weight	693													
Soft point	67	°C												
Weight loss @ 339°C in air, 10°C/min	50	%												

Naugard® DLTDP
Chemtura

Request For Information Technical Assistance *Tech Direct* Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant>> Thioester

Chemical composition:	Dilauryl thiodipropionate	
Physical form:	Flakes	
CAS Number:	123-28-4	
Food contact approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Dilauryl thiodipropionate. Used as an antioxidant for polyolefins and other polymeric systems and as an auxiliary stabilizer in conjunction with primary antioxidant for polypropylene, polyethylene, and synthetic rubbers to promote long-term ambient aging properties. Offers very good color, processing and aging stability.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PP, Polypropylene • Rubbers • PE, Polyethylene 		
Typical properties	Value	Unit
Molecular weight	683	
Melt point	67	°C

Naugard® BHT
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Book in my library Print

Additive
Antioxidant
Heat Stabilizer >> Organic

Chemical composition:	2,6-di-t-butyl-p-cresol
Physical form:	Crystals
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Cost effective, general purpose, antioxidant.

Best suitable Polymer

- PP, Polypropylene
- PS, Polystyrene
- PE, Polyethylene
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene

Typical properties	Value	Unit
Melting point	99	°C
Color	10	APHA
Specific gravity @ 20°C	1.05	
Flash point, TOC	127	°C
Molecular weight	220	

Naugard® 76
Chemtura

Request For Information [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers [Save in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition:	Octadecyl-3,5-di-tert-butyl-4-hydroxyhydrocinnamate
Physical form:	Powder
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Octadecyl 3,5-di-tert-butyl-4-hydroxyhydrocinnamate.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PS, Polystyrene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Melting range	51.5 - 52.5	°C
Color	97.0	
Specific gravity @ 20°C	1.02	
Flash point, TCC	273	°C
Molecular weight	531	

Naugard® 412S
Chemtura

Request for Information  Search amongst 10,000+ Additives and Modifiers  Print

Additive
Antioxidant >> Thioester

Chemical composition:	Pentaerythritol tetrakis
Physical form:	Powder
Masterbatch / One Pack:	No

Product description
Low-volatility, odor-free, high molecular weight, thioester. Used as an antioxidant for high-temperature, long-term PP, PE, ABS, polystyrene and other engineering thermoplastic applications. Can be used in conjunction with a primary hindered phenolic antioxidant to improve stability. Provides outstanding color stability and very good extraction resistance. Suits for high-performance, mineral-filled applications.

Applications: water pipe, washing machine and dishwasher.

Best suitable Polymer

- PS, Polystyrene
- PP, Polypropylene
- ABS/SAN/ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene

Typical properties

	Value	Unit
Molecular weight	1162	
Mel point	47	°C
Specific gravity @ 55°C	0.93	
Bulk density	0.52	g/cc
Weight loss @ 374°C	50	%

Naugard® 10
Chemtura

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition: Tetraakis(Methylene(3,5-di-t-butyl-4-hydroxyhydrocinnamate))metha
 Physical form: Powder
 Masterbatch / One Pack: No

Product description: Tetraakis(Methylene(3,5-di-t-butyl-4-hydroxyhydrocinnamate))metha. Used as a versatile antioxidant. Provides long-term stability.

Best suitable Polymer

- PP, Polypropylene
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Melting point	111 - 127	°C
Color, Trans @ 20°C	95	
Specific gravity @ 20°C	1.2	
Flash point	299	
Molecular weight	1178	

Lowinox® TBM-6
Chemtura

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [PDF](#)

Additive
Antioxidant >> Phenolic

Chemical composition:	4,4'-thiobis (2-(1,1-dimethyl)-5-methyl) phenol
Physical form:	Powder
CAS Number:	96-69-5
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Non-staining and non-discoloring hindered thiophenol. Used for food packaging, high voltage cables and greenhouse films.

Best suitable Polymer

- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PP, Polypropylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Molecular weight	319	
Melting range	160 - 184	°C
Volatiles	< 0.5	%
Ash content	> 0.05	%

Lowinox DSTDP
Chemtura

Required For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my library Print

Additive
Antioxidant > Thioester

Chemical composition:	Distearyl-3,3'-thiodipropionate												
Physical form:	Solid												
CAS Number:	693-36-7												
Masterbatch / One Pack:	No												
Product description													
Sulfur containing antioxidant.													
Best suitable Polymer													
<ul style="list-style-type: none"> • PE, Polyethylene • PP, Polypropylene • ABS / SAN / ASA, Acrylonitrile-Styrenic based • PA, Polyamide 													
Typical properties <table border="1" style="width: 100%;"> <thead> <tr> <th></th> <th>Value</th> <th>Unit</th> </tr> </thead> <tbody> <tr> <td>Molecular weight</td> <td>653</td> <td></td> </tr> <tr> <td>Melting range</td> <td>63 - 67</td> <td>°C</td> </tr> <tr> <td>Specific gravity @ 25°C</td> <td>1.027</td> <td>g/ml</td> </tr> </tbody> </table>			Value	Unit	Molecular weight	653		Melting range	63 - 67	°C	Specific gravity @ 25°C	1.027	g/ml
	Value	Unit											
Molecular weight	653												
Melting range	63 - 67	°C											
Specific gravity @ 25°C	1.027	g/ml											

Lowinox DLTDP
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant >> Thioester

Chemical composition:	Dilauryl-3,3'-thiodipropionate	
Physical form:	Solid	
CAS Number:	123-28-4	
Masterbatch / One Pack:	No	
Product description		
Sulfur containing antioxidant. Used in some food packaging applications.		
Best suitable Polymer		
<ul style="list-style-type: none"> • TPU, Thermoplastic Polyurethane • PP, Polypropylene • PVC rigid, polyvinylchloride • ABS/ SAN ASA, Acrylonitrile-Styrenic based • PE, Polyethylene 		
Typical properties		
Molecular weight	515	Value
Melting range	38 - 41	Unit
Bulk density	0.58	°C
Specific gravity @ 70°C	0.895	g/ml

Chinox 168
Chitec Chemical

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers **N** Store my Library Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- PS, Polystyrene
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PVC, Polyvinyl Chloride
- BR, Butadiene Rubber, Polybutadiene
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PA, Polyamide
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library PDF

Chinox 1330
Chitec Chemical

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- Rubbers >> SBR, Styrene-butadiene rubber
- Thermoplastic other >> POM, Polyacetal, Polyformaldehyde
- PP, Polypropylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- Rubbers >> BR, Butadiene Rubber, Polybutadiene

Request For Information

Technical Assistance

Tech Direct

Chinox 1076
Chitec Chemical

Search amongst 10,000+ Additives and Modifiers

Store in my Library

Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Dust free, Free flowing.

Best suitable Polymer

- PVC rigid, polyvinylchloride
- PS, Polystyrene
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PU, Polyurethane
- Rubbers >> SBR, Styrene-butadiene rubber
- PC, Polycarbonate
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PMMA, Polymethylmethacrylate
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene

Chinox 1024
Chitec Chemical

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant >> Phenolic

Physical form:	Powder
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PA, Polyamide

Request For Information

Technical Assistance

Tech Direct

Chinox 1010
Chitec Chemical

Search amongst 10,000+ Additives and Modifiers

Store in my Library

Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description:
Dust free, Free flowing.

Best suitable Polymer

- PUR, polyurethane
- PS, Polystyrene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- TPU, Thermoplastic Polyurethane
- PVC, Polyvinylchloride
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Therephthalate

Weston® 505B
Chemtura

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Blend

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Blend of 83% Weston 399 phosphite and 17% Ultrinox 276. Appearance at room temperature is clear viscous liquid. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PVC rigid, polyvinylchloride
- ABS/ SAN ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties

	Value	Unit
Specific Gravity	0.98	
Flash Point, closed cup	217	°C
Solidification temperature	23	°C
Color, APHA	< 100	
Acid number, KOH	< 0.1	mg KOH/g
Density @ 25°C	8.2	lb/gal

Weston® 505
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant > Blend

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Is a blend of a primary and secondary stabilizer in one easy to handle liquid form: 63% Weston TNPP, 17% Ultranox 276. Improves color and inhibits degradation of molecular weight. Pre-blending of antioxidants are eliminated. Easy handling- accurate feeding rates. Is a low cost stabilizer.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PVC rigid, polyvinylchloride
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties

	Value	Unit
Color, APHA	<100	%
Ultranox 276	14 - 20	mg KOH/g
Acid number	<0.1	
Specific gravity @ 25°C	0.98	
Density @ 25°C	8.2	g/ml
Phosphorous content	3.5	%
Flash Point, closed cup	217	°C
Solidification temperature	23	

Weston® 504B
Chemtura

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save In My Library](#) [Print](#)

Additive
Antioxidant >> Blend

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Blend of 80% Weston 399 phosphite and 20% Ultrinox 276. Appearance at room temperature is semi-soft. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PVC rigid, polyvinylchloride
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Specific Gravity	0.98	
Flash Point, closed cup	218	°C
Solidification temperature	23	°C
Color, APHA	< 100	
Acid number, KOH	< 0.1	mg KOH/g
Density @ 23°C	0.2	kg/l

Weston® 504
Chemtura

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant >> Blend

Physical form:	Liquid
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Blend of 80% Weston TNPP phosphite and 20% Ultrinox 276. Appearance at room temperature is semi-soft. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PVC rigid, polyvinylchloride
- ABS/ SAN /ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Specific Gravity	0.98	
Flash Point, closed cup	218	°C
Softening temperature	22	°C
Color, APHA	< 100	
Acid number, KOH	< 0.1	mg KOH/g
Density @ 25°C	8.2	lb/gal

Weston® 502B
Chemtura

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant > Blend

Physical form:	Liquid	
Food contact approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Blend of 67% Weston 399 phosphite and 33% Ultrinox 278. Combined of a primary and secondary antioxidants. Pre-blending of antioxidants are eliminates. Risk of compounding errors and variability are minimizes. Easy handling-accurate feeding rates.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PVC rigid, polyvinylchloride • ABSI SAN ASA, Acrylonitrile-Styrene based • PE, Polyethylene >> HDPE, High Density Polyethylene 		
Typical properties	Value	Unit
Specific gravity	0.91	
Flash Point, closed cup	213	°C
Solidification temperature	32	°C
Density @ 25°C	7.9	lb/gal

Chinox 1790
Chitec Chemical

Request For Information 

Technical Assistance: [Search amongst 10,000+ Additives and Modifiers](#)

Additive
Antioxidant >> Phenolic

Physical form:	Powder
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PP, Polypropylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene

Eastman Poly TDP-2000
Eastman Chemical Company

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: Thiodipropionate polyester
 Physical form: Solid
 Masterbatch / One Pack: No

Product description
 Thiodipropionate polyester. Used as a secondary antioxidant along with phenolic primary antioxidants in plastics. Offers very good stability in high-temperature applications.

Best suitable Polymer
 • PP, Polypropylene

Typical properties	Value	Unit
Specific gravity @ 90°C	1.09	mgKOH/g
Acid Number	2.5	cP
Viscosity @ 40°C	2000	°C
Flash Point	249	
Hydronium Number	30	
Specific Gravity @ 90°C	1.06	
Color PC-D	>3.0	
Melting Point	133	°C

Cyanox® 1741
Cytec

Request For Information Technical Assistance: [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) Print

Additive
Antioxidant >> Phenolic

Chemical composition: 1,3,5-Tri(3,5-di-tert-butyl-4-hydroxybenzyl)-s-Triazine-2,4,6-(1H,3H,5H)-trione
Physical form: Powder
CAS Number: 27676-62-6
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
1,3,5-Tri(3,5-di-tert-butyl-4-hydroxybenzyl)-s-Triazine-2,4,6-(1H,3H,5H)-trione. Offers very good gas fade resistance. Possesses very good for color sensitive applications. Provides high performance in filled polyolefins.

Best suitable Polymer
• PP, Polypropylene
• PE, Polyethylene

Typical properties	Value	Unit
Molecular weight	784	
Melting point	219 - 222	°C
Specific gravity	1.03	
Assay	> 98	%

Hostanox SE 4 Flakes
Clariant

Request For Information Technical Assistance [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant
Heat Stabilizer >> Costabilizer

Physical form:	Flakes												
CAS Number:	693-36-7												
Food contact approval:	Yes												
Masterbatch / One Pack:	No												
Product description													
Sulphur containing costabilizer;													
Best suitable Polymer													
<ul style="list-style-type: none"> • Thermoplastic Elastomers, TPE • PP, Polypropylene • PE, Polyethylene >> HDPE, High Density Polyethylene 													
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;"></th> <th style="text-align: center;">Value</th> <th style="text-align: center;">Unit</th> </tr> </thead> <tbody> <tr> <td>Acid number</td> <td style="text-align: center;">< 2.0</td> <td style="text-align: center;">mg KOH/g</td> </tr> <tr> <td>Purity</td> <td style="text-align: center;">> 93</td> <td style="text-align: center;">%</td> </tr> <tr> <td>Volatility</td> <td style="text-align: center;">< 0.5</td> <td style="text-align: center;">%</td> </tr> </tbody> </table>			Value	Unit	Acid number	< 2.0	mg KOH/g	Purity	> 93	%	Volatility	< 0.5	%
	Value	Unit											
Acid number	< 2.0	mg KOH/g											
Purity	> 93	%											
Volatility	< 0.5	%											

200

Hostanox SE 10 Pwd
Clariant

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant
Heat Stabilizer >> Costabilizer

Physical form: Powder
CAS Number: 2500-88-1
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Sulphur containing costabilizer for plastics.

Best suitable Polymer
• Thermoplastic Elastomers, TPE
• PP, Polypropylene

Typical properties	Value	Unit
Drop point	58 - 62	°C
Color	< 5.0	Gardner

Hostanox SE 10 Gran
Clariant

Store in my Library Print

Additive
Antioxidant
Heat Stabilizer >> Costabilizer

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers

Physical form:	Granules	
CAS Number:	2500-88-1	
Masterbatch / One Pack:	No	
Product description		
Sulphur containing costabilizer for plastics.		
Best suitable Polymer		
• Thermoplastic Elastomers, TPE		
• PP, Polypropylene		
Typical properties	Value	Unit
Drip point	88 - 92	°C
Color	< 3.0	Gardner

Hostanox PAR 62 Pwd
Clarant

Request For Information Technical Assistance: Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite

Physical form:	Powder	
CAS Number:	28741-53-7	
Food contact approval:	Yes	
Masterbatch / One Pack:	No	
Product description		
Aromatic phosphite based processing stabilizer.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol • Thermoplastic Elastomers, TPE • PP, Polypropylene • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PA, Polyamide • PC, Polycarbonate • PE, Polyethylenes >> HDPE, High Density Polyethylene 		
Typical properties		
Acid number	Value: ~ 1.0	Unit: mg KOH/g
Melting point	Value: 170 - 180	Unit: °C
Viscosity	Value: < 0.5	Unit: S
2,4-di- <i>tert</i> -butylphenol	Value: < 1.0	Unit: S

Hostanox OSP 4 Powder
Clariant

Request For Information Technical Assistance Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Metal deactivator
Antioxidant >> Phosphite

Physical form:	Powder
CAS Number:	32697-78-8
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Stabilizer and metal desactivator for plastic materials. Used for wire & cable applications.

Best suitable Polymer
• PE, Polyethylene

Typical properties	Value	Unit
Melting point	221 - 232	°C
Volatility	< 0.5	%
Purity	> 98	%

Hostanox OSP 4 FF
Clariant

Request For Information Technical Assistance Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Metal deactivator
Antioxidant >> Phosphite

Physical form: Powder
CAS Number: 32687-78-8
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Stabilizer and metal deactivator for plastic materials. Used for wire & cable applications.

Best suitable Polymer
• PE, Polyethylene

Typical properties	Value	Unit
Melting point	221 - 232	°C
Volatility	< 0.5	%
Purity	> 98	%

Hostanox O 35
Clariant

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive
Heat Stabilizer
Antioxidant
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	41494-35-9
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Good synergy leading to a significant improvement of long term thermal stability.

Best suitable Polymer

- PE, Polyethylene
- PMMA, Polymethylmethacrylate
- PP, Polypropylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PA, Polyamide

Typical properties	Value	Unit
Melting point	65 - 75	°C
Volatility	< 0.3	%
Ash content	< 0.1	%

Hostanox O 310 Micro Pills
Clariant

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive	Granules	
Antioxidant	6683-19-8; 32509-68-3	
Heat Stabilizer >> Organic	Yes	
Physical form:	No	
CAS Number:		
Food contact approval:		
Masterbatch / One Pack:		
Product description		
Antioxidant for demanding applications. Used in HDPE blow or injection molded articles or PE/PP pipes.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PP, Polypropylene • PE, Polyethylene >> HDPE, High Density Polyethylene • PS, Polystyrene • PMMA, Polymethylmethacrylate • TPU, Thermoplastic Polyurethane • PA, Polyamide • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PBT, Polybutylene Terephthalate • PET / PETG , Polyethylene Terephthalate / Polyethylene Therephthalate Glycol 		
Typical properties	Value	Unit
Bulk density	560 - 700	g/l

Hostanox O 3 Pwd
Clariant

Requires Log In
Technical Assistance
Tech Direct

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	32509-86-3
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phenolic antioxidant. Offers high extraction resistance.	
Best suitable Polymer	
<ul style="list-style-type: none"> • Thermoplastic Elastomers, TPE • PVDF, Polyvinylidenechloride • PP, Polypropylene • PE, Polyethylene >> HDPE, High Density Polyethylene • ABS/ SAN/ ASA, Acrylonitrile-Styrene based • PA, Polyamide 	
Typical properties	
Color	Value: < 3.0
Melting point	Value: > 167
Volatility	Value: < 1.0
	Unit: Gardner
	Unit: °C
	Unit: %

Hostanox O 3 Pills
Clariant

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Prills
CAS Number:	32509-66-3
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Phenolic antioxidant. Offers high extraction resistance.

Best suitable Polymer

- Thermoplastic Elastomers, TPE
- PMMA, Polymethylmethacrylate
- PP, Polypropylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- ABS/SAN/ASA, Acrylonitrile-Styrenic based
- PA, Polyamide

Typical properties	Value	Unit
Color	< 3.0	Gardner
Melting point	< 167	°C
Volatile	< 1.0	%

Hostanox O 16 Pwd
Clariant

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	2082-79-3
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phenolic antioxidant for plastics in particular for polyolefins and engineering thermoplastic elastomers.	
Best suitable Polymer	
<ul style="list-style-type: none"> • Thermoplastic Elastomers, TPE • PS, Polystyrene • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PP, Polypropylene • TPU, Thermoplastic Polyurethane • PE/Ethylenically > LDPE, Low Density Polyethylene • EVA, Ethylene Vinyl Acetate Copolymer • ABS/ SAN/ ASA, Acrylonitrile-Styrene based • PE, Polyethylene >> HDPE, High Density Polyethylene • PC, Polycarbonate 	
Typical properties	Value
Purity	> 98
Visibility	< 0.5

Hostanox O 16 Gran
Clariant

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers [Save in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Granules
CAS Number:	2082-79-3
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Phenolic antioxidant for plastics in particular for polyolefins and engineering thermoplastic elastomers.

Best suitable Polymer

- Thermoplastic Elastomers, TPE
- PS, Polystyrene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- TPU, Thermoplastic Polyurethane
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Purity	> 98	%
Volatility	< 0.5	%

Hostanox O 16 FF
Clariant

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	2082-79-3
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Phenolic antioxidant for plastics in particular for polyolefins and engineering thermoplastic elastomers.

Best suitable Polymer

- Thermoplastic Elastomers, TPE
- PS, Polystyrene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- TPU, Thermoplastic Polyurethane
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS, SAN/ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Purity	> 98	%
Volatility	< 0.5	%

Hostanox O 14 Pwd
Clariant

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in My Library Print

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	27676-62-6
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phenolic antioxidant. Offers longterm thermal stabilization.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PS, Polystyrene • PMMA, Polymethylmethacrylate • Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde • PP, Polypropylene • TPU, Thermoplastic Polyurethane • PE, Polyamide • ABS, SAN, ASA, Acrylonitrile-Styrenic based • PBT, Polybutylene Terephthalate • PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol • PE, Polyethylene >> HDPE, High Density Polyethylene 	
Typical properties:	Value
Melting point:	218 - 223
	Unit
	°C

Hostanox O 10 TC Pwd
Clariant

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [PDF](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	6683-19-8
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Phenolic antioxidant.

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PP, Polypropylene
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PBT, Polybutylene Therephthalate
- PET / PETG , Polyethylene Terphthalate / Polyethylene Therephthalate Glycol
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Volatility	< 0.5	%
Purity	> 98	%

Hostanox O 10 TC FF
Clariant

[Request For Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	6683-19-8
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phenolic antioxidant.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PS, Polystyrene • PVAc, Polyacrylate • POM, Polyacetal, Polyformaldehyde • PP, Polypropylene • TPU, Thermoplastic Polyurethane • PA, Polyamide • ABS/ SAN/ ASA, Acrylonitrile-Styrene based • PBT, Polybutylene Terephthalate • PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol • PE, Polyethylene >> HDPE, High Density Polyethylene 	
Typical properties	Value
Volatility	< 0.5
	Unit
	%

Hostanox O 10 Pwd
Clariant

[Request For Information](#) Technical Assistance: [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	6883-19-8
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Phenolic antioxidant.

Best suitable Polymer

- PS, Polystyrene
- PMMA, Poly(methylmethacrylate)
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PP, Polypropylene
- TPU, Thermoplastic Polyurethane
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PBT, Polybutylene Terephthalate
- PET / PETG , Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Volatility	< 0.5	%
Putty	> 98	%

Hostanox O 10 FF
Clariant

[Research For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Physical form:	Powder
CAS Number:	6683-19-8
Food contact approval:	Yes
Masterbatch / One Pack:	No
Product description	
Phenolic antioxidant.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PS, Polystyrene • PMMA, Polymethylmethacrylate • Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde • PP, Polypropylene • TPU, Thermoplastic Polyurethane • PA, Polyamide • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PBT, Polybutylene Terephthalate • PET, PETG , Polyethylene Terephthalate / Polyethylene Terephthalate Glycol • PE, Polyethylene >> HDPE, High Density Polyethylene 	
Typical properties	Value
Viscosity	< 0.5
Purity	> 99%
	Unit
	%

Hostanox M
Clariant

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save in my Library](#) [Print](#)

Additive
Antioxidant

Physical form: Granules
Masterbatch / One Pack: No

Product description
Phenol-phosphite blend in various ratios. Also available as powder.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PET / PETG, Polymethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polycrolylene
- PV, Polyvinyl Chloride
- PE, Polyethylene >> HDPE, High Density Polyethylene
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PA, Polyamide
- PC, Polycarbonate
- PBT, Polybutylene Therephthalate

Chinox PEPQ
Chitec Chemical

Request For Information Technical Assistance Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- PS, Polystyrene
- PBT, Polybutylene Terephthalate
- PA, Polyamide
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Chinox B245
Chitec Chemical

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Physical form:	Powder:
Masterbatch / One Pack:	No
Product description	
Dust Free, Free flowing	
Best suitable Polymer	
<ul style="list-style-type: none"> • PP, Polypropylene • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based 	
Typical properties	
Chinox 3114, content	Value
Chinox 618, content	Unit
	%
	%

Request For Information

Technical Assistance

Tech Direct

Chinox 626
Chitec Chemical

Search amongst 10,000+ Additives and Modifiers

Store in my Library

Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- PVC rigid; polyvinylchloride
- PP, Polypropylene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- EVA, Ethylene Vinyl Acetate Copolymer
- PE, Polyethylene >> HDPE, High Density Polyethylene

Chinox 618
Chitec Chemical

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Free flowing, Dust free.

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PV, Polyvinyl
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- EVA, Ethylene Vinyl Acetate Copolymer
- PE, Polyethylene >> HDPE, High Density Polyethylene

Chinox 3114
Chitec Chemical

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [View Items In my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Physical form: Powder
Food contact approval: Yes
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> HDPE, High Density Polyethylene

Chinox 2002
Chitec Chemical

Request For Information Technical Assistance: [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Physical form: Powder
Masterbatch / One Pack: No

Product description

Best suitable Polymer

- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Therephthalate
- PC, Polycarbonate

Antiox WX
Ichemco

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant

Physical form: Masterbatch / One Pack:	Emulsion No	
Product description Is a milk white emulsion of liquid stabilizers in water with some presence (6% approx.) of toluene. It is very stable and suitable for use in resins/resins dispersion or emulsion. This emulsion grants the protective effect of a special primary phenolic antioxidant, the long-lasting effect of thioesters and the high temperature protection of phosphites. The result is a well balanced formulation, having a wide spectrum of protection to the negative effects of oxidation, light and heat. ANTIOX WX is used for all water systems, containing resins and elastomers, sensitive to above mentioned effects, particularly: natural latices, SBR and NBR latices, copolymers; PVA and EVA latices; resins dispersed in water (rosin esters, hydrocarbons, therpenics, etc.).		
Best suitable Polymer		
<ul style="list-style-type: none"> • Rubbers >> SBR, Styrene-butadiene rubber • Rubbers >> NBR, Acrylonitrile-butadiene Rubber • EVA, Ethylene Vinyl Acetate Copolymer 		
Typical properties	Value	Unit
Solids content	51 - 53	%

Antiox W1
Ichemco

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library PDF

Additive
Antioxidant

Masterbatch / One Pack: No

Product description
 Is a synergistic combination of 3 liquid antioxidants, properly dispersed in water, in order to be easily added to elastomers/resins dispersions.
 Gives the protective effect of a special primary phenolic antioxidant (Food Grade type), the long-lasting effect of thioesters and the high temperature protection of phosphites.
 The result is a well balanced formulation, having a wide stabilisation spectrum to the negative effects of oxidation, light and heat.
 Is used for all water systems, containing resins and elastomers, sensitive to above mentioned effects, particularly: natural latices, SBR and NBR latices, copolymers; PVA and EVA latices, P.U. latices; resins dispersed in water (rosin esters, hydrocarbons, therpenics, etc.).

Best suitable Polymer

- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- EVA, Ethylene Vinyl Acetate Copolymer

Typical properties	Value	Unit
Viscosity, Brookfield	800 - 1800	cPs
pH	4.5 - 6.5	
Solids content	59 - 61	%

Kinox -76
High Polymer Labs

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant

Masterbatch / One Pack: No

Product description
Used as basic stabiliser.

Best suitable Polymer
• PE, Polyethylene

Evernox® B410
Everspring Chemical Company Limited

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) and Tris (2,4-di-tert-butylphenyl) phosphite
Physical form: Granules
CAS Number: 6883-19-8 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as an excellent antioxidant for processing and long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- PUR, polyurethane
- PS, Polystyrene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Terephthalate

Typical properties	Value	Unit
Voraties	< 0.5	%
Melting point	110 - 186	°C
Flash point	> 150	°C
Decomposition temperature	> 350	°C
Specific gravity	1.02 - 1.05	g/cm³
pH (1% solution)	5.89	

Evernox® B401
Everspring Chemical Company Limited

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate and Tris (2,4-di-tert-butylphenyl) phosphite
Physical form: Granules
CAS Number: 2082-79-3 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as an excellent antioxidant for processing and long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- PUR, polyurethane
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS / SAN / ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Therephthalate

Typical properties	Value	Unit
Volatile	< 0.5	%
Melting point	110 - 180	°C
Flash point	> 150	°C
Decomposition temperature	> 350	°C
Specific gravity	1.02 - 1.05	g/cm³
pH (1% solution)	5.85	

Evernox® B310
Everspring Chemical Company Limited

[Request For Information](#) [Technician Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [PDF](#)

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) and Tris (2,4-di-tert-butylphenyl) phosphite
Physical form: Granules
CAS Number: 6683-19-8 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as a good antioxidant for processing and long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- PUR, polyurethane
- PS, Polystyrene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PBT, Polybutylene Therephthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Volatiles	< 0.5	%
Melting point	110 - 188	°C
Flash point	> 150	°C
Decomposition temperature	> 350	°C
Specific gravity	1.02 - 1.05	g/cm ³
pH (1% solution)	5.89	

Evernox® B210
Everspring Chemical Company Limited

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) and Tris (2,4-di-*t*-butylphenyl) phosphite
Physical form: Granules
CAS Number: 6683-19-8 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as an antioxidant for processing and good long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PUR, polyurethane
- PS, Polystyrene
- PP, Polypropylene
- Specialty Polymers >> PSU, polysulfone
- Rubbers >> SBR, Styrene-butadiene rubber
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PBT, Polybutylene Theraphthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Volatiles	< 0.5	%
Melting point	110 - 195	°C
Flash point	> 150	°C
Decomposition temperature	>350	°C
Specific gravity	1.02 - 1.05	g/cm3
pH (1% solution)	5.89	

Evernox® B201
Everspring Chemical Company Limited

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate and Tris (2,4-di-tert-butylphenyl) phosphite
Physical form: Granules
CAS Number: 5683-19-8 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as an antioxidant for processing and good long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- PS, Polystyrene
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PP, Polypropylene
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PUR, polyurethane
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PBT, Polybutylene Therephthalate

Typical properties	Value	Unit
Volatiles	< 0.5	%
Melting point	110 - 195	°C
Flash point	> 150	°C
Decomposition temperature	> 350	°C
Specific gravity	1.02 - 1.05	g/cm³
pH (1% solution)	5.80	

Evernox® B110
Everspring Chemical Company Limited

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store In My Library](#) [Print](#)

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Chemical composition: Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) and Tris (2,4-di-tert-butylphenyl) phosphite
Physical form: Granules
CAS Number: 6683-19-8 and 31570-04-4
Masterbatch / One Pack: No

Product description
Stable synergistic blend of phenolic and phosphite compounds. Used as an antioxidant for processing and good long-term heat stability. Forms low color and keeps original melt flow.

Best suitable Polymer

- PUR, polyurethane
- PS, Polystyrene
- PET / PETG , Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PBT, Polybutylene Therephthalate
- PA, Polyamide
- ABS, SAN, ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Volatile	< 0.5	%
Melting point	110 - 186	°C
Flash point	> 150	°C
Decomposition temperature	> 350	°C
Specific gravity	1.02 - 1.05	g/cm ³
pH (1% solution)	5.89	

Evernox® 76GF
Everspring Chemical Company Limited

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in My Library Print

Additive
Antioxidant > Phenolic

Chemical composition:	Octadecyl-3-(3,5-di-tert-4-hydroxyphenyl)-propionate
Physical form:	Granules
CAS Number:	2082-79-3
Masterbatch / One Pack:	No

Product description
Stable, sterically hindered phenolic compound. Used as an antioxidant for manufacturing, processing and long-term thermal stabilization. Possesses good compatibility, high resistance to extraction and is odorless.

Best suitable Polymer

- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- PUR, polyurethane
- PP, Polypropylene
- Thermoplastics, other >> HIPS, High Impact Polystyrene
- PBT, Polybutylene Therephthalate
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PET / PETG , Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PE, Polyethylene

Typical properties	Value	Unit
Ash	< 0.1	%
Volatiles	< 0.5	%
Color, APHA	< 25	
Melting point	56 - 58	°C
Fusion point	273	°C
Specific gravity @ 20°C	1.02	g/cm³
Bulk density	470 - 520	g/l

Evernox® 76
Everspring Chemical Company Limited

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers **Save in my Library** Print

Additive
Antioxidant >> Phenolic

Chemical composition: Octadecyl-3-(3,5-di-tert-4-hydroxyphenyl)-propionate
Physical form: Powder
CAS Number: 2082-79-3
Masterbatch / One Pack: No

Product description
Stable, sterically hindered phenolic compound. Used as an antioxidant for manufacturing, processing and long-term thermal stabilization. Possesses good compatibility, high resistance to extraction and is odoreless.

Best suitable Polymer

- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- PU/P, polyurethane
- PP, Polypropylene
- Thermosolastics, other >> HIPS, High Impact Polystyrene
- PBT, Polybutylene Terephthalate
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PET / PETG, Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
- PE, Polyethylene

Typical properties	Value	Unit
Ash	< 0.1	%
Volatiles	< 0.5	%
Color, APHA	< 25	
Density	90 - 95	kg/m ³
Flash point	273	°C
Specific gravity @ 20°C	1.02	g/cm ³
Bulk density	260 - 320	g/l

Evernox® 3114
Everspring Chemical Company Limited

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers [View my library](#) [Print](#)

Additive
Antioxidant >> Phenolic

Chemical composition:	Tris-(3,5-di-tert.butyl-4-hydroxybenzyl)-isocyanurate																
Physical form:	Powder																
CAS Number:	27876-62-6																
Masterbatch / One Pack:	No																
Product description																	
Stable phenolic compound. Used as an antioxidant for long-term thermal stabilization.																	
Best suitable Polymer																	
<ul style="list-style-type: none"> • Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS) • Thermoplastics, other >> HIPS, High Impact Polystyrene • PP, Polypropylene • PVC rigid; polyvinylchloride • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PE, Polyethylene • PS, Polystyrene 																	
Typical properties <table border="1" style="width: 100%;"> <thead> <tr> <th></th> <th>Value</th> <th>Unit</th> </tr> </thead> <tbody> <tr> <td>Ash</td> <td>< 0.05</td> <td>%</td> </tr> <tr> <td>Volatiles</td> <td>< 0.2</td> <td>%</td> </tr> <tr> <td>Melting point</td> <td>218 - 223</td> <td>°C</td> </tr> <tr> <td>Molecular weight</td> <td>784</td> <td></td> </tr> </tbody> </table>				Value	Unit	Ash	< 0.05	%	Volatiles	< 0.2	%	Melting point	218 - 223	°C	Molecular weight	784	
	Value	Unit															
Ash	< 0.05	%															
Volatiles	< 0.2	%															
Melting point	218 - 223	°C															
Molecular weight	784																

Evernox® 10GF
Everspring Chemical Company Limited

[Request / or Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant > Phenolic

Chemical composition: Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)
Physical form: Granules
CAS Number: 6683-19-8
Masterbatch / One Pack: No

Product description
Stable, sterically hindered phenolic compound. Used as antioxidant for manufacturing, processing and long-term thermal stabilization. Possesses good compatibility, high resistance to extraction, low volatility and is odorless.

Best suitable Polymer

- Rubbers >> EPM/ EVM, Ethylene based
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PVC rigid, polyvinylchloride
- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- PP, Polypropylene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- Thermoplastics, other >> HIPS, High Impact Polystyrene
- PBT, Polybutylene Terephthalate
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- PE, Polyethylene
- PUR, polyurethane
- PS, Polystyrene
- PET / PETG , Polyethylene Terephthalate / Polyethylene Terephthalate Glycol

Typical properties	Value	Unit
Ash	< 0.1	%
Vinolines	< 0.5	%
Color, APHA	< 40	
Melting point	110 - 125	°C
Flash point	297	°C
Specific gravity @ 20°C	1.15	g/cm ³
Bulk density	450 - 570	g/l

Evernox® 10
Everspring Chemical Company Limited

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Chemical composition: Pentaerythritol Tetraakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)
 Physical form: Powder
 CAS Number: 6663-19-8
 Masterbatch / One Pack: No

Product description
 Stable, sterically hindered phenolic compound. Used as antioxidant for manufacturing, processing and long-term thermal stabilization. Possesses good compatibility, high resistance to extraction, low volatility and is odorless.

Best suitable Polymer

- Rubbers >> EPM/ EVM, Ethylene based
- Rubber Compounds, Thermoplastic Polypropylene Diene Rubber
- PVC rigid, polyvinylchloride
- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- PP, Polycaprolene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- Thermoplastics, other >> HIPS, High Impact Polystyrene
- PBT, Polybutylene Therephthalate
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- PE, Polyethylene
- PUR, Polyurethane
- PS, Polystyrene
- PET / PETG , Polyethylene Terephthalate / Polyethylene Therephthalate Glycol

Typical properties	Value	Unit
Ash	< 0.1	%
Unities	< 0.5	%
Color, APHA	< 40	
Melting point	110 - 125	°C
Flash point	297	°C
Specific gravity @ 20°C	1.15	g/cm³
Bulk density	530 - 630	g/l

Everfos® 168
Everspring Chemical Company Limited

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in myLibrary Print

Additive
Antioxidant >> Phosphite

Chemical composition:	Tris (2,4-di-tert-butylphenyl) phosphite	
Physical form:	Powder	
CAS Number:	31570-04-4	
Masterbatch / One Pack:	No	
Product description		
Hydrolytically stable phosphite processing stabilizer. Used as a secondary antioxidant. Reacts during processing with hydroperoxides. Prevents molecular weight change and discoloration.		
Best suitable Polymer		
<ul style="list-style-type: none"> • PVC, rigid, polyvinylchloride • PS, Polystyrene • PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol • PP, Polypropylene • Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS) • Rubbers >> BR, Butadiene Rubber, Polybutadiene • PV, Polyvinyl • EVA, Ethylene Vinyl Acetate Copolymer • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PE, Polyethylene • PC, Polycarbonate • PBT, Polybutylene Therephthalate 		
Typical properties		
Volatiles	Value	Unit
Melting point	< 0.3	%
Specific gravity @ 20°C	183 - 187	°C
Bulk density	1.03	g/cm ³
	480 - 570	g/t

Wingstay® 29
Eliokem

Request For Information Technical Assistance Search amongst 10,000+ Additives and Modifiers Scan my Library Print

Additive
Antioxidant >> Amine

Chemical composition:	Para oriented styrenated diphenylamines																			
Physical form:	Liquid																			
CAS Number:	66442-68-2																			
Food contact approval:	Yes																			
Masterbatch / One Pack:	No																			
Product description																				
Mixed para oriented styrenated diphenylamines. Possesses very low volatility and low staining characteristics. Provides resistance to heat and flex fatigue in general rubber applications such as belts and tyres, and is especially effective in polychloroprene. Use in cable applications particularly for the protection of medium and high voltage polyethylene cables.																				
Best suitable Polymer																				
<ul style="list-style-type: none"> • Rubbers • PE, Polyethylene 																				
Typical properties <table border="1"> <thead> <tr> <th></th> <th>Value</th> <th>Unit</th> </tr> </thead> <tbody> <tr> <td>Molecular weight, average</td> <td>390</td> <td></td> </tr> <tr> <td>Viscosity @ 25°C</td> <td>30000</td> <td>mPa.s</td> </tr> <tr> <td>Benzene solv.</td> <td>1.08</td> <td></td> </tr> <tr> <td>Color, Gardner</td> <td>5</td> <td></td> </tr> <tr> <td>Refractive index @ 25°C</td> <td>1.839</td> <td></td> </tr> </tbody> </table>				Value	Unit	Molecular weight, average	390		Viscosity @ 25°C	30000	mPa.s	Benzene solv.	1.08		Color, Gardner	5		Refractive index @ 25°C	1.839	
	Value	Unit																		
Molecular weight, average	390																			
Viscosity @ 25°C	30000	mPa.s																		
Benzene solv.	1.08																			
Color, Gardner	5																			
Refractive index @ 25°C	1.839																			

BNX® 1010
Mayzo

Technical Assistance: [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Store in my Library | Print

Additive
Antioxidant
Heat Stabilizer >> Organic

Chemical composition: Tetraakis [Methylene-3 (3',5'-di-tert-butyl-4-hydroxyphenyl)propionate] methane.

Physical form: Powder.

CAS Number: 6883-19-8

Masterbatch / One Pack: No

Product description
High molecular antioxidant.
Effective, non-discoloring stabilizer that provides excellent long-term heat stability by preventing thermo-oxidative degradation during processing and service life.
Also provides good compatibility with resins and excellent extraction resistance.
Can be applied in polyolefins, such as polyethylene, polypropylene, polybutene and olefin copolymers such as ethylene-vinyl acetate copolymers.
Also provides excellent stabilization in other polymers such as polycelals, polyamides and polyurethanes, polyesters, PVC, styrene homo- and copolymers, ABS, elastomers such as butyl rubber, SBS, SEBS, EPM, and EPDM as well as other synthetic rubbers, latex, adhesives, natural and synthetic tackifier resins.
Also suggested for use with polyethylene wire and cable insulation and for use with synthetic diester fluids, oils, fats, waxes, and other organic substrates.

Best suitable Polymer

- Rubbers >> IIR, Butyl Rubber
- Rubbers >> EPM/ EVM, Ethylene based
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PP, Polypropylene
- Thermoplastic other
- Thermoplastic Elastomers, TPE >> SBC, styrene block copo (SBS, SEBS, SIS)
- PA, Polyamide
- EVA, Ethylene Vinyl Acetate Copolymer
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PVC rigid, polyvinylchloride
- PUR, polyurethane
- PE, Polyethylene

Typical properties	Value	Unit
Molecular weight	1177.7	
Melting range	110 - 125	°C
Volatiles	< 0.5	%

Benefos® 1680
Mayzo

[Request for Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Phosphite

Chemical composition: Tris(2,4-di-tert-butylphenyl)phosphite
 CAS Number: 31570-04-4
 Masterbatch / One Pack: No

Product description
 Secondary antioxidant (when combined with Mayzo's antioxidants).
 Low volatility.
 Particularly resistant to hydrolysis and provides excellent protection to organic polymers. Particularly useful in polyolefins and olefin-copolymers and ethylene vinyl acetate copolymers.
 Can also be used in adhesives, natural and synthetic tackifier resins.
 Can be used in combination with UV absorbers and light stabilizers to provide enhanced performance.
 Prevents discoloration.
 Protects polymers from chain scission and crosslinking, and is resistant to hydrolysis.

Best suitable Polymer

- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PS, Polystyrene
- Rubbers >> IR, Polysoprene
- PP, Polypropylene
- Thermoplastic, other
- EVA, Ethylene Acrylate Copolymer
- ABS/SAN/ASA, Acrylonitrile-Styrenic based
- PA, Polyamide
- PE, Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Molecular weight	647	
Melting range	183 - 187	°C
Volatile	< 0.5	%
Specific gravity @ 20 °C	1.03	g/cm³
Decomposition temperature	> 300	°C

KP 1460
Kolon Chemical

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Share in my Library Print

Additive
Antioxidant >> Phosphite

Chemical composition:	Tetra(tridecyl)-4, 4'-butylene-bis(6-t-butyl-2-methyl)diphenol)diphosphite
Physical form:	Liquid
Masterbatch / One Pack:	No

Product description
Improving early color of PP and PE.
Rigid PVCgelling promoter.
Catalyst for rigid PVC.

Best suitable Polymer

- PP, Polypropylene
- PVC rigid, polyvinylchloride
- PE, Polyethylene

Typical properties	Value	Unit
Specific gravity @ 25°C	0.953	
Refractive index @ 25°C	1.496	
Viscosity @ 25°C	600 - 1400	cps
Heat loss	<0.5	%

KP 1419
Kolon Chemical

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers  

Additive
Antioxidant >> Phosphite

Chemical composition:	Diphenyl tridecyl phosphite
Physical form:	Liquid
Masterbatch / One Pack:	No

Product description

It enables good weatherability and light stability.
 Flexible PVC gelling promoter,
 Viscosity controller for PVC sol.
 Improving restoration property (PVC foam).

Best suitable Polymer

- PP, Polypropylene
- PVC rigid, polyvinylchloride
- ABS/ SAN ASA, Acrylonitrile-Styrene based

Typical properties	Value	Unit
Specific gravity @ 23°C	1.01	
Refractive index @ 23°C	1.51	
Viscosity @ 25°C	< 40	cps

KP 1416
Kolon Chemical

Technical Assistance Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phosphite

Chemical composition:	Diphenyl isodecyl phosphite												
Physical form:	Liquid												
Masterbatch / One Pack:	No												
Product description													
It enables good weatherability and light stability. Flexible PVC gelling promoter. Viscosity controller for PVC sol. Improving restoration property (PVC foam).													
Best suitable Polymer													
<ul style="list-style-type: none"> • PP, Polypropylene • PVC rigid, polyvinylchloride • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based 													
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th style="text-align: center;">Value</th> <th style="text-align: center;">Unit</th> </tr> </thead> <tbody> <tr> <td>Specific gravity @ 25°C</td> <td style="text-align: center;">1.03</td> <td></td> </tr> <tr> <td>Refractive index @ 25°C</td> <td style="text-align: center;">1.515</td> <td></td> </tr> <tr> <td>Vicosity @ 25°C</td> <td style="text-align: center;">< 40</td> <td style="text-align: center;">cps</td> </tr> </tbody> </table>			Value	Unit	Specific gravity @ 25°C	1.03		Refractive index @ 25°C	1.515		Vicosity @ 25°C	< 40	cps
	Value	Unit											
Specific gravity @ 25°C	1.03												
Refractive index @ 25°C	1.515												
Vicosity @ 25°C	< 40	cps											

KP 1406
Kolon Chemical

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phosphite

Chemical composition:	Diphenyl isooctyl phosphite
Physical form:	Liquid
Masterbatch / One Pack:	No

Product description
It enables good weatherability and light stability.
Flexible PVC gelling promoter.
Viscosity controller for PVC sol.

Best suitable Polymer

- PP, Polypropylene
- PVC rigid, polyvinylchloride
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based

Typical properties.	Value	Unit
Specific gravity @ 25°C	1.035	
Refractive index @ 25°C	1.515	
Viscosity @ 25°C	< 50	cps

BNX® 1035
Mayzo

Technical Assistance: [Request for Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers [Store in my library](#) [Print](#)

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Chemical composition: Thiodiethylene bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]
 Physical form: Powder
 CAS Number: 41484-35-9
 Masterbatch / One Pack: No

Product description
 Effective, non-discoloring, sulfur containing stabilizer that provides excellent long-term heat stability by preventing thermo-oxidative degradation.
 Widely used for the process stabilization of polyethylene wire and cable resins, for polyethylene during extruder compounding.
 Can also be applied in styrenic polymers, polypropylene, elastomers such as EPDM and SBR and for carboxylated SBR latex, polybutadiene rubber and polyisopropene rubber.
 Also provides excellent stabilization in other petroleum products such as turbine oil and in petroleum, and higher aliphatic hydrocarbons such as 1-butene and 4-methyl-1 pentene plus polyurethanes, polyesters, segmented block copolymers, ABS, and other rubber modified polymers.

Best suitable Polymer

- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- Rubbers >> SBR, Styrene-butadiene rubber
- Thermoplastics, other
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene
- PUR, polyurethane

Typical properties		Value	Unit
Molecular weight*		642	
Melting range		53 - 68	°C
Volatiles	< 1		%
Ash	< 0.01		%
Assay	> 99		%
Specific gravity @ 20°C	1.19		gram/cm ³

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user must contact project manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable. However, the data is provided without express warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory in any way for any damages representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

BNX® 1076
Mayzo

Technical Assistance Search amongst 10,000+ Additives and Modifiers Print

Additive
Antioxidant >> Phenolic
Heat Stabilizer >> Organic

Chemical composition: Stearyl-3-(3',5'-di-tert-butyl-4-hydroxyphenyl) propionate
 Physical form: Powder
 CAS Number: 2082-79-3
 Masterbatch / One Pack: No

Product description
 Effective, non-discoloring stabilizer that provides excellent long-term heat stability by preventing thermo-oxidative degradation during processing and service life.
 Also provides good compatibility with resins and excellent extraction resistance.
 Can be used in a wide variety of organic substrates such as plastics, synthetic fibers, elastomers, adhesives, waxes, oils, and fats.
 Can be applied in polyolefins, such as polyethylene, polypropylene, polybutene-1 and other polymers such as engineering plastics, styrene homo- and copolymers, polyurethane, elastomers, adhesives, and other organic substrates, styrenics, rubber modified styrenes including ABS, SAN and segmented block copolymers, saturated and unsaturated elastomers, PVC, urethane and acrylic coatings, adhesives and petroleum products.

Best suitable Polymer

- PVC rigid; polyvinylchloride
- Thermoplastics, other >> Ethylene copolymer
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene
- PUR, polyurethane

Typical properties	Value	Unit
Molecular weight	530.8	
Melting range	49 - 54	°C
Volatiles	< 0.5	%
Ash	< 0.1	%

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

BNX® 1077
Mayzo

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Light Stabilizer / UV Absorber >> Benzotriazole
Antioxidant >> Blend

Chemical composition: Mixture of benzene propanoic acid, 3,5-bis (1,1-dimethyl ethyl)-4-hydroxy-, isotridecyl ester
Physical form: Liquid
CAS Number: 847488-62-4
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
 UV absorber in the 300-400 nm region.
 High degree of photostability. The properties and structure are unchanged over long periods of light exposure.
 Provides ultraviolet protection in a wide variety of polymers.
 Thermally stable up to processing temperatures as high as 600°F.
 Excellent resistance to oxidizing and reducing agents used in polymerization and curing.
 Imparts little or no initial color to substrates. Does not discolor during light or heat aging. Exhibits antioxidant and thermal stabilization properties.

Best suitable Polymer

- > Rubbers >> BR, Butadiene Rubber, Polybutadiene
- > Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- > Rubbers >> SBR, Styrene-butadiene rubber
- > ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- > PE, Polyethylene >> LDPE, Low Density Polyethylene
- > PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene

Typical properties	Value	Unit
Molecular weight	460.7	g/mol
Specific gravity @ 25°C	0.94	
Freeze Point	-56	°C
Boiling Point	230	°C
Vapor Pressure@20°C	1.86	kPa

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. Specialchem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full details on the scope and nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem S. A.

BNX® 1225
Mayzo

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant
Heat Stabilizer

Masterbatch / One Pack: No

Product description
Synergistic blend of BNX 1010 and Benefos 1680. Provides excellent heat stability and antioxidant, with good compatibility with resins and excellent extraction resistance. Synergistic blend is used in polyolefins and olefin-copolymers such as polyethylene, polypropylene, polybutene and ethylene-vinyl acetate copolymers. Can also be used in other polymers such as engineering plastics, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Best suitable Polymer
 • Thermoplastic rubber
 • PIP, Polypropylene
 • PUR, polyurethane
 • EVA, Ethylene Vinyl Acetate Copolymer
 • PE, Polyethylene

Typical properties		Value	Unit
BNX 1010 content		45 - 55	%
Benefos 1680 content		45 - 55	%
Volatiles		< 0.5	%

Disclaimer
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of profit, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S. A.

BNX® 1235
Mayzo

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant
Heat Stabilizer

CAS Number: 6683-19-8; 31570-04-4
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Blend of tetrakis [Methylene-3 (3',5'-di-tert-butyl-4-hydroxyphenyl) propionate]methane and triis (2, 4- di-tert-butylphenyl) phosphite. Offers long-term thermal stability. Provides low color formation and low volatility.

Best suitable Polymer
• Thermoplastic Elastomers, TPE
• PP, Polypropylene
• PE, Polyethylene
• PUR, polyurethane

Disclaimer
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without implied warranties of any kind. Specialties shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss or revenue, loss of profit, loss of business, loss of equipment, loss of goodwill, or general damages, even if advised of the possibility of such damages. It is the user's responsibility to consult regulatory agencies to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S. A.

BNX® 1900
Mayzo

[Request for Information](#) Technical Assistance: [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Share in my Library](#) [Print](#)

Additive
Antioxidant
Heat Stabilizer

Masterbatch / One Pack: No

Product description
Synergistic blend of BNX 1076 and Benefos 1680.
Provides excellent heat stability and anti-oxidation, with good compatibility with resins and excellent extraction resistance.
Used in polyethylene and ethylene-copolymers such as ethylene-vinyl acetate copolymers.
Can also be used in other polymers such as engineering plastics, polycarbonates, polyesters, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.

Best suitable Polymer

- PUR, polyurethanes
- Thermoplastics, other
- PE, Polyethylene
- EVA, Ethylene Vinyl Acetate Copolymer
- PC, Polycarbonate

Typical properties	Value	Unit
BNX 1076 content	17.5 - 22.5	%
Benefos 1680 content	77.5 - 82.5	%
Volatiles	< 0.5	%

BNX® DLTDP
Mayzo

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Plasticizer
Antioxidant
Heat Stabilizer

Chemical composition:	Dilauryl Thiodipropionate
Physical form:	Flakes
CAS Number:	123-28-4
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Dilauryl Thiodipropionate. Offers very good compatibility with plastics, rubber, petroleum. Improves the weather and heat resistance.

Best suitable Polymer

- Thermoplastics, other
- PP, Polypropylene
- Rubbers >> NR, Natural Rubber
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene

Typical properties	Value	Unit
Molecular weight	514.66	
Melting range	39 - 42	°C
Flash point	204	°C
Specific Gravity	0.898	
Acid value	<1.0	

BNX® MD 1024
Mayzo

Technical Assistance: [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

[Store in my Library](#) [Print](#)

Additive
Antioxidant
Metal deactivator

Chemical composition:	1,2-bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl)hydrazine
Physical form:	Powder
CAS Number:	32687-78-8
Masterbatch / One Pack:	No

Product description

Antioxidant and metal deactivator highly effective in hindering the harmful effect of copper conductors upon polypropylene, high and low density polyethylene and some thermoplastic elastomers used as primary insulation in wire and cable applications.

Also recommended for use in EPDM, peroxide and radiation crosslinked polyethylene, nylon, polyacetal and other organic substrates and for evaluation in polybutene-1, polyurethanes, styrene copolymers, unsaturated rubber substrates, polyvinyl chloride, polyvinylbutyral and other polymers where reactive metals may affect polymer properties, hot melt and solution adhesives, polymer powder coatings and other coatings on metals, rubber or plastic gaskets and plastic fabricated parts in contact with catalytic metals, oils and lubricants in high temperature contact with metals and contaminants and acid acceptor in polyacetal and other polymers.

Best suitable Polymer

- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- Rubbers
- Thermoplastics, other >> Polyvinyl (excluding PVC)
- Thermoplastics, other
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PVC rigid, polyvinylchloride
- PUR, polyurethane

Typical properties

	Value	Unit
Molecular weight	553	
Molecular range	224 - 229	°C
Volatile	< 0.5	%
Flash point	> 180	°C
Specific gravity	1.11	
Decomposition temperature	> 350	°C
pH (1% solution)	6	

BNX® MD 1097
Mayzo

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive
Antioxidant
Metal deactivator

Chemical composition: 2,2'-oxamidobis[ethyl 3-(3,5-di-t-butyl-4-hydroxyphenyl) propionate]
Physical form: Powder
CAS Number: 70331-94-1
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Hindered Phenolic Antioxidant. Used for wire and cable insulation, film and sheet manufacture as well as automotive parts. Provides long term thermal stabilization properties. Exhibits very good metal deactivation properties.

Best suitable Polymer

- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- Rubbers
- Thermoplastics, other >> Polyvinyl (excluding PVC)
- Thermoplastics, other
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PVC rigid; polyvinylchloride
- PUR, polyurethane

Typical properties	Value	Unit
Molecular weight	697	
Melting range	170 - 190	°C
Specific gravity	1.12	

Songnox® 1010
R. T. Vanderbilt

Request For Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Amine

Chemical composition: Tetrakis [methylene 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate] methane
 Physical form: Various
 CAS Number: 6683-19-8
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description
 Tetrakis [methylene 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate] methane. Used as an antioxidant for organic polymers PE, PP, POM, PA, PET, PVC, and elastomers. Provides long term heat stability. Exhibits a synergistic effect.

Best suitable Polymer

- PA, Polyamide
- PE, Polyethylene
- PET / PETG ,Polyethylene Terephthalate / Polyethylene Terephthalate Glycol
- PP, Polypropylene
- PVC rigid; polyvinylchloride
- PVC, flexible; polyvinylchloride
- Thermoplastic Elastomers, TPE
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde

Typical properties	Value	Unit
Melting range	110 - 125	°C
Ash	< 0.10	%
Volatile loss	< 50	%
Assay	≥ 98	%
Purity	≥ 95	%
Molecular weight	3178	

Disclaimers
 All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. The information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2009 SpecialChem, S. A.

Songnox® 1024
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Amine

Chemical composition:	1,2-Bis (3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl) hydrazine	
Physical form:	Various	
CAS Number:	32687-78-8	
Masterbatch / One Pack:	No	
Product description		
1,2-Bis (3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl) hydrazine. Used as an antioxidant for wire and cable. Provides high level of extraction resistance.		
Best suitable Polymer		
<ul style="list-style-type: none"> • Thermoplastic Elastomers, TPE • Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde • Rubbers >> EPDM, Ethylene Propylene Diene Rubber • PE, Polyethylene • PP, Polypropylene 		
Typical properties:	Value	Unit
Melting range	221 - 232	°C
Ash	< 0.10	%
Volatile loss	< 0.50	%
Assay	> 88	%
Molecular weight	553	

Songnox® 1035
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Buy](#)

Additive
Antioxidant >> Amine

Chemical composition:	1Thiodiethylene bis [3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate]	
Physical form:	Various	
CAS Number:	41484-35-9	
Masterbatch / One Pack:	No	
Product description		
Thiodiethylene bis [3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate]. Used as an antioxidant for PE - i.e. wire and cable resins. Provides high molecular weight and low volatility. Exhibits long-term heat stability.		
Best suitable Polymer		
> PE, Polyethylene		
Typical properties		
Melting range	Value	Unit
As%	> 95	°C
Volatile less	< 0.10	%
Assay	< 0.30	%
Molecular weight	> 98	%
	643	

Songnox® 1076
R. T. Vanderbilt

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate
Physical form: Various
CAS Number: 2082-79-3
Food contact approval: Yes
Masterbatch / One Pack: No

Product description
Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate. Used as primary antioxidant for organic polymers PE, PC, PVB, PVC, PU, acrylics, styrenics, and elastomers. Provides long term heat stability. Protects physical properties during storage and use of end-product. Exhibits non-discoloring, nonstaining, odorless and tasteless. Possesses synergistic effect.

Best suitable Polymer

- PVC rigid; polyvinylchloride
- PVC, flexible; polyvinylchloride
- Thermoplastic Elastomers, TPE
- PC, Polycarbonate
- PE, Polyethylene
- PUR, polyurethane

Typical properties	Value	Unit
Melting range	>49	°C
Ash	< 0.10	%
Volatile loss	< 0.50	%
Assay	>99	%
Molecular weight	531	

Songnox® 1077 LQ
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition:	Isotridecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate	
Physical form:	Liquid	
CAS Number:	847488-62-4	
Masterbatch / One Pack:	No	
Product description		
Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate. Used as primary antioxidant for organic polymers, including ABS, acrylics, PE, PU, PVC, and elastomers, such as BR, CR, EPEM, NBR and SBR. Provides very good long term heat stability. Exhibits a synergistic effect in combination with phosphates.		
Best suitable Polymer		
<ul style="list-style-type: none"> • Rubbers >> EPDM, Ethylene Propylene Diene Rubber • Rubbers >> CR, Chloroprene Rubber/ Chloroprene • Rubbers >> NBR, Acrylonitrile Butadiene Rubber • Thermoplastic Elastomers, TPE • Rubbers >> SBR, Styrene-Butadiene rubber • Rubbers >> BR, Butadiene Rubber, Polybutadiene • PE, Polyethylene • ABS/ SAN/ ASA, Acrylonitrile-Styrenic based • PUR, polyurethane • PVC, flexible, polyvinylchloride • PVC rigid; polyvinylchloride 		
Typical properties		
Ash	Value	Unit
Assay	< 0.10	%
Molecular weight	> 92	%
Viscosity @ 25°C	470	cP
Specific gravity @ 25°C	< 1200	
Refractive index @ 25°C	0.932 - 0.952	
	1.480 - 1.500	

Songnox® 1098
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Add to My Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: N,N-Hexamethylenebis (3,5-di-tert-butyl-4-hydroxyhydrocinnamamide)
 Physical form: Various
 CAS Number: 23128-74-7
 Masterbatch / One Pack: No

Product description:
 N,N-Hexamethylenebis (3,5-di-tert-butyl-4-hydroxyhydrocinnamamide). Used as an antioxidant for wire and cable application of PP, HDPE, LDPE and elastomers for primary insulation. Provides effective thermal stability and very good metal deactivation.

Best suitable Polymer
 • PP, Polypropylene
 • Thermoplastic Elastomers, TPE
 • PE, Polyethylene >> HDPE, High Density Polyethylene
 • PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Melting range	156 - 182	°C
Ash	< 0.10	%
Volatile loss	< 0.30	%
Assay	> 98	%
Molecular weight	637	

Songnox® 1135 LQ
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: Iso-octyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate
Physical form: Liquid
CAS Number: 125643-61-0
Masterbatch / One Pack: No

Product description:
 Iso-octyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate. Used as primary antioxidant that can be used in a wide range of organic polymers, such as ABS, PE, PVC, and rubbers such as BR, NBR and SBR. Provides very good long term stability. Exhibits a synergistic effect in combination with phosphites.

Best suitable Polymer

- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- Rubbers >> SBR, Styrene-butadiene rubber
- PVC, flexible; polyvinylchloride
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene
- PVC rigid; polyvinylchloride

Typical properties	Value	Unit
Ash	< 0.10	%
Assay	> 92	%
Molecular weight	399	
Viscosity @ 25°C	250 - 500	cps
Specific gravity @ 25°C	0.950 - 0.970	
Refractive index @ 25°C	1.486 - 1.503	

Songnox® 3114
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#)

[Search amongst 10,000+ Additives and Modifiers](#)

[Store in my Library](#) [Print](#)

Additive	Antioxidant	
Chemical composition:	Tris-(3,5-di-tert-butylhydroxybenzyl) isocyanurate	
Physical form:	Various	
CAS Number:	27876-62-6	
Masterbatch / One Pack:	No	
Product description		
Tris-(3,5-di-tert-butylhydroxybenzyl) isocyanurate. Used as primary antioxidant for organic polymers. Provides low volatility, good color stability and high extraction resistance. Exhibits a synergistic effect when used in combination with phosphite antioxidants.		
Best suitable Polymer		
• PP, Polypropylene		
Typical properties		
Molecular weight	Value	Unit
100	< 0.01	%
Melting point	784	
Volatile Limn	218 - 223	°C
Assay	< 0.20	%
Fo Content	> 98	%
	< 10	ppm

Songnox® 311B
R. T. Vanderbilt

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save in my Library](#) [Print](#)

Additive
Antioxidant

CAS Number:	31570-04-4 ; 27678-62-6
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description
Mixture of SONGNOX 1880 and SONGNOX 3114. Used as primary hindered phenolic antioxidant. Provides very good melt-flow and color protection during processing of polyolefins. Affords long term heat stability by protecting physical properties during storage and in the end use applications. Exhibits gas fade resistance in polyolefins and avoids the negative effects of discoloration.

Best suitable Polymer

- PP, Polypropylene
- PE, Polyethylene

Typical properties	Value	Unit
Volatile Loss	< 0.50	%
Color of solution 425nm	> 95	%
Color of solution 500nm	> 97	%

Songnox® 321B
R. T. Vanderbilt

Technical Assistance Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant

CAS Number: 31570-04-4 ; 27078-62-6
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description
 Mixture of SONGNOX 1680 and SONGNOX 3114. Used as primary hindered phenolic antioxidant. Provides very good melt-flow and color protection during processing of polyolefins. Affords long term heat stability by protecting physical properties during storage and in the end use applications. Exhibits gas fade resistance in polyolefins and avoids the negative effects of discoloration.

Best suitable Polymer
 - PP, Polypropylene
 - PE, Polyethylene

Typical properties	Value	Unit
Volatile Loss	< 0.50	%
Color of solution 425nm	> 95	%
Color of solution 500nm	> 97	%

Songnox® 4150
R. T. Vanderbilt

[Request For Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition: 4,4'-Thiobis (6-tert-butyl-m-cresol)
Physical form: Powder
CAS Number: 96-69-5
Masterbatch / One Pack: No

Product description
4,4'-Thiobis (6-tert-butyl-m-cresol). Used as an antioxidant in HDPE, LDPE for water and gas pipes and high-voltage cables. Offers high resistance to thermo-oxidative degradation. Provides very good compatibility with peroxides and shows good synergism with carbon black.

Best suitable Polymer

- PVC rigid; polyvinylchloride
- PS, Polystyrene
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PVC, flexible; polyvinylchloride
- PE, Polyethylene >> HDPE, High Density Polyethylene
- ABSI SAN ASA, Acrylonitrile-Styrene based
- PP, Polypropylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Ash	< 0.10	%
Molecular weight	358	
Melting point	158 - 164	°C
Volatile Loss	< 0.50	%
Assay	> 98	%

Songnox® DLTDP
R. T. Vanderbilt

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition:	Dilauryl thiodipropionate
Physical form:	Powder
CAS Number:	123-28-4
Masterbatch / One Pack:	No

Product description
Dilauryl thiodipropionate. Used as an antioxidant. Enhances aging and light stability.

Best suitable Polymer

- PE, Polyethylene
- PP, Polypropylene
- Thermoplastics, other >> HIPS, High Impact Polystyrene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PA, Polyamide
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Molecular weight	515	
Melting point	38 - 41	°C
Volatile Loss	< 0.50	%
Acid value	< 0.10	mgKOH/g
Ash	< 0.50	%

Songnox® DSTDP
R. T. Vanderbilt

Request For Information Technical Assistance: **Tech Direct** Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant

Chemical composition:	Distearyl thiodipropionate
Physical form:	Powder
CAS Number:	693-36-7
Masterbatch / One Pack:	No
Product description	
Distearyl thiodipropionate. Used as an antioxidant. Enhances aging and light stability.	
Best suitable Polymer	
<ul style="list-style-type: none"> • PP, Polypropylene • Thermoplastics, other >> HIPS, High Impact Polystyrene • PE, Polyethylene >> HDPE, High Density Polyethylene • ABS/ SAN/ ASA, Acrylonitrile-Styrene based • PA, Polyamide 	
Typical properties	
Molecular weight	683
Melting point	61.5 - 68.5 °C
Volatile Loss	< 0.50 %
Acid value	< 0.10 mgKOH/g
Ash	< 0.55 %

Vanox® 1030
R. T. Vanderbilt

[Request for Information](#) [Technical Assistance](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant

Chemical composition:	Polypropylene
Physical form:	Powder
Masterbatch / One Pack:	No

Product description

Very soluble in chloroform and toluene.
 Moderately soluble in acetone.
 Slightly soluble in ethyl alcohol, hexane and gasoline.
 Insoluble in water.
 Very effective synergistic antioxidant for filled and unfilled polypropylene.

Best suitable Polymer

- PP, Polypropylene

Typical properties	Value	Unit
Bulk density	40.5	kg/m ³
Density @ 25°C	1.04	Mg/m ³
Melting Point, initial	> 61	°C
Ash	< 0.25	%

Vanox® 1030A
R. T. Vanderbilt

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store In My Library Print

Additive
Antioxidant

Physical form: Powder
Masterbatch / One Pack: No

Product description
Very soluble in chloroform and toluene.
Moderately soluble in acetone.
Slightly soluble in ethyl alcohol, hexane and gasoline.
Insoluble in water.
Very effective synergistic antioxidant for filled and unfilled polypropylene.

Best suitable Polymer
• PP, Polypropylene

Typical properties	Value	Unit
Density @ 25°C	1.04	Mg/m ²

Vanox® 854
R. T. Vanderbilt

Request For Information Technical Assistance: [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers Store in my library Print

Additive
Antioxidant >> Blend

Physical form: Powder
Masterbatch / One Pack: No

Product description
Antioxidant blend.

Best suitable Polymer
• PE, Polyethylene

Typical properties	Value	Unit
Density @ 25°C	1.62	Mg/m³
Zinc (Zn) content	2.6 - 3	%

Vanox® GT
R. T. Vanderbilt

Request For Information Technical Assistance: [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant

Chemical composition: Tris-(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate
 Physical form: Powder
 Masterbatch / One Pack: No

Product description
 Very soluble in acetone, chloroform and dimethylformamide.
 Moderately soluble in toluene.
 Slightly soluble in methanol, hexane and petroleum ether.
 Insoluble in water.
 Polypropylene, polyethylene and polyurethane as well as other polymers requiring oxidation stability.

Best suitable Polymer
 - PP, Polypropylene
 - PUR, Polyurethane
 - PE, Polyethylene

Typical properties	Value	Unit
Melting Point, Initial	216	°C
Density @ 25°C	1	Mg/m ³

Ralox 3114
Raschig

 Request For Information Technical Assistance  Tech Direct  Search amongst 10,000+ Additives and Modifiers  Store in my Library  Print

Additive
Antioxidant >> Phenolic


Chemical composition: Tris-(3,5-di-*t*-butyl-4-hydroxybenzyl)-isocyanurate
CAS Number: 27676-62-6
Masterbatch / One Pack: No

Product description
Low volatility, good UV stability and non-discoloring properties.

Best suitable Polymer
• PP, Polypropylene

Ralox 530
Raschig

Technical Assistance 

Search amongst 10,000+ Additives and Modifiers  

Additive
Antioxidant >> Phenolic

Chemical composition: Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate
CAS Number: 1811-68-1
Masterbatch / One Pack: No

Product description
Non-staining sterically hindered phenolic antioxidant with low volatility due to the high molecular weight.

Best suitable Polymer
• PVC rigid, polyvinylchloride
• PP, Polypropylene
• PE, Polyethylene
• PS, Polystyrene

Ralox TMQ
Raschig

Request for Information Technical Assistance **Tech Direct** Search amongst 10,000+ Additives and Modifiers Store in Library Print

Additive
Antioxidant >> Amine

Chemical composition: 2,2,4-Trimethyl-1,2-dihydroquinoline, polymer
CAS Number: 26780-96-1
Masterbatch / One Pack: No

Product description
Used for the stabilisation of black elastomers based on SBR, NR, IR, BR, NBR and latexes.
Also used in PE and lubricants.

Best suitable Polymer

- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- Rubbers >> NR, Natural Rubber
- Rubbers >> SBR, Styrene-butadiene rubber
- PE, Polyethylene
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- Rubbers >> IR, Polysisoprene

Seenox 104S
Shipro Kasei Kaisha

Request For Information Technical Assistance: [Tech Direct](#) Search amongst 10,000+ Additives and Modifiers Store In My Library Print

Additive
Antioxidant >> Blend

Physical form:	Powder
CAS Number:	29598-76-3; 6683-19-8
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PUR, polyurethane
- PP, Polypropylene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PVC rigid, polyvinylchloride
- PE, Polyethylene Therephthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PC, Polycarbonate
- PE, Polyethylenes >> LDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Ast	< 0.1	%
Melting point	> 45	
Heat loss	< 0.5	%

Seenox 114BS
Shipro Kasei Kalsha

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant >> Blend

Physical form:	Powder
CAS Number:	29598-76-3; 95-69-5
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PUR, polyurethane
- PP, Polypropylene
- Rubbers >> SBR, Styrene-butadiene rubber
- PS, Polystyrene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Ash	< 0.1	%
Melting point	> 45	%
Heat Ins.	< 0.3	%

Seenox 1479S
Shipro Kasei Kalsha

Store in my Library Print

Technical Assistance **Tech Direct**

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Blend

Physical form:	Powder
CAS Number:	29598-75-3; 40601-78-1
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PUR, polyurethane
- PP, Polypropylene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PVC, Polyvinylchloride
- PBT, Polybutylene Therephthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PC, Polycarbonate
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Ash	< 0.1	%
Melting point	> 45	
Heat loss	< 0.5	%

Seenox 326M
Shipro Kasei Kaisha

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store In My Library Prod

Additive
Antioxidant >> Phenolic

Chemical composition:	1,3,5-trimethyl-2,4,6-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-benzene
Physical form:	Powder
CAS Number:	1709-70-2
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Rubbers >> NR, Natural Rubber
- PUR, polyurethane
- PBT, Polybutylene Therephthalate
- PE, Polyethylene
- ABS SAN ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene

Typical properties	Value	Unit
Molecular weight	775.2	
Melting point	244 - 249	
Heat less	< 0.5	%
Ash	< 0.1	%

Seenox 412S
Shipro Kasei Kalsha

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Save in my Library](#) [Print](#)

Additive
Antioxidant >> Thioester

Chemical composition:	pentaerythritol tetrakis-(3-dodecythiopropionate)
Physical form:	Powder
CAS Number:	29598-76-3
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Thermoplastics, other >> PCM, Polyacetal, Polyformaldehyde
- PUR, polyurethane
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PBT, Polybutylene Terephthalate
- PA, Polyamide
- ABS, SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Molecular weight	1182	
Melting point	49 - 52	
Heat loss	< 1	%
Ash	< 0.1	%

Seenox BCS
Shipro Kasei Kalsha

Search amongst 10,000+ Additives and Modifiers

Store in my Library Print

Additive
Antioxidant

Chemical composition: 4,4'-Bis(2-tert.-butyl-5-methylphenol)
 Physical form: Powder
 CAS Number: 96-89-5
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description

Best suitable Polymer

- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PU, Polyurethane
- PP, Polystyrene
- Rubbers >> SBR, Styrene-butadiene rubber
- PS, Polystyrene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- ABS SAN ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Molecular weight	358.5	
Melting point	185 - 184	°C
Heat loss	< 1	%
Ash	< 0.1	%

Seenox DL
Shipro Kasei Kaisha

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Antioxidant >> Thioester

Chemical composition:	dodecyl thiiodipropionate
Physical form:	Powder
CAS Number:	123-28-4
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PE, Polyethylene
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PBT, Polybutylene Terephthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Molecular weight	514.9	
Melting point	39 - 42	%
Heat loss	< 0.3	%
Ash	< 0.1	%

Seenox DM
Shipro Kasei Kaisha

Request For Information Technical Assistance Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Thioester

Chemical composition:	dilertadecyl thiodipropionate
Physical form:	Powder
CAS Number:	16545-54-3
Food contact approval:	Yes
Masterbatch / One Pack:	No

Product description

Best suitable Polymer

- PS, Polystyrene
- PMMA, Polymethylmethacrylate
- PET / PETG, Polyethylene Terephthalate / Polyethylene Therephthalate Glycol
- PP, Polypropylene
- Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde
- PUR, polyurethane
- PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene
- PE, Polyethylene Terephthalate
- PA, Polyamide
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PE, Polyethylene >> LDPE, Low Density Polyethylene
- PE, Polyethylene >> HDPE, High Density Polyethylene
- PC, Polycarbonate

Typical properties	Value	Unit
Molecular weight	571	
Melting point	48 - 54	%
Heat loss	< 0.3	%
Ash	< 0.1	%

Seenox DS
Shipro Kasei Kaisha

Technical Assistance [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Thioester

Chemical composition:	diiodadecyl thioldipropionate															
Physical form:	Powder															
CAS Number:	693-36-7															
Food contact approval:	Yes															
Masterbatch / One Pack:	No															
Product description																
Best suitable Polymer <ul style="list-style-type: none"> • PS, Polystyrene • PMMA, Polymethylmethacrylate • PET, Poly(1,4-Polyethylene Terephthalate) / Polyethylene Terephthalate Glycol • PP, Polypropylene • Thermoplastics, other >> POM, Polyacetal, Polyformaldehyde • PUR, polyurethane • PE, Polyethylene >> LLDPE, Linear Low Density Polyethylene • PBT, Polybutylene Terephthalate • PA, Polyamide • ABS and ASA, Acrylonitrile-Styrenic based • PE, Polyethylene >> LDPE, Low Density Polyethylene • PE, Polyethylene >> HDPE, High Density Polyethylene • PC, Polycarbonate 																
Typical properties <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th style="text-align: right;">Value</th> <th style="text-align: right;">Unit</th> </tr> </thead> <tbody> <tr> <td>Molecular weight</td> <td style="text-align: right;">683.2</td> <td></td> </tr> <tr> <td>Melting point</td> <td style="text-align: right;">61 - 64</td> <td>%</td> </tr> <tr> <td>Heat less</td> <td style="text-align: right;">< 0.3</td> <td>%</td> </tr> <tr> <td>Ash</td> <td style="text-align: right;">< 0.1</td> <td>%</td> </tr> </tbody> </table>			Value	Unit	Molecular weight	683.2		Melting point	61 - 64	%	Heat less	< 0.3	%	Ash	< 0.1	%
	Value	Unit														
Molecular weight	683.2															
Melting point	61 - 64	%														
Heat less	< 0.3	%														
Ash	< 0.1	%														

Songnox™ 1024
Songwon

[Request For Information](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Modifiers](#) [Store in my Library](#) [Print](#)

Additive
Metal deactivator
Antioxidant >> Phenolic

Chemical composition: t,2-Bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamoly) hydrazine
 Physical form: Various
 CAS Number: 32687-78-8

Product description
1,2-Bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamoly) hydrazine. Used as metal deactivator and antioxidant for wire and cable.

Best suitable Polymer

- Thermoplastic Elastomers, TPE
- PP, Polypropylene
- PE, Polyethylene
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber

Typical properties	Value	Unit
Melting point	231 - 232	°C
Abs	< 0.10	%
Volatile loss	< 0.50	%
Assay	> 98	%
Molecular weight	553	

SpecialChem Polymer Additives & Colors

Home Products Web Contact My SpecialChem Log-out

Songnox™ 1135 LQ
Songwon

Request for Information Technical Assistance Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant > Phenolic

Chemical composition: Iso-octyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate
Physical form: Liquid
CAS Number: 125643-51-0

Product description: Isobutidoxyl-3-(2,5-di-tert-butyl-4-hydroxyphenyl) propionate. Used as primary antioxidant for organic polymers. Provides very good long term heat stability. Exhibits a synergistic effect.

Best suitable Polymer

- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- Rubbers >> BR, Butadiene Rubber, Polybutadiene
- PVC flexible, polyvinylchloride
- Rubbers >> SBR, Styrene-butadiene rubber
- PE, Polyethylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrene based
- PVC rigid, polyvinylchloride
- PS, Polystyrene

Typical properties

	Value	Unit
Asn	<0.10	%
Ascar	~98	%
Molecular weight	399	
Viscosity @ 25°C	300 - 500	cP
Specific gravity @ 25°C	0.950 - 0.960	
Rotational viscosity @ 25°C	1420 - 1490	

Disclaimer
All technical information on this site is given for information purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable, however, the data is provided without liability whatever of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenue, loss of profits, loss of business or income, consequential, special or punitive damages, even if advised of the possibility of such losses. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem, S. A.

Specialty Polymer Additives & Compounds

Search Bookmarks SpecialityPolymers.com Free newsletter subscription > Eldar Zeynalov RSS feed

Songnox™ 2246
Songwon

Search among 10,000+ Additives and Modifiers

Additive
Polymerization inhibitor
Antioxidant >> Phenolic

Chemical composition: 2,2-Methylene-bis(4-methyl-6-tert-butylphenol)
Physical Form: Powder
CAS Number: 139-67-1

Product description
Octabenzo[4,5-d;4',5'-d']-4,4'-methylene-propene oxide, used as primary antioxidant for organic polymers. Provides long term heat stability. Protects physical properties during storage and use of aromatic hydrocarbons, a synergistic effect.

Best suitable Polymer
 - Thermoplastics, other >> PVC, Polyacrylate, Polyvinylidene dichloride
 - PVC, styrene
 - PE, Polyethylene
 - ABS, SAN, ASA, Acrylonitrile-Styrene copolymer
 - LLDPE, Linear Low Density Polyethylene

Typical properties:	Value	Unit
Melting point	135–142	°C
MPN	> 2.0	g
Stability	> 1.00	%
Odor/taste	NA	

Disclaimer
All products are sold on the basis of a general product specification. Before ordering any product, our distributor and/or supplier must be consulted for detailed information on the specific product. The distributor and/or supplier reserves the right to make changes in the product specification at any time for reasons of technological development, market conditions or otherwise. Products are sold "as is" without express or implied warranties. No liability will be accepted for any damage resulting from the use of any product. By using our catalogue, products mentioned and their applications it is understood that the user has read and agreed to these terms and conditions. © 2007 Speciality Polymers Inc. All rights reserved.

SpecialChem.com Polymer Additives & Colors

Home About Us Products Newsletters Contact Us Log In

Bookmark SpecialChemProducts Free newsletter subscription > Elmar Zeynalov

Songnox™ 311B
Songwon

Technical Assistance Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic
Antioxidant >> Phenolic

Physical form: Various
GHS Number: 31573-34-4 ; 21670-62-8

Product description:
Blend of hindered phenolic antioxidant and secondary phosphite antioxidant. Provides very good melt flow and color protection. Offers long term heat stability.

Best suitable Polymer:
- PE, Polypropylene

Properties	Value	Unit
Melt flow rate, g/min	<45	g
Color, °E	<2.50	

DISCLAIMER:
We believe our information to be reliable. For information regarding other offerings, please contact your product supplier. We do not warrant the accuracy or completeness of the information contained herein. Please do not rely on this information for your specific needs. It is your responsibility to determine whether the information is appropriate for your specific application. We are not responsible for any errors or omissions in this document. Please contact your product supplier for a copy of the most recent and complete information to determine your specific requirements.

Specialty Polymer Additives & Compounds

Home Resources Technical Support About Us Log out

Search [] [Brenntag Specialty Polymers](#) [E-mail newsletter subscription](#) [Eldar Zeynalov](#)

Songnox™ 321B
Songwon

[Search for another](#) [Tech Direct](#) [Search amongst 10,000+ Additives and Monomers](#)

Additive
Antioxidant >> Phosphite
Antioxidant >> Phenolic

Physical form: VERSO, S
CAS Number: 31570-94-4, 22666-62-8

Product description:
Blend of primary phenolic antioxidant and secondary phosphite antioxidant. Provides very good melt flow and color protection. Offers long term thermal stability.

Base available Polymer:
• PP: Polypropylene
• PE: Polyethylene

Typical properties	Value	Unit
Melting point	147 - 170	°C
Viscosity	> 0.5	cP

Disclaimer:
The data information on this site is given for reference purposes only. It is not to be used, relied upon or construed as a guarantee, warranty, or specification. In order to ensure complete satisfaction and to determine the suitability of any product for your specific needs, we recommend that you contact our technical support department. We do not warrant that the products described herein will be suitable for all applications mentioned. Products mentioned are fed under a license from another company. The user assumes full responsibility for their application. Eldar Zeynalov does not assume any liability for damages resulting from the use of any products mentioned.

© 2010 Songwon S. C.

SpecialChem Polymer

Search

Bookmarked SpecialChem Polymer Free newsletter subscriber Eldar Zeynalov Log out

Songnox™ 4120
Songwon

Technical Assessment Test Version Search amongst 10,000+ Additives and Modifiers Search by Name Search by CAS No. Search by EINECS No. Search by IUPAC No. Search by Supplier

Additive
Antioxidant >> Triolester

Chemical structure
Physical form: Powder
CAS Number: 29028-75-3

Product description
Diaminotriakis(2-benzothiophenyl) ester, also known as secondary antioxidant for organic polymers. Offers low cost and high performance. Provides high heat resistance and low leaching properties.

Best suitable Polymer
 PS, Polycarbonate
 Thermotropic Liquid Crystalline Polymers
 PE, Polyethylene
 ABS/PCX/ASX, Acrylonitrile-Styrene-based
 PC, Polycarbonate
 PV, Polyvinylidene fluoride

Typical properties	Value	Unit
Water point	0.03	C
ASTM D-2857	0.52	%
Wet tensile	0.52	%
ASTM D-2857	5.66	%

Disclaimer:
All products mentioned in this document are for reference purposes only. Please contact our sales office for detailed product information or to place an order. We make no warranty, express or implied, concerning the suitability of the products mentioned herein for any particular purpose. All products mentioned herein are subject to change without notice. It is the responsibility of the user to determine the suitability of the products for their intended use. We do not accept responsibility for any damage resulting from the use of any of our products. Please consult the Safety Data Sheet (SDS) for each product for detailed information on handling and storage conditions for the product(s) mentioned.

© 2014 SpecialChem S.A.

SpecialChem Polymer Additives & Colors

Search (0) © 2009 SpecialChem Polymer Additives & Colors Free newsletter subscription Eldar Zeynaliov Log out

Songnox™ 4150
Songwon

Search amongst 10,000+ Additives and Modifiers Search in e-Library

Additive
Antioxidant > Phenolic

Chemical composition: 4,4'-bis(4-tert-butylphenol)-diesel
Physical form: Powder
CAS Number: 6270-8

Product description:
4,4'-Bis(4-tert-butylphenol). Used as primary and/or secondary antioxidant for organic polymers. Offers high resistance to thermo oxidation degradation and very good compatibility.

Best suitable Polymer:

- PP/PE/PM, Ethylene Propylene Diene Rubber
- PVC rigid polyvinylchloride
- Thermoplastic Elastomer, TFE
- PVC flexible polyvinylchloride
- LDPE/LDPE/LLDPE/HDPE/LLDPE/HDPE/HDPE
- ABS/PS/ASA, Acrylonitrile Styrene based
- PE Polyethylene or LDPE, Low Density Polyethylene
- POM polyacetal
- PS polystyrene

Typical properties	Value	Unit
Diss. point	> 310°C	°C
ASTM D2857	> 0.3	g
ASTM D2857	> 0.32	g
ASTM D2857	> 98	g

Disclaimer:
All technical information on this site is given in good faith and is believed to be accurate. However, no guarantee is given for the correctness of such information. It is the responsibility of the customer to verify the suitability of the product(s) described on this website for their intended use. SpecialChem does not accept liability for any damage, loss or expense arising from any use of the products described on this website. All products have been carefully compounded, tested or otherwise tested, and found to be safe for their intended use. Products may contain minor amounts of residual monomers and/or by-products which are inherent to the production of such products. Products may also contain minor amounts of impurities believed to not exceed a food contact safety level. No claim is made for any specific physical or chemical characteristics of the products.

Special Polymer Additives & Color

Home Products Additives Color News Events About Us Contact Us Log In

Search: Bookmarked Products Free newsletter subscription > Eldar Zeynalov KC Log in

Songnox™ DLTDP
Songwon

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant > Thinner

Chemical composition: Dibutyl Phthalopropone
 Physical form: Powder
 CAS Number: 123-25-4

Product description:
 Dibutyl Phthalopropone. Used as secondary H-Block ester antioxidant for styrene polymers. Curtails aging and hydro stability.

Best suited Polymer:
 • Impact-modified ABS & HIPS, High Impact Polystyrene
 • PE, Polypropylene
 • PVC, Polyvinyl Chloride
 • ABS/SAN/ASA, Acrylonitrile Styrene based
 • PA, Polyamide

Typical properties:

	Value	Unit
Aromatic	<0.2	mg/g
Molecular weight	5-7	-
Dew point	<40	°C
Viscosity	<0.05	cps
Water solubility	<1.0	%
UV-shield	>10	-

Disclaimer:
 As an aid, information is furnished free of charge to interested parties only, before working with KCI products, user shall make his/her own evaluation to determine if such products are suitable for purposes of intended use. One cannot guarantee the safety of any product. User agrees that he/she will assume full responsibility for any damage resulting from his/her use of any product. The user shall not hold KCI liable for any damages resulting from the use of any product. Technical assistance or local contact person are subject to their knowledge and experience. Technical data or other information contained in this catalog are general in nature. These data are not to be construed as recommendations for specific applications. Other conditions than those indicated in this catalog are often critical.

SpecialChem4Polymers | Polymer Additives & Colors

Home Search Bookmarks Technical My Specifications Logout

Songnox™ DSTDP
Songwon

Technical Assistance: [Request for Information](#) [Tech Direct](#)

Search amongst 10,000+ Additives and Modifiers

[Store in my library](#) [Print](#)

Additive
[Antioxidant >> Thioester](#)

Chemical composition: Diisobutyl thiodipropionate
 Physical form: Powder
 CAS Number: 693-36-7

Product description:
 Diisobutyl thiodipropionate. Used as secondary antioxidant for organic polymers. Enhances aging and light stability.

Best suitable Polymer
 • Thermoplastics, other >> HIPS, High Impact Polystyrene
 • ABS
 • Polypropylene
 • Polyethylene
 • ABS/SAN/ASA, Acrylonitrile-Styrenic based
 • PA, Polyamide

Typical properties	Value	Unit
Acid value	< 0.10	mgKOH/g
Melting point	60	
Dens.	< 0.6	g/cm ³
Melting point	63.5 - 68.5	°C
Ash	< 0.05	%
Water content	< 0.50	%
Assay	> 99	%

Disclaimer
 All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information contained herein is intended to be valuable, however, the data is given without any warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory for any damages, whether direct, indirect, special, incidental, or consequential, arising out of the use of these products, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
 © 2002 SpecialChem S. A.

Special Polymer Additives & Colours

Home | Contact Us | About Us | Special Colours | Colours | My Special Client | +31 22 460 00 00

Bookmark SpecialColoursSystems | Free newsletter subscription | Eldar Zeynalov | Search

Songnox™ 1035
Songwon

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic

Chemical composition: Bisphenol A-[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionato] Phenol
Name: Songnox™ 1035
CAS Number: 41454-26-9

Product description: Thick greyish oil (3,5-di-tert-butyl-4-hydroxyphenylpropionate). Used as antioxidant for organic polymers (e.g. PVC and cable resins). Provides both primary and secondary antioxidant protection. Exhibits low volatility, 20ms long-term heat stability.

Best suitable Polymer	Value	(unit)
> 90% Polyethylene	≥ 0.0	%
Typical properties		
Melting point	≥ 110	°C
Viscosity	< 0.0	mm²/s
Dense	≥ 0.9	g/cm³
Water solubility	≤ 0.0	g/g

Disclaimer: All products mentioned on this site are for information purposes only. Before using any product, user shall first consult the Material Safety Data Sheet (MSDS) or other appropriate documents representing a detailed description of the product, its potential hazards or risks, and/or instructions for safe handling and disposal. The use of the products described herein is subject to prior consultation and consent granted by the manufacturer or supplier. Please note that the information contained herein is not intended for applications and end-users.

Search	<input type="text" value="50"/>	<input checked="" type="checkbox"/> Both main, Basic & Advanced	<input type="checkbox"/> True newsletter subscription	<input type="checkbox"/> E-mail Zeynab	<input type="checkbox"/> E-mail Corporate	<input type="checkbox"/> E-mail Technical															
Home																					
Lowinox 1790 Chemtura																					
Search amongst 10,000+ Additives and Modifiers																					
<input style="width: 100px; height: 25px; border: 1px solid black; border-radius: 5px; padding: 5px; margin-right: 10px;" type="button" value="Search"/> <input style="width: 100px; height: 25px; border: 1px solid black; border-radius: 5px; padding: 5px;" type="button" value="Print"/> <input style="width: 100px; height: 25px; border: 1px solid black; border-radius: 5px; padding: 5px;" type="button" value="Email"/>																					
Information Tech Direct																					
Additive Antioxidant > Phenolic																					
<p>Chemical composition: 1,3,5-tris(4-tert-butyl-5-hydroxy-2,6-dimethylbenzyl)-1,3,5-triaxial-2,4,6-(1-⁹H,3H)-</p> <p>Product form: Solid</p> <p>CGN Number: 46305-76-1</p> <p>User control approval: Yes</p> <p>Waterbatch / Grie Pack: No</p>																					
<p>Product description: High performance, sterically hindered phenolic antioxidant. Offers very good gas fading resistance. Provides high molecular weight and high oxidation resistance.</p>																					
<p>Best suitable Polymer:</p> <ul style="list-style-type: none"> • PU, Thermoplastic Polyurethane • PP, Polypropylene • PA, Polyamide • Thermoplastics other 																					
<p>Typical properties:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 30%;"></th> <th style="width: 30%; text-align: center;">Value</th> <th style="width: 30%; text-align: center;">Unit</th> </tr> </thead> <tbody> <tr> <td>Stability</td> <td style="text-align: center;">400</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Viscosity</td> <td style="text-align: center;">100</td> <td style="text-align: center;">cps</td> </tr> <tr> <td>Melting point</td> <td style="text-align: center;">159 - 162</td> <td style="text-align: center;">°C</td> </tr> <tr> <td>Specific gravity @ 20°C</td> <td style="text-align: center;">1.12</td> <td style="text-align: center;">g/cm³</td> </tr> </tbody> </table>								Value	Unit	Stability	400	°C	Viscosity	100	cps	Melting point	159 - 162	°C	Specific gravity @ 20°C	1.12	g/cm ³
	Value	Unit																			
Stability	400	°C																			
Viscosity	100	cps																			
Melting point	159 - 162	°C																			
Specific gravity @ 20°C	1.12	g/cm ³																			
<p>Information: Chemtura's information on this site is given for informational purposes only. Before using any product, user must conduct its own research to determine the suitability of the product for its intended use. User must also make its own determination as to whether its use of the product is in accordance with current applicable laws, rules, codes and regulations. Chemtura's products are sold "AS IS" and "WHERE AS IS". Chemtura makes no representations or warranties, express or implied, about its products, including without limitation, merchantability, fitness for a particular purpose, title, non-infringement of third party rights, or the results to be obtained from their use. Chemtura's products are not designed for use in food, pharmaceutical, medical devices, or other applications where safety, accuracy, and control are essential for a given application or a given industry. Chemtura's products are not designed for use in food, pharmaceutical, medical devices, or other applications where safety, accuracy, and control are essential for a given application or a given industry.</p>																					

SpecialChem Polymer Additives & Others

Home Bookmarks TechDirect My SpecialChem Log-out

Lowinox CA22
Chemtura

Search Go Bookmarks SpecialChemPolymers Free newsletter subscription >> Eldar Zeynalov Log-out

Request for Information Tech Direct Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Chemical composition: 1,1,3-tris(2'-methyl-4'-hydroxy-5'-t-butylphenyl)butane
 Physical form: Solid
 CAS Number: 1643-03-4
 Masterbatch / One Pack: No

Product description
 High performance hindered phenol antioxidant. Provides very good extraction resistance and color performance.

Best suitable Polymer
 • PP, Polypropylene
 • PVC, flexible polyvinylchloride
 • PE, Polyethylene >> HDPE, High Density Polyethylene
 • PE, Polyethylene >> LDPE, Low Density Polyethylene

Typical properties	Value	Unit
Molecular weight	545	%
Melting range	182 - 184	
Absolute gravity (at 25°C)	1.01	g/cm³
Frac. point	107	°C

Disclaimer: All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information on this website is believed to be reliable; however, the data is provided without liability whatsoever of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full details on the scope of food approvals and for extension to other applications and other countries.

© 2009 SpecialChem S.A.

SpecialChem Polymer Additives & Colors

Anox 1315 Chemtura

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Phenolic

Chemical composition: 3,5-Bis(1,1-dimethylethyl)-4-hydroxy-benzenepropionic acid

Physical form: Liquid

CAS number: 111603-90-0

Food contact approval: Yes

Markets: Consumer

Product description: 3,5-Bis(1,1-dimethyl-1-phenylmethyl)-4-hydroxy-benzenepropionic acid

Most suitable Polymer:

- Rubber >> NBR, Acrylonitrile Butadiene Rubber
- Rubber >> IR, Isobutylene Isoprene Copolymer
- PVC, Polyvinyl chloride
- PU, Polyurethane
- ABS and ASA, Acrylonitrile-Styrene-Iso
- PET, Polyethylene terephthalate
- PVC, Polyvinyl chloride

Typical properties:

	Value	Unit
Specific Gravity	1.04	kg/l
Viscosity	1.9	cP
Color	274	U
Substance	213	mg/m ²
Dissolve in DMF	200	mL/g

© 2008 SpecialChem. All rights reserved. No part of this document may be reproduced without permission. Before using any product, please refer to its Safety Data Sheet for detailed information. The use of this website does not constitute an endorsement of any product. SpecialChem makes no claims, express or implied, regarding the quality and/or safety of any products mentioned herein. Any liability arising from the use of any products mentioned herein, or any claims based thereon, shall be limited to the amount paid for such products. SpecialChem reserves the right to discontinue any product at any time. Please contact SpecialChem for further information.

SpecialChem Polymer Additives & Modifiers

Search [] Home Search Products My SpecialChem Logout

Search amongst 10,000+ Additives and Modifiers

Westco 1076
Western Reserve Chemical

Request for Information Tech Support Free newsletter subscriber >> Eldar Zeynalyov

Additive Antioxidant

Chemical composition: Octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate
Product form: Powder
CAS Number: 2392-78-3
Manufacture/Distributor: Ro

Product description: Octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate. This substance has the following general characteristics:

Best suitable Polymer:
-PS, Polystyrene
-PE, Polyethylene

Typical properties:

	Value	Unit
Tg (°C)	>100	°C
ASTM D2857	>0.1	g
ASTM D2857	>0.5	g
ASTM D2857	>0.9	g

Disclaimer: All technical information contained in this document is based on available data at the time of publication. It is not to be taken as a guarantee of product performance or quality. It is the responsibility of the user to determine the suitability of the product for his/her specific application. The user must also take into account all applicable laws and regulations relating to the use of this product. No liability is accepted for any damage resulting from the use of this product. No liability is accepted for any damage resulting from the use of this product. No liability is accepted for any damage resulting from the use of this product.

© 2001 SpecialChem Inc. All rights reserved.

Specialty Polymer

Search: Bookmarks [Bookmarks](#) [Favorites](#) [Logout](#)

Westco 1010
Western Reserve Chemical

Request for quote

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant

Chemical composition: Tetraakis [methylbenzyl] (3,5-di-tert-butyl-4-hydroxyphenyl) methane
 Physical form: Powder
 CAS Number: 6662-19-8
 Molecular Weight: 500
 Molecular Weight / One Pack: 500

Product description:
 Versatile antioxidant. Offers very good processing stability and long term heat aging characteristics.

Best suitable Polymer:
 • PP: Polypropylene
 • PE: Polyethylene

Typical properties:	Value:	Unit:
Color (HIPS)	<10	WT%
Molecular Wt	>90	WT%
TG	>0.1	WT%
Viscosity	>0.5	WT%
Flame Retardancy	>10	WT%

Disclaimer:
 Technical information contained herein is given to inform the customer of the product. User shall consult a technical manual or contact the supplier for detailed information on the safe use of the product. However, reliable experience has led us to believe that the product will be safe for its intended use. We do not warrant that the product will be safe for any other use. It is the responsibility of the user to determine the suitability of the product for his/her specific application. The user agrees to hold the supplier harmless from any claims arising from the use of the product.

-2009 Specimen 2-A

SpecialChem Polymer Additives & Dyes

Home

Search Bookmarks SpecialChemPolymers Free newsletter subscription >> Eldar Zeynalov Logout

Ekaland NDBC Coated
Sovereign Chemical

Request for Information Tech Direct Search amongst 10,000+ Additives and Modifiers Save in my Library Print

Additive
Antioxidant
Antioxidant
Light Stabilizer / UV Absorber >> Nickel organic

Chemical composition: Nickel Dibutylthiocarbamate.
Physical form: Powder
Masterbatch / One Pack: No

Product description
Oil powder.
Staining
Antioxidant for Hypalon (is a registered trademark of Dupont).

Best suitable Polymer

- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- PP Polypropylene
- PE Polyethylene

Disclaimer
All technical information on this site is given for information purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information on this website is believed to be reliable; however, the data is provided without liability regardless of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for information on the exact nature of food approval and its extension to other applications and other countries.

© 2005 SpecialChem S. A.

SpecialChem Polymer Additives & Compounds

Home Search Bookmarks Newsletter subscription Logout

Mixland NDBC 75 GA F200
Sovereign Chemical

Search amongst 10,000+ Additives and Modifiers Add to my library Print

Additive
Antioxidant
Antioxidant >> Thioester
Light Stabilizer / UV Absorber >> Nickel organic

Chemical composition:
Masterbatch / One Pack
Nickel dibutylthiocarbamate
No.

Product description

Best suitable Polymer

- Rubbers >> SBR, Styrene-butadiene rubber
- Rubbers >> NBR, Acrylonitrile-butadiene Rubber
- PE, Polyethylene

Disclaimer:
All technical information on this site is given for informative purposes only. Before dealing with any product, user shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable; however, the data is provided "as-is" and implies no warranty of any kind. Sovereign shall not be liable or obligated under any contract, including, either implied or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S.A.

SpecialChem Polymer

Search [] Bookmarked Products Free newsletter subscription > Elder Zeynaliw Home Products Suppliers News Events My SpecialChem

Carabat® DLTDPA
Struktur

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant > Thioester

Chemical composition: T-diester
 Physical form: + alkoⁿ
 Food contact approved: Yes
 Masterbatch / One Pack: No

Prominent properties:
 Thioester stabilizer is particularly effective as a long term heat aging stabilizer when used in conjunction with primary antioxidants.
 Non-yellowing stabilizer suitable for use in food thermoplastics.

Best suitable Polymer:
 - PP, Polypropylene
 - PE, Polyethylene >> HDPE, High Density Polyethylene
 - ABS/PS/PC/ASA, Acrylonitrile-Styrene blends

Typical properties	Value	Link
Anti Oxidant	26	
Molecular Weight	2.4	
Viscosity (mPa s)	41	
Stability @ 230°C/100h	2460	
Stability @ 230°C/100h	35	#1254
Stability @ 230°C/100h	35	#1255
Stability @ 230°C/100h	52	#1256

Disclaimer:
 All technical information on this site is given for informative purposes only. Information will not be implied, direct or implied, to constitute product specifications. It is made available solely for the purpose of helping you to decide whether to purchase the products. In such event, it is your responsibility to make your own evaluations and conclusions before ordering and installing the products. SpecialChem shall not be liable under any circumstances for any damage resulting from the use of its products, even where such damage may have been caused by the negligence of SpecialChem or its employees. It is your responsibility to determine whether the products are suitable for your specific application. If you have any questions concerning the use of our products, please contact us at 1-800-334-5555 or email us at sales@specialchem.com.

Specialty Polymer Additives & Compounds

Home Resources TestMaster My Product Center Log Out

Carstab® DSTDP
Struktur

Search amongst 10,000+ Additives and Modifiers

Additive
Antioxidant >> Thibester

Chemical composition: Triester
Physical form: Flakes
Food-related opinion: Yes
Masterbatch / One Pack: No

Product description:
Thiobester is a triester that is particularly effective as a g-twin heating stabilizer when used in conjunction with primary antioxidants.
Non-toxic stabilizer and antimicrobial and corona toxicity.

Best suitable Polymer:
 - PP Polypropylene
 - PE Polyethylene >> -DPE, High Density Polyethylene
 - ABS SAN ASA, Acrylonitrile-Styrene-Liquid

	Value	Unit
Arch Hardness	592	
Melting Point	125	°C
Density (20°C)	1.066	
Softening Point (20°C)	200	°C

Disclaimer:
All information on this page is subject to alteration, revision or deletion. All communication with our products, including general product information or specific technical data, does not constitute a warranty or guarantee. However, the data is intended to provide key information that can be used in design studies, research, R&D, feasibility studies, and other applications. It is the responsibility of the user to verify the suitability of our products for their specific applications. Technical support is available through our website or by contacting our customer service department. Please contact our application engineers for further information on the exact nature of our products and assistance in their applications. Other commercial applications are not covered by this document.

SpecialChem Polymer Additives & Colors

Search Bookmarks SpecialChemPolymers Free newsletter subscription >> Elder Zeynalov NO Log-out

Anox 29 Chemtura

Technical Assistance Tech Direct

Search amongst 10,000+ Additives and Modifiers Store in my Library Print

Additive
Antioxidant >> Phenolic

Chemical composition: 2,2'-ethyldenebis(4,6-di-t-butylphenol)
Physical form: Solid
CAS Number: 36958-30-6
Masterbatch / One Pack: No

Product description
Highly effective, sterically hindered bisphenol antioxidant.

Best suitable Polymer

- PVC rigid, polyvinylchloride
- Rubbers >> EPDM, Ethylene Propylene Diene Rubber
- PP, Polypropylene
- PA, Polyamide
- PS, Polystyrene
- PUR, polyurethane

Typical properties	Value	Unit
Molecular weight	436	
Melting range	161 - 164	°C
Bulk density	0.98	g/ml
Specific gravity @ 20°C	1.01	g/ml
Frost point	> 193	°C

Disclaimer
All technical information on this site is given for information purposes only. Before working with any product, user must consult product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or entitled under any contract, negligence, strict liability or other legal or equitable theory to any party for any amounts representing loss of revenue, loss of profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for the information on the exact nature of food approval and its extension to other applications and other countries.
© 2009 SpecialChem S.A.

Anox 70
Chemtura

Search amongst 10,000+ Additives and Modifiers

Typical properties	Value	Unit
Specific gravity @ 25°C	1.01	g/cm³
Viscosity range	53 - 78	cP
Flash point	279	°C
Bulk density	0.73	g/cm³
Molecular weight	642	

Disclaimer:
All technical information on this site is given for informative purposes only. Before working with any product, user shall contact product manufacturer in order to receive complete information about the product. Information on this site is believed to be reliable; however, the user of products at their own risk. No implied warranties of any kind. Suppliers shall not be liable or engaged under any contract, negligence, strict liability or other legal or equitable theories for any damages including loss of revenue, loss of profits, loss of business or market, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact official supplier for full information on the exact nature of food approvals and its extension to other applications and other countries.

© 2008 SpecialChem S.A.

Anox® BB 011
Chemitura

Search amongst 10,000+ Additives and Modifiers

Product Information

Product Name: Anox® BB 011

Supplier: Chemitura

Category: Additive > Blend

Properties:

Color:	White
Odor:	None
Flammability:	Non-combustible
Reactivity:	Inert
Corrosivity:	None
Storage:	Keep away from heat and direct sunlight.
Handling:	Handle with care to avoid skin contact.
Disposal:	Do not contaminate waterways or landfills.

Product description:

Anoxic flame retardant blend

Best suitable Polymer:

- PE: Polyethylene >> LDPE, Low Density Polyethylene
- PE: Polyethylene >> LDPE, Linear Low Density Polyethylene
- PP: Polypropylene
- ABS & PN: ABS, Acrylonitrile Styrene based
- PC: Polycarbonate
- PE: Polyethylene >> HDPE, High Density Polyethylene

General information:

All products mentioned in this SDS is subject to alternative designations with similar safety and/or health hazard properties. Technical or scientific names, commercial product names, trademarks, and/or registered trademarks are used to describe products. Specific names, formulas, or trade names, which may be used, are not intended to be all-inclusive, nor do they imply that they are the only safe or effective products for any purpose. No product mentioned in this SDS is recommended for any use. It is the responsibility of the user to determine the suitability of any product for any particular application. No legal liability is assumed for any damage resulting from the use of any product mentioned in this SDS. The user must assume full responsibility for any such damage.

Special Polymer Additives & Compounds

Home Resources Technical Services Newsletters Special Events Products E-mail newsletter subscription > Eldar Zeynalov

Anoxid BB 021
Chemtura

Search amongst 10,000+ Additives and Monomers

Additives Antioxidant >> Blend

Chemical composition: Phenolic/Phosphite Blend
Physical form: Powder
CAS Number: 6533-19-2; 81870-04-4
Food contact approval: Yes
Manufacturers/Units Price: N/A

Product description: Phenolic/Phosphite Blend. Provides very good resistance to extraction.

Compatible Polymer: - PE Polyethylene >> LLDPE, Linear Low Density Polyethylene
- Thermoplastic, other
- PP Polypropylene
- PE Polyethylene >> LDPE, Low Density Polyethylene
- ABS/SAN/ASA, Acrylonitrile Styrene based
- PC Polycarbonate
- PEI Polyimide >> HDPE, High Density Polyethylene

Disclaimer: All technical information on the use of products for industrial purposes can, when requested, be provided, upon shall except product manufacturers. Under no circumstances can the products contained in the website be held to be reliable, accurate, or up-to-date. It is recommended that potential users consult with a technical specialist and/or the manufacturer prior to use. The information contained in this website is not intended to supersede the manufacturer's instructions for use. The manufacturer's instructions for use should always be consulted before use. No reference is made to a specific application or process. These materials are not intended for use in food or pharmaceutical applications.

Anox® BB 140
Chemtura

Search amongst 10,000+ Additives and Modifiers

GHS number: 2022-79-0; 31670-04-4
Food contact: No
Microbiocides: One Product
Product description:
Fatty soya oil additive. Used in food packaging. Provides very good stabilization against thermooxidative degradation during long term aging.

Best suitable Polymer:
• Thermoplastic: other
• PE Polyethylene >> LDPE Linear Low Density Polyethylene
• PP Polypropylene
• TPU Thermoplastic Polyurethane
• PVC Polyvinyl chloride
• ABS Acrylonitrile Butadiene Styrene
• LDPE Polyethylene >> LDPE Low Density Polyethylene
• PE Polyethylene >> HDPE High Density Polyethylene



SpecialChem Polymer Additives & Chemicals

Search Go

Resources Products My SpecialChem Log Out

Anoxox® BB 2777
Chemtura

Search amongst 10,000+ Additives and Modifiers

Request a quote Technical Assistance Term Vary

Additive
Antioxidant >> Blend

GHS Number: B32/BH3;B15/BH4;C
Food contact approval: Yes
Manufacture / Distributor: No

Product description:
Inert synergistic blend. Used in hot processing. Provides very good stabilization against thermooxidative degradation during long term aging.

Other suitable Polymer:

- PE Polyethylene >> LDPE Linear Low Density Polyethylene
- T-polymer plasticizers
- PP Polypropylene
- PE Polyethylene >> LDPE Linear Low Density Polyethylene's
- ABS (SAN/ASA) Acrylonitrile Styrene based
- PC Polycarbonate
- PEI Polyimide >> IMID High Thermal Polyimide

Disclaimer: SpecialChem makes no claims or warranties as to the suitability of any of the products listed for the specific applications mentioned. It is the customer's responsibility to determine whether the product is suitable for their specific application. The products described in this document are trademarks of Chemtura Corporation and/or its affiliates. Other products may be trademarks of other companies. Chemtura and its affiliates do not warrant that they are the original or sole right holders to any part of the information representing any of the products, processes, or technologies described in this document. Products described in this document are sold subject to the terms and conditions of sale set forth in the applicable sales contract. Please refer to the applicable sales contract for a complete description of the rights and obligations of both parties.

© 2006 Chemtura Corp. All rights reserved.



Special Polymer Additives & Compounds

Home Search Bookmarks Social ChemDirect Free newsletter subscription >> Elder Zeynalov Logon

Alkanox® P-27
Chemtura

Request for Invoicing Tech Direct Search amongst 10,000+ Additives and Modifiers Download Library Print

Additive
Antioxidant >> Phosphite

Chemical composition:
Physical form: Powder
CAS Number: 25741-55-2; EINECS: 288-968-8
Item number: internal: Vca
Masterbatch / One Pack: No

Product description:
High performance, high molecular weight organo phosphite. Provides very good color stabilization.

Best suitable Polymer:
 • PVC and polyvinyl chloride
 • PE, Polyethylene >> LDPE, Linear Low Density Polyethylene
 • LDPE
 • Thermoplastic elastomers
 • PC, Polycarbonate
 • ABS/ASA/ASR, Acrylonitrile-Styrene-based
 • PE, Polyethylene >> LDPE, Low-Density Polyethylene
 • PE, Polyethylene >> HDPE, High-Density Polyethylene

Typical properties	Value	Unit
Molar mass	674	
Viscosity	400 - 750	cP
Tg (T _m)	155	°C
Softening point (T _s)	177	°C

Disclaimer:
All technical information is based on available knowledge at the time of publication. Actual product performance may vary depending on application conditions. To ensure acceptable results, it is recommended to test the product under actual conditions before use. Chemtura reserves the right to change product specifications at any time. Since some of the products described herein may be used in the manufacture of articles subject to regulation by governmental agencies, users of such products are responsible for determining the compatibility of such products with respect to such regulations. All information is provided "as is" without warranty or guarantee. Chemtura is not liable for any damages resulting from the use of any information contained herein.

SpecialChem Polymer Additives & Compounds

Search | Bookmarks SpecialChemPolymers | Free newsletter subscription >> Eldar Zeynalov | Log-out

Alkanox TNPP
Chemtura

Technical Assistance: [Tech Direct](#) | Search amongst 10,000+ Additives and Modifiers | Store in my Library | Print

Additive
Antioxidant > Phosphite

Chemical composition: Tris(4-n-nonylphenyl) phosphite
 Physical form: Liquid
 CAS Number: 26523-78-4
 Food contact approval: Yes
 Masterbatch / One Pack: No

Product description: Phosphite antioxidant.

Best suitable Polymer

- Rubbers SBR, Acrylonitrile-butadiene Rubber
- Rubbers >> SBR, Styrene-butadiene rubber
- PP, Polypropylene
- ABS/ SAN/ ASA, Acrylonitrile-Styrenic based
- PE, Polyethylene
- PS, Polystyrene

Typical properties	Value	Unit
Molar Weight	688	
Specific gravity@ 20°C	0.99	
Pure solid	405	°C

Disclaimer:
 All technical information on this site is given for information purposes only. Before working with any products, users shall contact product manufacturer in order to receive complete information about the products. Information on this website is believed to be reliable; however, the data is provided without implied warranties of any kind. SpecialChem shall not be liable or obligated under any contract, negligence, strict liability or other legal or equitable theory, in any event, for any damages, including lost profits, loss of business or indirect, consequential, special or punitive damages, even if advised of the possibility of such damages. Products mentioned as food contact approved are believed to have received a food contact approval for a given application in a given country. Please contact our supplier for full information on the exact nature of food approval and its relevance to other applications and other countries.
 © 2009 SpecialChem S.A.

SpecialChem Polymer Additives & Colors

Home Bookmarks Composites PVC TPE Thermosets My SpecialChem Log-out

Search Bookmarks SpecialChemPolymers Free newsletter subscription >> Eldar Zeynalov

Alkanox P-24

Technical Assistance: Tech Direct Search amongst 10,000+ Additives and Modifiers

Additive Antioxidant >> Phosphite

Chemical composition: Bis (2,4-di-t-butylphenyl) pentaerythritol diphosphite
 Physical form: Powder
 CAS Number: 26741-53-7
 Masterbatch / One Pack: No

Product description: High performance, high molecular weight organo-phosphite. Provides very good color stabilization.

Best suitable Polymer:
 • PVC rigid; polyvinylchloride
 • PE: Polyethylene >> LDPE, Linear Low Density Polyethylene
 • PP: Polypropylene
 • Thermoplastic ether
 • PVC: Polyvinylchloride
 • ABS/ SAN/ ASA, Acrylonitrile-Styrene based
 • IML: Polyethylene >> LDPE, Low Density Polyethylene
 • PE: Polyethylene >> HDPE, High Density Polyethylene

Typical properties

Property	Value	Unit
Molecular weight	934	%
Melting range	150 - 175	°C
Specific gravity @ 20 °C	0.43	g/ml
Frac. polar	168	%

Disclaimer:
 All technical information on this site is given for estimating purposes only. Before making any purchase, please contact product manufacturer in order to receive complete information about the serviceability or other legal or equitable theory to any party for any amounts representing loss of revenues, loss of profits, loss of business or interest, consequential, special or punitive damages, even if advised in advance on the exact amount of loss-allowed and/or extension to other applications and other countries.
 © 2009 SpecialChem S.A.

SpecialChem Polymer Additives & Colours

Alkanox 240-3T
Chemtura

Product description:
Synthetic blend of the phosphite selected Alkox 240 and 5% of the triisopropyl citrate/3,3'-dichloropropionic (DCTP).

Base suitable Polymer:

- Thermoplastics, other
- TPU - Thermoplastic Polyurethane
- PE - Polystyrene
- PA - Polyamide
- ABS/ SAN/ ASA, Acrylonitrile Styrene/Isobutene
- PP, Polypropylene
- PE, Polyethylene

Physical property	Value	Unit
Melting point	52	°C
Melting range	49 - 100	°C

Disclaimer:
All products described in this section are for industrial purposes only. After working with any product, user shall conduct process validation in order to assess process efficiency and the commercial viability of the product. Therefore, the stated values are not to be considered exact. Such values should be taken as approximate under typical conditions. The user shall determine the suitability of any product for his/her specific application. The manufacturer does not guarantee the quality of any product. The manufacturer is not liable for any damage or loss resulting from the use of any product. The manufacturer is not liable for any damage or loss resulting from the use of any product.

Special - Polymer Additives & Colors

Home Resources WebCenter NewsCenter

Search (23) Bookmarks SpecialChem4Polymer Free newsletter subscription Edit Zeynabov

Moresitol® 18 DSTDP
Struktol

Search amongst 10,000+ Additives and Modifiers

Expo for Plastics Technical Assistance Tech Direct

Additive Antioxidant >> Thioester

Chemical composition: Physical form: Powder
Food contact approval: Yes
Vanderbatch / One Pack: No

Product description:
Thioester synergist that is particularly effective as a long-term heat aging stabilizer when used in conjunction with primary antioxidants. Moresitol stabilizes antioxidant use and extends its life.

Best suitable Polymer:
 - PE: 20 properties
 - PTFE: 10 properties
 - HDPE: High Density Polyethylene
 - ABS/SAN/ASA: Acrylonitrile Styrene copolymers

Typical properties:

	Value	Unit
TGA: 100% weight loss	-	-
Impact Strength: 100% IZOD	532	ft-lb/in
Flexural Strength: 100% IZOD	2950	psi
Stiffness: 100% IZOD	2	psi/mm
Stiffness: 100% IZOD	13	MPa

Disclaimer: The information contained in this document is believed to be reliable. However, the data provided herein is based on research and development work, and is not necessarily representative of actual product performance. We do not warrant the accuracy or completeness of the data. Specifications are not to be construed as quality standards. No claim of liability is assumed for damages resulting from the use of these data. It is the responsibility of the user to determine the suitability of the products for their specific application. It is recommended that the user test the product under actual end-use conditions before committing to large quantities.

© 2006 SpecialChem4Polymer. All rights reserved.



TECHNICAL DATA SHEET

Polymer Additives

BRUGGOLEN® H 161

Heat Stabilizer and Antioxidant for Thermoplastics

Product Description	BRUGGOLEN® H 161 is a mixture of phenolic antioxidants and synergists.
Application and Properties	<p>BRUGGOLEN® H 161 is a non discoloring antioxidant and heat stabilizer with outstanding performance especially in polyamides (PA 6, PA 66, PA 11, PA 12, PA – Copolymers), but also suited for polyesters (PET, PBT), polycarbonates (PC) and their blends, as well as styrenics (PS, ABS, SAN) and polypropylenes (PP).</p> <p>Besides the use in injection moulded applications this stabilizer can also be used in film and fibre applications.</p> <p>BRUGGOLEN® H 161 provides excellent protection against embrittlement and premature fatigue of the mechanical properties of the finished parts under long term stress, both in unreinforced and glassfibre reinforced or mineralfilled polymers.</p> <p>Typical applications and advantages of this stabilizer are as follows:</p> <ul style="list-style-type: none">➤ Long term heat stability in applications up to 150 °C.➤ Efficient process stabilization against yellowing and degradation.➤ Low volatility during processing.➤ Excellent compatibility, low extractability.➤ Long term protection of bright coloured polymers against yellowing.➤ High efficiency especially in glassfibre reinforced or mineralfilled types.➤ Complete dispersion, giving clear transparent films and fibres.➤ No deposits ('plate – out') in fibre spinning.
Dosage	<p>The recommended level of addition of BRUGGOLEN® H 161 is about 0.2 – 0.8 %, depending on the polymer and the desired properties of the finished parts.</p> <p>The effect of long term stability will be achieved at 0.5 – 0.8 %.</p> <p>An addition of 0.2 – 0.4 % should be used for a basic stabilization.</p>

Processing	The addition to the polymer is best done by compounding on twin screw extrusion machines. Also dry blending along with the polymer granules will often lead to the desired homogeneous dispersion of the additive in the melt during injection moulding. Preparing a "dry blend" on adhesive oil should be used additionally, such as 0.2 % BRUGGOLEN® P 50 or 0.1 % BRUGGOLEN® P 60. Please note also our Technical Information: Methods of Dosing and Product Form.						
Typical Properties	<table> <tr> <td>Appearance</td> <td>white powder</td> </tr> <tr> <td>Melting range (DSC)</td> <td>> 170 °C</td> </tr> <tr> <td>Bulk density</td> <td>300 – 400 g/l</td> </tr> </table>	Appearance	white powder	Melting range (DSC)	> 170 °C	Bulk density	300 – 400 g/l
Appearance	white powder						
Melting range (DSC)	> 170 °C						
Bulk density	300 – 400 g/l						
Product Safety	<p>According to 67/24/EC on the protection of the health and safety of workers from the risks related to chemical agents at work BRUGGOLEN® H 161 is defined as a chemical agent which meets the criteria for classification as a dangerous preparation.</p> <p>For this reason an assessment of the risks is required. The information on safety and health provided by the corresponding safety data sheet has to be taken into consideration.</p> <p>The aforementioned remarks are deducted from the European legal system. Deviating or additional regulations in other legal systems must be observed accordingly when using the product.</p>						
Packing	2kg cardboard boxes with PE liner.						
Storage and Shelf Life	If kept properly unopened under standard conditions (dry, 25°C) the shelf life of BRUGGOLEN® H 161 is at least 12 months. Protect against heat and moisture.						
Additional Information	<p>For other specific applications especially tailored BRUGGOLEN® additives can be offered.</p> <p>For more detailed information please contact our technical service department under our phone number +49 / 731 1576 – 179 or see our website http://www.bruggeleman.com</p>						

**Bruggeleman H 161 Products:**

Werner 1087
The Werner 1087 series is designed to reduce overall cost per part and improve quality while maintaining the results of a standard grade of rubber compounds. However, because of the many factors which can affect the final quality and control which can affect the use of these products, we cannot accept responsibility for any damage resulting from their use.

2



TECHNICAL INFORMATION

Polymer Additives

BRUGGOLEN® H 175
Heat Stabilizer and Antioxidant for Thermoplastics

Product Description	BRUGGOLEN® H 175 is a synergistic mixture of sterical hindered phenolic antioxidants and phosphonates.
Application and Properties	<p>BRUGGOLEN® H 175 is a highly efficient non discolouring antioxidant and heat stabilizer with outstanding performance especially in polyamides (PA 6, PA 66, PA 11, PA 12, PA – Copolymers), but also in other thermoplastics such as polyesters (PET, PBT), polycarbonates (PC) and their blends, styrenics (PS, ABS, SAN) and polypropylene (PP).</p> <p>BRUGGOLEN® H 175 is giving an excellent protection to the finished parts against embrittlement and premature fatigue of mechanical properties under aggressive conditions, both in unreinforced as well as reinforced and filled polymers.</p> <p>Typical applications and advantages of this stabilizer are as follows:</p> <ul style="list-style-type: none">➤ Long term heat stability in applications up to 150 °C.➤ Efficient process stabilization against yellowing and degradation.➤ Best protection of organic pigments against discolouration at high processing temperatures up to approx. 320°C.➤ Low volatility during processing.➤ Excellent compatibility, low extractability.➤ Long term protection of bright coloured polymers against yellowing under aggressive conditions (heat, moisture, chemicals).➤ Very effective in glassfibre reinforced or mineral filled polymers.
Dosage	The best level of addition of BRUGGOLEN® H 175 is about 0.2 – 0.6 %, depending on the polymer and the desired properties of the finished parts. Long term stability will be achieved as a rule at 0.4 – 0.6 %. As a rule an addition of 0.2 – 0.3 % should be used for a basic stabilization.
Processing	The addition to the polymer is best done by compounding on twin screw extrusion machines. Also dry blending along with the polymer granules will often lead to the desired homogenous dispersion of the additive in the melt during injection moulding. Preparing a 'dry blend' an adhesive oil should be used additionally, like 0.2 % BRUGGOLEN® P 50 . Please note also our Technical Information: Methods of Dosage and Product Form.

Typical Properties	Appearance Composition Melting range (DSC) Bulk density	white powder mixture of phenolic antioxidants and synergistic co - stabilizers > 150 °C 400 – 500 g/l
Labelling	BRUGGOLEN® H 175 has to be labelled according to the EEC - Guideline. Regulatory Information: R – Phrases : R 52/53 S – Phrases : S 61 Please note the corresponding and valid up-to-date material safety data sheet according to 91/155/EEC.	
Packing	50 kg (110 lbs) drums with PE-inliner.	
Storage and Shelf Life	If kept properly unopened under standard conditions (dry, 25°C) the shelf life of BRUGGOLEN® H 175 is at least 12 months . Protect against heat and moisture.	
Transport	HS-Code 38 12 30 20	
Additional Information	For other specific applications especially tailored BRUGGOLEN® - additives can be offered. For more detailed information please contact our technical service department under our phone number ++49 (0) 7131-1575 – 179 or see our website http://www.brueggemann.com .	
QM-System	 DIN EN ISO 9001 since 1994 DIN EN ISO 14001 since 2000	



TECHNICAL INFORMATION

Polymer Additives

BRUGGOLEN® H 1761 Heat Stabilizer and Antioxidant for Thermoplastics

Product Description	BRUGGOLEN® H 1761 is a synergistic mixture of sterical hindered phenolic antioxidants and phosphonates.
Application and Properties	<p>BRUGGOLEN® H 1761 is a highly efficient non discoloring antioxidant and heat stabilizer with outstanding performance especially in polyamides (PA 6, PA 66, PA 11, PA 12, PA – Copolymers), but also in other Engineering Thermoplastics such as styrenics (PS, ABS, SAN), polyesters (PET, PBT), polycarbonates (PC) and its blends and polypropylene (PP).</p> <p>BRUGGOLEN® H 1761 is giving an excellent protection to the finished parts against embrittlement and premature fatigue of mechanical properties under aggressive conditions. Typical applications and advantages of this stabilizer are as follows:</p> <ul style="list-style-type: none">➤ Long term heat stability in applications up to 150 °C.➤ Efficient process stabilization against yellowing and degradation.➤ Best protection of organic pigments against discolouration at high processing temperatures up to approx. 320°C.➤ Low volatility during processing.➤ Excellent compatibility, low extractability.➤ Long term protection of bright coloured polymers against yellowing under aggressive conditions (heat, moisture, chemicals).➤ Very effective in glassfibre reinforced or mineralfilled polymers.➤ Recommended for applications in contact with food stuff.
Example of application: Stabilization against hydrolysis of PA	Protection of PA 66 GF 30 against embrittlement (polymer degradation) under the influence of hot water (80 to 90 °C). During application time only very small quantities of polymer components may be absorbed by the water. Very good results can be achieved with the following combination : 0.3 – 0.5 % BRUGGOLEN® H 1761 (colour stable heat stabilizer and antioxidant) 0.2 – 0.5 % BRUGGOLEN® P 12 (hydrolysis protection agent, mould release agent, good surface) 0.05 – 0.2 % BRUGGOLEN® P 22 (nucleating agent for a fine crystalline structure, improved dimensional stability, less warpage).
Dosage	The best level of addition of BRUGGOLEN® H 1761 is about 0.2 – 0.6 % , depending on the polymer and the desired properties of the finished parts.

Processing	The addition to the polymer is best done by compounding on twin screw extrusion machines. Also dry blending along with the polymer granules will often lead to the desired homogenous dispersion of the additive in the melt during injection moulding. Preparing a 'dry blend' an adhesive oil should be used additionally, like 0.2 % BRUGGOLEN® P 50. Please note also our Technical Information: Methods of Dosage and Product Form.	
Typical Properties	Appearance Composition Melting range Bulk density	white powder mixture of phenolic antioxidants and synergistic organic phosphite > 150 °C 400 – 500 g/l
Labelling	BRUGGOLEN® H 1761 has not to be labelled according to the EEC - Guideline, but however using this product, the conventional industrial protections should be applied. For further information please note the corresponding, valid up-to-date material safety data sheet according to 91/155/EEC.	
Food Contact Applications	The ingredients of BRUGGOLEN® H 1761 are recommended according to BgVV - regulations (Bundesamt für gesundheitlichen Verbraucherschutz und Veterinärmedizin, Germany) and to the FDA - regulations (Food and Drugs Administration, USA) concerning incorporation of additives into plastics used in food packaging. In an actual case please consult our service – department.	
Packing	50 kg (110 lbs) drums with PE-inner liner.	
Storage and Shelf Life	If kept properly unopened under standard conditions (dry, 25°C) the shelf life of BRUGGOLEN® H 1761 is at least 12 months. Protect against heat and moisture.	
Transport	HS-Code 38 12 30 20	
Additional Information	For other specific applications especially tailored BRUGGOLEN® - additives can be offered. For more detailed information please contact our technical service department under our phone number ++49 (0) 7131-1575 – 179 or see our website http://www.brueggemann.com .	
QM-System	 	DIN EN ISO 9001 since 1994 DIN EN ISO 14001 since 2000



TECHNICAL DATA SHEET

Polymer Additives

BRUGGOLEN® L 20

Light Stabilizer for Engineering Thermoplastics

Product Description	BRUGGOLEN® L 20 is a mixture of HALS – UV Stabilizer, UV – Co stabilizer, a sterical hindered phenolic antioxidant, a processing stabilizer and a special dispersion auxiliary.										
Application and Properties	BRUGGOLEN® L 20 is a non discolouring light stabilizer and antioxidant with outstanding performance in Engineering Thermoplastics such as polyamides (PA 6, PA 66, PA 11, PA 12, PA – Copolymers) , polyesters (PET, PBT) , styrenics (ABS, SAN) and polyolefins (PP, HDPE) , giving a powerful protection against ageing and embrittlement to all kinds of unreinforced and reinforced types. The advantages using BRUGGOLEN® L 20 are: <ul style="list-style-type: none">➤ Long term UV - stabilization in outdoor applications.➤ Good surface gloss over a long period.➤ Protection of coloured plastics against discolouration.➤ Long - term heat stabilization in applications up to 150 °C.➤ Efficient process stabilization against yellowing and degradation.➤ Low volatility during processing.➤ Excellent compatibility to polymers, low extractability										
Dosage	The recommended level of addition of BRUGGOLEN® L 20 is about 0.5 – 1.5 %, depending on the polymer and the desired properties of the finished parts.										
Processing	The addition to the polymer granules is best done by compounding on twin screw extrusion machines. But also dry blending along with the polymer granules will often lead to the desired homogenous dispersion of the additive in the melt during injection moulding. Preparing a 'dry blend' an adhesive oil should be used additionally, such as 0.2 % BRUGGOLEN® P 50 or 0.1 % BRUGGOLEN® P 60. Please note also our Technical Information: Methods of Dosage and Product Form.										
Typical Properties	<table><tr><td>Appearance</td><td>White powder</td></tr><tr><td>Composition</td><td>Mixture of UV – stabilizers, antioxidants and processing auxiliaries</td></tr><tr><td>Melting range</td><td>> 120 °C</td></tr><tr><td>Volatile matter</td><td>max. 0.5 %</td></tr><tr><td>Bulk density</td><td>approx. 700 g/l</td></tr></table>	Appearance	White powder	Composition	Mixture of UV – stabilizers, antioxidants and processing auxiliaries	Melting range	> 120 °C	Volatile matter	max. 0.5 %	Bulk density	approx. 700 g/l
Appearance	White powder										
Composition	Mixture of UV – stabilizers, antioxidants and processing auxiliaries										
Melting range	> 120 °C										
Volatile matter	max. 0.5 %										
Bulk density	approx. 700 g/l										

Product Safety	According to 98/24/EC on the protection of the health and safety of workers from the risks related to chemical agents at work BRUGGOLEN® L 20 is defined as a chemical agent which meets the criteria for classification as a dangerous preparation. For this reason an assessment of the risks is required. The information on safety and health provided by the corresponding safety data sheet has to be taken into consideration. The aforementioned remarks are deducted from the European legal system. Deviating or additional regulations in other legal systems must be observed accordingly when using the product
Packing	25 kg cardboard boxes with PE-inliner.
Storage and Shelf Life	If kept properly unopened under standard conditions (dry, 25°C) the shelf life of BRUGGOLEN® L 20 is at least 12 months. Protect against heat and moisture.
Additional Information	For other specific applications especially tailored BRUGGOLEN® - additives can be offered. For more detailed information please contact our technical service department under our phone number +49 7131-1575 – 179 or see our website http://www.brueggemann.com .





Technical Data Sheet

TDS Number: 1005

Product Name

THANOX 412s Thioester Antioxidant

A sulfur containing antioxidant with the high molecular weight and high heat-resistance.

Pentaerythrityl tetrakis (3-laurylthiopropionate)
CAS No.: [29598-76-3]

Typical Properties				
[C ₁₂ H ₂₅ S(CH ₂) ₂ CO ₂ CH ₂] ₄ C				Appearance White, Crystalline Powder
				Bulk density, kg/L 0.52
				Molecular Weight 1162
				Specific Gravity @ 55°C, g/ml 0.93
				Melting Range, °C 48-54
TGA(10mg@10 °C/minute under N ₂)				
Weight Loss, % 1 5 10 15				
Temperature, °C 295 335 351 361				
Solubility@20 °C(g/100g solvent)				
Water	Insoluble	Toluene	Soluble	
Cyclohexane	Soluble	n-Hexane	Soluble	

Specifications

Appearance:	White Crystalline Powder
Melting Range:	48.0-54.0°C
Volatiles:	≤0.50%
Ash:	≤0.10%
Assay(HPLC):	≥98.0%
Acid No.(mgKOH/g):	≤1.00

THANOX 412s is a sulfur containing antioxidant with high molecular weight, and the characteristics of low volatility and high continuous performance, showing outstanding heat-resistance and low leaching properties. Therefore, it performs as a better synergist with phenolic antioxidant than THANOX DSTDP and THANOX DLTDP etc. It mainly used in PP, PE, ABS and engineering thermoplastics, etc., especially suitable in polyolefin products, which easily suffer from water soaking or need to be used under the strict climate condition. And it has high application value in polymer fibre.

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the date of manufacturing. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

If agglomeration occurs in the process of storage, it is a normal and don't effect the quality.

Rionlon(Tianjin)Chemical Co., Ltd.
BLDG 7-A-7 No.15 Rongyuan Road,
Huayuan Industry Development Area, Tianjin 300348 China
TEL: +86-22-83718817 FAX: +86-22-83718815


Revised: April 2006

Page 1 of 1

Product Name
THANOX 1010 Phenolic Antioxidant

A high molecular weight hindered phenolic antioxidant that provides very low volatility and excellent resistance to extraction from polymer compounds.

Tetrakis(methylene(3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
CAS No.: [6683-19-8]


Typical Properties

Appearance	White, free flowing solid		
Bulk Density, kg/L	0.55		
Molecular Weight	1178		
Specific Gravity @ 20°C, g/ml	1.045		
Melting Range, °C	110-125		
Flash point, °C	299		
TGA(10mg@10 °C/minute under N₂)			
Weight Loss, %	5	10	25
Temperature, °C	350	365	387
Solubility@20 °C(g/100g solvent)			
Water	0.03	Benzene	>100
Chloroform	>100	Acetone	>100
		Methanol	2
		Hexane	0.45

Specifications

Appearance:	White to off-white powder or granules		
Melting Range:	110.0-125.0°C		
Volatiles:	≤0.50%		
Ash:	≤0.10%		
Transmittance:			
(5g/50ml Toluene)			
@425nm	≥97.0%		
@500nm	≥98.0%		
Assay(HPLC):	≥98.0%		

THANOX 1010 is particularly effective against polymer degradation during long-term aging. It is also very effective as a process stabilizer. **THANOX 1010** exhibits good resistance to discoloration at the high temperatures that are encountered in thermoplastic polymer processing.

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

Product Name

THANOX 1035 Phenolic Antioxidant

A sulfur containing primary (phenolic) antioxidant and heat stabilizer used for the process stabilization of polyethylene wire and cable resins.

2,2'-Thiodiethylene bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]

CAS No.: [41484-35-9]



Typical Properties	
Molecular Weight	642
Appearance	White, free flowing solid
Specific Gravity @20°C	1.01g/ml
Melting Range, °C	63-83
TGA(10mg@10 °C/minute under N₂)	
Weight Loss, %	5 10 25
Temperature, °C	291 309 335
Solubility@20 °C(g/100g solvent)	
Water	<0.01
Methanol	6.0
Ethyl acetate	48
Mineral oil	0.27
Chloroform	>50
Acetone	>50
Hexane(@50°C)	4.5

Specifications

Appearance:	White to off-white powder
Melting Range:	63.0-82.0°C
Volatile:	≤0.50%
Ash:	≤0.10%
Transmittance: (1g/50ml Methanol) @425nm	≥97.0%
Assay(HPLC):	≥98.0%

The world's most widely used antioxidant for PE and XLPE wire and cable resins, **THANOX 1035**, provides efficient processing stabilization and long-term thermal stability with excellent system compatibility and low color. The high quality of **THANOX 1035** eliminates the concern over microcontaminants that can effect the insulation properties of the wire. **THANOX 1035** offers excellent heat stability and is very unlikely to exude. **THANOX 1035** prevents scorching of PUR flexible foams in combination with an amine antioxidant and is used as a replacement for Antioxidant BHT.


Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

Product Name
THANOX 1076 Phenolic Antioxidant

A high molecular weight hindered phenolic antioxidant available in both powder and granular form.

Octadecyl-3-(3',5'-di-t-butyl-4'-hydroxyphenyl)propionate
CAS No.: [2082-79-3]



		Typical Properties		
Appearance		White, free flowing solid		
Bulk density, kg/L	0.45			
Molecular Weight	531			
Specific Gravity @ 20°C, g/ml	1.07			
Melting Range, °C	50-55			
Flash point, °C	273			
TGA(10mg@10 °C/minute under N₂)				
Weight Loss, %	5	10	25	
Temperature, °C	260	278	302	
Solubility@20 °C(g/100g solvent)				
Water	Insoluble	Xylene	104	Methanol <1
Acetone	50	Chloroform	140	Mineral oil 10
Ethyl acetate	95	Hexane	52	

Specifications

Appearance:	White powder or granules
Melting Range:	50.0-55.0°C
Volatile:	≤0.20%
Ash:	≤0.10%
Transmittance: (5g/50ml Toluene)	
@425nm	≥97.0%
@500nm	≥98.0%
Assay(HPLC):	≥98.0%

THANOX 1076 effectively reduced oxidative degradation of most polymeric substances during processing and end-use applications. **THANOX 1076** is an excellent stabilizer for polyolefins, impact modified styrenics, block co-polymers, elastomers, adhesives, PVC and polyurethanes.


Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

Product Name
THANOX 3114 Phenolic Antioxidant

A high molecular weight hindered phenolic antioxidant that provides very low volatility and excellent resistance to extraction from polymer compounds.

1,3,5-Tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione
CAS No.: [27676-62-6]



Typical Properties			
Appearance			White crystalline powder
Specific Gravity @20°C			1.03g/ml
Melting Range, °C			218-223
TGA(10mg@10 °C/minute under N₂)			
Weight Loss, %	5	10	25
Temperature, °C	305	319	337
Solubility@20 °C(g/100g solvent)			
Water	Insoluble	Methanol 0.5	Chloroform 32
Ethanol	1.5	Acetone 22	n-Hexane 0.1

Specifications

Appearance:	White to off-white powder
Melting Range:	218.0-223.0°C
Volatiles:	≤0.50%
Ash:	≤0.10%
Transmittance: (5g/50ml Chloroform) @425nm	≥95.0%
@500nm	≥97.0%
Assay(HPLC):	≥98.0%



THANOX 3114 is an antioxidant with photo-and thermo-stability, not volatile, insoluble in water, no pollution and no discoloring under the process temperature. Suitable for PP, PE, polystyrene, ABS, PVC, nylon, polyurethane, etc. The synergistic action appears when THANOX 3114 is used with light stabilizer.

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

Product Name
THANOX B215 / B225 Phenolic /Phosphite Blend

A family of binary synergistic blends used to protect polymers during processing and long term aging.

	THANOX 1010	THANOX 168
	 Tetrakis(methylene(3,5-di-tert-butyl-4-hydroxyphenyl)methane CAS No. [6683-19-8]	 Tris-(2,4-di-tert-butyl phenyl) phosphite CAS No. [31570-04-4]
THANOX B215	33%	67%
THANOX B225	50%	50%

Specifications

Appearance:	THANOX B215	THANOX B225
	White to off-white powder or granules	White to off-white powder or granules
Volatiles:	≤0.50%	≤0.50%
Transmittance:		
(5g/50ml Toluene)		
@425nm	≥96.0%	≥96.0%
@500nm	≥97.0%	≥97.0%
Content of THANOX 1010:	28.3-38.3%	45.0-55.0%
Content of THANOX 168:	61.7-71.7%	45.0-55.0%

The combination of a high molecular weight hindered phenol, **THANOX 1010**, and phosphite, **THANOX 168**, provide excellent protection in polyolefins. The low volatility of **THANOX 1010**, and **THANOX 168**, allows the **THANOX B215/B225** to be used at relatively high temperatures while providing excellent resistance to extraction from polymer compounds. The blends are active during polymer processing and provide excellent stabilization against thermo-oxidative degradation during long term aging. **THANOX B215/B225** are used for process stabilization of a wide range of thermoplastic polymers such as polyolefins (PP, HDPE, LDPE, LLDPE), polycarbonates, ABS, and polyesters.



THANOX 1010 and **THANOX 168** are allowed by the FDA for use in food packaging applications in accordance with regulations.

Adhesives	Acrylic and Modified Acrylic plastics
Elastomers used in Rubber articles	Ethylene-vinyl acetate copolymers
Nylon	Olefin polymer
Polycarbonates	Polystyrene and Rubber Modified Polystyrene

THANOX B215 and **THANOX B225** may be used in articles, which may come into contact with foodstuffs according to the regulations of different countries.

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.

Product Name	THANOX B220 <i>Synergistic Processing and Long-Term Thermal Stabilizer System</i>	
Chemical name	THANOX B220 - a processing and long-term thermal stabilizer system - is a synergistic blend of THANOX 168 and THANOX 1010	
CAS number	75% THANOX 168 + 25% THANOX 1010	
Structure	Preparation   THANOX 168 THANOX 1010	
Molecular weight	646.9g/mol 1178g/mol	
Applications	THANOX B220 is used in polyolefins and olefin-copolymers such as polyethylene, polypropylene, polybutene and ethylene-vinylacetate copolymers. The blend can also be used in other polymers such as engineering plastics, styrene homo-and copolymers, polyurethanes, elastomers e.g. Butyl, Polyisoprene (synthetic and natural), adhesives, and other organic substrates. THANOX B220 is also recommended for use in combination with HALS type and UV absorber type light stabilizers.	
Features/benefits	THANOX B220 is a convenient blend addressing a range of stabilization needs. The relatively high phosphite content of THANOX B220 addresses applications with demanding processing conditions. In the recommended applications THANOX B220 provides significant benefits, such as <ul style="list-style-type: none"> • Maintenance of original melt flow • Low color formation • Long-term thermal stability Blends of THANOX 1010 and THANOX 168 are particularly effective.	
Guidelines for use	In polyolefins, the concentration levels for THANOX B220 range typically between 0.1% and 0.25% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of THANOX B220 in various organic polymers and applications are available upon request.	
Product Form	Code: THANOX B220 Appearance: White, free-flowing powder	
Physical Properties	Bulk Density Powder 530-630g/l	

Business Unit or Division	Polymer Additives Rionlon(Tianjin) Chemical Co., Ltd. No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China TEL.: +86-22-83718817 FAX.: +86-22-83718815	2007-3
Page 1 of 2		



Technical Data Sheet

TDS Number: 1021

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 12 months from the date of manufacturing. For additional handling and toxicological information, consult the **RionlonChem** Material Safety Data Sheet.

Registration

THANOX 168 [Tris(2,4-di-tert-butylphenyl)phosphite] and **THANOX 1010** Pentaerythritol Tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) are listed on following inventories:

The components are registered in:

Australia	AICS
Canada	DSL
China	Draft Inventory
Europe	EINECS
Japan	ENCS
Korea	ECL
Philippines	PICCS
USA.	TSCA

THANOX 168 and **THANOX 1010** are approved in many countries for use in food contact applications. For detailed information please call your local sales representative.

IMPORTANT: The following supercedes Buyer's documents.

SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin or blood is intended; or for uses for which implantation within the human body is intended.

Business Unit or Division Polymer Additives **2007-3**
Rionlon(Tianjin) Chemical Co., Ltd.
No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China
TEL.: +86-22-83718817 FAX.: +86-22-83718815

Page 2 of 2

Product Name	THANOX B561 Synergistic Processing and Long-Term Thermal Stabilizer System	
Chemical name	THANOX B561 - a processing and long-term thermal stabilizer system - is a synergistic blend of THANOX 168 and THANOX 1010	
CAS number	80% THANOX 168 + 20% THANOX 1010	
Structure	Preparation 	
Molecular weight	THANOX 168 646.9g/mol	THANOX 1010 1178g/mol
Applications	THANOX B561 is used in polyolefins and olefin-copolymers such as polyethylene, polypropylene, polybutene and ethylene-vinylacetate copolymers. The blend can also be used in other polymers such as engineering plastics, styrene homo-and copolymers, polyurethanes, elastomers e.g. Butyl, Polyisoprene (synthetic and natural), adhesives, and other organic substrates. THANOX B561 can be used in combination with light stabilizers of the THASORB UV range.	
Features/benefits	THANOX B561 is a convenient blend addressing a range of stabilization needs. The relatively high phosphite content of THANOX B561 addresses applications with demanding processing conditions. In the recommended applications THANOX B561 provides significant benefits, such as <ul style="list-style-type: none"> • Maintenance of original melt flow • Low color formation • Long-term thermal stability Blends of THANOX 1010 and THANOX 168 are particularly effective.	
Guidelines for use	In polyolefins, the concentration levels for THANOX B561 range typically between 0.1% and 0.25% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of THANOX B561 in various organic polymers and applications are available upon request.	
Product Form	Code: THANOX B561	Appearance: White, free-flowing powder
Physical Properties	Bulk Density Powder	530-630g/l

Business Unit or Division	Polymer Additives Rionlon(Tianjin) Chemical Co., Ltd. No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China TEL.: +86-22-83718817 FAX.: +86-22-83718815	2007-3
Page 1 of 2		



Technical Data Sheet

TDS Number: 1022

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 12 months from the date of manufacturing. For additional handling and toxicological information, consult the **RionlonChem** Material Safety Data Sheet.

Registration

THANOX 168 [Tris(2,4-di-tert-butylphenyl)phosphite] and **THANOX 1010** Pentaerythritol Tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) are listed on following inventories:

The components are registered in:

Australia	AICS
Canada	DSL
China	Draft Inventory
Europe	EINECS
Japan	ENCS
Korea	ECL
Philippines	PICCS
USA.	TSCA

THANOX 168 and **THANOX 1010** are approved in many countries for use in food contact applications. For detailed information please call your local sales representative.

IMPORTANT: The following supercedes Buyer's documents.



SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin or blood is intended; or for uses for which implantation within the human body is intended.

Business Unit or Division Polymer Additives
Rionlon(Tianjin) Chemical Co., Ltd.
No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China
TEL.: +86-22-83718817 FAX.: +86-22-83718815

2007-3

Page 2 of 2

Product Name	THANOX B900 <i>Synergistic Processing and Long-Term Thermal Stabilizer System</i>	
Chemical name	THANOX B561 - a processing and long-term thermal stabilizer system - is a synergistic blend of THANOX 168 and THANOX 1076	
CAS number	80% THANOX 168 + 20% THANOX 1076	
Structure	Preparation THANOX 168 THANOX 1076   Molecular weight 646.9/mol 531g/mol	
Applications	THANOX B900 is mainly used in polyethylene and ethylene co-polymers, such as ethylene-vinylacetate copolymers. The blend can also be used in other polymers such as engineering plastics e.g. polycarbonates, polyesters, styrene homo-and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates. THANOX B900 is also recommended for use in combination with HALS type and UV absorber type light stabilizers.	
Features/benefits	THANOX B900 is a convenient blend addressing a range of stabilization needs. The relatively high phosphite content of THANOX B900 addresses applications with demanding processing conditions. In the recommended applications THANOX B900 provides significant benefits, such as <ul style="list-style-type: none"> • Maintenance of original melt flow • Low color formation • Long-term thermal stability Blends of THANOX 1076 and THANOX 168 are particularly effective.	
Guidelines for use	In polyethylenes and ethylene co-polymers, the concentration levels for THANOX B900 range typically between 0.1% and 0.25% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of THANOX B900 in various organic polymers and applications are available upon request.	
Product Form	Code: THANOX B900 Appearance: White, free-flowing powder	
Physical Properties	Bulk Density	Powder 530-630g/l

Business Unit or Division Polymer Additives **2007-3**
Rionlon(Tianjin) Chemical Co., Ltd.
 No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China
 TEL.: +86-22-83718817 FAX.: +86-22-83718815

Page 1 of 2



Technical Data Sheet

TDS Number: 1023

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 12 months from the date of manufacturing. For additional handling and toxicological information, consult the **RionlonChem** Material Safety Data Sheet.

Registration

THANOX 168 [Tris(2,4-di-*tert*-butylphenyl)phosphite] and **THANOX 1076** Octadecyl 3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propionate are listed on following inventories:

The components are registered in:

Australia	AICS
Canada	DSL
China	Draft Inventory
Europe	EINECS
Japan	ENCS
Korea	ECL
Philippines	PICCS
Switzerland	BUWAL
USA.	TSCA

THANOX 168 and **THANOX 1076** are approved in many countries for use in food contact applications. For detailed information please call your local sales representative.

IMPORTANT: The following supersedes Buyer's documents.

SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin or blood is intended; or for uses for which implantation within the human body is intended.

Business Unit or Division Polymer Additives
Rionlon(Tianjin) Chemical Co., Ltd.
No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China
TEL.: +86-22-83718817 FAX.: +86-22-83718815

2007-3

Page 2 of 2

Product Name	THANOX B921 <i>Synergistic Processing and Long-Term Thermal Stabilizer System</i>	
Chemical name	- a processing and long-term thermal stabilizer system - is a synergistic blend of THANOX 168 and THANOX 1076	
CAS number	67% THANOX 168 + 33% THANOX 1076	
Preparation		
Structure	THANOX 168	THANOX 1076
Molecular weight	646.9g/mol	531g/mol
Applications	THANOX B921 is mainly used in polyethylene and ethylene co-polymers, such as ethylene-vinyl acetate copolymers. The blend can also be used in other polymers such as engineering plastics e.g. polycarbonates, polyesters, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates. THANOX B921 is also recommended for use in combination with HALS type and UV absorber type light stabilizers.	
Features/benefits	THANOX B921 is a convenient blend addressing a range of stabilization needs. The relatively high phosphite content of THANOX B921 addresses applications with demanding processing conditions. In the recommended applications THANOX B921 provides significant benefits, such as <ul style="list-style-type: none"> • Maintenance of original melt flow • Low color formation • Long-term thermal stability THANOX 168 - an organophosphite of low volatility and particularly resistant to hydrolysis-protects during processing organic polymers which are prone to oxidation. THANOX 1076 - a hindered phenolic antioxidant-contributes synergistically to the polymer's stabilization during processing and provides long-term thermal stability by preventing thermo-oxidative degradation during service life. Performance can be improved in synergistic combinations with other additives (e.g. thioethers). Blends of THANOX 1076 and THANOX 168 are particularly effective.	
Guidelines for use	In polyethylenes and ethylene co-polymers, the concentration levels for THANOX B921 range typically between 0.1% and 0.25% depending on substrate and processing conditions. The optimum level is application specific. Extensive performance data of THANOX B921 in various organic polymers and applications are available upon request.	

Business Unit or Division	Polymer Additives	2007-3
	Rionlon(Tianjin) Chemical Co., Ltd. No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China TEL.: +86-22-83718817 FAX: +86-22-83718815	Page 1 of 2



Technical Data Sheet

TDS Number: 1024

Physical Properties

Bulk Density	Powder	530-630g/l
--------------	--------	------------

Product Form

Code:	THANOX B921
-------	-------------

Appearance:	White, free-flowing powder
-------------	----------------------------

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 12 months from the date of manufacturing. For additional handling and toxicological information, consult the **RionlonChem** Material Safety Data Sheet.

Registration

THANOX 168 [Tris(2,4-di-*tert*-butylphenyl)phosphite] and **THANOX 1076** Octadecyl 3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propionate are listed on following inventories:

The components are registered in:

Australia	AICS
Canada	DSL
China	Draft Inventory
Europe	EINECS
Japan	ENCS
Korea	ECL
Philippines	PICCS
Switzerland	BUWAL
USA.	TSCA

THANOX 168 and **THANOX 1076** are approved in many countries for use in food contact applications. For detailed information please call your local sales representative.

IMPORTANT: The following supersedes Buyer's documents.

SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin or blood is intended; or for uses for which implantation within the human body is intended.


Business Unit or Division Polymer Additives
Rionlon(Tianjin) Chemical Co., Ltd.
No. 6 Huangshan Road, Chemical Park, TEDA Tianjin 300480 China
TEL: +86-22-83718817 FAX: +86-22-83718815

2007-3

Page 2 of 2

Product Name
THANOX MD-1024 Phenolic Antioxidant/Metal Deactivator

An excellent metal deactivator that additionally acts as a hindered phenolic antioxidant.

1,2-Bis(3,5-di-*tert*-butyl-4-hydroxyhydrocinnamoyl) hydrazine
CAS No.: [32687-78-8]


	Typical Properties			
Appearance	White, free flowing solid			
Bulk Density, kg/L	1.11			
Molecular Weight	553			
Melting Range, °C	221-232			

TGA(10mg@10 °C/minute under N₂)

	Weight Loss, %	5	10	50
Temperature, °C	284	295	330	

Solubility@20 °C(g/100g solvent)

	THF	Toluene	<0.01	Acetone	>1.0
Methylene Chloride	0.25	Water	<0.01	Paraffin Oil	<0.01

Specifications

Appearance:	White to off-white powder
Melting Range:	221.0-232.0°C
Volatile:	≤0.50%
Ash:	≤0.10%
Transmittance: (1g/50ml Methanol) @425nm	≥98.0%
Assay(HPLC):	≥98.0%

THANOX MD-1024 combines both an antioxidant and a metal deactivator for outstanding protection in a variety of polymers including polyolefins and elastomers used in applications such as wire and cable insulation. It provides excellent protection from the auto-oxidation process that can occur with the presence of trace metals in polymers from such things as catalyst residue. Its ideal melting range allows for ease of incorporation into many polymer systems without dispersion problems. **THANOX MD-1024** can be used in conjunction with phenolic antioxidants phosphates/phosphonites, thio-synergists and other coadditives. The compatibility of the product with these coadditives is very good.

Handling & Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 24 months from the manufacture date. For additional handling and toxicological information, consult the RionlonChem Material Safety Data Sheet.